

INDEX

- ALLOY LISTING 47
ALLOY SPECIFICATIONS 49
ALLOYED CAST IRON 40, 41, 46
ALUMINUM IN STAINLESS STEEL 19
ALUMINUM IN STEEL 2, 6
ANTIMONY IN STEEL 5
ARSENIC IN STEEL 5
- BISMUTH STEEL 5, 8
BORON IN STAINLESS STEEL 19
BORON IN STEEL 2
- CALCIUM IN STAINLESS STEEL 19
CALCIUM IN STEEL 6
CARBON STEEL 2, 3, 4, 44
CARBON STEEL SPECIFICATIONS 49
CAST IRON
 32, 33, 34, 35, 37, 38, 39, 40, 41, 42, 43, 46
CAST IRON WITH MAGNESIUM 34, 35, 36
COBALT ALLOY 9
COBALT IN STAINLESS STEEL 21
COPPER IN STAINLESS STEEL 20
Cr-Mo STEEL 6, 7
- DUCTILE IRON 33
- EPMA SETS 6
- GRAY IRON 33
- HIGH ALLOY STEEL 31, 32, 46
HIGH ALLOY STEEL SPECIFICATIONS 52
HIGH CHROMIUM CAST IRON 40, 41, 46
- IRON 2
- LEADED STEEL 8
LOW ALLOY STEEL
 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 45
LOW ALLOY STEEL SPECIFICATIONS 50
LOW ALLOY STEEL WITH $0.13\% < C < 0.3\%$ 13, 14
LOW ALLOY STEEL WITH $C < 0.13\%$ 15
LOW ALLOY STEEL WITH $C > 0.3\%$ 11, 12
LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS 13
- MAGNETIC ALLOY 9
MANGANESE STAINLESS STEEL 22
MANGANESE STEEL 8
MARAGING STEEL 21
- NICKEL BINARY 22
NITROGEN IN STEEL 6
NODULAR IRON 33
- PERMENDUR 2V 9
PHOSPHORUS IN STAINLESS STEEL 23
- RESULFURIZED STAINLESS STEEL 23
RESULFURIZED STEEL 9, 44
RESULFURIZED STEEL SPECIFICATIONS 49
- SELENIUM IN STAINLESS STEEL 23
SELENIUM STEEL 5
SET 2, 6, 8, 9, 16, 30, 32
Si-Mo CAST IRON 33
SILICON STEEL 10, 44
SOLUBLE ALUMINUM 2
SOLUBLE BORON 2
STAINLESS STEEL
 19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31, 46
STAINLESS STEEL SPECIFICATIONS 52
STAINLESS STEEL WITH $C < 0.05\%$ 28, 29
STAINLESS STEEL WITH $C > 0.05\%$ 26, 27
STAINLESS STEEL WITH $NI < 5.0\%$ 24, 25
SULFUR IN STAINLESS STEEL 23
- TOOL STEEL 16, 17, 18, 45
TOOL STEEL SPECIFICATIONS 51
TUNGSTEN IN STAINLESS STEEL 21
- WHITE IRON 36
- XRF 2, 6, 8, 9, 16, 30, 32

PURE IRON

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

17025

T = total

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	O
1	SRM 1265a	0.0067	0.0057	0.0011	0.0055	0.008	0.0058	0.041	0.007	0.0050	(0.0007)	0.007	.	.
1	BS 50F	0.0064	0.082	0.0066	0.0031	0.016	0.0088	0.016	0.022	0.0017	0.003	0.0023	0.0042	(0.0026)
2	CZ LA-0A	(0.006)	0.045	0.005	0.005	0.0015	0.012	0.028	0.022	(0.0044)	0.0015	0.002	0.0023	.
2	CZ LA-0B	(0.003)	0.038	0.0037	0.0023	(0.0043)	0.0074	0.0070	0.009	(0.0016)	(0.0010)	(0.0017)	0.0027	.
1	IARM 27G	(0.003)	(0.003)	(0.003)	0.0011	(0.07)	0.040	0.045	0.043	(0.002)	(0.0013)	(0.0009)	(0.0003)	0.025
1	BS LC-7B	0.0025	0.024	0.013	0.0029	(0.005)	0.0033	0.0081	0.0090	0.0034	0.0194	0.0018	0.0043	0.0020
1	BS LC-7A	0.0025	0.023	0.013	0.0030	0.0056	0.0038	0.0058	0.0074	0.0034	0.0194	0.0017	0.0043	(0.005)
1	BS 50G	0.0023	0.010	0.0088	0.0033	0.009	0.007	0.0045	0.008	(0.001)	0.008	0.0011	0.0019	0.0030
2	TH 1045D	0.0023	.	.	0.0043	0.0046	.
1	VS RG24/1	0.0022	0.015	0.0027	0.0069	0.017	0.011	0.037	0.037	0.0013	.	0.012	.	.
2	TL 1669 **	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.0011	0.03553T	0.0019	0.0024	.
1	ECRM 097-1D	(<0.002)	0.0064	0.0016	0.0022	(<0.01)	0.0020	0.0025	0.0016	(<0.001)	.	0.0037	0.0007	.
1	SRM 1768	0.0010	0.0014	0.0013	0.0003	.	0.0006	0.0014	.	.	0.0024	0.0025	0.002	0.036
1	ECRM 098-1D	0.00051	0.00008	(0.00006)	0.00031	0.00048	.	.	0.00571	0.00085	.	.	0.00024	.
1	ECRM 097-2D	.	0.012	0.00538	0.00181	0.00285	0.00793	0.0241	0.0213	0.00370	.	0.0139	0.00294	.

Number	As	B	Mg	Nb	Pb	Sn	Ti	V	W	Units
SRM 1265a	(0.0002)	0.00013	.	.	0.00001	.	(0.0001)	0.0006	.	disc 32 mm Ø x 19 mm
BS 50F	0.0013	(<0.0002)	(<0.0001)	(<0.0002)	(0.0003)	0.0010	0.0004	0.0004	(<0.0050)	disc 35 mm Ø x -7 mm
CZ LA-0A	(0.0015)	.	.	Sb:(0.0007)	(0.001)	(0.001)	0.001	.	.	disc -37 mm Ø x 25 mm
CZ LA-0B	0.0024	(0.0013)	.	.	.	disc -39 mm Ø x -25 mm
IARM 27G	(0.0016)	(0.0006)	(0.0002)	(0.002)	(0.002)	(0.001)	<0.005	(0.001)	<0.005	disc 31 mm Ø X 2 or 18 mm
BS LC-7B	0.0026	(0.0001)	(0.00008)	0.0007	(0.0003)	(0.0007)	(0.0001)	(0.0004)	(0.0006)	disc 38 mm Ø x 38 mm Fe:99.9
BS LC-7A	0.0024	(0.0001)	(0.0001)	(0.0005)	(0.0004)	(0.0007)	0.0004	(0.0004)	(0.0005)	disc 38 mm Ø x 38 mm Fe:99.9
BS 50G	0.0034	(0.0001)	(0.0002)	(0.0004)	(0.00007)	Sb:0.0005	(0.003)	(0.0003)	.	disc 38 mm Ø x 38 mm Fe:99.9
TH 1045D	disc 40 mm Ø x 40 mm
VS RG24/1	0.0010	.	.	disc -45 mm Ø x -28mm
TL 1669 **	0.0017	0.00038	.	0.00046	0.00013	0.0071	0.0504	(0.0006)	.	disc 38 mm Ø x 25 mm
ECRM 097-1D	0.0051	0.0003	.	.	.	(<0.0025)	.	(<0.001)	.	disc 35 mm Ø x 3, 25, or 30 mm
SRM 1768	disc 31 mm Ø x 19 mm
ECRM 098-1D	octagon 35 mm Ø x 25 mm
ECRM 097-2D	0.00281	0.00012	Sb:0.00012	Ta:0.00015	Zn:0.00014	0.00043	.	0.00011	0.00386	disc 38 mm Ø x 25 or 30 mm

** TL-1669 also contains in ppm Ca: 1.7, Sb: 4.9, Zn: 2.7

RM CARBON STEEL XRF SET

Part Number: BS CS-10

AVAILABLE INDIVIDUALLY

17025

~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Co	N	Sn	V
Pure Iron	BS 50F	0.0064	0.082	0.0066	0.0031	0.016	0.0088	0.016	0.022	0.0017	0.003	0.0013	0.0023	0.0042	0.0010	(0.0003)
1018	BS 1018	0.195	0.79	0.012	0.024	0.237	0.130	0.104	0.177	0.044	0.029	0.0041	0.0058	0.0079	0.0099	0.0009
1020	BS 57F	0.196	0.554	0.009	0.027	0.202	0.197	0.070	0.120	0.018	(0.002)	(0.006)	0.007	0.0077	0.008	0.063
1026	BS 4932	0.234	0.76	0.010	0.015	0.25	0.15	0.080	0.144	0.033	(0.001)	(0.005)	0.005	0.0080	0.008	0.060
1035	BS 4931	0.352	0.80	0.011	0.016	0.27	0.217	0.070	0.093	0.024	(0.001)	0.005	0.006	0.0080	0.009	0.058
1040	BS 3941	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0061	0.0019	0.0036	0.0042	0.0069	0.0019	0.0025
1045	BS 56E	0.483	0.72	0.010	0.025	0.24	0.015	0.015	0.021	0.005	0.062	0.0035	0.005	0.0056	(0.0006)	(<0.002)
1095	BS 64C	0.920	0.22	0.015	0.0024	0.22	0.016	0.038	0.261	0.008	(0.005)	.	0.004	0.0084	(0.001)	0.005
1522 (LF2)	BS 2932	0.208	1.20	0.008	0.020	0.186	0.060	0.034	0.077	0.026	0.022	(0.003)	0.004	0.0080	0.005	0.001
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	0.006	0.0056	(0.0004)	(<0.003)

CRM CARBON STEEL SET

AVAILABLE IN SET/6 ONLY

38 mm Ø x 30 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Al.Sol	Ti	Ti.Sol	V
NCS HS11719-5	1.19	2.20	0.011	0.013	0.751	0.046	0.164	0.439	0.036	0.034	0.029	0.028	0.0082
NCS HS11719-1	0.963	0.586	0.022	0.010	0.241	0.111	0.206	0.131	0.019	0.017	0.016	0.015	0.035
NCS HS11719-3	0.435	1.14	0.045	0.020	0.163	0.160	0.114	0.086	0.019	0.016	0.024	0.023	0.099
NCS HS11719-4	0.140	1.30	0.084	0.020	0.526	0.276	0.344	0.198	0.160	0.155	0.132	0.128	0.153
NCS HS11719-2	0.042	0.048	0.105	0.0053	0.154	0.411	0.432	0.247	0.296	0.292	0.161	0.154	0.207
NCS HS11719-6	0.0060	0.163	0.0053	0.035	0.014	0.0032	0.013	0.021	0.0021	0.0016	0.0010	(0.0008)	0.363

CRM SOLUBLE ALUMINUM AND SOLUBLE BORON STEEL SET

available in set/6 only as grouped .T = total .S = soluble

37 mm Ø x 30 mm

Number	Al.T	Al.S	B.T	B.S	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo
NCS HS93703-1a	0.59	0.58	0.036	0.034	1.04	2.10	0.023	0.030	0.650	0.033	0.063	4.05	0.0088	0.0040
NCS HS93703-2	0.92	0.91	0.0083	0.0080	0.055	0.021	0.027	0.0033	0.827	0.422	1.09	3.09	0.262	1.56
NCS HS93703-3	0.107	0.103	0.0041	0.0037	0.792	1.34	0.013	0.038	1.09	0.532	0.533	2.11	0.488	0.397
NCS HS93703-4	0.083	0.078	0.0050	0.0048	0.475	0.612	0.015	0.015	2.57	0.687	2.01	1.31	0.403	0.977
NCS HS93703-5	(1.29)	(1.27)	0.0017	0.0015	0.651	1.53	0.036	0.0052	0.024	0.236	2.98	0.021	0.094	0.631
NCS HS93703-6	0.64	0.63	0.0033	0.0030	0.246	0.211	0.045	0.0058	0.274	0.092	3.83	0.505	0.145	0.203

Number	As	Bi	Ca	Nb	Pb	Sb	Sn	Ti	V	W	Zr
NCS HS93703-1a	0.034	0.0013	(0.0001)	0.300	(0.0001)	(0.0004)	0.0035	0.069	0.021	0.313	(0.0005)
NCS HS93703-2	0.0034	0.0006	0.0010	0.254	0.0008	0.0020	0.0069	0.069	0.376	1.97	0.087
NCS HS93703-3	0.0019	0.0004	0.0010	0.506	0.0007	0.0040	0.054	0.016	0.071	0.755	0.014
NCS HS93703-4	0.056	(0.0002)	(0.0001)	0.167	0.0006	0.0095	0.012	0.035	0.709	1.48	0.069
NCS HS93703-5	0.0064	0.0015	0.0007	0.0057	0.0007	0.010	0.015	0.111	0.231	0.050	0.41

CARBON STEEL

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	B	Ca	Co	Mo
1	IRSID 1660	1.20	0.280	0.014	0.010	0.173	0.059	0.072	(0.026)	(0.009)
1	ECRM 090-1D	1.05	0.226	0.013	0.0095	0.281	.	0.053	0.121	0.009
1	SRM 1227	0.97	0.402	0.014	0.026	0.215	0.006	0.007	0.019	0.003	0.003
1	SS 602/2	0.94	0.66	0.023	0.031	0.057	(0.06)	(0.02)	(0.03)	0.096	(0.007)	(0.004)
2	BS 64C	0.920	0.22	0.015	0.0024	0.22	0.016	0.038	0.261	(0.005)	0.004	0.008
2	HRT FE2014-N	0.91	1.97	0.012	(0.004)	0.24	0.01	0.02	0.35	0.016	0.01
1	ECRM 056-2D	0.8181	0.5073	0.0103	0.0093	0.2006	0.0129	0.0218	0.0146	.	0.00024
1	SRM 1224	0.75	0.41	0.019	0.039	0.173	0.009	0.054	0.071	0.060	0.013
1	BS 54H	0.737	0.829	0.0030	0.0044	0.521	0.046	0.373	0.369	0.032	.	0.0036	(0.0001)	(0.0001)	0.0030	0.0106
1	VS RG28	0.70	0.84	0.031	.	1.161	0.050	0.154	0.135	0.066	0.090
1	VS RG28/1	0.68	0.91	0.031	0.0071	2.36	0.040	0.168	0.194	0.068	0.072	0.104
1	IARM 373A	0.63	0.70	0.0123	0.031	0.22	0.107	0.048	0.096	0.002	.	0.0046	0.0003	0.0005	0.005	0.0176
1	VS UG20/6	0.58	0.473	(0.008)	(0.02)	0.229	0.249	0.360	0.396
1	SS 435/1	0.52	0.41	0.033	0.031	0.54	.	0.060	0.14
1	SS 435/2	0.489	0.390	0.037	0.042	0.328	.	0.133	0.184	0.011	.
2	BS 56E	0.483	0.72	0.010	0.025	0.24	0.015	0.015	0.021	0.062	.	0.0035	.	(<0.0005)	0.005	0.005
1	IRSID 1636	0.47	0.78	0.029	0.037	0.40	0.135	0.092	(0.060)	(0.007)
1	SS 459/2	0.467	0.909	0.0482	0.0481	0.640	.	0.015	0.015	(0.013)	.	0.0110	.	.	0.0890	.
1	BS 1045	0.458	0.796	0.0069	0.023	0.215	0.190	0.060	0.108	(0.001)	.	0.0050	(0.0003)	0.0013	0.0056	0.0170
1	IARM 200D	0.453	0.749	0.0103	0.024	0.225	0.232	0.097	0.109	(0.004)	.	0.0050	.	.	0.007	0.0217
1	VS UG123	0.45	0.552	0.016	0.026	0.216	0.196	0.084	0.111	0.024
1	IRSID 1657	0.445	0.724	0.028	(0.013)	0.274	.	0.048	(0.022)	0.004	.	0.0051	.	.	.	(0.008)
1	NM 306	0.44	0.80	0.043	0.042	0.34	.	.	0.26
1	IRSID 1648	0.432	1.41	0.031	(0.070)	0.242	0.408	0.165	0.170	(0.004)	.	(0.038)	.	.	.	(0.028)
1	12X 10400A	0.420	0.754	0.0137	0.0305	0.220	0.140	0.0631	0.139	0.0323	.	0.0068	.	.	.	0.0169
1	NM EN-8	0.42	0.82	0.02	0.02	0.21
1	IRSID 1642	0.418	0.929	0.031	(0.031)	0.388	0.097	0.068	(0.035)	(0.020)	.	(0.042)	.	.	.	(0.009)
1	IRSID 1647	0.418	0.701	0.019	(0.027)	0.299	(0.104)	0.093	0.490	(0.060)	(0.0555)
1	IRSID 1646	0.414	0.701	0.020	0.027	0.293	0.104	0.093	0.493	0.056
1	IARM 210D	0.412	0.73	0.0052	0.030	0.230	0.273	0.122	0.096	(0.002)	.	0.0059	0.0004	0.0009	0.007	0.034
1	SS 434/1	0.41	1.49	0.050	0.027	0.31	.	0.044	0.055
1	IARM 349A	0.41	0.49	0.011	0.025	0.192	0.300	0.178	0.189	0.020	.	0.005	0.0003	0.0015	0.0085	0.059
1	BS 3941	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0019	.	0.0036	(0.0001)	0.0011	0.0042	0.0061
1	IRSID 1652	0.406	0.931	(0.017)	0.040	0.386	0.345	0.190	0.184	.	(0.0013)	0.038	.	.	.	(0.042)
1	IRSID 1637	0.401	0.940	0.030	0.030	0.378	0.097	0.068	(0.033)	0.022	.	0.042	.	.	.	(0.006)
1	SS 605/2	0.400	0.345	0.054	0.015	0.54	(0.06)	(0.05)	(0.06)	0.027	(0.008)	(0.01)
1	IRSID 1644	0.394	0.594	0.021	0.031	0.287	0.265	0.158	0.138	(0.017)
1	ECRM 084-1D	0.391	0.860	.	0.029	0.265	0.267	0.154	0.033
1	IRSID 1645	0.388	0.610	0.021	0.030	0.286	0.261	0.157	0.140	0.015	(0.0124)
1	IRSID 1649	0.384	0.930	0.045	(0.047)	0.250	0.418	0.226	0.321	0.004	.	0.037	.	.	.	0.043
1	SS 460/2	0.383	0.616	0.0374	0.0099	0.126	.	.	.	0.024	(0.019)	.	0.0027	.	0.0106	.
1	VS RG30	0.38	0.357	.	0.013	0.45	0.161	0.62	3.06	0.50	0.62
1	BS 1035	0.362	0.758	0.0100	0.028	0.246	0.241	0.123	0.151	0.0008	.	0.0051	(0.0002)	0.0017	0.0073	0.049
1	IRSID 1655	0.355	1.018	(0.018)	(0.060)	0.443	0.415	0.188	0.157	(0.004)	.	(0.036)	.	.	.	(0.043)
1	IRSID 1663	0.353	0.967	0.0090	0.034	0.235	0.180	0.148	0.206	0.037	.	0.028	.	.	.	0.042
1	VS UG90	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	0.0044	.	.	.	0.046
1	VS UG19/6	0.34	0.274	(0.03)	(0.03)	0.136	0.148	0.262	0.227
1	IARM 360A	0.331	0.733	0.008	0.023	0.260	0.235	0.078	0.113	0.0016	.	0.0060	0.0004	0.0017	0.0067	0.024
1	BS 1030	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0055	0.0003	0.0012	0.0069	0.0182
1	IARM 209D	0.322	0.68	0.0084	0.021	0.268	0.243	0.079	0.137	(0.003)	.	0.0060	0.0002	0.002	0.007	0.037
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	B	Ca	Co	Mo
1	IRSID 1653	0.312	0.962	0.034	(0.039)	0.400	0.453	0.218	0.358	<0.004	.	(0.039)	.	.	.	(0.038)
1	VS RG27	0.30	0.91	0.054	0.0032	0.42	0.188	0.135	1.53	0.88	0.071	0.222
1	SS 434/2	0.275	1.54	0.061	0.0141	0.51	.	0.037	0.238
1	IRSID 1654	0.270	0.979	0.036	(0.047)	0.354	0.441	0.241	0.328	.	.	0.040	.	.	.	(0.043)
1	IARM 359A	0.267	0.686	0.0094	0.020	0.233	0.186	0.068	0.121	0.002	.	0.0073	0.0003	0.0013	0.0069	0.023
1	BS 1026	0.260	0.715	0.0171	0.0191	0.268	0.247	0.096	0.163	0.0330	.	0.0100	(0.0002)	0.0017	0.0072	0.0289
1	VS UG94	0.26	0.186	0.0037	0.0026	0.101	0.088	0.178	0.206	0.017	0.0005
1	VS UG18/6	0.242	0.213	(0.003)	(0.003)	0.20	0.063	0.273	0.237
2	HRT FE2016-N	0.23	0.85	0.015	0.011	0.32	0.02	0.15	0.21	0.033
1	BS 1020	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0074	(0.0001)	0.0022	0.0070	0.018
1	IARM 213C	0.201	0.922	0.007	0.025	0.25	0.149	0.068	0.099	0.0019	.	0.0058	0.0003	0.0014	0.0074	0.022
1	IRSID 1664	0.2008	0.472	0.0106	0.0259	0.0616	0.0820	0.0547	0.0707	.	0.0193	0.0115	(0.0002)	(0.0005)	(0.0084)	0.0157
1	VS RG25/1	0.196	0.29	0.019	0.0088	0.100	0.065	0.037	0.060	0.067	0.012	0.010
1	BS 1018	0.195	0.79	0.012	0.024	0.237	0.130	0.104	0.177	0.029	.	0.0041	(0.0002)	(0.0004)	0.0058	0.044
1	BS LF2B	0.176	1.05	0.007	0.0067	0.209	0.318	0.115	0.138	0.0287	.	0.0052	(0.0002)	0.0010	0.0071	0.0382
1	IARM 28K	0.174	0.80	0.012	0.027	0.291	0.171	0.0638	0.107	(0.0025)	.	(0.005)	0.0005	.	0.0060	0.0210
1	BS 1016	0.172	0.77	0.011	0.030	0.193	0.153	0.107	0.091	0.0200	.	0.0066	(0.0003)	(0.0004)	0.0193	0.040
1	12X 10180C	0.171	0.803	0.0150	0.0200	0.147	0.0500	0.0284	0.0793	0.198	.	0.0029	.	.	.	0.047
1	12X 10180B	0.169	0.722	0.0101	0.0056	0.114	0.0544	0.0333	0.0451	0.043	.	0.0059	.	.	.	0.062
2	TL 1000	0.1692	1.4281	0.0142	0.0164	0.2258	0.0120	0.0312	0.0635	0.0226	.	(0.0016)	0.00018	0.00039	0.0042	0.0076
1	VS RG25	0.167	0.131	0.014	.	0.084	.	0.046	0.057	0.015	0.0028
1	VS UG124	0.165	1.41	0.019	0.032	0.384	0.020	0.015	0.035	0.039
1	VS UG109	0.161	0.353	0.020	0.0037	0.151	0.082	0.0053	0.048	0.0093
1	IARM 213D	0.158	0.725	0.0120	0.031	0.226	0.207	0.076	0.093	(0.003)	.	(0.006)	(0.0004)	.	0.009	0.0131
1	SS 456/2	0.112	0.220	0.0212	0.0221	0.297	.	.	.	0.0017	(0.0013)	.	0.0015	.	0.0504	.
1	DSZU C041	0.107	1.35	0.0126	0.0055	0.63	0.059	0.040	0.067	0.017	.	0.0033	(0.0004)	0.0024	0.003	0.005
1	SS 432/1	0.102	1.34	0.024	0.039	0.043	.	0.14	0.31
1	VS UG93	0.100	0.140	0.0033	0.0024	0.48	0.028	0.126	0.137	0.15	0.0008
1	VS UG17/6	0.097	0.106	(0.003)	(0.004)	0.37	(0.02)	0.105	0.127
1	SS 433/2	0.096	1.188	0.011	0.0083	0.007	.	0.037	0.026
1	IRSID 1661	0.086	1.48	0.018	(0.006)	0.406	(0.013)	(0.029)								

CARBON STEEL													CONTINUED FROM THE PREVIOUS PAGE												
Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units													
IRSID 1660	37 mm Ø x 30 mm													
ECRM 090-1D	0.0146	0.00043	.	0.00239	0.00090	.	.	0.204	.	0.00209	.	44 mm Ø x 25 or 30 mm													
SRM 1227	0.002	.	.	.	32 mm Ø x 19 mm													
SS 602/2	(0.001)	.	.	(<0.005)	44 mm Ø x 19 mm													
BS 64C	0.0084	(<0.003)	.	.	.	(0.001)	(0.002)	0.005	.	.	.	44 mm Ø x ~7 or 19+ mm													
HRT FE2014-N	0.0052	0.066	.	.	.	~35mm Ø x 20 mm													
ECRM 056-2D	44 mm Ø x 25 or 30 mm													
SRM 1224	0.002	.	.	.	32 mm Ø x 19 mm													
BS 54H	0.0039	(0.0003)	(0.001)	(0.001)	(0.001)	0.0030	0.0009	0.0008	(0.003)	Fe:97.0	(0.0008)	44 mm Ø x 19+ mm 17025													
VS RG28	.	0.029	0.0041	0.022	0.006	.	.	~45 mm Ø x ~28mm													
VS RG28/1	.	0.041	0.022	0.035	0.0041	.	.	~45 mm Ø x ~28mm													
IARM 373A	0.0088	0.001	0.002	(0.001)	(0.002)	0.0069	0.0017	0.023	(0.002)	(0.003)	(0.003)	31 mm Ø x 2 or 18 mm													
VS UG20/6	~45 mm Ø x ~28 mm													
SS 435/1	.	0.039	38 mm Ø x 19 mm													
SS 435/2	.	0.134	38 mm Ø x 19 mm													
BS 56E	0.0056	(<0.002)	.	(0.0001)	0.0004	(0.0006)	(0.001)	(<0.002)	.	.	.	44 mm Ø x ~7 or 19+ mm													
IRSID 1636	48 mm Ø x 30 mm													
SS 459/2	.	0.0102	.	0.0044	0.0121	.	.	0.0585	.	.	(0.074)	38 mm Ø x 19 mm													
BS 1045	0.0113	0.026	0.0040	(0.0005)	0.0017	0.0084	0.0011	(0.002)	(0.0007)	Fe:98.1	(0.0009)	38 mm Ø x ~7 or 19+ mm 17025													
IARM 200D	0.009	0.0010	.	.	.	0.0079	(0.0013)	0.0244	(0.003)	.	.	31 mm Ø x 2 or 18 mm													
VS UG123	0.0078	0.0019	.	.	.	~45 mm Ø x ~28mm													
IRSID 1657	(0.001)	.	.	.	42 mm Ø x 30 mm													
NM 306	40 mm Ø x 25 mm													
IRSID 1648	0.033	40 mm Ø x 28 mm													
12X 10400A	0.0133	0.0127	.	.	.	0.0033	.	~40 mm Ø x ~15 mm													
NM EN-8	40 mm Ø x 20 mm													
IRSID 1642	(0.002)	.	.	.	45 mm Ø x 30 mm													
IRSID 1647	41 mm Ø x 30 mm													
IRSID 1646	42 mm Ø x 30 mm													
IARM 210D	0.011	0.001	0.0034	0.001	0.002	0.010	0.0104	0.024	(0.002)	.	(0.001)	31 mm Ø x 2 or 18 mm													
SS 434/1	.	0.078	38 mm Ø x 19 mm													
IARM 349A	0.0100	0.0012	0.003	(0.001)	(0.003)	0.015	0.0013	0.027	0.004	(0.003)	(0.002)	31 mm Ø x 2 or 18 mm													
BS 3941	0.0069	0.033	0.0055	0.0010	0.0005	0.0019	0.0017	0.0025	(0.0004)	.	(0.0003)	41 mm Ø x ~7 or 19+ mm 17025													
IRSID 1652	0.030	45 mm Ø x 30 mm													
IRSID 1637	(0.002)	.	.	.	45 mm Ø x 30 mm													
SS 605/2	(0.001)	.	44 mm Ø x 19 mm													
IRSID 1644	(0.12)	45 mm Ø x 30 mm													
ECRM 084-1D	0.023	38 mm Ø x 25 or 30 mm													
IRSID 1645	45 mm Ø x 30 mm last													
IRSID 1649	0.028	40 mm Ø x 28 mm													
SS 460/2	.	0.068	.	0.0005	(0.0006)	.	.	0.0322	.	.	(<0.0005)	38 mm Ø x 19 mm													
VS RG30	.	0.139	0.63	0.91	.	.	~45 mm Ø x ~28mm													
BS 1035	0.0105	(0.001)	0.0036	(0.001)	(0.002)	0.0027	0.0007	0.026	0.0020	Fe:97.9	(0.0009)	40 mm Ø x ~7 or 19+ mm 17025													
IRSID 1655	0.046	40 mm Ø x 34 mm													
IRSID 1663	0.0143	0.051	44 mm Ø x 30 mm													
VS UG90	0.015	.	.	.	0.0011	.	0.039	~47 mm Ø x ~30 mm													
VS UG19/6	~45 mm Ø x ~28 mm													
IARM 360A	0.0102	0.0015	0.004	(0.001)	0.0023	0.010	0.0010	0.039	(0.001)	(0.003)	(0.001)	31 mm Ø x 2 or 18 mm													
BS 1030	0.0107	(0.0004)	0.005	0.0005	0.0024	0.0114	0.0005	0.031	0.0012	.	(0.0002)	38 mm Ø x ~7 or 19+ mm 17025													
IARM 209D	0.0107	0.0014	0.005	0.001	0.004	0.012	0.0011	0.042	(0.002)	(0.003)	.	31 mm Ø x 2 or 18 mm													
Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units													
IRSID 1653	0.066	40 mm Ø x 34 mm													
VS RG27	0.064	0.170	.	.	~45 mm Ø x ~28mm													
SS 434/2	0.0104	0.038	38 mm Ø x 19 mm													
IRSID 1654	0.030	40 mm Ø x 34 mm													
IARM 359A	0.0094	0.002	0.0044	(0.001)	(0.002)	0.0100	0.0009	0.027	(0.001)	.	(0.001)	31 mm Ø x 2 or 18 mm													
BS 1026	0.0083	(0.0004)	0.0031	(0.0002)	0.0019	0.0112	(0.0004)	0.0016	0.0021	.	(0.0002)	38 mm Ø x ~7 or 19+ mm 17025													
VS UG94	0.053	(0.001)	.	.	.	~40 mm Ø x ~28 mm													
VS UG18/6	~45 mm Ø x ~28 mm													
HRT FE2016-N	0.0055	35 mm Ø x 20 mm													
BS 1020	0.0109	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	0.0363	(0.0004)	.	(0.0005)	44 mm Ø x ~7 or 19+ mm 17025													
IARM 213C	0.0116	0.0011	0.0042	0.0011	0.002	0.0081	0.0010	0.035	(0.002)	(0.006)	(0.0004)	31 mm Ø x 2 mm													
IRSID 1664	0.0072	(0.0002)	.	0.0002	0.0012	0.0108	0.0013	(0.0005)	<0.002	(0.0007)	(0.0001)	37 mm Ø x 30 mm													
VS RG25/1	.	0.016	0.055	0.0110	.	.	.	~45 mm Ø x ~28mm													
BS 1018	0.0079	(0.0006)	0.0014	(0.0006)	(0.001)	0.0099	0.0009	0.0009	0.0014	Fe:98.2	(0.001)	38 mm Ø x ~7 or 19+ mm 17025													
BS 1F2B	0.0078	(0.0003)	0.0024	(0.0001)	0.0018	0.0092	0.0009	0.0300	0.0027	17025	Fe:97.9	38 mm Ø x ~7 or 19+ mm													
IARM 28K	(0.008)	0.0017	(0.005)	.	.	0.0075	(0.0015)	(0.0014)	.	.	.	31 mm Ø x 2 or 18 mm													
BS 1016	0.0113	(0.0009)	(0.003)	(0.004)	Fe:98.4	0.013	0.0010	0.0011	(0.0013)	17025	(0.001)	Hexagon ~60 mm Ø x 19+ mm													
12X 10180C	0.0052	0.0024	.	.	.	0.0005	.	~40 mm Ø x ~15 mm													
12X 10180B	0.0071	0.0065	.	.	.	0.0079	.	~40 mm Ø x ~15 mm													
TL 1000	(0.0093)	0.0293	.	Mg: (0.00005)	.	(0.00106)	0.0011	(0.0033)	(0.0002)	.	.	36 mm Ø x 20 mm													
VS RG25	0.039	~45 mm Ø x ~28mm													
VS UG124	0.0072	0.0043	.	.	.	~45 mm Ø x ~28mm													
VS UG109	0.071	~45 mm Ø x ~25 mm													
IARM 213D	(0.008)	(0.0012)	(0.01)	.	(0.0032)	0.0147	0.0011	0.0010	(0.003)	(0.002)	(0.0015)	31 mm Ø x 2 or 18 mm													
SS 456/2	.	0.0057	.	0.0189	0.0172	.	.	0.0221	.	.	(0.014)	38 mm Ø x 19 mm													
DSZU C041	0.0046	0.0017	.	.	.	0.0038	0.0019	0.003	(0.003)	.	.	40 mm Ø x 25 mm													
SS 432/1	.	<0.002	38 mm Ø x 19 mm													
VS UG93	0.075	0.0008	.	.	.	~40 mm Ø x ~28 mm													
VS UG17/6	~45 mm Ø x ~28 mm													
SS 433/2	.	0.059	38 mm Ø x 19 mm													
IRSID 1661	(0.0005)	(0.0085)	40 mm x 42 mm x 30 mm													
VS UG125	0.0112	0.035	.	.	.	~45 mm Ø x ~28mm													
VS UG108	0.071	.	0.074	.	.	~45 mm Ø x ~25 mm													
SRM 1228	<0.001	.	.	.	32 mm Ø x 19 mm													
ECRM 057-2D	0.0023	38 mm Ø x 25 or 30 mm													
NM 305	40 mm Ø x 20 mm													
ECRM 083-2D	0.00157	0.00439	.	39 mm Ø x 28 mm													
DSZU C03	.	(0.002)	.	(0.009)	(0.003)	0.011	0.002	0.004	(0.009)	(0.0037)	(0.0006)	40 mm Ø x 30 mm													
VS RG26	0.121	.	.	0.0052	.	~45 mm Ø x ~28mm													
SS 431/2	0.0052	0.0040	38 mm Ø x 19 mm													
VS UG2/11	(0.007)	~45 mm Ø x ~28 mm													
RM Fe 1/5	0.002	<0.005	.	<0.002	.	0.0008	<0.0005	<0.0005	0.002	.	<0.005	40 mm Ø x 40 mm													
VS UG2/5	.	(0.002)	(0.01)	0.005	(0.02)	.	.	~45 mm Ø x ~28 mm													
BS 1005	0.0044	0.0008	0.0058	(0.0003)	(0.0007)	0.0009	0.0010	(0.0007)	(0.0003)	Fe:99.6	(0.0008)	38 mm Ø x ~7 or 19+ mm 17025													
BS 1009	0.0043	(0.0008)	0.0060	(0.0004)	(0.0009)	0.0007	0.0007	(0.0006)	(0.001)	Fe:99.6	(0.0006)	38 mm Ø x ~7 or 19+ mm 17025													
SS 111/1	0.0025	0.0006	0.0004	0.0002	.	.	.	44 mm Ø x 19 mm													
VS 005	0.0021	0.0047	~45 mm Ø x ~25 mm													
VS UG2/10	(0.006)	0.0017	0.0070	~45 mm Ø x ~28 mm last													
SS 432/2	0.0066	0.0174	38 mm Ø x 19 mm													
VS 003	0.0020	0.0063	~45 mm Ø x ~25 mm													
CZ LA-1B	0.003	(0.001)	.	(0.0007)	(0.002)	(0.001)	(0.001)	0.004	0.010	.	(0.002)	~37 mm Ø x 25 mm													
IMZ 110A	0.0037</																								

ARSENIC AND ANTIMONY IN STEEL

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	As	Sb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Sn	Ti
2	CZ CM-2B	0.12	0.020	0.247	0.894	0.082	0.0114	1.95	0.99	1.20	1.53	0.046	.	0.45	0.33	0.091	0.342
1	12X 12749X	0.081	.	0.176	1.41	0.023	0.066	0.48	0.253	0.47	0.453	0.202	.	0.426	0.195	0.018	0.0178
1	12X 120	0.065	0.031	0.60	0.40	(0.049)	0.026	0.34	0.10	0.085	0.20	0.033	.	.	.	0.008	.
1	12X 15266V	0.0640	.	0.455	1.240	0.0344	0.0258	0.674	0.226	1.317	3.49	0.526	.	0.286	0.298	0.0082	.
1	12X 350C	0.057	.	0.159	0.758	0.0296	0.040	0.467	0.196	0.160	0.335	0.290	.	0.030	0.147	0.0382	0.076
1	IRSID 1656	0.055	.	0.477	0.730	0.027	0.013	0.277	.	(0.048)	(0.017)	(0.002)	.	.	(0.007)	.	.
1	12X 355C	0.0331	0.0796	0.159	0.508	0.0214	0.0241	0.494	0.657	0.0710	0.113	0.1104	.	0.0495	0.1010	0.0564	0.153
1	12X 354B	0.023	.	0.252	5.03	0.0478	0.0105	0.200	0.0679	0.082	0.0487	0.0150	.	0.0237	0.0328	0.0154	0.0248
1	BS 1762	0.025	(0.02)	0.363	2.04	0.032	0.037	0.38	0.133	1.16	0.929	0.049	.	0.064	0.347	0.079	0.096
1	ECRM 055-2D	0.0187	0.00376	0.5199	0.687	0.0102	0.0205	0.3094	0.2089	0.3121	0.3217	.	.	0.0257	0.0960	0.0162	0.00104
1	12X 357D	0.0127	0.018	0.312	0.219	0.0101	0.066	0.211	0.203	0.188	0.21	0.138	.	0.198	0.025	0.0145	0.074
1	BS 1030	0.0055	0.0024	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0069	0.0182	0.0114	0.0005
1	VS UG90	0.0044	0.0011	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	.	0.046	.	0.039
1	VS UG89	0.0043	0.0011	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	0.420	0.01	0.007	.	0.044	.	0.012
1	VS UG92	0.0027	0.0005	0.69	0.79	0.05	0.0029	1.98	0.111	0.155	0.200	0.091	0.08	.	0.119	.	0.022
1	IRSID 1670	0.0018	.	0.0011	0.3981	0.0128	0.0075	0.0046	0.0134	0.0142	0.0174	0.0479	.	0.0018	0.0009	0.0017	0.0078
1	VS UG88	0.0007	0.0003	0.62	1.26	0.0026	0.0043	1.22	0.171	0.52	0.474	0.01	0.009	.	0.104	.	0.107
1	VS UG91	0.0004	0.00009	0.49	.	0.0038	0.0021	2.23	0.057	0.039	0.064	0.048	0.048	.	0.058	.	0.038
1	SS 458/2	.	0.089	0.198	0.479	0.0281	0.0314	0.504	.	.	.	0.055	0.053	0.198	.	.	.
1	SS 457/2	.	0.050	0.307	0.327	0.0098	0.0448	0.105	.	.	.	0.088	0.084	0.0217	.	.	.

Number	B	Bi	Ca*	Ce*	Mg*	N	Nb	O*	Pb	Se	Ta	V	W	Zn	Zr	Units
CZ CM-2B	0.0010	0.0062	(0.58)	.	0.087	.	.	0.109	0.22	.	0.013	~39 mm Ø x ~25 mm
12X 12749X	0.016	.	.	0.068	0.036	.	.	~40 mm Ø x ~15 mm
12X 120	0.0115	.	.	0.077	40 mm Ø x 40 mm
12X 15266V	1.438	.	.	.	0.116	0.106	.	.	.	~40 mm Ø x ~15 mm
12X 350C	0.0115	0.260	.	.	~40 mm Ø x ~15 mm
IRSID 1656	(0.002)	.	.	.	40 mm Ø x 35 mm
12X 355C	(0.0012)	0.0023	0.023	.	.	0.0395	.	0.1265	0.037	.	0.0192	~40 mm Ø x ~15 mm
12X 354B	0.0027	0.0802	0.0204	0.0248	.	.	~40 mm Ø x ~15 mm
BS 1762	0.0048	.	(20)	.	(3)	0.017	0.074	64	(0.011)	Fe:93.9	(0.03)	0.193	0.029	(0.01)	(0.01)	37 mm Ø x 25 mm 17025
ECRM 055-2D	0.01069	0.00245	0.0166	.	.	38 mm Ø x 25 or 30 mm
12X 357D	0.0036	0.0024	.	.	.	0.011	.	.	0.040	0.0057	.	0.127	0.0213	.	0.0049	~40 mm Ø x ~15 mm
BS 1030	0.0003	.	12	.	(2)	0.0107	(0.0004)	50	0.0005	.	(0.001)	0.031	0.0012	.	(0.0002)	38 mm Ø x ~7 or 19+ mm 17025
VS UG90	0.015	~47 mm Ø x ~30 mm
VS UG89	0.017	0.0043	.	0.0003	.	.	0.021	.	.	.	~47 mm Ø x ~30 mm
VS UG92	0.016	0.034	.	0.00017	.	.	0.024	.	.	.	~47 mm Ø x ~30 mm
IRSID 1670	0.0007	.	.	(2)	.	0.0016	(0.0003)	(0.0005)	.	.	.	37 mm Ø x 30 mm
VS UG88	0.020	0.059	.	0.00015	.	.	0.117	.	.	.	~47 mm Ø x ~30 mm
VS UG91	0.010	0.097	.	0.00006	.	.	0.049	.	.	.	~47 mm Ø x ~30 mm
SS 458/2	0.0069	0.0510	.	0.0140	.	.	0.105	.	.	(0.064)	38 mm Ø x 19 mm
SS 457/2	0.0046	0.0174	.	0.0098	.	.	0.153	.	.	0.025	38 mm Ø x 19 mm

BISMUTH AND SELENIUM STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Bi	Se	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N
2	BS 4140A	0.105	.	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.016	0.005	0.010	0.16	0.0098
2	BS 53MOD	0.102	.	1.01	0.36	0.011	0.012	0.26	0.070	0.072	1.37	0.019	0.004	0.007	0.024	0.0086
2	BS 4140B	0.087	.	0.43	0.76	0.027	0.037	0.20	0.006	0.012	0.84	0.036	(0.002)	0.005	0.16	0.0064
2	BS 4150MOD	0.070	.	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	0.005	0.012	0.21	0.0087
2	CZ CM-16A	0.039	.	0.355	0.92	0.043	0.033	0.77	0.293	0.72	0.70	0.125	0.058	0.056	0.405	0.015
Number	B	Ca	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units			
BS 4140A	.	(0.0003)	.	(0.0025)	(0.001)	.	0.011	(0.003)	0.004	.	.	last	38 mm Ø x ~7 or ~12 mm			
BS 53MOD	.	(0.001)	.	(0.002)	0.0005	.	0.008	.	0.005	.	.	.	38 mm Ø x ~7 or 19+ mm			
BS 4140B	.	(0.0002)	.	(0.002)	0.004	.	(0.002)	0.003	0.005	.	.	.	38 mm Ø x ~7 or 19+ mm			
BS 4150MOD	.	0.0010	.	(0.003)	0.0010	.	0.013	(0.002)	0.008	.	.	last	38 mm Ø x ~7 mm			
CZ CM-16A	0.012	0.0006	0.066	.	0.053	0.027	0.025	0.099	0.319	0.141	0.021	0.062	~39 mm Ø x 25 mm			

CALCIUM IN STEEL

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Ca	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	V
1	BS HiCal-1	0.0140	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0024	0.379	.	0.0027
1	SS 115	0.0058	0.6224	0.682	0.0123	0.00093	0.2078	.	0.0196	0.0198	0.0527	.	.	.	0.0067	.
1	BS 9325A	0.0039	0.203	0.969	0.0079	0.0045	0.612	0.163	3.29	1.50	0.0056	.	0.0093	0.358	0.0076	(0.0024)
1	SS 116	0.0036	0.617	0.6756	0.0092	0.00176	0.201	.	0.0155	0.0141	0.0587	.	.	.	0.0069	.
1	BS XCCS-1	0.0024	0.0441	0.356	0.0068	0.0022	0.292	0.0143	0.0132	0.0288	0.061	.	0.0017	0.0060	0.0052	0.0012
1	BS 1020	0.0022	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0070	0.018	0.0109	0.0363
2	HRT FE2009-N	0.0020	0.12	0.55	0.010	0.003	0.32	0.08	0.25	2.56	0.030	.	.	1.02	.	0.015
1	IRSID 1665	0.0017	0.1209	0.446	0.0104	0.0135	0.187	0.0469	0.0308	0.0363	.	0.0379	0.0046	0.0047	0.0049	(0.0006)
1	BS 3941	0.0011	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0019	.	0.0042	0.0061	0.0069	0.0025
2	BS 4150MOD	0.0010	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	.	0.012	0.21	0.0087	0.008
2	BS 4330V	0.0010	0.318	0.91	0.008	0.0009	0.240	0.181	1.91	0.91	0.021	.	0.011	0.475	0.0076	0.094
1	BS 4130	0.0007	0.303	0.541	0.0105	0.0113	0.245	0.221	0.088	0.924	0.0242	.	0.0065	0.168	0.0072	0.0037
2	BS 4942	0.0006	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	(0.004)	.	0.010	0.54	0.0080	0.28
1	BS PP20	0.0003	0.382	1.41	0.018	0.0070	0.262	0.119	1.00	1.94	0.0132	.	0.0145	0.212	0.0080	0.066
1	IMZ 111	0.0003	0.106	0.31	0.010	0.039	0.55	0.036	0.23	0.072	0.017	0.007	.	0.084	0.0133	0.022
2	TL 1669	0.00017	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.03553 (tot)	.	0.0019	0.0011	0.0024	(0.0006)

Number	As	B	Bi	Nb	O	Pb	Sb	Sn	Ti	W	Zr	Other			
BS HiCal-1	0.0022	(0.0001)	.	(0.002)	.	(0.0005)	.	(0.0002)	0.0037	(0.0009)	(0.0008)	~38 mm Ø x ~30 mm	17025		
SS 115	0.0027	.	.	38 mm Ø x 19 mm			
BS 9325A	0.0024	(0.0001)	.	0.0017	.	(0.0003)	Fe: 92.8	(0.0003)	0.0030	0.024	(0.001)	~40 mm Ø x ~30 mm	17025		
SS 116	0.00012	.	.	0.00171	.	.	44 mm Ø x 19 mm			
BS XCCS-1	0.0024	(0.0004)	.	(0.001)	Fe: 99.2	(0.0006)	(0.0005)	0.0002	0.0015	(0.003)	0.0006	~40 mm Ø x ~30 mm	17025 Fe: 99.2		
BS 1020	0.0074	(0.0001)	.	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	(0.0004)	(0.0005)	44 mm Ø x ~7 or 19+ mm	17025		
HRT FE2009-N	Zn: 0.004	40 mm Ø x 40 mm			
IRSID 1665	0.0067	(0.00032)	.	.	.	(0.0014)	(0.0008)	0.0031	(0.0008)	.	.	37 mm Ø x 30 mm			
BS 3941	0.0036	(0.0001)	.	0.033	0.0055	0.0010	0.0005	0.0019	0.0017	(0.0004)	(0.0003)	41 mm Ø x ~7 or 19+ mm	17025		
BS 4150MOD	0.005	.	0.070	.	(0.003)	0.0010	.	0.013	(0.002)	.	.	38 mm Ø x ~7 or 19 mm last			
BS 4330V	0.0018	.	.	0.010	.	.	.	37 mm Ø x ~7 mm last			
BS 4130	0.0048	(0.0002)	.	0.0015	0.0015	(0.00003)	(0.0021)	0.0099	0.0009	0.0011	Mg: 0.0002	38 mm Ø x ~7 or 19+ mm	17025		
BS 4942	0.005	.	.	.	(0.0021)	.	.	0.014	.	.	.	38 mm Ø x ~7 or 19+ mm last			
BS PP20	0.0049	0.00011	.	0.0048	(0.0010)	.	0.0013	0.0069	0.0007	0.0058	.	38 mm Ø x ~7 or 19+ mm	17025		
IMZ 111	40 mm Ø x 40 mm			
TL 1669	0.0017	0.00038	.	0.00046	.	0.00013	0.00049	0.0071	0.0504	.	(0.00021)	38 mm Ø x 25 mm	Zn: 2.7*		

CRM AL, Ca, AND N IN LOW ALLOY STEEL

Number	Al	Ca	N	Units
IMZ 133	.	.	0.0360	40 mm Ø x 40 mm
IMZ 131	0.0043	.	0.0333	40 mm Ø x 40 mm
IMZ 135	0.0274	0.0008	0.0238	40 mm Ø x 40 mm
IMZ 169	0.075	.	0.0193	40 mm Ø x 40 mm
IMZ 141	0.0071	.	0.0154	40 mm Ø x 40 mm
IMZ 130	0.0046	0.0024	0.0153	40 mm Ø x 40 mm
IMZ 139	(0.029)	0.0031	0.0113	40 mm Ø x 40 mm
IMZ 132	0.0021	0.0002	0.0097	40 mm Ø x 40 mm
IMZ 137	0.0017	0.00025	0.0083	40 mm Ø x 40 mm
IMZ 140	0.0307	0.0015	0.0083	40 mm Ø x 40 mm
IMZ 138	0.0022	.	0.0063	40 mm Ø x 40 mm
IMZ 134	0.0124	0.0005	.	40 mm Ø x 40 mm
IMZ 136	0.0034	0.00031	.	40 mm Ø x 40 mm

C-Mo and Cr-Mo STEEL XRF SET

= class, where 1 = CRM ISO 17025 and 2 = RM, Set Part Number: BS MOLY-5 AVAILABLE INDIVIDUALLY ~7 mm discs

#	Grade	Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Sn	V
2	C-.5Mo	4419	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.519	0.048	.	(0.0005)	.	.
1	1.25Cr-.5Mo	F-11	BS 45B	0.140	0.502	0.0068	0.017	0.583	0.101	0.136	1.14	0.60	0.030	0.0090	0.0066	0.0069	0.0083
1	2.25Cr-1Mo	F-22	BS 46B	0.126	0.472	0.0087	0.0187	0.219	0.128	0.081	2.28	1.00	0.020	0.0074	0.0100	0.0073	0.0073
2	5Cr-.5Mo	F-5	BS 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.47	0.015	0.011	0.018	0.008	0.016
1	9Cr-1Mo	F-9	BS 48B	0.110	0.365	0.0228	0.0068	0.75	0.070	0.165	8.78	0.949	0.0157	0.0165	0.0088	0.0049	0.033

CRM EPMA SETS

available in sets only, as grouped 4x10x15mm

Number	Cr	Number	Ni
NMIJ 1001-a	5.00	NMIJ 1006-a	5.04
NMIJ 1002-a	14.96	NMIJ 1007-a	10.05
NMIJ 1003-a	19.87	NMIJ 1008-a	20.02
NMIJ 1004-a	29.84	NMIJ 1009-a	39.92
NMIJ 1005-a	39.69	NMIJ 1010-a	60.07

Cr-Mo STEEL (Cr > 1, Mo > 0.1)

= Class, where 1 = CRM and 2 = RM * Provisional Analysis

#	Number	Cr	Mo	C	Mn	P	S	Si	Cu	Ni	Al	As	Co	N	Sn	V
1	BS 48B	8.78	0.949	0.110	0.36	0.0228	0.0068	0.75	0.070	0.165	0.0157	0.0048	0.0165	0.0088	0.0049	0.033
1	BS 9905A	8.75	0.95	0.113	0.465	0.0133	0.0040	0.34	0.091	0.152	0.0186	0.0065	0.0136	0.034	0.0060	0.216
1	13X 90901A	8.43	0.905	0.102	0.447	0.0148	0.0009	0.429	0.039	0.249	0.021	0.0021	0.0472	0.0020	0.208	0.208
1	BS H-13	5.14	1.24	0.402	0.386	0.0103	0.0202	0.99	0.197	0.109	0.0152	0.0066	0.0092	0.0108	0.0093	0.98
2	HRT FE2012-H	5.13	2.78	0.37	0.41	0.019	0.002	0.42	0.07	0.20						0.42
1	BS H-13A	5.11	1.32	0.391	0.445	0.0187	(0.003)	1.13	0.083	0.139	(0.03)	0.0050	0.033	0.034	(0.005)	0.92
2	BS 47B	4.78	0.45	0.122	0.39	0.014	0.022	0.22	0.12	0.105	0.018	0.004	0.015	0.023	0.006	0.004
1	IARM 37C	4.34	0.500	0.096	0.408	0.014	(0.004)	0.31	0.121	0.148	(0.010)	0.009	0.015	0.008	0.009	0.017
2	BS 47A	4.22	0.47	0.130	0.44	0.017	0.015	0.27	0.11	0.12	0.015		0.011	0.018	0.008	0.016
1	12X 40CDV12A	3.29	0.946	0.401	0.604	0.0060	0.0013	0.250	0.0978	0.1062	0.0208	0.0040	0.0197	0.0155	0.0049	0.198
1	SRM 1772	3.10	1.39	0.477	0.61	0.008	0.0031	0.264	0.083	0.105						0.236
1	SS 407/2	3.03	0.83	0.490	0.195	0.038	0.0105	0.66	0.397	0.527	0.040		0.0068	(0.011)		0.19
1	IMZ 160	2.64	0.98	0.077	0.38	0.023	0.004	0.34	0.42	0.30	0.031					0.10
1	IMZ 159	2.64	0.98	0.075	0.39	0.022	0.005	0.33	0.41	0.31	0.024					0.10
2	HRT FE2009-N	2.56	1.02	0.12	0.55	0.010	0.003	0.32	0.08	0.25	0.030					0.015
1	IARM 36C	2.43	0.98	0.14	0.49	0.009	0.014	0.25	0.142	0.085	(0.017)	(0.005)	(0.008)	0.008	(0.008)	0.0061
1	IARM 196A	2.35	0.129	1.08	2.40	0.040	0.014	0.35	0.25	0.61	0.015	0.025	0.013	0.0084	0.033	0.157
1	SRM 1270	2.34	0.956	0.077	0.626	0.0065	0.0065	0.247	0.114	0.174			0.038			0.013
1	BS 46B	2.28	1.00	0.126	0.472	0.0087	0.0187	0.219	0.128	0.081	0.020	0.0041	0.0074	0.0100	0.0073	0.0073
1	IMZ 169	2.20	1.03	0.099	0.54	0.015	0.0155	0.35	0.128	0.073	0.075		0.012	0.0193	0.062	(0.016)
1	ECRM 190-1D	2.18	0.410	0.395	1.28	0.0112	0.0044	0.278		0.934			0.034			
1	SRM 1139a	2.1	0.51	0.79	0.92	0.012	0.013	0.80	0.47	0.98						0.26
1	BS PP20	1.94	0.212	0.382	1.41	0.018	0.0070	0.262	0.119	1.00	0.0132	0.0049	0.0145	0.0080	0.0069	0.066
1	BS 55G *	1.8	0.42	0.38	0.85	0.011	0.003	0.57	0.11	0.13	0.012	0.006	0.009	0.008	0.008	0.006
1	IRSID 1749	1.734	0.257	0.411	0.733	0.0104	0.0157	0.193	0.188	0.190	1.034	0.0134	0.0141	0.0066	0.0148	(0.0036)
1	ECRM 129-3D	1.702	0.206	0.3684	0.371	0.0110	0.0165	0.2087	0.0804	1.022	1.016	0.0049	0.0148	0.0046	0.0067	
1	TL 1100	1.664	0.3349	0.3487	0.6284	0.0124	0.0049	0.2839	0.1767	3.727	0.0374		0.0283	0.0116	0.0083	
1	ECRM 195-1D	1.56	0.77	0.757	0.571	0.017	0.012	0.467	0.036	0.33				0.010		0.31
1	SRM 1286	1.53	0.344	0.196	0.152	0.008	0.017	0.130	0.043	2.81	0.109	0.019	0.116		0.012	0.0057
2	BS 68B	1.51	0.309	0.39	0.52	0.010	0.020	0.26	0.163	0.165	1.08		0.010	0.0073	0.010	0.007
1	BS 68E	1.49	0.322	0.406	0.560	0.005	0.0004	0.296	0.134	0.147	1.09	(0.003)	0.007	0.0030	0.0097	0.0010
1	12X 24065A	1.412	0.1716	0.370	0.502	0.0129	0.0044	0.218	0.216	0.271	1.035	0.0074	0.013	0.0076	0.0120	0.0040
2	BS 58E	1.40	0.110	0.100	0.63	0.009	0.002	0.29	0.154	3.22	0.029	0.003	0.013	0.0033	0.003	0.006
1	12X 15CDV6A	1.397	0.875	0.171	0.839	0.0056	0.0086	0.152	0.0231	0.044	0.019	0.0041	0.0070	0.0069	0.0011	0.242
1	IARM 35L	1.35	0.607	0.119	0.535	0.007	0.014	0.679	0.123	0.071	0.017	0.0045	0.0070	0.0072	0.0088	0.0037
1	SS 112	1.236	0.190	0.394	0.436	0.0043	0.0026	0.289	0.149	1.461	0.0148	0.0021	0.0175	0.0024	0.0086	
1	12X 43400A	1.181	0.223	0.422	0.592	0.0164	0.0284	0.259	0.177	1.378	0.013	0.0084	0.0090	0.0089	0.007	
1	BS 45B	1.14	0.60	0.140	0.502	0.0068	0.017	0.583	0.101	0.136	0.030	0.0066	0.0090	0.0066	0.0069	0.0083
1	IRSID 1745	1.130	0.222	0.295	0.850	0.0077	0.081	0.220	0.202	0.188	0.0202	0.0262		0.0134	(0.004)	
1	12X 11572A	1.107	0.499	0.111	0.498	0.0069	0.0025	0.649	0.0576	0.0977	0.0290	0.0030		0.0058	0.0049	
1	12X 14072A	1.061	0.573	0.430	0.680	0.0151	0.0061	0.322	0.203	0.136	0.0039		0.0098	0.0103	(0.011)	0.301
2	BS 1962	1.05	0.229	0.41	0.94	0.007	0.011	0.242	0.224	0.16	0.018	0.007	0.008	0.0095	0.010	0.004
1	IPT 501	1.05	0.210	0.277	0.723	0.016	0.030	0.208	0.083	0.063	0.034		0.008	0.0076	0.008	
1	IARM 299A	1.03	0.99	0.469	0.70	0.008	0.002	0.22	0.100	0.57	0.092	0.003	0.0054	0.0028	0.0055	0.120
2	BS 4150MOD	1.01	0.21	0.47	0.90	0.024	0.079	0.21	0.19	0.15	0.012	0.005	0.012	0.0087	0.013	0.008

Number	B	Ca	Nb	O	Pb	Sb	Ta	Ti	W	Zr	Units
BS 48B	(0.0002)	(0.003)	(0.001)	0.0022	(0.0002)	(0.001)	.	0.0031	0.026	(0.002)	38 mm Ø x -7 or 19+ mm 17025 Fe: 88.7
BS 9905A	(0.0005)	(0.0002)	0.074	0.0024	(0.002)	(0.003)	(0.01)	0.0023	0.0024	(0.002)	38 mm Ø x -7 or 19+ mm 17025 Fe: 88.9
13X 90901A			0.070					(0.0025)	0.009		-40 mm Ø x -15 mm
BS H-13	(0.0002)	(0.0003)	(0.0004)	0.0018	(0.0003)	0.0020	(0.003)	(0.0019)	0.0022	(0.0014)	38 mm Ø x -7 or 19 mm 17025 Fe: [90.4]
HRT FE2012-H			(0.007)								40 mm Ø x 20 mm
BS H-13A	(0.0007)	(0.0006)	0.0052	(0.016)	(0.0004)	(0.002)	.	(0.03)	0.100	(0.002)	38 mm Ø x -7 or 19+ mm 17025 Fe: 90.2
BS 47B				(0.004)							38 mm Ø x -7 or 19+ mm
IARM 37C			(0.004)					(0.0025)	(0.012)		31 mm Ø x 2 or 18 mm
BS 47A			0.002	(0.003)				0.003			38 mm Ø x -7 or 19+ mm
12X 40CDV12A											38 mm Ø x -15 mm
SRM 1772											34 mm Ø x 19 mm
SS 407/2											38 mm Ø x 19 mm
IMZ 160									0.26		40 mm Ø x 40 mm
IMZ 159									0.26		40 mm Ø x 40 mm
HRT FE2009-N		0.0020								Zn: 0.004	40 mm Ø x 40 mm
IARM 36C											31 mm Ø x 2 or 18 mm
IARM 196A	0.0017	0.0002	0.087	0.0021	0.001	0.006	.	0.014	0.189	0.006	31 mm Ø x 18 mm
SRM 1270											32 mm Ø x 19 mm
BS 46B	(0.0006)	0.0009	(0.003)	0.0026	(0.001)	(0.002)	.	(0.001)	0.0008	(0.002)	38 mm Ø x -7 or 19+ mm 17025 Fe: 95.7
IMZ 169			(0.0045)		(0.001)			0.001			40 mm Ø x 40 mm
ECRM 190-1D											35 mm x 35 mm x 30 mm
SRM 1139a											32 mm Ø x 13 mm
BS PP20	0.00011	0.0003	0.0048	(0.0010)	.	0.0013	.	0.0007	0.0058	.	38 mm Ø x -7 or 19+ mm 17025
BS 55G *	0.0002	0.0014	0.003	0.002	<0.005	<0.005	.	0.005	0.03	0.002	38 mm Ø x -7 or 19+ mm Fe: [95.6]
IRSID 1749		(0.0002)	(<0.0005)	0.0002	(<0.0002)	0.0018	.	0.0031	(<0.0030)	(<0.0003)	41 mm Ø x 25 mm Mg: 9 ppm
ECRM 129-3D						0.00059	.	0.0030	.	.	39 mm Ø x 25 mm
TL 1100											40 mm Ø x 20 mm
ECRM 195-1D											38 mm Ø x 28 to 35 mm
SRM 1286	(0.006)		(0.012)		(0.0002)			0.040	(0.013)	(0.021)	32 mm Ø x 19 mm
BS 68B								0.005			41 mm Ø x 15-19 mm last
BS 68E	0.0002	(0.0003)	(0.002)	0.0011	(0.0002)	0.0024	.	0.0012	(0.002)	.	38 mm Ø x -7 or 19+ mm Mg:0.0004 17025
12X 24065A								0.0028		Zn:0.0034	-40 mm Ø x -15 mm
BS 58E	(0.0002)	(0.0002)		0.0008				(0.002)			38 mm Ø x -7 or 19+ mm
12X 15CDV6A											-40 mm Ø x -15 mm
IARM 35L	0.00044		(0.0026)					(0.0015)	(0.004)		31 mm Ø x 2 or 18 mm
SS 112	0.0007		0.0065					0.0100			44 mm Ø x 19 mm
12X 43400A											-40 mm Ø x -15 mm Zn: 0.0027
BS 45B	(0.0003)	0.0008	(0.002)	0.0015	(0.15)	(0.003)	.	0.0024	(0.0038)	(0.0009)	38 mm Ø x -7 or 19+ mm 17025 Fe: 96.7
IRSID 1745								(0.003)			48 mm Ø x 30 mm
12X 11572A										Zn:0.0009	38 mm Ø x -15 mm
12X 14072A											-38 mm Ø x -15 mm
BS 1962					(0.001)			0.004			41 mm Ø x -7 mm 25(pre-17025)
IPT 501								0.0015			34 mm Ø x 18 mm
IARM 299A	0.0003	(0.001)	0.006	(0.002)	(0.001)	(0.002)	.	0.0038	0.010	(0.001)	31 mm Ø x 2 or 18 mm
BS 4150MOD		0.0010		(0.003)	0.0010		.	(0.002)		last	38 mm Ø

LEADED STEEL

= Class, where 1 = CRM and 2 = RM

OES regularly requires extension of preburn time

#	Number	Pb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N	Sn	V
1	BS 74C	0.328	0.077	0.94	0.082	0.294	(0.002)	0.005	0.011	0.019	(<0.002)	0.004	.	0.008	0.0040	(<0.002)	0.0016
1	14X 12144A	0.328	0.0800	1.227	0.0630	0.325	0.0093	0.0106	0.0162	0.0807	0.0034	0.0022	.	0.0089	0.0066	.	.
2	CZ CM-15C	0.29	0.075	1.13	0.063	0.32	0.006	0.141	0.072	0.052	.	.	(0.01)	0.021	.	.	.
1	BS 74D *	0.28	0.070	1.0	0.075	0.27	0.008	0.006	0.012	0.018	0.014	0.006	0.005	0.006	0.004	0.001	0.0015
1	BS 75G	0.247	0.161	1.08	0.0085	0.114	0.011	0.0300	0.045	0.079	0.0016	0.0028	0.0031	0.0174	0.0030	0.0014	0.0005
2	BS 75F	0.202	0.165	1.05	0.009	0.116	0.004	0.030	0.044	0.080	0.002	.	.	0.018	.	.	.
1	BS 73C	0.21	0.206	0.86	0.0111	0.031	0.280	0.025	0.56	0.574	0.028	0.0035	0.0028	0.180	0.0040	(0.002)	0.0031
1	IARM 182B	0.19	0.21	0.81	0.016	0.037	0.27	0.017	0.47	0.49	0.038	(0.003)	0.006	0.172	0.0040	0.0019	0.004
1	IARM 183C	0.18	0.079	1.06	0.078	0.31	0.004	0.016	0.019	0.055	0.0021	0.003	(0.002)	0.010	0.0049	0.003	0.002
2	BS 72B	0.174	0.497	0.87	0.029	0.029	0.26	0.21	0.169	0.985	0.020	(0.006)	0.012	0.187	0.0081	0.014	0.004
2	BS 73B	0.139	0.200	0.83	0.009	0.030	0.250	0.141	0.416	0.512	0.022	0.004	0.008	0.170	0.0113	0.008	(<0.002)
2	BS 70B	0.135	0.40	0.90	0.009	0.022	0.27	0.13	0.25	1.00	0.024	.	.	0.205	.	.	.
1	BS 70C *	0.13	0.39	0.90	0.01	0.02	0.27	0.12	0.25	0.97	0.02	<0.05	0.009	0.20	<0.05	0.01	0.002

Number	B	Ca	Nb	O	Sb	Ti	W	Zn	Grade	Units
BS 74C	.	.	(<0.005)	12L14	41 mm Ø x ~7 or 19+ mm
14X 12144A		-40 mm Ø x ~15 mm
CZ CM-15C		-39 mm Ø x 25 mm
BS 74D *	<0.005	<0.005	<0.05	<0.05	<0.05	.	.	.	12L14	41 mm Ø x ~7 or 19+ mm
* Provisional Analysis										
BS 75G	(0.0002)	(0.0002)	(0.0003)	0.0155	.	(0.0004)	0.0004	.	11L17	41 mm Ø x ~7 or 19+ mm
BS 75F	11L17	40 mm Ø x ~7 mm
BS 73C	(0.0002)	(0.0005)	(0.002)	0.0013	(0.002)	0.0024	(0.006)	.	86L20	38 mm Ø x ~7 or 19+ mm
IARM 182B	(0.0003)	(0.0005)	(0.003)	(0.003)	(0.003)	(0.003)	(0.01)	(0.001)	86L20	31 mm Ø x 2 mm
IARM 183C	0.0011	.	0.0010	0.016	(0.001)	0.0009	(0.002)	0.001	12L14	31 mm Ø x 2 or 18 mm
BS 72B	.	.	(0.001)	.	.	(0.002)	.	.	41L50	37 mm Ø x ~7 or 19+ mm
BS 73B	86L20	41 mm Ø x ~17 or 19 mm
BS 70B	41L40MOD	41 mm Ø x ~7 or 19+ mm
BS 70C *	<0.005	.	<0.05	<0.05	.	0.002	.	Zr:<0.05	41L40MOD	41 mm Ø x ~7 or 19+ mm

RM LEADED AND BISMUTH STEEL XRF SET

Part Number: BS PB-BI-7

AVAILABLE INDIVIDUALLY

~7 mm discs

17025

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Bi	Pb	Sn	V	N
11L17	BS 75F	0.165	1.05	0.009	0.116	0.004	0.030	0.044	0.080	0.018	0.002	.	0.202	.	.	.
12L14	BS 74E	0.08	0.91	0.087	0.316	0.002	0.006	0.012	0.019	0.008	(0.002)	.	0.34	.	.	.
41L40	BS 70B	0.40	0.90	0.009	0.022	0.27	0.13	0.25	1.00	0.205	0.024	.	0.135	.	.	.
41L50	BS 72B	0.497	0.87	0.029	0.029	0.26	0.21	0.169	0.985	0.187	0.020	.	0.174	0.014	0.004	0.0081
4140 + Bi & S	BS 4140A	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.16	0.016	0.105	(0.001)	0.011	0.004	0.0098
4150 + Bi & S	BS 4150 MOD	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.21	0.012	0.070	0.0010	0.013	0.008	0.0087
8620 + Bi & S	BS 8620A	0.184	0.80	0.008	0.079	0.21	0.15	0.44	0.48	0.16	0.016	0.073	(0.001)	0.009	0.004	0.0107

MANGANESE STEEL

14X:~40Øx-15-17mm BS:32Øx-15-17mm CZ:~39Øx25mm DSZU:39Øx20mm ECRM:35Øx25mm IMN:50-56Øx15mm SS 491:50Øx10mm other SS:48x42x12mm VS:~38Øx-18mm

#	Number	Mn	C	P	S	Si	Cu	Ni	Cr	Al	Mo	N	Nb	Sn	V	Other
1	DSZU C013	28.8	0.89	0.025	(0.002)	0.29	0.108	(0.20)	(0.14)	(8.6)	(0.44)	(0.002)	(0.46)	.	(0.1)	.
1	VS LG68	28.8	0.39	(0.02)	0.003	.	0.11	0.20	0.13	8.6	0.46	.	0.46	.	1.09	.
1	IMZ 199	28.74	0.90	0.022	(0.0006)	0.294	0.110	0.20	0.164	8.65	0.43	.	0.43	.	0.026	B:(0.001) Ti:(0.004)
1	IRSID 1833	22.57	0.605	0.0345	(0.0005)	0.193	0.030	0.0494	0.268	0.0025	0.0133	0.012	0.0026	0.0043	0.203	As, Co, Pb, and Ti **
1	14X MN1AL	22.08	0.597	0.053	0.0054	0.944	0.178	0.692	1.321	(0.23)	0.499	0.0585	0.0096	0.0393	0.0226	Ta:(0.011) Ti: 0.0346
1	DSZU C012	20.9	0.39	0.021	0.0072	0.31	0.087	0.103	0.17	(2.9)	(0.03)	(0.013)	.	.	(1.14)	.
1	VS LG67	20.9	0.39	0.020	0.007	0.31	0.090	0.11	0.19	2.88	0.46	.	0.46	.	1.09	.
2	BS 17	19.59	0.63	0.047	0.007	0.21	0.075	0.03	1.46	(0.02)	0.46	.	.	(0.012)	(0.02)	~15mm height
2	BS 17A	19.38	0.588	0.043	0.005	0.22	0.135	0.060	1.37	0.052	0.52	0.038	.	0.06	0.012	Co: 0.013
1	VS LG69	18.6	0.45	0.033	0.0048	0.50	0.088	0.178	0.428	2.78	0.020	0.011
1	DSZU C011a	17.4	0.45	0.042	0.008	0.43	0.089	0.11	0.36	(2.8)	(0.014)
1	IMZ 198	16.10	0.44	0.031	0.0090	0.423	0.104	0.058	0.30	2.80	(0.008)	Ti:(0.005)
1	VS LG66	16.1	0.44	0.031	0.010	0.41	0.104	0.059	0.30	2.6
1	DSZU C011	16.09	0.44	0.031	0.0093	0.41	0.105	0.058	0.30	(2.6)	(0.01)	(0.010)
2	CZ SP-2C	14.5	1.40	0.037	0.016	0.29	0.35	0.050	1.56	0.030	0.050	0.027	Co:0.044	0.037	0.051	Ti: 0.014 W: 0.033
1	14X MN4AC	13.62	0.938	0.073	0.0194	0.900	0.270	1.052	1.983	0.20	0.796	0.0450	0.153	0.0634	0.0332	Ti: 0.075
1	DSZU C023	13.09	0.79	0.052	0.0062	0.291	0.111	3.15	0.313	(0.006)	(0.02)	(0.018)	(0.02)	.	(0.02)	B:(0.001) Ti:(0.004)
1	DSZU C022	12.89	1.15	0.087	0.0057	0.34	0.103	0.122	0.192	(0.007)	(0.03)	(0.013)	(0.01)	.	(0.03)	B:(0.001) Ti:(0.006)
1	14X MN2S	12.3	0.80	0.024	0.0080	2.20	0.089	0.726	0.364	0.020	1.08	0.038	0.23	0.015	0.089	Ta:(0.006) Ti: 0.018
1	DSZU C010	12.25	1.20	0.082	0.0035	0.49	0.120	0.108	0.187	(0.006)	(0.01)	(0.017)
1	VS LG65	12.2	1.19	0.080	0.0033	0.49	0.119	0.11	0.19	0.006
1	DSZU C021	11.23	1.32	0.035	0.010	0.105	0.32	0.36	0.62	(0.003)	0.096	(0.013)	(0.03)	.	0.124	B:(0.002) Ti:(0.005)
1	SS 493/3	11.15	0.819	0.12	0.009	0.861	0.017	3.24	0.259	0.035	1.04	0.025	.	.	0.025	.
1	14X MN3U	10.2	1.09	0.0239	0.015	1.11	0.135	0.387	0.599	0.045	0.343	0.025	0.398	0.0254	0.022	Ta: 0.010 Ti:(0.10)
2	BS 19A	8.76	1.57	0.092	0.009	1.46	0.51	1.48	3.75	0.057	1.97	0.039	0.040	0.037	0.10	Co: 0.014
1	DSZU C020	8.85	0.97	0.024	(0.015)	0.091	0.53	1.36	0.96	(0.004)	0.13	(0.020)	(0.02)	.	0.152	B:(0.002) Ti:(0.003)
1	14X MN5U	8.78	1.36	0.0552	0.0273	1.47	0.691	2.10	3.18	0.0257	1.93	0.0231	0.102	0.0228	0.0490	Ti: 0.93
1	SS 492/3	8.33	1.18	0.0318	0.0093	0.299	0.0211	4.17	1.076	0.131	1.318	0.0225	.	.	(0.004)	Co: 0.0048
1	14X MN5V	8.02	1.42	0.057	0.0207	2.27	0.551	3.09	3.28	0.145	2.26	0.0146	0.041	0.0278	0.0810	Ta:(0.004) Ti: 0.51
2	CZ CM-9B	2.27	0.17	(0.008)	(0.010)	0.89	0.040	0.023	1.36	0.049	(0.002)	.	(0.06)	(0.003)	(0.006)	+7 informational

* Provisional Analysis ** IRSID 1833 also contains As: 0.0034, Co: 0.0089, Pb: 0.00007, and Ti: 0.0011. Sample size 35 mm Ø x 25 mm.

CRM MANGANESE STEEL SET

AVAILABLE IN SET/6 ONLY

30 mm Ø x 24 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	B	Co	Mo	N	Ti	V
NCS HSI1720-6	2.38	5.36	0.029											

#	Number	SILICON STEEL				# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties											Sn	Ti
		Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N					
2	CZ SST-4A	4.73	0.062	0.376	0.031	0.020	0.111	0.082	0.105	0.514	0.019	0.0058	0.025	0.035				
2	CZ SST-3A	3.27	0.035	0.221	0.007	0.0093	0.096	0.061	0.043	0.009	0.036	0.0088	0.015	0.009				
1	SRM 1218	(3.2)	0.0029	0.014	(0.002)	0.0011	0.003	(0.002)	0.006	0.005	(0.003)	.	.	(0.004)				
1	SRM 1135	3.19	0.027	0.094	0.006	0.026	0.056	0.050	0.022	0.0028	0.014	.	0.004	.				
3	CZ SP-5B	3.07	0.20	1.86	0.108	0.023	0.15	3.00	0.38	0.18	0.13	.	0.08	0.35				
2	CZ SST-2A	3.07	0.083	0.160	0.026	0.0089	0.205	0.066	0.138	0.010	0.054	0.0078	0.055	0.016				
1	SRM 1134	2.889	0.0261	0.2751	0.0276	0.0095	0.0707	0.0375	0.0198	(0.329)	0.0087	.	0.034	.				
2	CZ SST-1A	2.57	0.072	0.062	0.041	0.0043	0.654	0.155	0.209	0.061	(0.002)	0.0059	0.110	0.004				
1	VS UG4/9	2.23	0.53	1.28	0.017	0.016	0.099	0.71	0.139	0.023	0.117	(0.004)	0.081	0.126				
1	VS UG91	2.23	0.49	.	0.0038	0.0021	0.057	0.039	0.064	0.048	0.058	0.010	.	0.038				
1	12X 15251U	2.05	1.017	0.910	0.0253	0.0215	0.1194	0.896	0.612	0.1085	.	0.205	0.0031	0.0108				
1	VS UG92	1.98	0.69	0.79	0.05	0.0029	0.111	0.155	0.200	0.091	0.08	0.119	0.016	0.022				
1	KUT T4/1	1.97	0.17	0.23	0.012	0.041	0.16	0.077	0.24	(<0.005)				
1	12X 15259Q	1.81	0.603	0.401	0.0401	0.0704	0.200	4.02	0.512	0.1488	.	0.407	0.0151	0.053				
1	ECRM 196-2D	1.808	0.0060	0.364	0.00369	0.00065	0.0057	0.0401	0.0282	0.2167	.	0.0142	0.00178	0.00047				
1	VS UG4/5	1.80	0.56	1.26	(0.008)	(0.006)	0.098	0.68	0.17	0.010	.	0.087	.	0.17				
1	NCS HS11751a	1.76	0.574	0.792	0.020	0.014	0.011	0.019	0.024				
2	CZ LA-2E	1.725	0.081	0.111	0.060	0.044	0.577	2.015	0.149	0.357	.	0.652	0.0071	0.087				
1	ECRM 186-1D	1.72	0.610	0.870	0.022	0.035	0.281	0.190	0.218	0.014	.	0.048	.	0.343				
1	BS 300	1.68	0.410	0.721	0.0046	0.0006	0.118	1.867	0.803	0.099	.	0.370	0.0023	0.0053				
														17025				
1	12X 44220A	1.662	0.417	0.874	0.0050	0.0009	0.031	1.89	0.846	0.029	.	0.401	0.0030	0.0019				
3	CZ CM-2A	1.66	0.20	0.97	0.10	0.012	1.01	1.20	1.50	0.03	.	0.33	.	0.34				
1	VS UG11	1.64	0.52	0.625	0.0028	0.0035	0.065	0.036	0.058	0.049	.	0.039	.	0.025				
1	VS UG1/9	1.63	0.63	0.84	0.030	0.017	0.020	0.105	0.046	0.027	.	0.135	(0.002)	0.069				
1	IARM 340A	1.63	0.414	0.755	0.011	0.001	0.103	1.80	0.84	0.062	.	0.39	0.0020	0.005				
1	IARM 342A	1.63	0.257	1.37	0.006	0.0051	0.110	1.76	0.38	0.019	.	0.42	0.0102	0.0028				
1	VS UG4/10	1.61	0.695	0.834	0.031	0.0060	0.050	0.156	0.130	0.064	.	0.089	0.0192	0.0044				
1	KUT B1/1	1.58	0.97	0.205	0.017	0.032	0.14	3.96	1.66				
1	12X 15261X	1.513	0.546	0.483	0.090	0.0518	0.308	0.0985	0.496	1.648	.	1.594	.	0.172				
1	VS UG1/10	1.51	0.51	0.659	0.0053	0.0042	0.096	0.190	0.067	0.015	.	0.051	0.0164	0.0030				
2	CZ LA-2D	1.48	0.065	0.26	0.011	0.052	0.53	2.00	0.135	0.18	.	0.57	0.008	0.085				
1	KUT A11/1	(1.46)	0.043	0.21	0.011	0.0137	0.047	0.04	0.02	0.02	.	1.20	.	0.002				
1	VS UG4/6	1.25	0.59	1.23	(0.003)	0.0008	0.169	0.47	0.400	0.032	.	0.083	(<0.0005)	0.017				
1	VS UG87	1.25	0.59	1.18	0.026	0.022	0.030	0.50	0.260	0.024	0.02	0.044	0.010	0.103				
1	VS UG1/5	1.23	0.62	0.79	(0.02)	(0.03)	(0.01)	0.048	0.069	0.022	.	0.061	.	0.045				
1	VS UG88	1.22	0.62	1.26	0.0026	0.0043	0.171	0.52	0.474	0.01	0.009	0.104	0.020	0.107				
1	DSZU C046	1.21	0.785	0.257	0.025	0.0153	0.211	1.47	2.67	0.47	.	0.69	0.0099	0.0033				
1	KUT A12	1.19	0.031	0.31	0.014	0.082	0.18	2.43	1.25	0.18	.	0.47	.	0.05				
2	CZ CM-14B	1.18	0.55	1.63	0.017	0.023	0.36	1.10	1.38	0.26	.	0.400	0.0072	0.040				
2	CZ CM-14A	1.15	0.523	1.58	0.051	0.028	0.30	1.14	1.13	0.063	.	0.395	0.0095	0.027				
1	12X 15258P	1.01	0.392	1.23	0.067	0.032	0.109	0.497	0.631	0.087	.	0.361	.	0.071				
1	SS 603/2	0.97	0.79	0.236	0.020	0.056	(0.05)	(0.03)	(0.04)	0.076	.	(0.004)	.	.				
1	SS 405/2	0.947	0.044	0.903	0.0095	0.058	0.022	0.102	0.206	0.330	.	0.025	(0.011)	.				
1	SS 113	0.931	0.837	1.207	0.0595	0.0294	0.179	0.0784	1.248	0.0151	.	0.056	0.0109	0.0067				
2	CZ LA-3F	0.88	0.467	0.782	0.036	0.031	0.218	1.017	1.024	0.061	.	0.347	0.012	0.028				
1	SS 604/2	0.75	0.199	1.91	0.016	0.072	(0.07)	(0.09)	(0.06)	0.008	.	(0.02)	.	.				
#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti			
Number	As	B	Ca	Co	Nb	O	Pb	Sb	Ta	V	W	Zr	Units					
CZ SST-4A	0.004	0.0006	.	0.012	.	.	0.008	(0.003)	.	0.031	0.026	(0.003)	~37 mm	Ø x 25 mm				
CZ SST-3A	(0.003)	0.0019	.	0.038	.	Zn:0.011	0.013	.	.	0.041	0.016	.	~37 mm	Ø x 25 mm				
SRM 1218	.	.	.	(0.002)	(<0.001)	.	(0.002)	32 mm	Ø x 19 mm				
SRM 1135	<0.01	.	.	31 mm	Ø x 19 mm				
CZ SP-5B	0.19	0.14	.	0.135	0.09	.	0.09	0.07	.	0.71	0.62	.	~39 mm	Ø x 25 mm				
CZ SST-2A	.	0.0089	.	0.022	.	Zn:0.011	0.015	0.008	.	0.024	0.019	0.017	~37 mm	Ø x 25 mm				
SRM 1134	31 mm	Ø x 19 mm				
CZ SST-1A	(0.002)	0.0003	.	0.005	.	.	(0.002)	(0.002)	.	0.006	.	.	~37 mm	Ø x 25 mm				
VS UG4/9	(0.001)	(0.0003)	.	.	(<0.001)	.	0.008	.	.	0.054	0.061	.	~45 mm	Ø x ~28 mm				
VS UG91	0.0004	.	.	.	0.097	.	0.00006	0.00009	.	0.049	.	.	~47 mm	Ø x ~30 mm				
12X 15251U	.	.	.	0.228	0.266	0.391	0.0393	.	~40 mm	Ø x ~15 mm				
VS UG92	0.0027	.	.	0.034	.	.	0.00017	0.0005	.	0.024	.	.	~47 mm	Ø x ~30 mm				
KUT T4/1	30-35 mm	Ø x 39 mm				
12X 15259Q	.	.	.	0.141	0.249	0.139	0.49	.	~40 mm	Ø x ~15 mm				
ECRM 196-2D	0.00033	0.00014	0.00071	0.0138	Mg:0.00075	0.00368	.	Zn:0.00019	38 mm	Ø x 25 mm				
VS UG4/5	0.053	0.054	0.14	.	~45 mm	Ø x ~28 mm				
NCS HS11751a	40 mm	Ø x 25 mm				
CZ LA-2E	0.083	0.0043	.	0.268	0.111	.	0.068	0.033	.	0.310	0.307	.	~37 mm	Ø x 25 mm				
ECRM 186-1D	38 mm	Ø x 25 or 30 mm				
BS 300	0.0030	0.0003	0.0008	0.0079	0.0031	(0.0004)	(0.00026)	0.0007	(0.0012)	0.070	0.0009	(0.0002)	38mm	Ø x ~7 or 19+mm Fe:93.8				
12X 44220A	0.0026	0.0764	.	.	~38 mm	Ø x ~15 mm				
CZ CM-2A	0.11	0.0005	.	0.43	0.48	.	0.06	0.008	0.027	0.10	0.23	0.03	~39 mm	Ø x 25 mm				
VS UG11	0.058	0.056	.	~45 mm	Ø x ~28 mm				
VS UG1/9	(0.001)	(0.0003)	.	.	0.124	.	(0.002)	.	.	0.024	0.063	.	~45 mm	Ø x ~28 mm				
IARM 340A	(0.004)	0.0004	(0.0004)	0.006	0.015	(0.001)	(0.001)	0.0021	.	0.064	(0.005)	(0.002)	31 mm	Ø x 2 or 18 mm				
IARM 342A	(0.006)	0.0004	(0.0001)	0.008	(0.002)	0.0006	0.0008	0.0021	.	0.023	(0.005)	(0.002)	31 mm	Ø x 2 or 18 mm				
VS UG4/10	.	.	.	0.030	0.0239	0.006	.	~45 mm	Ø x ~28 mm				
KUT B1/1	0.001	30-35 mm	Ø x 39 mm				
12X 15261X	0.0051	.	.	0.333	0.601	0.122	0.269	0.0297	~40 mm	Ø x ~15 mm				
VS UG1/10	0.091	0.042	0.074	.	~45 mm	Ø x ~28 mm				
CZ LA-2D	0.095	0.007	(0.0004)	0.26	0.24	.	0.050	0.040	.	0.30	0.29	0.003	~37 mm	Ø x 25 mm last				
KUT A11/1	.	.	.	0.16	0.16	.	.	< 0.001	.	0.46	.	.	30-35 mm	Ø x 39 mm				
VS UG4/6	(0.001)	.	.	(0.004)	(0.03)	.	(0.005)	(<0.0005)	.	0.051	0.111	.	~45 mm	Ø x ~28 mm				
VS																		

LOW ALLOY STEEL WITH C > 0.3%				CONTINUED ON THE NEXT PAGE							# = Class, where 1=CRM, 2=RM, 3=RM no uncertainties						
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti	
1	VS UG0/6	1.40	0.329	(0.006)	(0.003)	0.221	0.286	0.55	0.73	0.129	(0.002)	(0.01)	0.079			0.0052	
1	CKD 182B	1.39	0.370	0.008	0.016	0.176	0.293	2.80	1.22	0.023	0.017	0.171	0.011	0.0049	0.001	0.004	
1	CKD 182C	1.36	0.363	0.009	0.008	0.171	0.294	2.80	1.23	0.028		0.171	0.012	0.0049	(0.001)	(0.002)	
1	VS UG0/9	1.33	0.208	0.0040	0.0045	0.170	0.307	0.36	0.55	0.139	(0.001)		0.024	0.0022	0.041	0.029	
1	VS UG0/10	1.321	0.268	0.0090	0.0044	0.244	0.265	0.353	0.596	0.101			0.052	0.0120	0.0033	0.017	
1	VS UG0/5	1.32	(0.2)	(0.01)	(0.007)	(0.2)	0.265	0.351	0.60	0.108			(0.05)		(0.01)	(0.01)	
1	SS 402/2	1.311	0.288	0.0161	0.0138	0.111	0.302	0.808	0.652	0.161			0.140	0.0069			
1	ECRM 035-2D	1.277	0.305	0.0038	0.011	0.216	0.0085	0.0190	0.0104	0.0193			0.0056	0.0230		0.0030	
1	IMZ 65/2	1.19	0.27	0.013	0.007	0.13	0.059	0.067	0.079	0.030							
1	DSZU C049	1.17	0.237	0.0166	0.0147	0.227	0.069	0.044	0.131	(0.005)		(0.003)	(0.002)	(0.007)		(0.003)	
1	KUT A18	1.16	(1.99)	0.014	0.007	0.15	0.066	0.125	0.90	(0.02)					0.035	0.011	
1	VS UG0/11	1.16	0.196	0.0054	0.0078	0.233	0.134	0.114	0.163	0.009		0.0109	0.011	0.005		0.0041	
3	CZ CM-5B	1.09	1.28	0.021	0.012	0.39	0.13	0.23	2.07	0.083		0.022	0.10	0.0135	0.06	0.05	
1	14X 72305A	1.085	0.349	0.0128	0.0028	0.206	0.149	0.089	0.425	0.0049			0.0231	0.0068			
1	SRM 1761a	(1.05)	0.679	0.042	0.037	0.182	0.298	1.981	0.222	0.055		(0.027)	0.103	(0.0042)	0.021	0.173	
2	CZ CM-5C	1.04	1.17	0.029	0.021	0.54	0.151	0.42	2.45	0.063		0.022	0.132	0.014	0.014	0.031	
1	VS UG9/9	1.04	0.310	0.0053	0.021	0.319	0.163	0.242	0.310	0.073	(0.003)		0.308	0.0027	0.0046	0.130	
1	IMZ 172	1.03	0.71	0.018	0.047	0.21	0.128	0.12	4.47	0.062		0.012	0.96	0.0192		(0.002)	
1	IARM 49E	1.03	0.364	(0.006)	(0.002)	0.248	0.076	0.043	1.43	0.024		(0.006)	0.017	(0.003)	(0.003)	0.0060	
1	12X 52986A	1.023	0.372	0.0049	0.0011	0.246	0.077	0.0411	1.418	0.0258	(0.002)		0.0169	(0.002)			
2	BS 53G	1.02	0.35	0.014	0.015	0.23	0.160	0.090	1.53	0.019		0.008	0.034	0.0084		(0.002)	
1	NILAB 100LA D	1.002	0.333	0.012	0.018	0.23	0.160	0.090	1.53	0.019		0.008	0.034	0.0084		(0.002)	
1	IRSID 1747	0.990	0.333	0.0078	0.0068	0.222	0.1243	0.0850	1.501	0.005		0.007	0.012	0.0046		0.0007	
1	IARM 324A	0.99	1.01	0.009	0.028	0.163	0.22	0.081	0.42	0.002	0.0392		0.0110	0.0141	(0.00025)	0.0041	
2	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.017		0.010	0.029	0.0060		0.003	
1	KUT B15	0.98	0.69	0.030	0.031	0.80	0.14	0.15	3.70	0.13		0.21	1.20			(0.01)	
1	VS UG75	0.98	0.286	0.0127	0.0089	0.248	0.111	0.201	1.43	(0.03)			(0.01)			(0.001)	
2	CZ LA-4C	0.95	1.63	0.012	0.012	0.31	0.146	0.056	0.045	0.008		(0.006)	0.008	0.012	0.053	(0.002)	
1	VS UG9/11	0.94	0.895	0.027	0.0085	0.312	0.163	0.354	0.985	(0.04)			0.094	0.0119		0.010	
1	12X 19965A	0.936	0.600	0.0196	0.0081	0.247	0.148	0.141	1.713	0.0256			0.210	0.0087			
1	SS 401/2	0.935	1.19	0.026	0.0078	0.60	0.101	0.049	0.138	0.074		0.0042	0.49	0.0159			
1	IMZ 119	0.93	0.75	0.018	0.006	0.16	0.042	0.019	0.062	0.010	0.007		0.044	0.0086		(0.0007)	
1	VS UG89	0.92	1.16	0.025	0.005	0.385	0.373	0.51	0.420	0.01	0.007		0.007	0.017	0.0043	0.012	
1	VS UG110	0.91	0.86	0.063	0.0050	0.342	0.377	0.491	0.47	0.006			0.0052			0.0015	
1	VS UG21/6	0.83	0.74	(0.02)	(0.01)	0.312	0.346	0.47	0.50	0.006							
2	IARM 172A	0.78	0.010	0.007	0.004	1.29	0.40	0.025	3.52	0.39		0.006	0.014	0.0004	0.004	0.003	
1	SS 403/2	0.750	1.677	0.055	0.0381	0.209	0.221	0.223	0.463	0.0485			0.088	(0.010)			
1	IMZ 64/2	0.75	0.47	0.012	(0.005)	0.22	0.12	0.12	0.090	0.020							
1	VS UG8/11	0.728	1.97	0.036	0.0019	0.31	0.160	0.291	1.74	(0.01)			0.622	0.0138			
1	ECRM 059-2D	0.721	0.495	0.0046	0.0084	0.188	0.0074	0.0198	0.0090	0.00045	0.00020		0.0018	0.0051			
2	CZ CM-1C	0.72	1.73	0.023	0.025	0.31	0.18	0.52	0.47	0.034		0.026	0.084	0.009	0.054	0.066	
2	CZ CM-4B	0.72	0.50	0.023	0.012	0.80	0.40	1.40	2.23	0.025		0.115	0.33	0.013	0.071	0.12	
1	SS 404/2	0.696	0.532	0.0479	0.0228	1.121	0.427	0.393	0.774	0.017			0.307	0.0089			
1	IMZ 118	0.69	1.72	0.026	(0.049)	0.30	0.18	0.19	0.14	(0.014)	(0.004)		0.058	0.0120			
1	IMZ 116	0.64	0.94	0.025	0.035	0.25	0.33	0.022	0.72	0.025	0.012		0.074	0.0130		(0.0008)	
1	VS UG1/11	0.61	0.667	0.0098	0.011	1.74	0.155	0.080	0.108	0.032		0.0195	0.0067	0.0100		0.0047	
1	VS UG96	0.60	0.52	0.0046	0.0029	0.290	0.256	0.396	0.399	0.031			0.042			0.0025	
1	SRM 1764a	0.592	1.193	0.0210	0.0118	0.0595	0.1578	0.2006	1.468	0.0098		(0.012)	0.2007	(0.0023)	0.0416	0.0286	
1	DSZU C07	0.589	0.903	0.033	0.037	1.00	0.130	0.263	0.201	0.039		0.165	0.377		0.091	0.059	
1	VS UG119	0.55	0.70	0.012	(0.02)	1.63	0.207	0.142	0.195	0.039			0.0113	0.0047		0.0030	
1	12X 10550	0.549	0.685	0.0184	0.0055	0.281	0.0290	0.0247	0.338	0.0325			0.0086	0.0051			
1	12X 61500A	0.530	0.912	0.0104	0.0102	0.240	0.157	0.0976	1.023	(0.007)	0.0067		0.0195				
2	CZ CM-6A	0.52	0.37	0.016	0.058	0.27	0.05	0.19	0.37	0.02		0.03	0.04	0.009	0.028	0.03	
2	CZ BO-2B	0.515	0.745	0.0293	0.0016	0.309	0.100	0.057	0.212	0.0196		0.0055	0.006	0.004		0.0017	
1	12X LA3C	0.500	1.693	0.0274	0.0442	0.163	0.213	0.280	0.375	0.0410		0.0475	0.303	0.0039			
1	IARM 34C	0.50	0.739	0.0090	0.0011	0.30	0.078	0.085	0.914	0.068		0.005	0.022	0.0030	0.004	0.0045	
2	BS 43A	0.491	0.811	0.008	0.026	0.252	0.184	0.242	0.93	0.003		0.008	0.059	0.0074		0.002	
2	BS 4941	0.490	0.79	0.012	0.017	0.27	0.106	0.074	0.96	0.024		0.008	0.039	0.0076			
1	IMZ 103A	0.49	0.78	0.066	0.051	0.42	0.27	0.57	0.98	0.026		0.002	0.18		0.040	0.17	
1	IMZ 117	0.49	0.77	0.038	0.015	0.34	0.41	0.29	0.94	0.023	0.013		0.024	0.0154	0.041	(0.0014)	
1	BS 1144	0.483	1.55	0.022	0.243	0.262	0.462	0.097	0.193	(0.002)		0.011	0.017	0.0093	(0.004)	0.002	
1	IPT 503	0.456	0.682	0.027	0.027	0.218	0.129	0.063	0.160	0.018		0.006	0.020	0.0082		0.0011	
1	SRM C1173	0.453	0.174	0.031	0.092	1.38	0.204	4.04	2.63				1.46			0.037	
1	12X 41450A	0.445	1.45	0.0293	0.031	0.261	0.1318	0.197	1.14	0.0220			0.340			0.080	
1	VS UG5/11	0.445	0.64	0.010	0.007	0.40	0.145	0.40	0.912	0.041		0.0195	0.269	0.0119			
2	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.033		0.006	0.007	0.0056	(0.002)	(0.002)	
1	12X LA3B	0.439	1.176	0.0215	0.0379	0.16	0.173	0.300	0.357	0.0300		0.0300	0.302	0.0080			
1	NM PC-4	0.43	0.80	0.043	0.045	0.34	0.26	0.063	0.26				0.020				
1	IARM 307F	0.425	0.58	0.011	0.012	0.453	0.131	0.063	0.077	0.020		0.0071</					

LOW ALLOY STEEL WITH 0.13 % < C < 0.3 % - CONTINUED ON THE NEXT PAGE

#=Class, where 1=CRM and 2=RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	12X 15254AA	0.299	1.151	0.065	0.0460	0.831	0.0853	0.311	1.830	0.625	.	.	0.498	0.711	.	0.0458	0.298
1	IARM 330A	0.299	1.00	(0.005)	(0.001)	0.273	0.074	1.80	0.90	0.045	.	(0.003)	0.0063	0.404	0.0024	0.0039	0.071
1	12X 16604A	0.299	0.444	0.0064	0.0018	0.239	0.131	1.892	1.912	0.0111	.	.	0.0366	0.334	0.0046	0.0060	0.0069
1	SRM 1269	0.298	1.35	0.012	0.0061	0.189	0.095	0.108	0.201	0.016	.	.	.	0.036	.	.	0.004
1	ECRM 086-1D	0.297	0.879	0.024	0.037	0.206	0.320	0.168	0.150	.	.	0.023	.	.	.	0.026	.
2	CZ CM-3A	0.295	0.37	0.016	0.0013	0.27	0.16	1.82	1.87	0.05	.	0.005	0.012	0.33	0.007	0.007	0.007
1	VS UG9/10	0.294	0.616	.	(0.003)	0.235	0.169	0.144	0.170	0.280	.	.	.	0.282	0.015	0.0017	1.25
1	VS RG27/1	0.290	0.74	0.044	0.0043	0.28	0.208	0.142	1.83	1.07	.	.	0.025	0.191	.	.	0.072
1	IMZ 178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	.	.	0.015	0.20	0.0160	0.011	0.011
1	SRM 1225	0.274	0.48	0.007	0.014	0.221	.	0.018	0.91	0.166	.	.	0.004
1	BS HiCal-1	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0022	0.0024	0.379	.	(0.0002)	0.0027
1	IARM 380A	0.268	1.24	0.021	0.025	0.181	0.265	0.114	0.192	0.0029	.	(0.007)	(0.010)	0.059	(0.012)	0.0117	0.0475
2	RM Fe 2/4	0.26	0.61	0.039	0.016	0.30	0.30	0.68	0.70	(0.001)	.	0.04	0.29	0.47	0.020	0.04	0.46
2	BS 69B	0.258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.024	.	.	0.035	0.39	0.0057	0.006	(0.002)
1	12X 12750U	0.258	0.510	0.0078	0.0053	0.599	0.106	0.786	0.792	0.253	.	.	0.581	0.088	.	0.110	0.102
1	12X 32250A	0.257	1.350	0.0061	0.0054	1.59	0.108	1.750	0.377	0.0178	.	0.0054	.	0.417	0.0101	0.0206	0.0222
2	BS 6418	0.255	1.42	0.010	0.004	1.54	0.11	1.74	0.34	0.027	.	0.0044	0.010	0.42	0.0066	0.006	0.003
1	IARM 380B	0.243	1.27	0.016	0.027	0.238	0.307	0.182	0.153	(0.0021)	.	0.0058	0.014	0.055	(0.013)	0.0132	0.049
2	HRT FE2018-N	0.24	0.74	0.012	(0.003)	0.29	0.06	0.43	1.46	0.017	.	.	.	0.75	0.0066	.	0.30
1	IMZ 113	0.24	0.50	0.022	0.025	0.10	0.11	0.13	1.25	0.007	0.004	.	.	0.050	0.0154	.	0.039
1	12X 722M24A	0.236	0.510	0.0135	0.0199	0.262	0.200	0.208	3.094	0.0187	.	0.0075	.	0.497	.	0.0116	0.0080
1	VS UG6/5	0.232	0.39	(0.006)	(0.008)	0.51	0.257	(0.2)	1.85	(0.4)	.	.	.	(0.2)	.	.	0.34
1	12X 356D	0.228	0.325	0.057	0.040	0.235	0.402	0.070	0.246	0.031	.	0.025	0.110	0.0299	0.0107	0.0372	0.071
2	DSZU C043A	0.222	2.14	0.060	0.064	0.131	0.51	2.93	0.49	0.066	.	(0.001)	.	0.146	(0.009)	0.0023	0.25
1	IARM 229B	0.220	0.858	0.0073	0.0106	0.329	0.0153	0.030	0.017	0.025	.	(0.002)	0.0116	0.495	0.0072	0.0012	0.0059
1	IARM 197-1D	0.219	0.792	0.0073	0.0232	0.275	0.152	0.148	0.451	0.0313	.	0.0083	0.0135	0.402	0.0114	0.0097	.
2	BS 3961	0.215	0.565	0.016	0.022	0.236	0.133	1.67	0.510	0.022	.	0.0083	(0.010)	0.27	0.0079	(0.008)	(0.002)
2	TL 1668	0.2146	1.643	0.0137	0.0012	1.645	0.0108	0.0164	0.0173	0.0371	.	0.0016	0.0031	(0.0014)	0.0043	0.0047	0.0016
1	BS 8620F	0.212	0.85	0.0090	0.033	0.243	0.234	0.427	0.547	0.040	.	0.0078	0.0089	0.206	0.0106	0.0102	0.0054
1	DSZU C048	0.212	0.467	0.0102	0.0059	0.273	0.262	0.105	0.175	0.0293	.	0.0085	0.015	0.016	(0.011)	0.016	.
2	TL 1001	0.2108	0.8645	0.0141	0.0236	0.2141	0.1902	0.5378	0.5290	0.0191	.	(0.0051)	(0.0070)	0.1987	0.0102	0.0090	.
1	IPT 502	0.210	0.823	0.018	0.026	0.198	0.121	0.408	0.485	0.024	.	.	0.0083	0.155	0.0069	.	.
1	VS UG4/11	0.21	0.59	0.024	0.0069	0.285	0.074	0.173	1.21	0.032	.	.	0.0108	0.87	0.020	.	0.78
1	IARM 333D	0.209	0.593	0.009	0.023	0.207	0.072	1.78	0.139	0.026	.	0.0035	0.008	0.229	0.0053	0.005	0.002
2	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.048	.	.	.	0.519	(0.0005)	.	.
1	ECRM 187-2D	0.2038	1.257	0.0066	(0.0300)	0.2111	0.1288	0.1755	1.132	0.0223	.	0.0057	0.0112	0.0623	0.0105	0.0237	0.0122
1	BS 9325A	0.203	0.969	0.0079	0.0045	0.612	0.163	3.29	1.50	0.0056	.	0.0024	0.0093	0.358	0.0076	(0.0003)	(0.0024)
1	BS 4820A	0.203	0.64	0.008	0.014	0.185	0.212	3.28	0.116	0.029	.	0.006	0.008	0.203	0.0076	0.0097	0.0010
1	VS RG29/1	0.202	0.29	.	0.0090	0.22	1.25	4.71	0.89	0.0050	.	.	0.115	1.01	.	.	0.40
1	12X 12747V	0.201	1.240	0.0648	0.0275	0.298	0.232	0.494	0.58	0.0271	.	0.0075	0.211	0.606	0.025	0.144	0.0272

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	VS RG31/1	0.200	0.191	0.0039	0.0058	0.28	0.39	2.12	1.28	0.30	.	.	0.273	0.30	.	.	0.200
1	KUT B3	0.20	0.14	(0.012)	0.025	0.53	0.25	.	5.94	1.16
1	VS UG5/5	(0.2)	0.52	(0.005)	(0.03)	0.145	0.37	0.42	1.42	0.19	.	.	.	0.44	.	.	0.29
1	IARM 155F	0.199	0.617	0.008	(0.013)	0.223	0.219	3.36	0.144	0.0356	.	(0.006)	0.012	0.244	(0.005)	0.0084	0.0015
1	12X 86200A	0.198	0.849	0.0110	0.0104	0.299	0.213	0.598	0.602	0.0305	.	0.0051	.	0.224	0.0091	0.0100	0.0045
1	12X LA2E	0.195	0.57	0.0241	0.0263	0.678	0.786	0.783	0.813	1.381	.	0.282	0.0306	0.136	0.0173	0.0066	0.0990
1	IMZ 112B	0.195	0.43	0.022	0.016	0.27	0.055	0.046	0.034	(0.03)	.	.	.	0.043	0.010	0.15	0.045
1	VS UG8/10	0.192	1.81	0.0064	(0.005)	0.61	0.198	0.348	0.729	0.082	.	.	.	0.030	0.0185	0.0052	0.0016
1	VS UG114	0.190	1.65	0.010	0.0074	0.59	0.173	0.345	1.03	0.146	.	.	.	0.016	.	.	0.0031
2	BS 51F	0.190	0.52	0.016	0.018	0.24	0.231	1.68	0.157	0.021	.	(0.0024)	0.009	0.224	0.0060	0.009	0.003
1	IMZ 162	0.19	1.31	0.021	0.014	0.59	0.077	1.64	0.91	(0.040)	.	.	.	0.52	.	.	0.045
1	VS UG113	0.189	1.55	0.0087	0.0070	0.59	0.185	0.186	1.12	0.263	.	.	.	0.010	.	.	0.0040
2	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.032	.	0.0084	0.012	0.24	0.0078	0.013	(0.0008)
1	ECRM 192-1D	0.1875	1.377	0.0029	0.0010	0.219	0.0453	0.755	0.0717	0.0306	0.0285	.	0.0055	0.482	0.0118	.	.
1	VS UG112	0.186	1.63	0.0065	0.0050	0.60	0.157	0.185	0.98	0.026	.	.	.	0.021	.	.	0.014
2	BS LF3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.017	.	0.006	0.056	0.056	0.0054	0.006	(0.002)
2	HRT FE2012-N	0.18	0.70	0.010	0.008	0.31	0.14	0.13	0.25	0.030	.	.	.	0.26	.	.	.
1	IMZ 74A	0.179	1.19	0.008	0.010	0.34	0.209	0.130	0.197	0.012	.	.	0.0043	0.047	0.0118	.	0.072
1	12X 19MNV56A	0.174	1.563	0.0114	0.0245	0.357	0.203	0.110	0.1087	0.0101	.	.	.	0.0270	0.0210	0.0214	0.0939
1	ECRM 087-1D	0.174	0.671	0.010	0.046	0.263	0.171	0.118	0.078	.	.	0.024	0.015	0.021	.	0.017	.
1	12X 15180A	0.170	1.196	0.0110	0.0022	0.212	0.141	0.1030	0.118	0.018	.	0.0117	.	0.0231	0.0051	0.0115	.
1	ECRM 194-2D	0.1694	1.282	0.0137	0.00049	0.2974	0.0313	0.3316	0.760	0.0669	.	0.00208	0.00328	0.402	0.00319	.	0.00161
2	BS 3962	0.168	0.58	0.007	0.018	0.244	0.146	1.83	0.138	0.023	.	0.005	0.007	0.219	0.0072	0.007	(0.001)
1																	

LOW ALLOY STEEL WITH 0.13 % < C < 0.3 %

CONTINUED FROM THE PREVIOUS PAGE

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
12X 15254AA	0.0039	.	.	.	0.310	.	.	.	(0.003)	0.285	0.310	.	.	-40 mm Ø x ~15 mm
IARM 330A	0.0003	0.0010	.	.	(0.003)	(0.0009)	(0.0004)	(0.001)	.	0.006	(0.004)	.	0.0015	31 mm Ø x 2 mm
12X 16604A	-40 mm Ø x ~15 mm
SRM 1269	0.005	32 mm Ø x 19 mm
ECRM 086-1D	38 mm Ø x 25 or 30 mm
CZ CM-3A	0.0002	.	.	.	0.006	0.006	0.015	.	.	-39 mm Ø x 25 mm
VS UG9/10	0.163	1.34	.	.	-45 mm Ø x ~28 mm
VS RG27/1	0.110	0.170	.	.	-45 mm Ø x ~28 mm
IMZ 178	0.105	0.017	.	.	40 mm Ø x 40 mm
SRM 1225	32 mm Ø x 19 mm
BS HiCal-1	(0.0001)	0.0140 [91.9]	.	(0.0003)	(0.002)	.	(0.0005)	.	.	0.0037	(0.0009)	.	(0.0008)	-38 mm Ø x ~30 mm 17025
IARM 380A	(0.0020)	(0.009)	.	.	31 mm Ø x 2 or 18 mm
RM Fe 2/4	(0.0027)	<0.001	.	.	(0.011)	.	<0.02	<0.03	.	(0.0065)	0.19	.	<0.02	40 mm Ø x 40 mm
BS 69B	(0.002)	.	.	.	38 mm Ø x ~7 or 19+ mm
12X 12750U	0.111	0.159	0.100	.	.	-40 mm Ø x ~15 mm
12X 32550A	-38 mm Ø x ~15 mm
BS 6418	0.0012	.	.	.	0.003	.	.	.	57 mm Ø x ~7 or 19+ mm
IARM 380B	(0.0016)	0.0011	(0.003)	.	.	31 mm Ø x 2 or 18 mm
HRT FE2018-N	(0.0003)	36 mm Ø x 20 mm
IMZ 113	40 mm Ø x 40 mm
12X 722M24A	0.0028	.	-38 mm Ø x ~15 mm
VS UG6/5	(0.01)	(0.01)	0.16	.	.	-45 mm Ø x ~28 mm
12X 356D	(0.002)	Ca:0.0063	.	Se:0.010	0.019	.	0.034	0.0203	.	0.016	0.086	0.011	.	-40 mm Ø x ~15 mm
DSZU C043A	(0.001)	0.0004	.	.	0.006	0.041	0.092	.	.	40 mm Ø x 25 mm
IARM 229B	(0.0006)	(0.0003)	.	.	(0.0019)	(0.0017)	(0.0005)	(0.0006)	(0.003)	0.0019	(0.003)	.	(0.0008)	31 mm Ø x 2 or 18 mm
ECRM 197-1D	0.0005	.	.	.	38 mm Ø x 25 mm
BS 3961	(<0.003)	.	.	.	44 mm Ø x ~7 or 19+ mm
TL 1668	(0.00024)	0.0019	.	(0.0003)	(0.0002)	.	(0.0007)	(0.0003)	.	0.0032	.	0.0008	(0.0003)	37 mm Ø x 20 mm
BS 8620F	(0.0003)	0.0020	97.1	(0.0002)	0.0025	0.0026	(0.002)	(0.002)	17025	0.0016	0.0016	.	(0.0008)	38 mm Ø x ~7 or 19+ mm
DSZU C048	.	(0.0017)	40 mm Ø x 25 mm
TL 1001	(0.0134)	.	.	.	40 mm Ø x 20 mm
IPT 502	0.0016	.	.	.	36 mm Ø x 20 mm
VS UG4/11	0.071	0.034	0.0092	.	.	-45 mm Ø x ~28 mm
IARM 33D	0.0002	(0.0003)	.	.	0.002	0.0013	<0.001	(0.002)	.	0.003	<0.005	.	<0.002	31 mm Ø x 2 or 18 mm
BS 3952	39 mm Ø x ~7 or 19+ mm
ECRM 187-2D	0.00048	39 mm Ø x 28 mm
BS 9325A	(0.0001)	0.0039	92.8	(0.0002)	0.0017	.	(0.0003)	.	(0.010)	0.0030	0.024	17025	(0.001)	-40 mm Ø x ~30 mm
BS 4820A	0.0002	0.0003	.	0.0003	(0.002)	0.0011	(0.0002)	0.0024	.	0.0012	(0.002)	17025	.	38 mm Ø x ~7 or 19+ mm
VS RG29/1	0.044	0.020	0.62	.	.	-45 mm Ø x ~28 mm
12X 12747V	0.099	0.0276	.	.	-40 mm Ø x ~15 mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
VS RG31/1	0.21	0.39	.	.	-45 mm Ø x ~28 mm
KUT B3	1.19	.	.	30-35mm Ø x 39 mm
VS UG5/5	(0.01)	(0.003)	0.38	.	.	-45 mm Ø x ~28 mm
IARM 155F	0.0016	(0.003)	.	.	.	0.0020	(0.004)	.	.	31 mm Ø x 2 or 18 mm
12X 86200A	-38 mm Ø x ~15 mm
12X LA2E	-40 mm Ø x ~15 mm
IMZ 112B	0.013	0.010	.	.	.	40 mm Ø x 40 mm
VS UG8/10	(0.003)	0.0034	.	.	.	-45 mm Ø x ~28 mm
VS UG114	0.006	.	.	0.065	-45 mm Ø x ~25 mm
BS 51F	(0.0001)	(0.0005)	.	(0.0001)	(0.0005)	0.0020	(0.00007)	(0.0011)	.	(0.0012)	(0.0030)	(0.0002)	.	38 mm Ø x ~7 or 19+ mm
IMZ 162	0.12	.	.	.	40 mm Ø x 40 mm
VS UG113	0.006	0.007	.	0.169	-45 mm Ø x ~25 mm
BS 4620	0.00006	0.0001	.	0.0001	0.0001	0.0009	0.0002	0.0024	.	0.0026	0.0009	0.0002	.	38 mm Ø x ~7 or 19+ mm
ECRM 192-1D	-35 mm Ø x ~30 mm
VS UG112	0.0028	0.005	.	0.0047	-45 mm Ø x ~25 mm
BS LF3	0.0001	(0.0001)	.	.	.	0.004	38 mm Ø x ~7 or 19+ mm
HRT FE2012-N	40 mm Ø x 20 mm
IMZ 74A	(0.002)	(0.0004)	.	.	0.041	0.022	.	.	.	43 mm Ø x 20 mm
12X 19MNV56A	-40 mm Ø x ~15 mm
ECRM 087-1D	0.0046	38 mm Ø x 25 or 30 mm
12X 15180A	0.0016	.	-40 mm Ø x ~20 mm
ECRM 194-2D	0.00155	.	.	.	0.0290	0.00322	.	.	.	39 mm Ø x 28 mm
BS 3962	37 mm Ø x ~7 or 19+ mm
VS UG7/11	0.20	0.385	.	.	-45 mm Ø x ~28 mm
CZ CM-8A	0.004	.	.	.	0.034	(0.001)	0.01	.	.	-39 mm Ø x 25 mm
HRT FE1999-N	0.0002	.	.	.	0.002	0.001	.	.	.	40 mm Ø x 20 mm
BS XCCT	(0.001)	(0.005)	(<0.001)	(0.0004)	.	(0.002)	.	.	(<0.002)	36 mm Ø x ~7 or 19+ mm
IMZ 176A	(0.015)	.	.	40 mm Ø x 40 mm
BS 15A	(0.0002)	(0.0005)	.	.	0.041	.	(0.0003)	(0.003)	.	0.008	(0.004)	.	0.022	32 mm Ø x 17 mm last
ECRM 193-1D	0.0232	(0.0013)	.	.	.	36-41 mm Ø x 28-35 mm
BS 47A	0.002	(0.003)	.	.	.	0.003	.	.	.	38 mm Ø x ~7 or 19+ mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
--------	---	----	----	----	----	---	----	----	----	----	---	----	----	-------

LOW ALLOY STEEL WITH C < 0.13 %

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Sn	V
1	IMZ 76	0.129	1.37	0.022	0.011	0.24	0.057	0.33	0.12	0.011	.	.	0.101	.	.	(0.006)
1	VS UG86	0.129	0.217	(0.005)	(0.007)	(0.3)	0.62	1.94	1.52	.	.	.	0.311	.	.	0.327
1	12X 15256Q	0.123	0.492	0.0125	0.0163	0.190	0.0550	5.33	0.362	0.1300	.	0.493	0.0740	0.0056	0.107	0.619
1	12X 93106A	0.122	0.605	0.0071	0.0103	0.206	0.199	3.255	1.107	0.0246	.	.	0.0879	0.0098	0.0094	0.0029
2	BS 47B	0.122	0.39	0.014	0.022	0.22	0.12	0.105	4.78	0.018	.	.	0.45	0.023	0.006	0.004
1	DSZU C042	0.120	0.562	0.0123	0.0058	0.319	0.131	0.203	0.962	0.023	.	0.009	0.286	0.0100	0.0064	0.178
1	VS UG115	0.115	0.43	0.0084	0.012	0.227	0.173	1.63	0.81	0.024	.	.	0.0126	0.013	.	.
1	IMZ 71	0.114	0.54	0.018	0.011	0.49	0.88	0.041	0.46	0.014	.	.	0.008	.	.	0.045
1	IMZ 75A	0.112	0.394	0.080	0.016	0.618	0.428	0.041	0.401	0.009	.	0.0037	0.018	0.0024	0.023	0.013
1	SRM 1138a	0.11	0.35	0.035	0.056	0.25	0.09	0.10	0.13	.	.	.	0.05	.	.	0.02
1	IPT 500	0.106	0.844	0.016	0.0048	0.282	0.270	0.018	0.612	0.046	.	0.0046	0.0013	0.0092	0.002	0.003
1	12X LALB	0.104	1.262	0.0090	0.060	0.777	0.0572	0.210	1.026	0.0104	.	0.0144	0.068	0.0144	.	0.448
1	KUT A13	0.104	0.49	0.053	0.073	0.81	0.166	1.93	0.14	0.042	.	0.011	0.91	.	0.060	0.23
1	VS UG6/6	0.104	0.227	(0.007)	(0.007)	0.337	0.616	2.05	1.40	0.47	.	(0.008)	0.34	.	0.0023	0.193
2	BS 58E	0.100	0.63	0.009	0.002	0.29	0.154	3.22	1.40	0.029	.	0.013	0.110	0.0033	0.003	0.006
1	IMZ 175	0.099	0.25	0.016	0.0040	0.22	0.130	3.12	0.515	0.043	.	(0.013)	0.025	0.0099	0.011	0.014
2	BS 58C	0.098	0.57	0.011	0.014	0.29	0.14	3.20	1.29	(0.055)	.	.	0.11	.	(0.012)	.
1	IMZ 73	0.097	0.68	0.019	0.013	0.12	0.17	0.13	0.079	0.010	.	.	0.013	.	.	0.022
1	VS UG6/11	0.091	0.691	0.028	0.022	0.96	0.449	0.640	0.759	0.0107	.	0.0392	0.0082	0.0083	.	0.0075
1	KUT T3/2	0.09	0.60	0.058	0.033	0.66	0.10	0.11	0.40
1	VS UG5/10	0.088	0.177	0.0067	0.0055	0.135	0.490	1.87	1.51	0.47	.	.	0.049	0.0059	0.0036	0.121
1	IARM 268B	0.087	0.58	0.011	0.035	0.21	0.31	0.127	0.094	0.002	.	0.003	0.033	0.0015	0.010	0.047
1	IMZ 204	0.085	0.36	0.014	0.008	0.40	0.075	0.034	0.111	4.21	.	(0.007)	(0.0052)	.	.	.
1	SRM 1226	0.085	0.274	0.0022	0.0044	0.231	0.125	5.42	0.467	0.054	.	0.029	0.446	.	(0.003)	0.0018
1	NCS HS20747	0.083	0.967	0.02	0.015	0.472
1	DSZU C050	0.082	1.21	0.040	0.065	0.287	0.304	0.118	0.075	(0.008)	.	.	0.48	.	(0.004)	0.007
1	IMZ 72	0.081	0.31	0.092	0.012	0.34	0.27	0.039	0.52	0.013	.	.	0.006	.	.	(0.002)
1	NCS HS20745	0.068	0.813	0.1	0.024	0.33	0.297	0.022
1	VS UG117	0.064	1.41	0.012	0.021	0.60	0.214	0.072	0.129	0.018	.	.	(0.005)	0.0085	.	.
1	SRM 1271	0.064	0.73	0.005	0.0013	0.334	1.48	3.34	0.552	0.020	.	.	0.543	.	.	0.003
1	SRM C1285	0.058	0.332	0.072	0.020	0.36	0.37	1.17	0.80	.	.	0.036	0.164	.	0.035	0.150
1	SRM 1767	0.052	0.022	0.0031	0.0090	0.026	0.0014	0.002	0.0015	0.004	.	0.0050	0.020	0.0008	0.006	0.033
2	CZ CM-7A	0.05	1.17	0.011	0.016	0.56	0.09	0.05	0.10	0.13	.	0.007	0.015	0.01	0.008	0.012
1	SS 421	(0.049)	(0.11)	(0.012)	(0.027)	(0.07)	(0.028)	.	.	(<0.02)
1	12X 15252Q	0.0478	0.818	0.0213	0.0580	0.265	0.154	2.03	0.887	0.074	.	0.154	0.248	.	0.0448	0.330
1	VS UG82	0.046	1.83	(0.003)	(0.004)	0.334	0.056	0.201	0.59	.	.	.	0.93	.	.	0.56
1	VS UG97	0.041	0.59	0.0036	0.0025	0.194	0.0040	0.0048	0.0080	0.51	.	.	0.019	.	.	(0.001)
1	SRM 1766	0.015	0.067	0.002	0.0024	0.010	0.015	0.021	0.024	0.012	.	0.0020	0.0035	0.0033	0.0010	0.009
1	SRM 1765	0.006	0.144	0.0052	0.0038	(0.004)	0.0013	0.154	0.051	(0.006)	.	0.0012	0.005	0.0010	0.002	0.0040
2	IARM 168A	0.003	0.12	0.030	0.064	0.46	0.009	2.32	0.004	0.19	.	0.003	0.69	0.0002	0.003	0.004
1	CKD 180B	(0.003)	0.047	0.004	0.0038	0.001	0.006	0.018	0.013	(0.001)	.	0.003	0.001	(0.0028)	0.0011	0.000
1	ECRM 064-2D	0.0026	0.1641	.	.	0.0065	0.0077	0.0115	.	.	.	0.0027	0.00077	0.0026	0.00051	0.00015

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Sn	V
	Number	As	B	Ca	Ce	Fe	Nb	O	Pb	Sb	Ti	W	Zr	Units		
	IMZ 76	.	(0.001)	.	.	.	0.068	.	.	.	(0.003)	40 mm Ø x 40 mm
	VS UG86	~40 mm Ø x ~28 mm
	12X 15256Q	0.0509	0.101	.	.	.	~40 mm Ø x ~15 mm
	12X 93106A	0.0050	~38 mm Ø x ~15 mm
	BS 47B	0.004	(0.004)	38 mm Ø x ~7 or 19+mm
	DSZU C042	0.0073	0.00023	0.0010	.	.	0.0025	.	.	.	0.0018	(0.006)	.	.	.	40 mm Ø x 25 mm
	VS UG115	0.0014	~45 mm Ø x ~25 mm
	IMZ 71	.	(0.002)	.	.	.	(0.005)	.	.	.	(0.002)	.	(0.002)	.	.	40 mm Ø x 40 mm
	IMZ 75A	.	0.0021	.	.	.	0.024	.	.	.	0.023	38 mm Ø x 20 mm
	SRM 1138a	32 mm Ø x 13 mm
	IPT 500	0.0020	0.008	.	.	.	0.0014	34 mm Ø x 18 mm
	12X LALB	0.0212	~40 mm Ø x ~15 mm
	KUT A13	0.070	(0.002)	0.024	0.11	.	last	.	.	30-35mm Ø x 39 mm
	VS UG6/6	(0.002)	(<0.0005)	.	0.125	0.39	.	.	.	~45 mm Ø x ~28 mm
	BS 58E	0.003	(0.0002)	(0.0002)	.	.	.	0.0008	.	.	(0.002)	38 mm Ø x ~7 or 19+mm
	IMZ 175	(0.019)	.	.	.	40 mm Ø x 40 mm
	BS 58C	low supply	no uncertainties	.	.	.	39 mm Ø x ~17 mm
	IMZ 73	(0.01)	.	.	.	(0.002)	.	(0.0025)	.	.	40 mm Ø x 40 mm
	VS UG6/11	~45 mm Ø x ~28 mm
	KUT T3/2	(<0.01)	30-35mm Ø x 39 mm
	VS UG5/10	(0.003)	.	.	.	0.027	0.43	.	.	.	~45 mm Ø x ~28 mm
	IARM 268B	<0.005	0.0011	.	.	.	0.006	(0.015)	<0.003	.	<0.001	0.01	<0.001	.	.	31 mm Ø x 2 mm
	IMZ 204	0.035	36 mm Ø x 30 mm
	SRM 1226	(0.005)	.	(0.0001)	.	0.0021	(0.005)	(0.010)	.	.	32 mm Ø x 19 mm
	NCS HS20747	0.052	35 mm Ø x 40 mm
	DSZU C050	(0.002)	(0.002)	(0.002)	40 mm Ø x 25 mm
	IMZ 72	(0.001)	.	.	.	0.021	40 mm Ø x 40 mm
	NCS HS20745	.	.	.	0.014	.	.	La: 0.0076	35 mm Ø x 40 mm
	VS UG117	0.018	~45 mm Ø x ~25 mm
	SRM 1271	0.025	32 mm Ø x 19 mm
	SRM C1285	.	.	.	0.021	32 mm Ø x 19 mm
	SRM 1767	0.0005	0.0010	(0.0003)	Ag: 8 ppm	.	0.010	.	.	0.0020	0.011	.	(0.004)	.	.	34 mm Ø x 19 mm
	CZ CM-7A	0.005	0.0003	.	.	.	0.004	.	(0.0014)	(0.0003)	0.14	0.01	0.042	.	.	~39 mm Ø x 25 mm
	SS 421	0.52	.	.	.	38 mm Ø x 19 mm
	12X 15252Q	0.10	40 mm Ø x 15 mm
	VS UG82	.														

RM LOW ALLOY STEEL XRF SET

Part Number: BS LAS-24 Set of 24 samples, each 35 - 45 mm Ø x 7 mm discs 17025

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
300M	BS 4340M	0.414	0.74	0.004	<0.001	1.65	0.134	1.78	0.78	0.35	0.076	0.007	.	0.013	0.0020	0.009	0.056
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	.	0.006	0.0056	(0.0004)	(<0.003)
3115	BS XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.020	0.006	0.004	.	0.017	0.0076	(0.002)	0.031
4130	BS 3932	0.321	0.54	0.016	0.018	0.33	0.200	0.19	1.00	0.229	0.020	0.004	0.0043	0.011	0.0070	0.012	0.005
4140	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.229	0.018	0.007	.	0.008	0.0095	0.010	0.004
4150 + S	BS 42	0.516	1.24	0.021	0.073	0.235	0.252	0.183	0.67	0.190	0.020	(0.004)	.	0.012	0.0080	0.012	0.003
4330	BS 4330V	0.318	0.91	0.008	0.0009	0.240	0.181	1.91	0.91	0.475	0.021	.	0.0010	0.011	0.0076	0.010	0.094
4340	BS 60E	0.408	0.70	0.012	0.024	0.26	0.153	1.73	0.86	0.249	0.024	0.007	0.0010	0.009	0.0087	0.009	0.004
4615	BS 51E	0.15	0.59	0.010	0.021	0.28	0.22	1.75	0.14	0.21	0.028	.	.	0.035	0.0086	0.010	(0.0011)
4620	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.24	0.032	(0.0084)	(0.0001)	0.012	0.0078	0.013	(0.0008)
4820	BS 4820	0.188	0.57	0.010	0.025	0.25	0.11	3.29	0.12	0.21	0.020	0.005	0.0046	0.008	0.0079	(0.008)	(0.002)
6150	BS 43A	0.491	0.811	0.008	0.026	0.252	0.184	0.242	0.93	0.059	0.003	.	.	0.008	0.0074	0.011	0.148
8620	BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.168	0.021	0.007	(0.0008)	0.012	0.0079	0.007	0.002
8822	BS 8822	0.228	0.92	0.011	0.025	0.26	0.17	0.47	0.52	0.34	0.022	0.007	(0.0004)	0.019	0.0085	0.011	0.003
8740	BS 67B	0.40	0.94	0.007	0.020	0.23	0.19	0.53	0.51	0.22	0.024	.	.	0.011	0.0078	0.009	(0.002)
9310	BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.14	0.042	.	.	0.009	0.0147	0.012	0.005
9325	BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.31	0.030	(0.004)	0.0049	0.010	0.0089	0.009	0.004
P-20	BS 55E	0.307	0.72	0.014	0.024	0.60	0.032	0.053	1.66	0.40	(0.004)	.	.	(0.005)	0.0096	0.002	0.019
AMS 6418	BS 69B	0.2258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.39	0.024	.	.	0.035	0.0057	0.006	(0.002)
A193	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	0.54	(0.004)	0.005	0.0006	0.010	0.0080	0.014	0.28
A485-1	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.029	0.017	0.006	.	0.010	0.0060	0.011	0.003
E52100	BS 53E	1.08	0.37	0.007	0.012	0.24	0.11	0.26	1.45	0.10	0.003	.	.	0.011	0.0086	0.005	0.004
Nitriding	BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	0.36	1.06	(0.004)	(0.0002)	0.011	0.0045	0.008	0.007
LF 3	BS LF 3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.056	0.017	0.006	(0.0001)	0.056	0.0054	0.006	(0.002)

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
-------	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	---	----	---

CRM SOLUBLE ELEMENTS IN LOW ALLOY STEEL SET

available in set/7 only

-S = Soluble, -T = Total

38 mm Ø x 30 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al-S	Al-T	B-S	B-T	Mo
NCS HS11717a-1	0.0023	0.018	0.012	0.0027	0.0054	0.0036	0.011	0.023	0.0069	0.0078	0.0002	0.0004	0.0053
NCS HS11717a-2	0.0028	0.104	0.014	0.011	0.077	0.049	0.045	0.042	0.024	0.026	0.0011	0.0012	0.304
NCS HS11717a-3	0.032	0.303	0.018	0.067	1.55	0.403	0.563	0.236	0.295	0.298	0.0018	0.0020	0.034
NCS HS11717a-4	0.096	0.669	0.012	(0.050)	1.09	0.316	0.400	0.102	0.214	0.216	0.0085	0.0096	0.144
NCS HS11717a-5	0.243	1.04	0.030	0.042	0.769	0.248	0.393	0.106	0.101	0.104	0.0071	0.0074	0.105
NCS HS11717a-6	0.387	1.47	0.038	0.030	0.436	0.167	0.206	0.409	0.050	0.051	0.0047	0.0049	0.071
NCS HS11717a-7	0.498	2.10	0.050	0.022	0.176	0.075	0.107	0.612	0.022	0.024	0.0031	0.0033	0.196

Number	As	Bi	Co	N	Nb	Pb	Sb	Sn	Ti	V
NCS HS11717a-1	0.0034	(<0.00001)	0.0015	0.0016	(<0.0005)	(<0.0001)	0.00041	0.00020	0.0002	(0.0001)
NCS HS11717a-2	0.011	(<0.00001)	0.058	0.0017	0.031	(<0.0001)	0.00031	0.00073	0.020	0.011
NCS HS11717a-3	0.019	(<0.00001)	0.099	0.0032	0.079	(<0.0001)	0.00041	0.016	0.049	0.052
NCS HS11717a-4	0.073	(0.00001)	0.146	0.0031	0.223	(<0.0001)	0.00044	0.049	0.202	0.098
NCS HS11717a-5	0.071	(0.00001)	0.296	0.0048	0.318	(<0.0001)	0.00052	0.099	0.178	0.257
NCS HS11717a-6	0.045	(0.00001)	0.248	0.0049	0.106	(<0.0001)	0.00048	0.151	0.124	0.201
NCS HS11717a-7	0.034	(0.00001)	0.198	0.0063	0.153	(<0.0001)	0.00050	0.197	0.088	0.147

RM TOOL STEEL XRF SET

Part Number: BS TS-18

AVAILABLE INDIVIDUALLY

17025

~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
A-2	BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	0.99	.	(0.04)	0.11	0.03	.
A-10	BS A-10	1.41	1.75	0.016	0.022	1.15	0.16	1.82	0.24	1.53	0.006	<0.005	(0.004)	(0.010)	.
D-2	BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	1.09	.	0.16	0.80	0.07	0.016
H-10	BS 49	0.36	0.33	0.014	0.015	0.92	0.072	0.20	3.51	2.41	0.004	0.31	0.62	2.00	0.0186
H-11	BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	1.27	.	(0.01)	0.46	(0.008)	.
H-12	BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	1.41	.	1.06	0.62	0.07	.
H-13	BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	1.24	.	0.10	0.94	0.031	.
L-6	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	0.17	(0.011)	.	(0.01)	(0.02)	.
M-1	BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	8.4	.	1.7	1.05	0.45	.
M-2	BS 32C	0.84	0.29	(0.018)	0.0010	0.29	0.13	0.35	3.98	4.85	(0.02)	6.3	2.03	0.31	.
O-1	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.035	(0.005)	0.46	0.181	0.012	.
O-6	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	0.23	(0.007)	0.035	0.046	.	.
S-1	BS 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.045	.	2.75	0.19	0.006	.
S-5	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.41	0.015	0.004	0.214	0.036	0.0081
S-7	BS TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	1.34	.	0.19	0.35	0.043	.
T-1	BS 30D	0.745	0.348	0.029	0.0010	0.301	0.116	0.191	3.93	0.342	0.0123	17.73	1.077	0.101	0.0168
	BS 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	1.30	<0.002	0.013	9.50	0.009	0.064
HP9-4-30	BS 9-4-30	0.30	0.22	0.008	<0.001	0.06	0.09	7.25	1.00	1.00	0.004	0.01	0.085	4.40	0.0015

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
-------	--------	---	----	---	---	----	----	----	----	----	----	---	---	----	---

TOOL STEEL

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	W	Al
1	BS PM15	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0330	1.22	0.111	0.0029	14.79	0.109	0.0025
2	BS 107	2.46	0.52	0.019	0.079	0.919	0.076	0.170	5.11	0.039	1.20	0.064	.	9.50	0.013	(<0.002)
1	DSZU C070	2.43	0.38	0.021	0.054	0.79	0.130	0.153	5.57	0.053	1.28	.	.	9.39	0.29	.
1	BS A-11	2.42	0.507	0.023	0.123	0.98	0.092	0.25	5.21	0.044	1.25	0.110	0.0019	9.24	(0.080)	0.0054
1	DSZU C082	2.32	0.33	0.029	0.014	0.36	0.118	0.239	12.24	0.035	1.11	.	.	4.02	0.17	.
1	ECRM 288-1D	2.08	0.292	0.024	(0.0012)	0.260	0.060	0.298	12.00	0.018	0.103	0.0151	.	0.055	(0.68)	0.012
1	DSZU C080	1.68	0.31	0.025	0.020	1.89	0.120	0.162	5.06	0.028	0.39	.	.	5.12	3.40	.
1	BS 37G	1.663	0.326	0.021	0.0007	0.352	0.044	0.152	11.77	0.0166	0.78	0.0310	0.0025	0.70	0.034	0.0060
1	BS TS15	1.64	0.27	(0.017)	0.067	0.067	0.068	(0.18)	4.32	4.87	0.48	0.045	0.0016	4.81	11.6	0.0032
1	ECRM 274-1D	1.397	0.397	0.016	0.0006	1.057	0.077	0.1291	8.236	(0.0230)	4.551	0.0769	(0.0011)	0.010	(0.0087)	(0.0025T)
2	CT D2	1.53	0.48	0.013	0.005	0.40	0.04	0.10	11.46	0.02	0.75	.	.	0.89	<0.01	.
1	IARM 41D	1.519	0.256	0.021	0.012	0.256	0.047	0.114	11.5	(0.020)	0.74	0.0152	(0.003)	0.77	0.034	0.014
2	BS 41A	1.50	0.93	0.004	0.001	0.97	0.034	0.17	0.20	0.006	0.19	0.0077	0.004	(0.003)	(<0.003)	0.010
1	IARM 45B	1.42	0.90	0.010	0.008	0.92	0.018	0.024	0.061	0.004	0.24	0.0080	0.002	(0.003)	(0.004)	0.010
2	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	.	0.23	.	.	0.046	0.035	(0.007)
2	BS A-10	1.41	1.75	0.016	0.022	1.15	0.016	1.82	0.24	(0.010)	1.53	.	.	(0.044)	<0.005	0.006
1	IARM 251A	1.398	0.33	0.014	0.058	0.58	0.13	0.131	4.21	0.129	5.16	0.044	0.003	3.9	5.5	0.01
2	IARM 45A	1.39	0.88	0.014	0.012	1.02	0.049	0.11	0.13	0.004	0.25	0.0079	0.003	0.005	.	0.011
1	DSZU C073	1.32	0.23	0.019	0.013	0.27	0.112	0.198	3.97	8.31	4.97	.	.	2.82	6.40	.
2	CT X27081	1.32	0.20	0.004	0.001	0.24	0.026	0.031	0.052	.	0.008	.	.	.	3.39	.
1	DSZU C072	1.30	0.29	0.024	0.019	0.55	0.106	0.192	4.25	0.011	5.39	.	.	3.59	6.33	.
3	CZ HS-2A	1.24	0.27	0.024	0.017	0.24	0.08	0.21	4.15	9.9	3.75	.	0.003	3.4	9.3	0.035
1	DSZU C077	1.16	0.19	0.030	0.024	0.40	0.142	0.271	4.07	7.73	3.05	.	.	2.04	12.17	.
1	DSZU C075	1.16	0.16	0.021	0.015	0.47	0.120	0.202	3.10	8.03	4.06	.	.	2.10	9.27	.
1	BS M-47	1.14	0.20	0.020	0.002	0.464	0.080	0.17	3.72	4.99	9.24	0.0219	(0.004)	1.23	1.36	(0.002)
1	IMZ 102/3	1.11	0.15	0.014	(0.0045)	1.06	0.13	0.021	1.59	.	0.43	.	.	(0.012)	.	0.017
1	DSZU C074	1.10	0.16	0.023	0.020	0.16	0.141	0.158	3.93	5.08	5.21	.	.	1.94	6.47	.
1	DSZU C071	1.06	0.20	0.020	0.028	0.38	0.162	0.149	3.77	8.10	9.67	.	.	1.07	1.74	.
1	SS 487/1	1.02	0.26	0.022	0.029	0.18	.	(0.14)	3.91	7.95	9.41	.	.	1.14	1.80	0.006
1	DSZU C081	1.01	0.32	0.017	0.011	1.10	0.124	0.207	7.78	0.029	2.13	.	.	0.25	0.05	.
2	CT M7	1.00	0.29	0.012	0.003	0.34	0.066	0.10	3.60	0.015	8.49	.	.	2.02	1.78	.
1	IARM 39B	0.99	0.54	0.017	0.003	0.35	0.10	0.14	4.79	0.014	1.01	0.0096	0.003	0.22	(0.026)	0.006
1	IARM 39C	0.99	0.45	0.019	0.007	0.28	0.077	0.144	4.99	0.013	0.97	0.011	0.0029	0.21	0.011	0.017
2	BS 36D	0.97	0.68	0.021	0.007	0.27	0.060	0.089	5.25	0.010	0.96	0.0108	.	0.29	0.028	0.010
2	CT A2	0.95	0.72	0.010	0.004	0.40	0.06	0.10	5.13	.	1.05	.	.	0.22	.	.
1	SS 485/1	0.94	0.41	0.043	0.039	0.30	.	(0.14)	4.02	4.97	0.66	.	.	1.02	17.8	(0.006)
1	IARM 320A	0.93	0.33	0.021	(0.0015)	0.36	0.091	0.204	4.22	4.90	4.79	(0.014)	0.0032	1.76	6.01	0.023
2	CT O1	0.91	1.27	0.009	0.004	0.36	0.05	0.06	0.49	.	0.07	.	.	0.25	0.51	.
1	ECRM 290-1D	0.91	0.24	0.016	0.015	0.09	0.081	0.13	4.38	5.12	4.24	0.0325	.	1.22	6.24	.
2	CT M10	0.88	0.27	0.016	0.004	0.30	0.061	0.14	3.97	0.012	7.89	.	.	1.99	0.008	.
2	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.012	0.035	.	(0.003)	0.181	0.46	(0.005)
1	IARM 304A	0.857	0.260	0.019	0.0016	0.36	0.14	0.133	3.55	0.278	8.04	0.034	0.002	1.23	1.65	0.009
2	14X 14946D	0.85	0.53	0.051	0.048	0.46	0.25	1.06	5.06	0.44	0.21	.	.	1.03	16.9	.
2	BS 32D	0.85	0.30	0.027	0.022	0.25	0.039	0.053	4.14	0.010	4.92	0.018	.	1.82	6.15	0.018
1	IARM 306B	0.84	0.24	0.006	(0.001)	0.21	0.058	0.095	4.12	0.010	4.2	0.0049	(0.002)	0.98	(0.01)	0.08
1	SRM 1157	0.836	0.34	0.011	0.004	0.18	0.088	0.228	4.36	0.028	4.86	.	.	1.82	6.28	.
1	BS M-80	0.834	0.244	0.009	(0.0009)	(0.205)	0.064	0.074	4.28	0.0151	4.29	0.0057	(0.0018)	0.99	0.0052	0.073
2	14X 14948C	0.83	0.65	0.011	0.017	0.26	0.04	0.29	4.04	0.16	0.14	.	.	0.65	18.8	.
2	CT M2	0.82	0.33	0.012	0.004	0.27	0.06	0.25	4.03	0.05	4.96	.	.	1.81	6.47	.
1	IARM 44C	0.82	0.301	0.027	0.004	0.31	0.12	0.132	4.04	0.247	5.02	0.033	0.004	1.91	6.0	0.05
2	CT M1	0.80	0.30	0.012	0.005	0.22	0.087	0.12	3.91	.	8.22	.	.	1.05	1.58	.
1	IARM FeTi-18	0.80	0.295	0.026	(<0.0010)	0.30	0.034	0.14	3.98	0.096	0.124	0.0195	0.026	1.05	18.0	0.054
1	BS 30D	0.745	0.348	0.029	0.010	0.301	0.116	0.191	3.93	0.101	0.342	0.0168	0.0189	1.077	17.73	0.0123
1	IARM 281A	0.74	0.30	0.015	0.019	0.29	0.096	0.15	3.89	4.8	0.49	0.0064	0.004	0.90	17.6	0.007
1	SS 486/1	0.74	0.21	0.029	0.021	0.27	.	(0.06)	4.54	0.08	5.20	.	.	1.82	5.80	(0.005)
1	IARM 40C	0.72	1.91	0.014	0.012	0.32	0.142	0.255	0.99	0.010	1.27	0.0083	0.008	0.010	0.009	0.019
1	14X HS1C	0.72	0.29	0.018	0.020	0.23	0.07	0.28	4.00	0.25	0.36	0.023	.	1.04	17.2	.
3	CZ HS-1A	0.72	0.28	0.023	0.011	0.28	0.08	0.14	4.15	4.7	0.06	.	0.003	1.33	17.5	0.03
1	IARM 43B	0.711	0.56	0.008	0.013	0.251	0.180	0.139	0.651	0.012	0.206	0.0093	0.0047	0.0035	<0.005	0.021
2	BS 40B	0.71	2.28	0.020	0.006	0.35	0.076	0.089	1.18	0.020	1.07	0.0076	0.002	0.10	0.11	0.002
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	W	Al
3	CZ CM-10A	0.694	1.00	0.040	0.022	0.817	0.31	2.38	5.48	0.114	1.234	.	0.0189	0.908	0.96	0.086
1	DSZU C076	0.69	0.18	0.024	0.022	0.58	0.120	0.213	5.75	13.88	4.29	.	.	2.03	9.81	.
1	SS 481/1	0.68	0.25	0.023	0.022	0.15	.	(0.09)	3.40	0.31	0.28	.	.	0.56	14.0	.
1	IARM 40B	0.68	1.98	0.012	0.003	0.39	0.050	0.096	1.04	0.015	1.22	0.0107	0.003	0.014	0.013	(0.006)
2	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	(0.02)	0.17	.	.	(0.01)	.	(0.011)
1	SS 482/1	0.67	0.26	0.027	0.027	0.14	.	(0.16)	3.95	0.29	0.40	.	.	1.04	17.8	.
1	DSZU C078	0.67	0.22	0.022	0.019	0.117	0.116	0.121	3.98	0.022	0.14	.	.	1.04	18.30	.
1	SS 483/1	0.65	0.22	0.023	0.023	0.16	0.08	(0.08)	2.90	2.06	0.18	.	.	0.22	9.28	.
2	BS 38C	0.60	0.81	0.0												

TOOL STEEL CONTINUED FROM THE PREVIOUS PAGE

Number	Als	As	B	Ca	Nb	O	Pb	Sb	Sn	Ta	Zr	Units
BS PM15	.	0.0040	(0.0002)	(0.0001)	0.014	0.0129	(0.00001)	(0.0010)	0.0034	(0.0003)	(0.0005)	38 mm Ø x 19+ mm 17025
BS 10V	41 mm Ø x ~7 or ~12 mm last
DSZU C070	~40 mm Ø x ~15 mm
BS A-11 Fe:79.5	.	0.0057	0.0008	(0.0002)	(0.0070)	0.028	(0.00006)	(0.001)	0.0055	.	(0.001)	~35 mm Ø x ~7 or 19+ mm 17025
DSZU C082	~35 mm Ø x 25 mm
ECRM 288-1D	.	(0.0065)	36-41 mm Ø x 28-35 mm
DSZU C080	~35 mm Ø x 25 mm
BS 37G	.	0.0026	0.0003	0.0014	0.0026	.	0.0005	0.0009	0.0010	.	.	34 mm Ø x ~7 or 19+ mm
BS 7S15	.	(0.006)	(0.0005)	(0.001)	0.009	(0.018)	.	Fe:71.4	0.0074	.	(0.003)	38 mm Ø x ~7 or 19+ mm 17025
ECRM 274-1D	.	(0.0013)	(0.0005)	.	.	(0.0026)	(0.000064)	(0.0002)	(0.0010)	.	.	38 mm Ø x 25 mm
CT D2	30-35 mm Ø x ~16 mm
IARM 41D	.	(0.01)	(0.0006)	(0.0008)	(0.004)	(0.003)	(0.0008)	.	(0.005)	.	(0.002)	31 mm Ø x 2 or 18 mm
BS 41A	.	0.002	.	0.0006	.	0.002	.	.	0.002	.	.	38 mm Ø x ~7 or 19+ mm 25(pre-17025)
IARM 45B	.	(0.002)	(0.0001)	(0.001)	(0.002)	(0.0005)	(0.001)	0.008	.	.	(0.001)	31 mm Ø x 2 or 18 mm
BS 41	(0.008)	.	.	42 mm Ø x 19+ mm 17025 last
BS A-10	40 mm Ø x ~7 or 19+ mm
IARM 251A	.	0.016	(0.002)	(0.0005)	0.016	(0.01)	(0.002)	31 mm Ø x 2 or 18 mm
IARM 45A	.	(0.003)	(0.0001)	.	0.002	(0.0017)	(<0.005)	.	0.011	(0.002)	.	31 mm Ø x 2 mm
DSZU C073	~40 mm Ø x ~15 mm
CT X27081	30-35 mm Ø x ~16 mm last
DSZU C072	~40 mm Ø x ~15 mm
CZ HS-2A	0.01	.	.	~39 mm Ø x 25 mm
DSZU C077	~40 mm Ø x ~15 mm
DSZU C075	~40 mm Ø x ~15 mm
BS M-47	.	0.006	.	(0.002)	(0.004)	0.0037	.	.	0.006	.	.	38 mm Ø x ~7 or 19+ mm 17025
IMZ 102/3	.	.	(0.0007)	(0.007)	40 mm Ø x 40 mm
DSZU C074	~40 mm Ø x ~15 mm
DSZU C071	~40 mm Ø x ~15 mm
SS 487/1	.	(0.012)	(0.006)	.	.	38 mm Ø x 19 mm
DSZU C081	~35 mm Ø x 25 mm
CT M7	30-35 mm Ø x ~16 mm
IARM 39B	0.006	.	.	.	0.004	.	.	31 mm Ø x 2 or 18 mm
IARM 39C	.	(0.005)	0.001	(0.001)	0.0040	0.001	(0.0001)	(0.002)	0.005	(0.002)	.	31 mm Ø x 2 or 18 mm
BS 36D	.	0.002	0.016	.	.	38 mm Ø x ~7 or 19+ mm
CT A2	30-35 mm Ø x ~16 mm
SS 485/1	.	(0.022)	0.019	.	.	38 mm Ø x 19 mm
IARM 320A	.	0.013	0.0011	.	(0.015)	(0.0021)	.	.	0.008	.	(0.003)	31 mm Ø x 2 or 18 mm
CT O1	30-35 mm Ø x ~16 mm
ECRM 290-1D	36-41 mm Ø x 28-35 mm
CT M10	30-35 mm Ø x ~16 mm
BS 35D	(0.001)	.	.	.	0.006	.	.	38 mm Ø x ~7 or 19+ mm 17025
IARM 304A	.	(0.01)	0.002	(0.002)	0.021	0.002	.	(0.001)	0.006	(0.002)	(0.002)	31 mm Ø x 2 or 18 mm
14X 14946	~40 mm Ø x ~15 mm
BS 32D	38 mm Ø x ~7 or 19+ mm
IARM 306B	.	(0.003)	(0.001)	.	0.007	(0.001)	(0.001)	0.0025	0.004	.	(0.002)	31 mm Ø x 2 or 18 mm
SRM 1157	32 mm Ø x 19 mm
BS M-50	.	0.0035	(0.0001)	(0.001)	0.0008	0.0010	(0.0001)	(0.0006)	0.0045	Fe:88.8	(0.0006)	38 mm Ø x ~7 or 19+ mm 17025
14X 14948C	40 mm Ø x 15 mm last of stock
CT M2	30-35 mm Ø x ~16 mm
IARM 44C	.	(0.01)	(0.002)	.	0.012	(0.003)	(0.002)	(0.004)	0.010	(0.004)	.	31 mm Ø x 2 mm
CT M1	30-35 mm Ø x ~19 mm
IARM FeT1-18	(0.004)	(0.0027)	.	.	(0.010)	.	.	31 mm Ø x ~2 or 18+ mm
BS 30D	.	0.0128	(0.0002)	0.0004	0.0071	0.0019	(0.0002)	0.0032	0.0246	(0.02)	(0.0001)	38 mm Ø x ~7 or 19+ mm 17025
IARM 281A	.	(0.02)	(0.003)	.	0.094	(0.003)	.	.	0.02	.	(0.002)	31 mm Ø x 2 or 18 mm
SS 486/1	.	(0.016)	0.014	.	.	38 mm Ø x 19 mm
IARM 40C	.	0.008	0.0009	(0.001)	0.003	0.0013	.	.	0.008	(0.002)	.	31 mm Ø x 2 or 18 mm
14X HS1C	(0.035)	.	.	40 mm Ø x 15 mm
CZ HS-1A	0.02	.	.	~39 mm Ø x 25 mm
IARM 43B	.	0.005	0.0002	.	0.004	0.0016	<0.0005	.	0.013	.	.	31 mm Ø x 2 or 18 mm
BS 40B	.	0.004	0.0006	0.005	.	.	41 mm Ø x ~7 or 19+ mm
Number	Als	As	B	Ca	Nb	O	Pb	Sb	Sn	Ta	Zr	Units
CZ CM-10A	.	0.03	0.05	0.062	.	.	~39 mm Ø x 25 mm
DSZU C076	~40 mm Ø x ~15 mm
SS 481/1	38 mm Ø x 19 mm last of stock
IARM 40B	.	.	(0.0010)	.	0.005	(0.0014)	.	.	0.004	.	.	31 mm Ø x 2 or 18 mm
BS 39B	(0.011)	.	.	41 mm Ø x ~7 or 19+ mm 17025
SS 482/1	38 mm Ø x 19 mm
DSZU C078	~40 mm Ø x ~15 mm
SS 483/1	38 mm Ø x 19 mm
BS 38C	.	0.011	.	.	(0.002)	.	0.022	.	0.022	.	.	38 mm Ø x ~7 or 19+ mm
ECRM 179-2D	0.00144	.	.	0.00175	.	.	.	30 to 35 mm Ø x 20 mm
IARM 47B	.	.	(<0.001)	.	(0.002)	(0.0014)	(0.0003)	.	0.008	.	.	31 mm Ø x 2 (LAST) or 18 (OK) mm
DSZU C079	~35 mm Ø x 25 mm
BS 33D	0.005	.	.	41 mm Ø x 12 mm
BS 33E	38 mm Ø x 12 mm
CT X67975	<0.001	.	0.003	.	.	30-35 mm Ø x ~16 mm
IARM 259A	.	0.006	0.0003	.	0.003	0.0014	<0.0005	.	0.004	.	0.001	31 mm Ø x 2 mm
BS D-6	.	0.011	(0.0003)	0.0011	(0.002)	(0.0008)	(0.0003)	0.0012	0.0104	Mg: 0.0002	.	38 mm Ø x ~7 or 19 mm 17025
IMZ 57/1	40 mm Ø x 40 mm
IARM 46B	.	(0.01)	0.0003	.	0.003	0.002	<0.002	.	0.016	.	.	31 mm Ø x 2 or 18 mm
IMZ 53/1	40 mm Ø x 40 mm
IMZ 56/1	40 mm Ø x 40 mm
BS H-19	.	0.0056	.	.	0.008	0.0071	.	.	0.0056	.	.	38 mm Ø x ~7 or 19+ mm 17025
IARM 255A	.	(0.002)	0.0004	(0.0004)	0.004	0.0011	<0.001	.	0.006	.	<0.005	31 mm Ø x 2 or 18 mm
BS H-13	.	0.0066	(0.0002)	(0.0003)	(0.0004)	0.0018	(0.0003)	0.0020	0.0093	(0.003)	(0.0014)	38 mm Ø x ~7 or 19 mm 17025
IMZ 58/1	40 mm Ø x 40 mm
IMZ 51/1	40 mm Ø x 40 mm
ECRM 276-2D	0.0133	.	.	38 mm Ø x 25 or 30 mm
BS H-13A Fe:90.2	.	0.0050	(0.0007)	(0.0006)	0.0052	(0.016)	(0.0004)	(0.002)	(0.005)	.	(0.002)	38 mm Ø x ~7 or 19+ mm 17025
CT H13	30-35 mm Ø x ~16 mm
IARM 255B	(0.006)	.	.	.	(0.006)	.	.	31 mm Ø x 2 or 18 mm
IARM 42C	.	(0.01)	0.0011	(0.0005)	(0.004)	0.003	0.0007	(0.004)	(0.006)	(0.004)	(0.002)	31 mm Ø x 2 or 18 mm
ECRM 271-1D	.	0.0057	.	0.0009	.	0.0020	.	.	0.0084	.	.	35 mm Ø x 25 mm
BS 49	(0.004)	.	.	49 mm Ø x ~7 or 19+ mm
BS 9-4-30	35 mm Ø x ~7 or 19+ mm
IARM 341A	.	(0.003)	0.0005	0.0011	(0.005)	0.0008	(0.001)	(0.001)	(0.005)	.	(0.003)	31 mm Ø x 2 or 18 mm
IMZ 196	.	.	0.065	.	0.073	37 mm Ø x 30 mm
IMZ 170	0.087	.	.	(0.002)	0.007	.	.	40 mm Ø x 40 mm
CZ CM-17A	0.0105	0.0060	0.0177	.	0.0109	.	.	~37 mm Ø x ~25 mm
VS LG43/1	~45 mm Ø x ~28 mm
IMZ 197	.	.	(0.007)	.	(0.011)	.	.	.	0.015	.	.	37 mm Ø x 30 mm
NCS HS20741	35 mm Ø x 40 mm
VS LG42/1	~45 mm Ø x ~28 mm
VS LG37/1	~45 mm Ø x ~28 mm
IMZ 179	.	(0.007)	.	.	(0.004)	.	.	.	0.010	.	.	40 mm Ø x 40 mm
IMZ 157	40 mm Ø x 40 mm
NCS HS20742	35 mm Ø x 40 mm
IMZ 177	40 mm Ø x 40 mm
13X 14713A	.	.	.	Mg:0.0016	0.008	.	.	~40 mm Ø x ~15 mm
SS 422								

ALUMINUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Al	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	ECRM 299-1D	5.33	0.172	22.32	0.0154	0.2678	0.0152	0.00022	0.299	0.0382	0.0187	0.0186	0.0198	.	0.1289	0.0329
1	IMZ 158	1.56	0.24	25.51	0.091	1.34	0.015	0.007	2.23	0.097	.	0.025	.	.	0.12	0.078
1	13X PH17700A	1.172	6.98	16.88	0.0732	0.496	0.0181	0.0008	0.551	0.146	0.0464	0.340	0.0192	0.0201	0.051	0.0390
1	BS 192	1.17	7.11	16.44	0.074	0.835	0.025	0.0005	0.387	0.412	0.104	0.430	0.0290	0.168	0.076	0.124
2	CT X92834	1.14	8.32	12.57	0.035	0.044	0.003	0.003	0.019	0.030	0.030	2.20	.	0.001	0.019	<0.004
1	IARMFel77PH-18	1.09	7.11	17.08	0.080	0.730	0.020	(0.0005)	0.51	0.36	0.048	0.350	0.0153	0.009	0.083	0.062
1	13X PH13800A	1.075	8.04	12.53	0.0386	0.0332	0.0064	0.0030	0.081	0.0449	0.0220	2.10	0.0041	.	0.0122	0.0188
1	IARM 21D	1.03	8.29	12.69	0.032	0.052	0.008	(0.0014)	0.039	0.017	0.078	2.23	0.0037	(0.005)	0.016	0.017
2	BS 184A	1.00	8.34	12.66	0.035	0.06	0.007	(0.001)	0.080	0.041	0.036	2.20	0.0045	(0.006)	0.051	0.014
1	BS 192A	0.98	7.01	16.44	0.066	0.768	0.021	<0.002	0.300	0.334	0.114	0.28	0.029	0.208	0.083	0.077
1	IARM 152C	0.94	7.30	16.99	0.072	0.74	0.024	0.0006	0.263	0.316	0.113	0.36	0.0172	0.012	0.098	0.072

Number	As	B	Ca	O	Sn	Ta	W	Zr	Units
ECRM 299-1D	0.0054	0.0002	0.1775	40 mm Ø x 25 mm
IMZ 158	40 mm Ø x 40 mm
13X PH17700A	.	0.0033	.	.	0.0055	.	0.009	.	~38 mm Ø x ~15 mm
BS 192	(0.005)	(0.0003)	0.0007	0.0014	0.008	(0.001)	0.05	.	38 mm Ø x ~7 or 19+ mm
CT X92834	.	0.0009	.	.	0.002	.	.	<0.001	30-35 mm Ø x x ~19 mm
IARM Fe177PH-18	.	(0.0017)	.	.	(0.006)	.	(0.011)	.	31 mm Ø x 2 or 18 mm
13X PH13800A	0.0051	.	.	.	~38 mm Ø x ~15 mm
IARM 21D	(0.012)	.	31 mm Ø x 2 or 18 mm
BS 184A	.	(0.0004)	(0.0003)	(0.0003)	(0.002)	.	0.032	.	38 mm Ø x ~7 or 19+ mm
BS 192A	(0.0035)	(0.0003)	(0.0006)	(0.0006)	0.008	.	0.048	.	38 mm Ø x ~7 or 19+ mm
IARM 152C	(0.004)	0.0029	(0.0005)	(0.001)	0.007	(0.005)	0.026	.	31 mm Ø x 2 mm

CRM BORON IN STAINLESS STEEL

35 mm x 45 mm x 16 mm

Number	B	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Ti	V	W
DSZU C61	2.14	(0.073)	(0.38)	(0.003)	(0.005)	(0.41)	(0.09)	(0.95)	(17.8)	(0.04)	(0.24)	(0.75)	(0.19)	(0.22)
DSZU C60	1.42	(0.058)	(0.50)	(0.002)	(0.006)	(0.35)	(0.01)	(0.51)	(11.9)	(0.11)	(0.37)	(2.70)	(0.41)	(0.20)
DSZU C62	1.15	(0.065)	(0.31)	(0.010)	(0.024)	(0.32)	(0.24)	(0.84)	(14.4)	(0.59)	(0.16)	(3.36)	(0.18)	(0.14)
DSZU C63	1.05	(0.070)	(0.27)	(0.014)	(0.006)	(0.30)	(0.39)	(0.48)	(11.3)	(0.25)	(0.09)	(0.70)	(0.08)	(0.10)

CALCIUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Ca	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	V	W
1	BS Ca304-4	0.0075	8.77	18.26	0.096	0.783	0.0205	0.0070	0.887	0.143	(0.007)	0.0041	0.061	0.063	0.0686	0.0056
2	BS CA304-1	0.0045	8.57	18.30	0.045	1.06	0.026	0.016	0.71	0.34	0.20	0.34	0.083	0.026	0.09	0.04
1	13X 14923A	0.0044	0.452	11.26	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.0207	0.819	0.0321	0.005	0.295	.
1	ECRM 379-1D	0.0033	30.83	26.79	0.0121	1.804	0.0166	0.0006	0.393	0.984	0.0390	3.290	0.0550	(0.0028)	0.0663	(0.0091)
1	13X 31603D	0.0029	10.04	17.58	0.0203	1.475	0.0363	0.0265	0.395	0.356	0.188	2.019	0.062	0.010	0.0722	0.040
2	BS 193	0.0020	1.82	18.48	0.104	12.11	0.018	0.002	0.66	0.088	0.028	0.21	0.37	0.014	0.107	(0.007)
2	BS SS4952	0.0019	0.23	13.15	0.347	0.41	0.016	0.003	0.66	0.045	0.030	0.049	0.027	0.004	0.089	(0.007)
2	BS 82E	0.0014	12.49	22.38	0.062	1.61	0.027	0.001	0.58	0.26	0.12	0.31	0.072	0.062	0.064	0.041
1	BS 9942	0.0014	13.55	18.21	0.021	1.84	0.025	0.006	0.49	0.305	0.086	3.30	0.071	0.005	0.072	0.032
1	BS 9842	0.0010	20.02	24.19	0.059	1.50	0.025	0.0016	0.99	0.147	0.237	0.111	0.037	0.026	0.075	0.011
1	ECRM 272-1D	0.00090	0.2445	11.927	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.0145	0.0030	0.0508	0.0028	0.0167	.
2	BS 94C	0.0008	0.43	25.90	0.057	0.45	0.024	0.002	0.62	0.056	0.042	0.20	0.065	0.032	0.12	(0.03)
2	BS 87F	0.0007	10.12	17.30	0.055	1.64	0.024	0.025	0.67	0.28	0.17	0.29	0.037	0.57	0.13	0.050
2	BS SS3951	0.0005	9.18	18.17	0.014	1.56	0.023	0.031	0.61	0.22	0.16	0.303	0.077	0.085	0.067	0.040

Number	Al	As	B	O	Pb	Sb	Sn	Ti	Zn	Units
BS Ca304-4	0.017	0.0063	0.0031	0.013	0.0008	(0.0002)	0.0024	0.0046	Zr:0.0036	~38 mm Ø x ~38mm
BS CA304-1	0.003	(0.003)	0.0006	0.0041	.	(0.0020)	0.010	0.028	.	38 mm Ø x ~5 mm last, sides not parallel
13X 14923A	0.003	0.004	.	.	~40 mm Ø x ~15 mm
ECRM 379-1D	(0.00246)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.00057	0.0021	(0.0014)	.	38 or 45 mm Ø x 25 mm
13X 31603D	0.006	0.0084	(0.0014)	.	~30 mm Ø x ~20 mm
BS 193	(0.003)	.	0.0007	(0.004)	.	.	0.004	0.003	.	32 mm Ø x ~7 or 19+ mm
BS SS4952	0.003	0.002	(0.0004)	0.005	.	.	0.004	0.002	.	38 mm Ø x ~7 or 19+ mm
BS 82E	0.006	.	0.0024	.	.	.	0.006	0.003	.	38 mm Ø x ~7 or 19+ mm
BS 9942	0.004	(0.004)	0.0014	(0.0023)	.	.	0.006	(0.002)	.	44 mm Ø x ~7 or 19+ mm
BS 9842	0.014	(0.002)	0.0025	(0.0044)	.	.	0.005	0.003	.	38 mm Ø x ~7 or 19+ mm
ECRM 272-1D	0.0046	0.0116	0.0018	.	.	0.0007	.	0.00096	0.0031	38 mm Ø x 25 or 30 mm
BS 94C	0.004	.	(0.0005)	0.0061	.	.	0.006	.	.	44 mm Ø x ~7 or 19+ mm
BS 87F	0.004	0.005	(0.0006)	0.005	.	.	0.004	0.004	.	41 mm Ø x ~7 or 19+ mm
BS SS3951	0.002	.	(0.0006)	0.0075	.	.	0.007	(0.002)	.	41 mm Ø x ~7 or 19+ mm

COPPER IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	Cu	Ni	Cr	C	Mn	P	S	Si	Co	Mo	N	Nb	Ti	V	W
1	13X PH 3N *	5.8	3.05	16.1	0.11	0.38	0.015	0.02	1.25	0.30	0.75	0.11	0.43	0.02	0.24	.
1	13X PH4P	5.53	4.07	15.5	0.033	0.69	0.021	0.019	0.64	0.50	0.255	0.082	0.355	0.075	0.55	.
1	13X PH 2M	4.03	3.56	16.80	0.0598	1.184	0.0201	0.0419	0.502	0.0927	1.009	0.052	0.143	0.049	0.1028	.
2	BS 9621	3.42	4.61	14.93	0.035	0.31	0.017	0.0011	0.468	0.029	0.063	0.013	0.27	(0.001)	0.096	(0.01)
2	BS 185A	3.41	4.43	14.46	0.033	0.49	0.022	0.002	0.38	0.026	0.30	0.027	0.32	(0.001)	0.048	(0.014)
2	BS 17-4PHB	3.35	4.53	15.60	0.042	0.56	0.021	0.024	0.42	0.040	0.11	0.046	0.31	.	0.059	.
2	BS 9622	3.34	4.34	14.34	0.032	0.63	0.019	0.004	0.42	0.040	0.27	0.028	0.33	(0.001)	0.074	(0.020)
2	BS 17-4PHA	3.30	4.69	15.40	0.018	0.85	0.023	0.022	0.40	0.072	0.34	0.022	0.204	.	0.043	.
2	CT 20 Cb-3	3.28	33.55	19.63	0.034	0.19	0.017	0.003	0.38	0.035	2.25	.	0.86	.	0.053	.
1	IARM 22C	3.24	4.63	14.28	0.042	0.63	0.027	0.0004	0.39	0.086	0.48	0.030	0.29	0.002	0.068	0.031
2	CT 630	3.25	4.20	15.94	0.036	0.39	0.018	0.013	0.63	0.11	0.11	0.028	0.36	.	0.022	.
1	BS 17-4PHC *	3.2	4.3	15.4	0.034	0.80	0.022	0.027	0.40	0.078	0.45	<0.05	0.26	<0.005	0.092	0.12
2	BS 187C	3.17	32.93	20.16	0.020	0.77	0.024	<0.002	0.77	0.096	2.07	0.022	0.36	(0.001)	0.059	.
2	BS 187A	3.10	33.06	19.75	0.022	0.52	0.017	0.0025	0.26	0.32	2.06	0.0157	0.57	(0.002)	0.10	(0.02)
1	13X PH17400A	3.09	4.252	15.74	0.0200	0.829	0.0202	0.0215	0.349	0.0411	0.061	0.0342	0.184	.	0.112	(0.0056)
1	ECRM 273-1D	3.046	4.85	14.747	0.0336	0.785	0.0131	0.0004	0.378	0.0391	0.2462	0.0444	0.221	.	0.0512	.
1	VS LG64	2.88	28.3	24.7	0.049	0.75	0.017	0.0032	0.76	.	2.89	.	0.048	0.64	0.094	0.013
1	SRM C2400	2.63	4.07	17.06	0.036	0.71	0.013	0.003	0.61	0.10	0.23	.	0.15	.	0.092	.
2	CT 455	2.32	8.22	11.37	0.012	0.074	0.010	0.005	0.13	.	0.027	0.002	0.28	1.18	.	.
2	BS SS1962	2.22	8.32	11.42	0.008	0.06	0.006	0.0025	0.06	(0.015)	0.008	0.0025	0.27	1.11	0.071	(<0.02)
1	13X 45500A	2.20	8.36	11.39	0.0041	0.0263	0.0049	0.0020	0.059	0.0152	0.0185	0.0030	0.250	1.187	0.0689	.
2	BS SS1961	2.11	8.31	11.61	0.009	0.049	0.008	0.0038	0.056	0.036	0.020	0.0025	0.26	1.16	0.074	(0.01)
1	IARM 16C	2.08	8.23	11.34	0.003	0.024	0.007	0.0046	0.03	0.017	0.009	0.0030	0.248	1.16	0.070	0.008
1	SS 475	1.94	5.66	14.14	0.050	0.89	0.037	0.008	0.21	0.22	1.59	.	0.22	.	0.088	.
1	BS 9812	1.65	6.61	14.82	0.031	0.485	0.018	0.004	0.43	0.110	0.76	0.0195	0.645	(0.005)	0.088	0.025
1	BS 9811	1.63	6.55	14.87	0.027	0.380	0.016	0.0010	0.36	0.055	0.744	0.0196	0.62	(0.003)	0.086	0.013
1	IARM 318B	1.63	5.71	15.9	0.050	1.02	0.022	0.0006	0.41	0.100	1.57	0.032	0.086	0.014	0.115	0.087
1	13X PH2S143A	1.61	5.20	13.45	0.044	0.544	0.0205	0.0022	0.478	0.0475	1.325	0.024	0.222	0.087	0.019	.
1	BS 179B	1.56	6.17	25.9	0.0161	0.890	0.0243	0.0002	0.371	0.0394	3.34	0.239	0.008	(0.0008)	0.079	0.053
1	IARM 15C	1.54	6.35	14.39	0.032	0.760	0.019	0.0018	0.26	0.024	0.722	0.0148	0.63	(0.002)	0.041	(0.020)
1	13X NSA 7B	1.53	6.37	25.69	0.013	0.864	0.0160	0.0005	0.278	0.047	3.28	0.232	(0.009)	.	0.080	0.133
1	BS 179C	1.53	6.10	25.9	0.0164	0.878	0.0236	0.0003	0.373	0.0386	3.34	0.236	0.009	(0.0005)	0.080	0.056
1	BS 450 *	1.52	6.2	14.4	0.03	0.60	0.016	0.001	0.32	0.03	0.67	0.02	0.59	<0.05	0.05	0.018
2	CT 450	1.49	6.36	15.20	0.036	0.39	0.014	0.006	0.29	0.16	0.80	0.028	0.67	.	0.043	.
1	ECRM 295-1D	1.481	24.40	19.51	0.0166	1.758	0.0167	0.0004	0.418	0.0450	3.996	0.0615	.	.	0.0453	.
1	IARM 239B	1.48	5.78	25.9	0.013	0.86	0.025	0.0005	0.39	0.048	3.42	0.25	0.024	0.002	0.099	0.106
1	13X NSA 7A	1.42	5.67	25.91	0.0209	0.951	0.022	0.0009	0.359	.	3.25	0.247	0.015	.	.	.
2	HRT FE2004-H	1.33	24.25	19.08	0.021	1.83	0.021	0.004	0.47	0.046	4.17	.	0.046	0.005	0.042	.
1	13X PH 7F	0.77	5.41	13.16	0.118	1.487	0.028	0.0057	1.402	0.049	2.52	0.044	0.241	0.0196	0.043	.

Number	Al	Ag	As	B	Ca	Cd	Fe	Mg	O	Pb	Sb	Sn	Ta	Units
13X PH 3N *	0.05	.	.	0.005	## BACKORDERD UNTIL FINAL	.	.	-40 mm Ø x -15 mm
13X PH4P	0.029	.	.	0.0031	-40 mm Ø x -15 mm
13X PH 2M	0.0419	.	.	0.0047	-40 mm Ø x -15 mm
BS 9621	0.003	.	.	0.0004	(0.0001)	0.003	(0.002)	38 mm Ø x -7 or 19+ mm
BS 185A	0.002	.	.	0.0017	(0.0002)	.	.	.	(0.0021)	.	.	0.007	(0.002)	38 mm Ø x -7 or 19+ mm
BS 17-4PHB	.	.	.	0.0036	(0.002)	41 mm Ø x -7 or 19+ mm
BS 9622	0.002	.	.	0.0004	0.006	.	38 mm Ø x -7 or 19+ mm
BS 17-4PHA	.	.	.	0.0016	last	(0.002)	38 mm Ø x -7 or 19+ mm
CT 20 Cb-3	.	0.0019	.	0.0023	0.002	.	0.003	.	30-35 mm Ø x -19 mm
IARM 22C	0.006	.	(0.004)	0.0006	(0.0002)	.	.	.	0.0021	(0.00003)	.	0.013	(0.004)	31 mm Ø x 2 or 18 mm
CT 630	.	0.0004	.	0.0018	0.001	.	0.007	.	30-35 mm Ø x -16 mm
BS 17-4PHC *	0.002	.	0.004	0.003	<0.005	.	[74.7]	.	<0.05	<0.005	.	0.010	.	44 mm Ø x -7 or 19+ mm
BS 187C	0.10	.	.	(0.0019)	0.0024	last of stock	.	0.004	(0.002)	44 mm Ø x 12 mm
BS 187A	(0.009)	.	.	0.0022	0.0029	last of stock	.	0.003	<0.002	41 mm Ø x -7 or -12 mm
13X PH17400A	41 mm Ø x -15 mm
ECRM 273-1D	.	.	0.0030	0.0021	.	40 mm Ø x 20 mm
VS LG64	0.189	-47 mm Ø x -30 mm
SRM C2400	32 mm Ø x 19 mm
CT 455	.	0.0002	.	0.0024	<0.001	.	0.004	.	30-35 mm Ø x -19 mm
BS SS1962	0.067	.	0.002	0.0018	(0.001)	.	.	0.004	.	38 mm Ø x -7 or 19+ mm
13X 45500A	0.073	0.0048	(0.0050)	-38 mm Ø x -15 mm
BS SS1961	0.069	.	0.004	0.0022	(0.002)	.	.	0.004	.	38 mm Ø x 12+ mm last
IARM 16C	0.072	.	(0.003)	0.0011	0.0014	.	.	(0.003)	.	31 mm Ø x 2 or 18 mm
SS 475	0.013	0.015	.	38 mm Ø x 19 mm
BS 9812	(0.002)	.	(0.005)	(0.0003)	0.0012	.	.	.	(0.007)	25(pre-17025)	.	0.004	.	50 mm Ø x -7 or 19+ mm
BS 9811	(0.003)	.	(0.003)	(0.0003)	0.0014	.	.	.	(0.0060)	25(pre-17025)	.	0.004	.	38 mm Ø x -7 or 19+ mm
IARM 318B	(0.004)	.	(0.004)	0.0003	0.009	.	.	0.004	(0.004)	31 mm Ø x 2 or 18 mm
13X PH2S143A	-40 mm Ø x -15 mm
BS 179B	0.0070	.	0.0036	0.0015	(0.0004)	17025	[61.5]	(0.0004)	0.0037	(0.00002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm
IARM 15C	(0.005)	.	0.0044	(0.0006)	(0.0004)	.	.	.	(0.003)	(0.003)	(0.003)	0.009	(0.004)	31 mm Ø x 2 or 18 mm
13X NSA 7B	0.0142	.	.	0.0018	0.0009	0.0020	.	.	-41 mm Ø x -15 mm
BS 179C	0.0078	.	0.0034	0.0015	(0.0003)	17025	[61.6]	(0.0004)	0.0038	(0.00002)	0.0005	0.0018	(0.0006)	38 mm Ø x -7 or 19+ mm
BS 450 *	0.004	.	0.003	<0.005	<0.005	.	[75.4]	.	<0.05	0.002	<0.05	0.004	.	44 mm Ø x -7 or 19+ mm
CT 450	.	0.0013	0.001	.	0.008	.	30-35 mm Ø x -15-19 mm
ECRM 295-1D	0.0203	.	0.0041	0.0018	.	.	48.36	(0.0003)	.	.	0.0007	0.0025	.	38 mm Ø x 25 or 30 mm
IARM 239B	0.008	.	0.0008	(0.004)	.	.	(0.003)	.	31 mm Ø x 2 mm
13X NSA 7A	(0.009)	42 mm Ø x 15 mm last
HRT FE2004-H	0.005	.	.	0.0021	32 mm Ø x 20 mm
13X PH 7F	0.012	-40 mm Ø x -15 mm

MARAGING STEEL AND COBALT IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM

#	Number	Co	Mo	Ni	Cr	C	Mn	P	S	Si	Cu	Al	B	N	Nb	Ti
1	IARM 326A	48.4	(0.002)	0.037	(0.002)	(0.002)	0.003	0.0013	0.0011	0.029	(0.002)	(0.003)	(0.001)	0.0004	0.038	(0.002)
2	CT ISO070A	29.00	0.006	24.47	5.54	0.014	0.015	0.003	<0.001	0.32	0.010	0.47	0.0038	.	4.63	0.82
1	IMZ 521	20.25	4.84	8.63	0.040	0.015	0.039	0.0031	0.0058	0.072	0.027	.	.	0.0113	.	.
1	IMZ 522	18.72	6.45	11.47	0.022	0.0088	0.032	(0.003)	0.0043	0.048	0.019	.	.	0.0045	(0.008)	0.54
1	IMZ 520	17.66	4.92	10.10	0.242	0.011	0.070	0.0043	0.019	0.094	0.080	.	(0.001)	0.0105	(0.008)	(0.007)
1	IARM 98B	17.0	0.010	29.4	0.012	0.007	0.18	0.002	0.0007	0.17	0.028	0.07	0.001	0.0024	0.002	0.03
1	IMZ 523	14.44	6.67	15.94	0.048	0.0098	0.051	(0.004)	0.0039	0.043	0.059	.	.	0.0037	(0.008)	0.70
1	IARM 242A	13.5	1.21	11.1	3.00	0.24	0.018	0.002	0.0004	0.02	0.007	0.004	(0.0005)	0.0003	0.004	0.009
2	CT ISO045A	13.39	1.18	11.38	3.12	0.228	0.002	0.001	0.0004	<0.010	0.006	0.004	.	.	.	0.005
1	IARM 309A	12.3	4.71	18.4	0.053	0.0059	0.018	0.004	0.0006	0.020	0.023	0.11	0.0032	0.0010	0.004	1.47
1	IMZ 524	12.25	4.95	13.75	0.085	0.012	0.68	(0.004)	0.004	0.13	0.024	.	.	0.0038	(0.007)	0.85
1	DSZU C093	12.08	3.79	15.80	0.42	0.013	0.32	(0.006)	(0.007)	(0.10)	(0.12)	0.17	.	.	.	1.56
1	BS 161A	9.22	4.82	18.40	0.12	0.004	0.031	0.004	0.0007	0.032	0.22	0.14	0.0023	(0.002)	(0.004)	0.65
2	CT 300	9.07	4.97	18.51	0.034	0.005	0.032	0.005	0.004	0.030	0.047	0.12	0.0020	.	.	0.69
1	13X 14934Q	9.03	4.22	17.60	0.388	0.0254	0.254	0.024	0.0288	0.502	.	0.15	.	0.0132	.	0.694
1	DSZU C091	8.07	4.98	18.20	0.12	0.035	0.092	(0.006)	(0.011)	(0.09)	(0.12)	0.05	.	.	.	0.81
1	IARM 308A	7.80	4.78	18.53	0.023	0.003	0.019	0.004	0.0005	0.014	0.018	0.097	0.0029	0.0013	0.003	0.46
1	ECRM 285-2D	7.76	4.99	18.07	0.0236	0.0018	0.0168	0.0053	0.0025	0.0117	0.0094	0.1067	0.0009	0.0007	.	0.520
2	CT 250	7.54	4.88	18.44	0.008	0.002	0.006	0.003	0.002	0.008	0.008	0.058	0.0024	.	.	0.41
2	DSZU C55	5.75	1.32	2.24	14.9	(0.19)	0.73	(0.042)	.	0.68	.	.	.	(0.11)	0.27	.
1	DSZU C092	5.21	5.50	20.12	0.23	0.015	0.27	(0.006)	(0.009)	(0.10)	(0.16)	(0.006)	.	.	.	(0.008)
2	DSZU C53	5.20	1.71	1.47	14.8	(0.26)	0.82	(0.036)	.	0.29	0.13	.
2	DSZU C54	5.19	1.47	1.88	18.5	(0.06)	0.60	(0.036)	.	0.56	.	.	.	(0.13)	0.40	.
2	DSZU C51	4.07	0.68	1.67	10.8	(0.16)	0.40	(0.019)	.	0.25	.	.	.	(0.09)	0.10	.
2	DSZU C52	3.35	1.08	1.68	11.0	(0.17)	0.24	(0.018)	.	0.12	0.15	.
1	BS 85D	0.97	0.59	9.98	17.09	0.048	1.69	0.024	0.024	0.54	0.45	0.13	(0.001)	(0.02)	0.062	0.48

Number	As	Ca	Fe	Mg	O	Sb	Sn	Ta	V	W	Zr	Units
IARM 326A	<0.005	.	49.6	(0.001)	0.0082	.	<0.001	(0.01)	1.94	(0.001)	0.002	31 mm Ø x 2 mm
CT ISO070A	.	.	34.66	<0.01	0.043	<0.01	.	30-35 mm Ø x ~16 mm
IMZ 521	(0.002)	.	3.97	5.23	.	38 mm Ø x 20 mm
IMZ 522	(0.001)	.	2.21	2.25	.	38 mm Ø x 20 mm
IMZ 520	(0.002)	.	4.03	4.90	.	38 mm Ø x 20 mm
IARM 98B	<0.002	<0.0005	52.9	0.0040	0.0021	.	0.002	<0.05	(0.003)	(0.02)	<0.01	31 mm Ø x 2 mm
IMZ 523	(0.001)	.	2.01	1.87	.	38 mm Ø x 20 mm
IARM 242A	0.0006	.	(0.001)	0.008	0.01	<0.01	.	31 mm Ø x 2 mm
CT ISO045A	.	.	70.70	30-35 mm Ø x ~19 mm
IARM 309A	0.0005	.	(0.001)	(0.006)	0.01	0.01	0.008	31 mm Ø x 2 or 18 mm
IMZ 524	(0.003)	3.02	1.84	.	38 mm Ø x 20 mm
DSZU C093	~40 mm Ø x 17 mm
BS 161A	(0.002)	(0.0008)	<u>25(pre-17025)</u>	(0.0004)	.	(0.0015)	(0.03)	0.031	(0.008)	(0.002)	(0.002)	38 mm Ø x ~7 or 19+ mm
CT 300	30-35 mm Ø x ~16 mm
13X 14934Q	40 mm Ø x ~12 mm last
DSZU C091	~40 mm Ø x 17 mm
IARM 308A	0.0005	.	0.001	<0.01	0.01	0.01	0.01	31 mm Ø x 2 or 18 mm
ECRM 285-2D	0.0050	38 mm Ø x 25 or 30 mm
CT 250	30-35 mm Ø x ~19 mm
DSZU C55	0.29	(1.17)	.	42 mm Ø x 25 mm
DSZU C092	~40 mm Ø x 17 mm
DSZU C53	0.33	(0.59)	.	42 mm Ø x 25 mm
DSZU C54	0.47	(0.71)	.	42 mm Ø x 25 mm
DSZU C51	0.15	(0.32)	.	42 mm Ø x 25 mm
DSZU C52	0.10	(0.91)	.	42 mm Ø x 25 mm
BS 85D	(0.01)	0.0004	[67.8]	.	(0.002)	(0.001)	0.0062	(0.001)	0.132	(0.07)	(0.004)	38 mm Ø x ~7 or 19+ mm

TUNGSTEN IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	W	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	VS LG57	4.24	25.2	13.70	0.016	0.52	0.011	0.0023	0.56	0.080	.	0.401	.	.	1.81	0.65
1	13X 14219K	4.17	12.66	21.46	0.0997	0.482	0.0401	0.0456	1.504	0.138	0.0475	0.169	.	0.140	.	0.0188
1	13X 14212S	3.68	8.81	21.64	0.119	0.166	0.032	0.0386	2.47	0.611	0.1090	0.520	0.0055	0.550	.	0.1175
1	VS LG59	3.08	35.1	15.81	0.073	1.15	0.011	0.0083	0.63	0.083	.	0.094	.	0.106	1.12	0.273
1	113X 14215L	3.02	15.86	22.89	0.136	1.110	0.0050	0.0068	0.596	0.0110	0.0057	0.0048	.	0.0196	.	0.0480
2	BS 183A	2.60	1.85	12.14	0.172	0.35	0.016	0.0040	0.37	0.093	0.036	0.12	0.0256	0.006	0.002	0.090
1	IARM 20C	2.59	1.93	12.15	0.18	0.30	0.018	0.007	0.35	0.060	0.031	0.12	0.0222	0.010	(0.003)	0.086
1	IMZ 161	1.05	0.55	12.90	0.074	0.29	0.023	0.023	0.65	0.56	.	1.10	.	.	.	0.33

Number	Al	As	B	Ca	O	Sb	Sn	Units
VS LG57	0.151	~47 mm Ø x ~30 mm
13X 14219K	~40 mm Ø x ~15 mm
13X 14212S	~40 mm Ø x ~15 mm
VS LG59	0.079	~47 mm Ø x ~30 mm
13X 14215L	~40 mm Ø x ~15 mm
BS 183A	0.002	(0.002)	(<0.0005)	0.0020	0.0065	(0.001)	0.003	38 mm Ø x ~7 or 19+ mm
IARM 20C	(0.004)	.	.	.	0.0068	.	0.004	31 mm Ø x 2 mm
IMZ 161	40 mm Ø x 40 mm

MANGANESE STAINLESS STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

* Provisional Analysis

# Number	Mn	Ni	Cr	C	P	S	Si	Cu	Mo	Al	Co	N	Nb	V	W
1 IARM 294A	21.6	2.9	19.7	0.017	0.026	0.0028	0.43	0.34	1.8	(0.01)	0.021	0.78	(0.03)	0.046	(0.01)
1 IARM 295A	19.7	1.84	18.0	0.021	0.028	0.0041	0.36	0.113	0.97	(0.01)	0.021	0.62	0.018	0.046	0.016
1 ECRM 294-1D	18.68	0.429	17.98	0.0657	0.0271	0.00031	0.283	0.0242	0.0861	(0.0095)	0.0288	0.566	(0.00117)	0.0694	(0.00114)
1 IARM 214A	18.3	2.33	12.36	0.018	0.033	0.002	1.00	0.36	0.44	(0.002)	0.021	0.27	0.23	0.04	0.02
1 VS RG20/1	15.77	0.673	14.35	0.064	(0.02)	(0.01)	0.81	0.265	0.089	.	.	.	0.175	0.166	0.007
1 VS RG22/1	13.41	3.94	13.25	0.054	(0.02)	(0.008)	0.63	0.358	0.121	.	.	.	0.38	0.125	0.137
2 BS 193	12.11	1.82	18.48	0.104	0.018	0.002	0.66	0.088	0.21	(0.003)	0.028	0.37	0.014	0.107	(0.007)
2 CT ISO035A	12.04	1.81	18.48	0.102	0.023	0.002	0.59	0.17	0.28	<0.004	0.037	0.33	0.004	0.058	0.002
1 IARM 296A	10.6	1.71	11.2	0.074	0.027	0.002	0.38	0.12	0.60	(0.005)	0.018	0.23	0.043	0.056	(0.01)
2 BS 190	9.72	6.74	19.57	0.022	0.015	0.001	0.46	0.072	0.15	(0.004)	0.044	0.255	(0.004)	0.11	0.015
2 CT ISO129A	9.31	6.86	19.62	0.030	0.002	<0.001	0.40	0.152	0.25	0.014	0.102	0.264	0.025	0.144	0.03
1 IARM 19C *	9.02	6.40	19.51	0.012	0.027	0.0007	0.31	0.45	0.40	0.007	0.087	0.32	0.028	0.090	0.037
1 13X NSC6A	8.85	6.52	20.47	0.0266	0.0049	0.0055	0.523	0.0064	(0.002)	(0.009)	.	0.235	.	0.0052	.
1 VS RG23/1	8.74	1.98	18.5	0.045	(0.02)	(0.004)	0.49	0.099	0.401	.	.	.	0.24	0.69	0.3
1 13X NSC3AA	8.43	5.00	22.32	0.868	.	0.0295	1.51	0.292	0.057	0.051	.	0.480	2.45	0.098	.
2 BS 181A	8.16	8.15	16.52	0.071	0.019	0.001	4.03	0.18	0.21	0.022	0.072	0.148	0.017	0.094	0.04
1 BS 181B	8.07	8.18	16.17	0.070	0.021	0.0009	3.94	0.206	0.173	0.0119	0.044	0.158	0.026	0.044	0.016
1 13X NSC2Q	8.02	3.63	20.95	0.574	0.033	0.014	1.02	1.01	0.339	0.37	0.037	0.299	2.03	0.293	0.063
1 13X 21800A	8.00	8.32	16.81	0.0765	0.032	0.0011	4.03	0.431	0.325	0.012	0.0943	0.125	0.007	0.0619	.
1 NM 303	7.21	1.59	12.68	0.16	0.035	0.050	0.40	0.68	0.17	.	0.063	.	.	0.071	.
1 SRM 1297	7.11	5.34	16.69	0.066	0.038	0.0033	0.397	0.442	0.331	.	0.127	.	.	0.080	.
1 VS RG21/1	6.39	7.52	15.53	0.169	(0.02)	(0.008)	1.95	0.17	0.88	.	.	.	0.48	1.71	(0.2)
3 CZ SL-5A	5.8	4.94	11.7	0.37	0.021	0.014	0.36	2.90	4.12	0.035	0.26	.	0.20	0.21	0.78
2 BS 191	5.71	5.34	16.33	0.098	0.024	0.023	3.73	0.33	0.36	(0.002)	0.11	0.117	0.024	0.083	0.033
1 VS RG19/1	5.63	17.73	24.5	0.064	(0.02)	(0.009)	0.90	(0.2)	0.166	.	.	.	0.108	0.407	0.206
1 13X NSA4B	5.55	17.62	23.85	0.115	0.0302	0.0095	0.519	0.595	4.32	0.0048	.	0.446	0.154	.	.
1 IARM FeNi50-18	5.27	11.90	21.0	0.030	0.026	(0.0013)	0.24	0.28	2.01	(0.006)	0.081	0.26	0.18	0.121	0.023
1 13X NSA10A	5.23	12.98	20.67	0.0180	0.0206	0.0007	0.375	0.170	2.636	0.060	0.060	0.342	0.143	0.151	(0.061)
2 BS 180A	5.05	13.19	21.09	0.018	0.012	0.001	0.32	0.067	2.04	0.012	0.039	0.334	0.20	0.20	0.02
1 IARM 292A	5.0	1.47	21.35	0.030	0.018	0.001	0.75	0.29	0.097	0.010	0.031	0.245	0.009	0.084	0.01
1 BS 180B	4.65	11.9	21.5	0.022	0.017	0.0008	0.46	0.201	2.20	(0.007)	0.111	0.315	0.131	0.149	0.050
2 HRT FE2017-H	4.43	15.45	20.15	0.015	0.022	0.002	0.34	0.21	3.17	.	.	0.311	0.131	.	.
1 IARM 17D	4.15	11.83	21.06	0.041	0.026	0.0018	0.416	0.412	1.52	0.0032	0.23	0.311	0.14	0.118	0.056
1 13X NSC7A	3.80	7.41	23.63	0.410	0.0155	0.0091	0.803	0.144	0.448	(0.096)	0.308	0.337	0.509	0.123	0.052
1 13X NSC7B	3.55	7.50	23.9	0.397	0.019	0.0098	0.88	0.220	0.435	0.204	0.297	0.429	0.82	0.167	0.041
1 13X NSC5C *	2.07	4.38	21.6	0.53	.	0.025	1.15	0.85	0.48	0.24	0.088	0.27	2.3	0.105	0.048

Number	As	B	Ca	O	Pb	Sb	Sn	Ta	Te	Ti	Zr	Units
IARM 294A	.	(0.003)	.	(0.003)	.	.	(0.006)	(0.003)	.	(0.002)	(0.002)	31 mm Ø x 2 or 18 mm
IARM 295A	.	0.002	.	(0.003)	.	.	0.004	.	.	0.0019	(0.001)	31 mm Ø x 2 or 18 mm
ECRM 294-1D	0.0037	(<0.00005)	(0.00026)	.	(0.000128)	(0.00053)	(0.0014)	.	(<0.00008)	(0.0008)	(0.0001)	40 mm Ø x 20 mm
IARM 214A	.	(0.001)	.	0.0026	.	.	0.008	.	.	0.002	.	31 mm Ø x 2 or 18 mm
VS RG20/1	0.093	.	-45 mm Ø x ~30 mm
VS RG22/1	0.33	.	-45 mm Ø x ~30 mm
BS 193	.	0.0007	0.0020	(0.004)	.	.	0.004	.	.	0.003	.	32 mm Ø x ~7 or 19+ mm
CT ISO035A	.	Fe: 65.91	.	(0.0001)	.	.	0.003	.	.	0.001	<0.001	30-35 mm Ø x ~19 mm
IARM 296A	.	(0.001)	.	(0.003)	.	.	0.007	.	.	(0.002)	.	31 mm Ø x 2 mm
BS 190	.	0.0005	.	0.0045	.	.	0.003	.	.	0.002	.	38 mm Ø x ~7 or 19+ mm
CT ISO129A	.	Fe: 62.62	30-35 mm Ø x ~16 mm
IARM 19C *	(0.004)	0.0011	.	0.003	.	.	0.0061	0.005	.	0.003	.	31 mm Ø x 2 or 18 mm
13X NSC6A	40 mm Ø x 13 mm HIP
VS RG23/1	0.21	.	-45 mm Ø x ~30 mm
13X NSC3AA	-40 mm Ø x ~15 mm
BS 181A	.	0.0009	.	0.0010	.	.	0.005	.	.	0.007	last	38 mm Ø x ~7 to ~9 mm
BS 181B	(0.002)	(0.0008)	(0.001)	0.0010	(0.0005)	(0.0007)	(0.004)	Fe:62.9	17025	0.0051	(0.0004)	38 mm Ø x ~7 or 19+ mm
13X NSC2Q	-40 mm Ø x ~15 mm
13X 21800A	.	(0.001)	-38 mm Ø x ~15 mm
NM 303	35 mm Ø x 20 mm
SRM 1297	32 mm Ø x 19 mm
VS RG21/1	0.18	.	-45 mm Ø x ~30 mm
CZ SL-5A	0.005	0.004	0.07	.	0.004	.	-39 mm Ø x 25 mm
BS 191	.	(0.0006)	.	0.002	.	.	(0.006)	0.002	.	0.012	.	38 mm Ø x ~7 or 19+ mm
VS RG19/1	0.14	.	-45 mm Ø x ~30 mm
13X NSA4B	-40 mm Ø x ~15 mm
IARM FeNi50-18	.	.	.	(0.006)	.	.	(0.007)	.	.	(0.002)	.	31 mm Ø x 2 or 18 mm
13X NSA10A	.	0.0031	-38 mm Ø x ~15 mm
BS 180A	.	(0.0023)	.	0.003	.	.	(0.002)	.	last	(0.002)	.	37 mm Ø x ~7 - ~45 mm
IARM 292A	.	0.0011	.	0.0024	.	.	0.004	(0.006)	.	0.005	.	31 mm Ø x 2 or 18 mm
BS 180B	(0.004)	0.0011	0.0009	0.0043	17025	(0.0007)	0.0040	(0.003)	Fe:58.5	(0.005)	(0.0009)	38 mm Ø x ~7 or 19+ mm
HRT FE2017-H	30 mm x 30 mm x 10 mm
IARM 17D	0.005	0.001	(0.002)	0.003	(0.0002)	(0.001)	0.0044	(0.003)	.	0.010	(0.002)	31 mm Ø x 2 or 18 mm
13X NSC7A	-40 mm Ø x ~13 mm last
13X NSC7B	-40 mm Ø x ~15 mm
13X NSC5C *	-40 mm Ø x ~15 mm

CRM NICKEL BINARIES

analysis listed in mass %

-40 mm Ø x ~15 mm

Number	Ni	C	Mn	P	S	Si	Cu	Cr	Al	Co	N	Mg	Mo	Nb	Ti	W
14X FeNi50C	51.5	0.0245	0.057	0.0168	0.16	0.151	0.089	0.066	0.319	0.416
14X FeNi45C	45.88	0.0082	0.0222	0.026	0.0015	0.77	0.089	0.076	0.98	0.572
14X 94100A	41.00	0.0055	0.443	0.0051	0.0027	0.103	0.0628	0.0265	.	0.0208	0.0016	0.0021	0.0053	(0.01)	0.0011	0.0017
14X FeNi35D	34.17	0.035	0.303	0.0400	0.146	0.255	0.0363	0.409	(0.004)	0.400
14X FeNi25C	25.10	0.0084	0.013	0.011	0.58	(0.020)	0.035	0.033	0.10	0.74
14X FeNi20B	20.06	0.0137	0.0284	0.010	0.0089	1.12	0.074	0.102	0.018	0.994	last
14X FeNi10A	10.12	0.095	0.272	0.015	0.027	0.061	0.029	0.070	0.025	.	0.0055
14X FeNi8A	8.10	0.097	0.330	0.015	0.029	0.097	0.030	0.250	0.029	.	0.0061
14X FeNi6A	6.08	0.100	0.330	0.0155	0.028	0.075	0.028	0.073	0.025	.	0.0055

SULFUR AND PHOSPHORUS IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	S	P	Ni	Cr	C	Mn	Si	Cu	Al	Co	Mo	N	Nb	Ti	V
2	CT 416	0.36	0.018	0.24	13.15	0.088	0.52	0.63	0.004	.	0.019	0.065	0.020	.	.	0.025
1	IARM 10D	0.334	0.0178	0.291	12.42	0.110	1.11	0.475	0.192	(0.0027)	0.0187	0.148	0.0241	0.0027	0.0015	0.051
2	BS 150	0.33	0.020	0.19	18.61	0.048	1.71	0.43	0.042	0.002	0.024	1.97	0.029	0.003	.	0.054
1	SRM 1223	0.329	0.018	0.232	12.64	0.127	1.08	0.327	0.081	.	.	0.053	.	.	.	0.068
2	BS 90F	0.328	0.023	0.30	13.01	0.085	0.53	0.58	0.12	(0.006)	0.021	0.14	0.037	0.011	.	0.076
1	BS 303	0.326	0.028	8.17	17.23	0.044	1.80	0.415	0.627	0.0019	0.071	0.410	0.023	0.008	0.017	0.056
1	13X 30300A	0.312	0.0205	8.60	17.62	0.041	1.83	0.422	0.025	.	0.0255	0.334	0.034	.	.	0.091
2	CT 303	0.31	0.029	9.08	17.78	0.070	1.64	0.58	0.49	.	0.16	0.41	.	.	.	0.044
1	IARM 355A	0.31	0.0186	0.427	17.81	0.0274	0.47	0.435	0.083	0.0016	0.047	0.337	0.0439	0.0095	0.0020	0.038
2	BS 154	0.302	0.027	0.25	17.58	0.030	0.40	1.26	0.063	(0.002)	0.019	0.31	0.039	0.005	.	0.046
2	13X 12549K	0.29	0.092	1.26	11.70	0.16	0.34	0.43	0.10	.	0.52	1.49	.	0.23	.	.
2	BS 153	0.280	0.018	0.140	17.38	0.026	0.41	0.53	0.052	0.002	0.017	0.30	0.021	0.002	(0.004)	0.045
2	BS 152	0.275	0.022	0.14	13.41	0.320	0.36	0.44	0.050	(0.002)	0.015	0.061	0.020	0.006	.	0.051
3	CZ SP-1A	0.26	0.024	8.6	17.7	0.047	1.87	0.33	0.52	0.004	0.095	0.42	.	0.012	0.02	0.058
1	13X 12548M	0.219	0.027	1.075	12.96	0.188	0.577	0.425	0.230	.	0.353	1.318	0.0500	0.586	.	.
1	IARM 352A	0.21	0.0182	0.269	13.11	0.341	1.13	0.357	0.148	(0.0025)	(0.016)	0.38	0.029	(0.012)	0.0015	0.028
1	13X 43020A	0.189	0.0246	0.517	16.07	0.147	1.439	0.415	0.0687	0.0047	0.0191	0.226	0.0212	0.0102	.	0.0542
1	IMZ 154	0.16	0.040	9.86	17.71	0.076	2.18	0.89	0.33	(0.16)	0.105	2.58	.	.	1.00	0.073
1	NCS HS41751A	0.16	0.035	8.07	17.41	0.075	1.70	0.71	0.26	.	0.13	0.33	0.077	.	.	0.068
2	BS 155	0.145	0.014	0.13	16.64	1.00	0.35	0.40	0.035	(0.001)	0.019	0.46	0.032	0.002	.	0.10
1	13X 12536S	0.136	0.052	12.07	15.30	0.149	0.406	0.865	0.065	0.049	0.298	2.54	0.062	.	0.105	.
1	13X 12536T	0.090	0.0449	12.12	16.09	0.146	0.374	0.546	0.0793	0.108	0.280	2.48	0.0084	0.060	0.444	0.0513
1	13X 12535BE	0.0591	0.0400	14.79	16.95	0.229	0.342	1.407	0.130	0.194	0.146	4.09	0.029	.	0.625	0.252
1	SRM C1154a	0.051	0.06	13.08	19.31	0.100	1.44	0.53	0.44	.	0.38	0.068	.	.	.	0.135
1	13X 19003C	0.046	0.0382	12.46	18.99	0.047	1.138	0.497	0.171	.	0.105	2.50	0.077	0.120	.	0.0486
1	VS LG58	0.0280	0.0135	4.26	23.4	0.48	0.99	0.292	0.388	.	.	2.41	.	0.214	0.039	0.264
1	13X 18004B	0.0191	0.068	12.67	21.57	0.099	1.400	1.21	0.050	0.011	0.211	0.601	0.061	0.749	.	0.161
2	13X 19004B	0.014	0.069	17.9	22.8	0.066	1.96	0.36	0.022	.	.	3.62	.	0.18	.	.
1	13X 19004C	0.0135	0.074	17.90	22.77	0.075	2.01	0.35	0.0112	0.030	0.0501	3.43	.	0.152	.	0.041

Number	Ag	As	B	O	Pb	Sn	Ta	W	Units
CT 416	0.0002	.	.	.	<0.001	0.005	.	.	30-35 mm Ø x ~16 mm
IARM 10D	.	(0.007)	(0.002)	(0.005)	.	0.010	.	(0.005)	31 mm Ø x 2 or 18 mm
BS 150	.	.	.	0.012	.	(0.003)	.	0.01	35 mm Ø x ~7 or 19+ mm
SRM 1223	32 mm Ø x 19 mm
BS 90F	.	.	.	0.011	.	0.005	.	0.032	38 mm Ø x ~7 or 19+ mm
BS 303	.	.	0.0013	0.0058	.	0.0091	.	0.023	44 mm Ø x ~7 or 19+ mm 17025
13X 30300A	.	.	0.0035	~40 mm Ø x ~15 mm
CT 303	0.0003	.	.	.	0.001	0.007	.	.	30-35 mm Ø x ~16 mm
IARM 355A	.	(0.004)	(0.0011)	(0.010)	(0.0002)	(0.005)	.	(0.018)	31 mm Ø x 2 or 18 mm
BS 154	.	.	.	0.008	.	(0.005)	.	(0.01)	38 mm Ø x ~7 or 19+ mm
13X 12549K	40 mm Ø x 15 mm
BS 153	.	(0.004)	.	.	(0.001)	0.002	.	(0.002)	35 mm Ø x ~7 or 19+ mm
BS 152	0.003	.	<0.01	41 mm Ø x ~7 or 19+ mm
CZ SP-1A	.	0.006	0.0007	.	.	0.01	.	0.03	~39 mm Ø x 25 mm
13X 12548M	Sb:0.022	.	0.031	40 mm Ø x 15 mm
IARM 352A	.	(0.005)	(0.0007)	(0.005)	.	0.0046	.	(0.005)	31 mm Ø x 2 or 18 mm
13X 43020A	.	.	(0.0032)	0.0108	~40 mm Ø x ~15 mm
IMZ 154	40 mm Ø x 40 mm
NCS HS41751A	38 mm Ø x 38 mm
BS 155	.	.	.	0.0048	.	(0.003)	.	.	36 mm Ø x ~7 or 19+ mm
13X 12536S	.	.	0.0274	.	.	0.018	0.091	.	~40 mm Ø x ~15 mm last
13X 12536T	.	.	0.0214	.	.	0.0068	0.104	.	~40 mm Ø x ~15 mm
13X 12535BE	.	.	0.0051	.	.	0.0194	(0.020)	.	~40 mm Ø x ~15 mm
SRM C1154a	0.017	.	.	.	32 mm Ø x 19 mm
13X 19003C	(0.005)	.	~40 mm Ø x ~15 mm
VS LG58	0.21	~47 mm Ø x ~30 mm
13X 19004B	40 mm Ø x 15 mm last
13X 18004B	~40 mm Ø x ~15 mm
13X 19004C	.	.	(0.001)	.	.	(0.001)	0.011	.	~40 mm Ø x ~15 mm

SELENIUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Se	Ni	Cr	C	Mn	P	S	Si	Cu	Al	Co	Mo	N	Nb	Ti
2	BS 151	0.328	0.24	13.19	0.090	0.41	0.021	0.018	0.65	0.11	(0.002)	0.018	0.088	0.022	0.005	(<0.003)
2	BS 186A	0.229	35.86	0.16	0.040	0.72	0.008	0.0053	0.19	0.016	(0.001)	0.028	0.0032	0.0026	(<0.002)	(<0.003)
1	IARM 253A	0.21	9.17	17.90	0.041	1.50	0.140	0.0089	0.50	0.223	0.003	0.088	0.348	0.0373	0.016	0.002
1	IARM 24B	0.19	35.86	0.121	0.053	0.82	0.009	0.0010	0.28	0.052	0.002	0.036	0.011	0.0017	<0.01	0.002
1	IARM 353A	0.17	0.265	17.01	0.98	0.95	0.019	0.025	0.49	0.13	0.0018	0.032	0.50	0.027	(0.011)	0.0015
2	CT ISO124A	0.167	48.07	0.079	0.011	0.73	0.007	0.006	0.40	0.015	.	0.012	0.009	.	.	.
2	BS 156	0.142	0.35	16.87	1.06	1.15	0.022	0.007	0.47	0.09	(<0.002)	0.047	0.50	0.041	0.005	0.001
1	IARM 253B	0.13	9.11	17.64	0.051	1.61	0.13	0.011	0.46	0.44	(0.004)	0.145	0.59	0.031	0.021	0.0027

Number	B	Fe	O	Sn	Ta	V	W	Zr	Units
BS 151	.	.	0.009	0.005	.	0.046	0.010	.	50 mm Ø x ~7 or 19+ mm
BS 186A	.	.	.	(0.002)	.	0.0012	(0.01)	.	38 mm Ø x ~7 or 19+ mm
IARM 253A	0.0003	.	0.009	0.01	.	0.106	0.10	.	31 mm Ø x 2 or 18 mm
IARM 24B	(0.001)	62.6	0.003	0.0018	<0.005	<0.005	<0.04	<0.005	31 mm Ø x 2 or 18 mm
IARM 353A	(0.0006)	.	(0.005)	0.0056	(0.004)	0.116	0.041	(0.002)	31 mm Ø x 2 or 18 mm
CT ISO124A	.	50.65	30-35 mm Ø x ~11 or ~19 mm
BS 156	.	.	0.0045	(0.004)	.	0.13	0.11	.	41 mm Ø x ~7 or 19+ mm
IARM 253B	0.0007	.	0.007	(0.012)	(0.003)	0.092	(0.05)	.	31 mm Ø x 2 or 18 mm

STAINLESS STEEL WITH NI < 5.0 %

CONTINUED ON THE NEXT PAGE

= Class, 1=CRM, 2=RM, and 3=RM with no uncertainties

** Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
3	CZ SL-4A	1.38	2.85	0.038	0.017	2.28	0.75	2.04	26.3	0.11	0.92	.	1.11	0.8	0.54	0.35
1	BS 156	1.06	1.15	0.022	0.007	0.47	0.09	0.35	16.87	0.047	0.50	0.041	0.005	0.001	0.13	0.11
1	BS 93F	1.047	0.59	0.0256	<0.0025	0.49	0.132	0.187	16.72	0.021	0.46	0.051	0.029	0.0012	0.057	0.0016
1	IARM 13D	1.040	0.697	0.0195	0.0012	0.614	0.184	0.256	16.36	0.0212	0.488	0.0492	0.0074	0.0035	0.058	0.046
1	13X 44004B	1.012	0.378	0.0232	0.0018	0.440	0.0687	0.197	16.50	0.0167	0.468	0.0308	0.008	(0.004)	0.0484	0.0156
2	BS 155	1.00	0.35	0.014	0.145	0.40	0.035	0.13	16.64	0.019	0.46	0.032	0.002	.	0.10	.
1	NCS HS41752	0.97	0.46	0.023	0.0016	0.48	0.082	0.192	17.61	.	0.057	.	.	.	0.088	.
1	ECRM 291-1D	0.90	0.81	0.017	0.0088	0.91	0.071	0.56	17.15	0.0233	2.10	0.1142	.	.	0.39	.
1	VS LG40/1	0.66	0.318	(0.02)	(0.006)	0.289	(0.15)	0.271	13.67	.	0.039	.	.	.	0.038	.
1	VS LG39/1	0.406	0.64	(0.02)	(0.007)	0.94	(0.12)	0.42	13.11	.	0.136	.	.	.	0.135	.
2	HRT FE2018-H	0.37	0.73	0.026	(0.003)	0.33	0.29	0.56	16.34	.	1.04	0.0134	.	.	0.064	.
1	13X 14122A	0.356	0.480	0.0177	0.0021	0.449	0.066	0.632	15.91	0.0224	0.855	0.0290	0.006	.	0.101	0.004
1	13X 40900A	0.035	0.716	0.0032	0.0059	0.616	0.134	0.231	10.98	0.053	0.102	0.007	0.032	0.530	0.099	.
2	BS SS4952	0.347	0.41	0.016	0.003	0.66	0.045	0.23	13.15	0.030	0.049	0.027	0.004	0.002	0.089	(0.007)
1	IARM 154C	0.339	0.423	0.0174	0.0043	0.37	0.120	0.215	12.41	0.016	0.036	0.054	0.014	0.0015	0.043	(0.005)
2	BS SS4951	0.333	0.58	0.016	0.0012	0.62	0.033	0.15	13.55	0.013	0.009	0.0127	0.006	0.002	0.032	.
2	BS 152	0.320	0.36	0.022	0.275	0.44	0.050	0.14	13.41	0.015	0.061	0.020	0.006	.	0.051	<0.01
1	IRSID 1825	0.305	0.650	0.019	0.022	0.336	0.100	0.308	12.90	0.026	0.052	.	.	.	0.052	.
1	13X 42027A	0.294	0.356	0.0139	0.0005	0.544	0.035	0.163	15.25	0.0191	0.990	0.402	0.004	(0.002)	0.048	0.019
1	ECRM 272-1D	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.2445	11.927	0.0145	0.0030	0.0508	0.0028	0.00096	0.0167	.
1	BS 462	0.279	0.598	0.015	0.020	0.421	(0.02)	0.246	11.93	(0.01)	(0.02)	.
1	VS LG38/1	0.255	0.73	(0.02)	(0.01)	0.81	(0.16)	0.551	11.75	.	0.344	.	.	.	0.190	.
1	IMZ 168	0.24	1.36	0.019	0.012	1.12	0.093	0.17	13.91	(0.019)	0.026	(0.057)	.	(0.003)	0.053	.
1	IARM 205D	0.232	0.736	0.0209	0.0028	0.257	0.122	0.841	12.18	0.043	1.002	0.0484	0.013	0.0022	0.319	1.07
1	BS 422	0.232	0.640	0.0169	0.0013	0.404	0.080	0.676	11.25	0.0293	0.896	0.050	0.045	0.0011	0.274	0.95
1	SS 472	0.227	1.02	0.032	0.029	1.05	(0.02)	1.95	15.82	(0.02)	0.661	.	.	.	(0.02)	.
1	13X 42200A	0.220	0.651	0.0182	0.0012	0.314	0.136	0.738	11.41	0.0114	1.042	0.0585	0.0203	.	0.246	1.177
1	NCS HS41749	0.21	0.39	0.023	0.012	0.56	1.15	1.52	12.27	.	0.158	.	.	.	0.074	.
1	13X 42000A	0.208	0.679	0.0241	0.0253	0.486	0.202	0.295	12.56	.	0.0398	0.0273	.	.	0.046	.
1	13X 14923A	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.452	11.26	0.0207	0.819	0.0321	0.005	.	0.295	.
1	VS LG41/1	0.200	0.91	(0.02)	(0.008)	0.64	(0.12)	1.53	15.90	.	0.277	.	.	.	0.303	.
1	IMZ 171	0.195	0.42	0.020	0.014	0.21	0.116	0.59	11.44	0.024	1.23	0.057	.	(0.001)	0.26	.
1	NCS HS41748	0.194	0.62	0.016	0.011	0.54	0.008	0.077	12.70	.	0.010	.	.	.	0.048	.
2	HRT FE2015-H	0.19	0.52	0.021	0.002	0.37	0.07	0.25	12.87	.	0.07	0.045	.	.	0.055	.
1	13X 12548M	0.188	0.577	0.027	0.219	0.425	0.230	1.075	12.96	0.353	1.318	0.0500	0.586	.	.	0.031
2	HRT FE2010-H	0.18	0.60	0.024	0.004	0.39	0.08	1.94	15.95	0.023	0.13	.	.	.	0.044	0.024
1	SS 70	0.18	0.38	0.024	0.020	0.35	(0.06)	0.40	16.35
1	IARM 20B	0.18	0.35	0.019	0.004	0.40	0.069	1.94	12.42	0.030	0.32	0.0434	0.010	0.004	0.17	3.52
1	IARM 20C	0.18	0.30	0.018	0.007	0.35	0.060	1.93	12.15	0.031	0.12	0.0222	0.010	(0.003)	0.086	2.59
1	IMZ 167	0.175	1.16	0.016	0.0025	0.755	0.106	0.16	13.07	(0.021)	0.024	0.053	.	(0.002)	0.054	.
1	SS 473	0.172	0.494	0.019	0.030	0.604	(0.02)	(0.06)	9.06	(0.01)	0.95	.	.	.	(0.02)	.
1	13X 41800A	0.172	0.328	0.0176	0.0006	0.316	0.104	2.05	12.30	0.0357	0.068	0.028	(0.006)	.	0.020	2.75
2	BS 183A	0.172	0.35	0.016	0.0040	0.37	0.093	1.85	12.14	0.036	0.12	0.0256	0.006	0.002	0.090	2.60
1	IARM Fe418-18	0.168	0.429	0.016	(0.0005)	0.32	0.22	2.00	12.4	0.029	0.104	0.031	(0.019)	.	0.046	2.63
1	13X 15024X	0.166	0.610	0.0284	0.0294	0.750	0.332	2.99	14.65	0.1059	0.299	0.0156	0.039	.	0.150	0.039
1	13X 43100A	0.166	0.378	0.0199	0.0050	0.335	0.134	2.10	16.39	0.0239	0.0768	0.075	0.006	.	0.0577	0.004
2	13X 12549K	0.162	0.34	0.022	0.29	0.43	0.10	1.26	11.70	0.52	1.47	.	.	.	0.03	.
1	IARM 12C	0.155	0.55	0.022	0.0032	0.34	0.33	2.23	15.78	0.048	0.125	0.056	0.020	(0.002)	0.040	0.015
1	SS 470	0.153	0.235	0.024	0.035	0.335	(0.02)	0.369	17.68	(0.02)	(0.02)	.
2	BS 92B	0.150	0.42	0.021	0.003	0.42	0.13	2.12	15.92	0.04	0.17	0.073	(0.006)	.	0.07	0.02
1	SRM 1219	0.149	0.42	0.026	0.001	0.545	0.162	2.16	15.64	.	0.164	0.078	.	.	0.056	.
1	BS 431	0.146	0.579	0.0232	0.0047	0.393	0.282	2.25	15.8	0.050	0.092	0.049	0.034	0.0007	0.062	0.012
1	IARM 335A	0.138	0.85	0.016	0.0005	0.39	0.086	4.27	15.30	0.063	2.72	0.085	0.015	(0.002)	0.094	0.008
1	BS 355	0.136	0.862	0.0171	0.0003	0.374	0.173	4.18	15.43	0.053	2.73	0.081	0.0103	0.0007	0.106	0.0069
1	13X 41001A	0.136	0.464	0.0142	0.0037	0.298	0.056	0.0939	12.06	0.0143	0.0102	0.0316	.	.	0.079	.
1	IARM Fe410-18	0.132	0.50	0.017	0.0014	0.29	0.046	0.280	12.2	0.012	0.146	0.046	0.0021	.	0.065	(0.008)
1	NCS HS28747	0.132	0.453	0.027	0.0068	0.502	0.126	1.79	16.24	0.051	0.153	0.030	.	(0.002)	0.075	.
1	13X 12540M	0.131	0.800	0.051	0.0512	0.805	0.181	4.975	27.44	0.109	0.993	0.054	0.107	.	0.210	0.097
1	BS 410C	0.131	0.381	0.0206	0.0051	0.366	0.084	0.352	12.78	0.0185	0.055	0.039	0.056	0.0006	0.042	0.0131
1	BS 0021	0.128	0.420	0.0201	0.0008	0.354	0.040	0.100	12.00	0.015	0.016	0.029	(0.001)	(0.003)	0.029	0.005
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	IARM 10C	0.128	0.35	0.026	0.29	0.37	0.155	0.24	12.25	0.022	0.08	0.015	0.003	0.002	0.024	0.011
1	SRM 1223	0.127	1.08	0.018	0.329	0.327	0.081	0.232	12.64	.	0.053	.	.	.	0.068	.
1	ECRM 296-1D	0.1166	0.676	0.0178	0.0026	0.242	0.1498	2.790	11.82	0.0218	1.700	0.0214	.	.	0.363	.
1	BS 416	0.116	0.64	0.0237	0.35	0.232	0.154	0.371	13.41	0.0241	0.030	0.043	(0.006)	0.0012	0.100	0.0034
1	13X I5035U	0.115	0.674	0.0415	0.0456	0.636	0.204	2.38	14.00	0.199	0.399	0.0584	0.500	.	0.160	0.048
1	13X 64152A	0.114	0.666	0.0123	0.0020	0.224	0.0622	2.50	11.34	0.0185	1.567	0.0339	.	.	0.275	.
1	13X 41600A	0.111	0.627	0.0253												

STAINLESS STEEL WITH NI < 5.0 %

CONTINUED FROM THE PREVIOUS PAGE

analysis listed in mass % except * which is mg/kg ** Provisional Analysis

Number	Al	As	B	Ca*	Mg*	Pb*	O	Sb	Se	Sn	Ta	Zn	Zr	Units
CZ SL-4A	0.12	.	0.0013	0.02	.	.	.	~39 mm Ø x 25 mm
BS 156	<(0.002)	0.0045	.	0.142	(0.004)	.	.	.	41 mm Ø x ~7 or 19+ mm
BS 93F	0.0052	0.0056	(0.0001)	19	(6)	(2)	0.0031	0.0016	.	0.0059	.	17025	(0.001)	38 mm Ø x ~7 or 19+ mm Fe:[80.2]
IARM 13D	(0.006)	(0.008)	0.0005	(7)	.	.	0.0031	(0.0027)	.	0.011	(0.004)	.	(0.0017)	31 mm Ø x 2 or 18 mm
13X 44004B	0.0160	~40 mm Ø x ~15 mm
BS 155	(0.001)	0.0048	.	.	(0.003)	.	.	.	36 mm Ø x ~7 or 19+ mm
NCS HS41752	(0.032)	38 mm Ø x 35 mm
ECRM 291-1D	36-41 mm Ø x 28-35 mm
VS LG40/1	~45 mm Ø x ~28 mm
VS LG39/1	~45 mm Ø x ~28 mm
HRT FE2018-H	0.010	.	(0.0004)	36 mm Ø x 20 mm
13X 14122A	(0.002)	0.0041	~40 mm Ø x ~15 mm
13X 40900A	0.0311	0.0080	~40 mm Ø x ~15 mm
BS SS4952	0.003	0.002	(0.0004)	19	.	.	0.005	.	0.004	38 mm Ø x ~7 or 19+ mm
IARM 154C	(0.0034)	(0.004)	0.0007	.	.	.	(0.0042)	(0.001)	(0.0003)	0.0058	.	.	(0.0014)	31 mm Ø x 2 or 18 mm
BS SS4951	0.002	0.002	0.0055	.	.	0.003	.	.	.	42 mm Ø x ~7 to 19+ mm
BS 152	(0.002)	0.003	.	.	.	41 mm Ø x 19+ mm
IRSID 1825	40 mm Ø x 30 mm
13X 42027A	0.004	0.0026	~40 mm Ø x ~15 mm
ECRM 272-1D	0.0046	0.0116	0.0018	9.0	(2)	.	.	0.0007	.	.	.	0.0031	.	38 mm Ø x 25 or 30 mm
SS 469	35 mm Ø x 19 mm
VS LG38/1	~45 mm Ø x ~28 mm
IMZ 168	(0.004)	0.009	40 mm Ø x 40 mm
IARM 205D	0.0021	0.004	0.0007	(20)	(7)	(20)	0.0053	<(0.007)<(0.005)	0.0047	<(0.005)<(0.005)	0.0022	.	.	31 mm Ø x 2 or 18 mm
BS 422	0.0135	0.0041	(0.0002)	31	(9)	(0.5)	0.0030	(0.0007)	.	0.0043	(0.0001)	17025	(0.001)	38 mm Ø x ~7 or 19+ mm Fe:84.5
SS 472	35 mm Ø x 19 mm
13X 42200A	0.0020	0.0052	~38 mm Ø x ~15 mm
NCS HS41749	38 mm Ø x 35 mm
13X 42000A	.	.	0.0013	0.0073	~38 mm Ø x ~15 mm
13X 14923A	0.003	.	.	44	0.004	~40 mm Ø x ~15 mm
VS LG41/1	~45 mm Ø x ~28 mm
IMZ 171	0.036	(0.003)	0.008	40 mm Ø x 40 mm
NCS HS41748	38 mm Ø x 35 mm
HRT FE2015-H	30 mm Ø x 20 mm
13X 12548M	0.022	40 mm Ø x 15 mm
HRT FE2010-H	35 mm Ø x 20 mm
SS 70	44 mm Ø x 13 mm
IARM 20B	0.006	0.0056	.	.	0.005	.	.	.	31 mm Ø x 2 mm
IARM 20C	(0.004)	0.0068	.	.	0.004	.	.	.	31 mm Ø x 2 mm
IMZ 167	(0.018)	0.009	.	.	.	40 mm Ø x 40 mm
SS 473	35 mm Ø x 19 mm
13X 41800A	(0.003)	0.0040	.	.	.	~38 mm Ø x ~15 mm
BS 183A	0.002	(0.002)	<(0.0005)	20	.	.	0.0065	(0.001)	.	0.003	.	.	.	38 mm Ø x ~7 or 19+ mm
IARM Fe418-18	(0.004)	(0.004)	.	.	(0.005)	.	.	.	31 mm Ø x 2 or 18 mm
13X 15024X	0.0049	~40 mm Ø x ~15 mm
13X 43100A	0.004	.	.	.	~38 mm Ø x ~15 mm
13X 12549K	~40 mm Ø x ~15 mm
IARM 12C	(0.004)	(0.004)	0.0004	7	(2)	(5)	(0.005)	.	.	0.008	(0.0005)	.	(0.001)	31 mm Ø x 2 or 18 mm
SS 470	35 mm Ø x 19 mm
BS 92B	(0.002)	.	.	(9)	.	.	0.0064	.	.	0.006	.	.	.	44 mm Ø x ~7 mm last
SRM 1219	34 mm Ø x 19 mm
BS 431	0.0019	0.0038	0.0003	7	(2)	.	0.0059	0.0011	.	0.0134	.	17025	(0.001)	38 mm Ø x ~7 or 19+ mm Fe: 80.2
IARM 335A	0.019	(0.01)	0.0007	(10)	.	.	0.0020	.	.	0.0034	(0.01)	.	(0.002)	31 mm Ø x 2 or 18 mm
BS 355	0.0192	0.0039	(0.0001)	(2)	(2)	(0.3)	0.0020	(0.0009)	.	0.0038	(0.0001)	.	(0.003)	41 mm Ø x ~7 or 19+ mm 17025
13X 41001A	(0.004)	.	.	10	0.0051	.	.	.	~41 mm Ø x ~15 mm
IARM Fe410-18	(0.003)	(0.009)	31 mm Ø x 2 or 18 mm
NCS HS28747	.	0.0063	.	.	.	1	.	.	.	0.0057	.	.	.	38 mm Ø x 35 mm
13X 12540M	~40 mm Ø x ~15 mm
BS 410C	0.0079	0.0029	(0.0001)	22	(3)	(1)	0.0051	(0.0002)	.	0.0023	(0.001)	.	(0.0002)	38 mm Ø x ~7 or 19+ mm 17025
BS 0021	0.008	(0.004)	<(0.0002)	(2)	.	.	(0.004)	.	.	0.003	.	25 (pre-17025)	.	40 mm Ø x ~7 or 19+ mm
Number	Al	As	B	Ca*	Mg*	Pb*	O	Sb	Se	Sn	Ta	Zn	Zr	Units
IARM 10C	0.003	.	<0.0005	.	.	.	0.008	.	.	0.009	.	last of stock		31 mm Ø x 2 or 18 mm
SRM 1223	32 mm Ø x 19 mm
ECRM 296-1D	0.0275	0.0139	(0.0003)	.	.	1.6	.	.	.	0.0131	.	.	.	38 mm Ø x 25 or 30 mm
BS 416	(0.002)	0.0039	(0.001)	(3)	(3)	(6)	0.0081	(0.002)	.	(0.005)	(0.004)	17025	(0.002)	38 mm Ø x ~7 or 19+ mm Fe:[84.3]
13X 15035U	(0.093)	~40 mm Ø x ~15 mm
13X 64152A	0.0315	0.0053	.	.	.	~38 mm Ø x ~15 mm
13X 41600A	(0.004)	0.0066	.	.	.	~41 mm Ø x ~15 mm
13X 12533Z	0.059	.	0.0100	0.0097	.	.	.	~40 mm Ø x ~15 mm
IARM 291A	(0.004)	.	0.001	.	.	.	0.014	.	.	0.004	(0.001)	.	<0.005	31 mm Ø x 2 or 18 mm
CT 410	0.015	0.006	.	.	.	30-35 mm Ø x ~16 mm Ag: 2 ppm
IMZ 156	(0.034)	40 mm Ø x 40 mm
SS 471	35 mm Ø x 19 mm
NCS HS11721-4	0.124	0.022	.	.	.	(2)	.	.	.	0.034	.	.	.	38 mm Ø x 30 mm last
IMZ 158	1.56	40 mm Ø x 40 mm
BS 151	(0.002)	0.009	.	0.328	0.005	.	.	.	50 mm Ø x ~7 or 19+ mm
13X 15023W **	0.003	~40 mm Ø x ~15 mm
13X 14742A	0.804	.	.	.	22	0.0046	.	0.0055	.	~40 mm Ø x ~15 mm
BS 90F	(0.006)	0.011	.	.	0.005	.	.	.	38 mm Ø x ~7 or 19+ mm
13X 14762A	1.318	0.0025	.	.	24	0.0048	.	.	.	~40 mm Ø x ~15 mm
IMZ 155	(0.20)	40 mm Ø x 40 mm
CZ SL-1A	0.86	0.01	.	.	.	~39 mm Ø x 25 mm
IMZ 161	40 mm Ø x 40 mm
IARM 11D	0.015	(0.005)	0.0006	(20)	(30)	(5)	(0.004)	(0.001)	0.006	(0.003)	(0.004)	(0.001)	.	31 mm Ø x 2 or 18 mm
BS 430	0.0015	0.0037	(0.0004)	(3)	(2)	(6)	0.0075	(0.001)	.	0.0084	(0.001)	17025	(0.001)	44 mm Ø x 19+ mm Fe: 81.7
IARM 14C	0.0041	(0.003)	0.0005	(10)	(5)	(1)	(0.006)	(0.002)	(0.0001)	0.004	(0.002)	(0.0003)	(0.001)	31 mm Ø x 2 or 18 mm
IMZ 163A	0.008	(0.0035)	.	.	.	(10)	.	.	.	(0.003)	.	.	.	40 mm Ø x 40 mm
BS 94C	0.004	0.0061	.	.	0.006	.	.	.	~44 mm Ø x 19+ mm
BS 0022	0.078	0.003	0.0007	8	<(5)	(6)	(0.002)	(0.0004)	.	0.004	.	25 (pre-17025)	.	38 mm Ø x ~7 or 19+ mm
BS 150	0.002	0.012	.	.	(0.003)	.	.	.	35 mm Ø x ~7 or 19+ mm
13X 14418A	(0.003)	0.005	.	.	.	~40 mm Ø x ~15 mm
NCS HS28748	.	0.0047	.	.	1	0.0063	.	.	.	38 mm Ø x 35 mm
BS 17-4PHB	.	.	0.0036	(0.002)	.	.	40 mm Ø x ~7 or 19+ mm
SRM C1296	0.035	32 mm Ø x 19 mm
SRM C2400	32 mm Ø x 19 mm
HRT FE2009-H	.	.	.	(10)	40 mm Ø x 40 mm
BS 9621	0.003	.	0.0004	(1)	0.003	(0.002)	.	.	38 mm Ø x ~7 or 19+ mm
ECRM 273-1	.	0.0030	0.0021	.	.	.	40 mm Ø x 20 mm
BS 185A	0.002	.	0.0017	(2)	.	.	(0.0021)	.	.	0.				

STAINLESS STEEL WITH C > 0.05 %

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	VS LG76	0.445	0.342	0.021	0.0076	0.455	0.098	13.39	13.77	.	0.263	0.031	.	0.020	0.041	2.38
1	VS LG74	0.373	0.962	0.024	0.0049	2.49	0.093	23.66	18.30	0.031	0.104	0.030	.	0.030	.	0.052
1	KUT S21	0.37	0.19	0.017	0.021	1.26	0.11	22.3	3.99	.	4.12	.	.	0.50	.	.
2	CZ CM-19A	0.361	0.783	0.0440	0.0182	1.588	0.986	15.27	13.12	0.222	1.023	(0.021)	0.091	0.254	1.235	0.311
1	VS LG79	0.313	1.28	0.017	0.0036	0.703	0.065	8.72	19.23	.	1.18	.	0.47	.	0.049	1.16
2	CZ SP-3C	0.30	0.43	0.026	0.011	0.84	0.185	5.31	16.42	0.041	0.26	.	(0.04)	(0.17)	0.19	0.12
1	DSZU C016	0.281	3.26	0.0192	0.0174	1.16	0.054	7.47	21.9	.	0.52	0.010	.	0.72	0.036	0.014
3	CZ SP-3B	0.27	0.29	0.023	0.008	0.72	0.62	5.65	15.1	0.02	0.24	.	.	0.13	0.10	0.12
1	KUT S19	0.26	0.32	0.012	0.021	2.32	0.19	12.8	7.00	.	0.11	.	0.81	0.048	.	.
1	SRM C1153a	0.225	0.544	0.030	0.019	1.00	0.226	8.76	16.70	0.127	0.24	.	.	.	0.176	.
1	13X 18001B	0.207	0.463	0.0090	0.0786	0.203	0.149	6.13	15.92	0.0231	0.816	0.0347	0.612	.	0.0996	.
1	KUT H6/1	0.20	0.49	0.021	0.024	0.67	0.10	0.15	18.9	0.10	.	(0.12)
2	CZ SP-3D	0.171	0.34	0.021	0.015	0.71	0.73	5.36	16.44	0.033	0.25	.	(0.04)	0.088	0.11	0.12
2	13X NSB1D	0.17	0.44	.	.	0.58	.	10.0	19.1	.	0.11	0.04
1	IARM 339A	0.16	1.71	0.004	0.009	0.64	0.021	12.9	17.0	0.007	2.79	0.0060	(0.005)	(0.002)	0.007	(0.0119)
1	13X 18002D	0.159	0.722	0.0245	0.0487	0.352	0.116	7.92	17.77	0.0514	0.209	0.072	1.531	.	0.0542	.
2	13X 12540L	0.15	0.44	.	.	1.05	.	5.17	27.88	.	0.54
2	CZ CM-18A	0.143	1.792	0.0182	0.0119	0.903	2.393	20.44	20.59	0.097	2.282	0.0848	.	.	0.113	0.097
1	SS 468/1	0.143	1.70	0.014	0.020	1.41	.	8.90	17.96	0.018
1	SRM C1152a	0.142	0.95	0.023	0.0064	0.64	0.097	10.86	17.76	0.22	0.44	.	.	.	0.033	.
1	VS LG32/5	0.138	0.54	0.0057	0.039	0.185	0.019	7.10	19.75	.	0.110	.	.	0.92	0.317	0.205
1	13X NSA2J	0.132	1.03	0.0252	0.0275	0.739	0.259	10.08	17.82	.	2.013	0.131	0.155	.	0.139	.
1	IARM 289A	0.126	1.67	0.006	0.0019	0.58	0.016	7.12	17.0	0.054	(0.005)	0.0032	0.008	0.028	0.01	0.01
1	IARM 241D	0.125	1.94	(0.003)	0.0023	1.00	0.242	8.98	18.12	0.022	(0.02)	(0.008)	0.028	0.018	0.031	(0.012)
1	DSZU C018	0.125	1.09	0.0268	0.0099	0.53	0.163	9.33	17.54	.	0.189	0.009	.	0.54	0.048	0.066
1	13X NSB3G	0.121	0.632	.	.	0.471	.	9.26	15.22	.	0.630	0.198
1	KUT H5	0.12	0.48	0.017	(0.003)	0.70	0.22	0.20	21.8	0.03	.	0.10
1	13X 18003C	0.113	1.000	0.0545	0.0245	0.805	0.0433	10.08	19.56	0.100	0.401	0.090	1.042	.	0.0750	.
1	IRSID 1819	0.112	0.903	0.023	0.0112	0.616	0.064	7.10	17.31	0.117	0.110	0.0288
1	13X 17002E	0.112	0.801	0.0409	0.0250	0.486	0.1012	7.87	17.45	0.0702	0.204	0.061	0.487	.	0.0587	.
1	NCS HS28743	0.110	0.841	0.024	0.0082	0.780	0.089	18.02	23.71	0.102	0.115	0.057	0.016	(0.003)	0.077	.
1	IMZ 166A	0.108	1.99	0.019	0.005	2.51	0.025	21.93	25.53	0.030	(0.025)	0.077	.	0.003	0.038	.
1	13X 12855N	0.107	0.918	0.0020	0.0063	0.863	0.340	11.79	16.29	0.155	2.96	0.0078	0.098	0.083	.	0.199
1	13X 14828A	0.104	1.52	0.0268	0.0067	2.19	0.409	11.25	19.3	0.143	0.301	0.037	0.016	.	0.080	0.0167
1	VS LG81	0.104	0.29	0.0121	0.0014	0.231	0.088	22.5	11.51	.	1.22	.	0.004	2.93	0.040	0.012
1	VS LG77	0.101	0.34	0.0149	0.0021	0.44	0.116	4.32	15.67	.	0.020	0.054	0.109	.	0.022	0.006
1	IMZ 164	0.100	1.77	0.019	0.002	0.82	0.26	6.75	20.96	0.035	3.48	0.249	0.049	(0.003)	0.053	(0.025)
2	13X 17003A	0.10	0.85	0.037	0.035	0.78	0.08	11.9	11.89	0.07	0.27	.	0.34	.	.	.
1	VS LG73	0.098	1.26	0.019	0.0073	0.570	0.140	17.74	22.60	0.247	0.061	0.0319	.	0.0022	.	0.102
1	KUT S20	0.097	1.50	0.011	0.025	1.80	0.44	18.2	2.06	.	3.15	.	1.22	(0.01)	.	.
1	VS LG80	0.097	0.709	0.025	0.0029	2.15	0.166	19.38	24.7	.	0.086	0.064	.	0.015	0.032	0.029
2	BS 253	0.094	0.58	0.018	<0.001	1.81	0.14	10.89	20.68	0.15	0.21	0.146	0.017	0.005	0.050	0.03
1	IARM 234C	0.092	1.93	0.0090	(0.0027)	0.88	3.41	9.00	18.15	0.034	0.012	(0.01)	0.053	0.026	0.055	(0.006)
1	SS 462	0.092	0.74	0.010	0.018	0.466	.	12.53	12.37
1	13X 12537T	0.0889	1.116	0.0382	0.0206	1.151	0.248	10.71	20.43	0.1520	3.05	0.048	0.102	0.273	0.0908	.
1	DSZU C015	0.087	0.420	0.0118	0.0059	0.214	0.070	12.15	15.36	.	0.89	0.020	.	0.177	0.021	0.023
1	SS 464/1	0.086	0.791	0.020	0.028	0.57	.	20.05	25.39	0.054
1	13X 17004B	0.084	0.497	0.018	0.039	1.23	0.0449	16.04	21.37	0.055	0.455	0.0086	0.179	0.034	.	.
1	IMZ 165	0.082	0.98	0.017	0.007	1.42	0.040	19.01	23.28	0.029	0.025	0.105	.	(0.002)	0.042	.
1	SS 467/1	0.082	0.788	0.018	0.019	0.52	.	9.21	18.09	.	.	.	0.99	.	.	.
1	13X 12854M	0.081	1.84	0.038	0.028	0.89	0.205	11.38	15.64	0.344	2.00	0.0097	0.33	0.052	.	0.141
1	VS LG35/5	0.078	0.81	0.042	0.0094	1.01	0.066	8.23	18.44	.	0.39	.	.	0.73	0.041	0.107
1	13X 17001C	0.0769	1.543	0.055	0.0134	0.215	0.0161	6.31	14.83	0.0979	0.0967	.	0.546	.	.	.
1	KUT S26	0.076	0.99	0.027	0.026	0.67	0.14	3.31	18.9	.	2.59	.	0.07	0.11	.	.
1	NCS HS41750	0.075	1.43	0.031	0.012	0.33	0.276	6.35	16.31	.	0.107	0.058	.	(0.001)	0.064	.
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	ECRM 270-1D	0.0742	0.540	0.0196	0.0007	1.517	0.1076	10.86	20.88	0.0685	0.2099	0.1417	.	(0.0019)	0.0256	(0.0244)
1	VS LG78	0.074	1.60	0.017	0.0017	0.58	0.053	35.4	14.71	.	0.061	0.0062	0.004	1.31	0.020	3.16
1	BS 192	0.074	0.835	0.025	0.0005	0.387	0.412	7.11	16.44	0.104	0.430	0.0290	0.168	0.076	0.124	0.05
2	BS 83G	0.073	1.66	0.024	0.004	0.56	0.114	19.15	24.50	0.153	0.085	0.026	0.061	(0.003)	0.077	0.007
1	NM 301	0.073	1.38	0.037	0.021	0.39	0.41	7.89	18.0	0.17	0.36	.	.	.	0.07	.
1	VS LG72	0.072	1.32	.	0.0050	0.334	0.306	12.4	16.36	0.090	2.07	0.0073	.	0.57	.	0.077
1	NM 302	0.072	1.06	0.031	0.018	0.49	0.40	10.12	16.92	0.19	2.03	.	.	.	0.066	.
1	13X 12534X	0.0716	0.589	0.0192	0.0086	0.811	0.0586	8.50	17.71	0.0602	2.04	.	0.201	0.348	0.110	0.010
1	IARM 316A	0.070	0.61	0.023	0.0011	1.50	0.19	10.81	21.07	0.118	0.250	0.16	(0.003)	(0.002)	0.042	0.022
1	IARM 18D	0.069	8.1	0.032	0.0025	3.68	0.421	8.39	16.7	0.086	0.325	0.170	(0.031)	0.012	0.064	(0.026)
1	13X 12853L	0.069	1.156	0.0053	0.0062	0.994	0.092	12.31	17.13	0.0415	2.718	0.0086	0.180	0.0455	.	0.089
1	VS LG63	0.068	0.356	0.010	0.0050	0.285	0.024	22.15	10.13	.	1.65	.	0.113	2.98	0.086	0.43
1	KUT S25	0.067	1.90	0.045	0.015	1.49	0.07	13.8	15.6	.	1.77	.	0.07	0.46	.	.
1	SRM 1171	0.067	1.81	(0.019)	(0.013)	0.536	0.12									

STAINLESS STEEL WITH C > 0.05 %

CONTINUED FROM THE PREVIOUS PAGE

Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
VS LG76	0.034	~45 mm Ø x ~28 mm
VS LG74	0.035	~45 mm Ø x ~28 mm
KUT S21	30-35 mm Ø x 18 or 40 mm
CZ CM-19A	0.0788	.	(0.091)	.	(0.0036)	0.0283	.	.	~37 mm Ø x ~25 mm
VS LG79	0.059	~45 mm Ø x ~28 mm
CZ SP-3C	0.095	(0.03)	1.67	(0.02)	.	.	~39 mm Ø x 25 mm
DSZU C016	0.007	.	.	.	0.0004	40 mm Ø x 25 mm
CZ SP-3B	0.08	.	0.88	0.01	.	.	~39 mm Ø x 25 mm
KUT S19	30-35 mm Ø x 18 or 40 mm
SRM C1153a	0.006	32 mm Ø x 19 mm
13X 18001B	0.0157	~40 mm Ø x ~15 mm
KUT H6/1	30-35 mm Ø x 18 or 40 mm
CZ SP-3D	0.037	(0.03)	2.45	(0.04)	.	.	~39 mm Ø x 25 mm
13X NSB1D	40 mm Ø x 15 mm
IARM 339A	0.004	(0.001)	0.0006	.	0.0014	.	0.016	.	.	(0.002)	(0.005)	(0.003)	31 mm Ø x 2 or 18 mm
13X 18002D	0.0617	~40 mm Ø x ~15 mm
13X 12540L	40 mm Ø x 15 mm
CZ CM-18A	0.0344	~37 mm Ø x ~25 mm
SS 468/1	38 mm Ø x 19 mm
SRM C1152a	0.0047	32 mm Ø x 19 mm
VS LG32/5	0.156	~38 mm Ø x ~25 mm
13X NSA2J	~40 mm Ø x ~15 mm
IARM 289A	0.01	.	0.0003	.	.	0.0104	.	.	.	(0.002)	<0.005	.	31 mm Ø x 2 mm
IARM 241D	0.022	(0.001)	0.0016	.	(0.0012)	.	(0.005)	(0.0003)	.	(0.0022)	(0.007)	(0.005)	31 mm Ø x 2 or 18 mm
DSZU C018	0.086	.	.	.	0.0003	40 mm Ø x 25 mm
13X NSB3G	0.006	42 mm Ø x 15 mm
KUT H5	30-35 mm Ø x 18 or 40 mm
13X 18003C	0.0292	~40 mm Ø x ~15 mm
IRSID 1819	.	.	(0.0004)	47 mm x 47 mm x 30 mm
13X 17002E	(0.030)	.	0.0012	(0.012)	.	~40 mm Ø x ~15 mm
NCS HS28743	0.0056	0.0042	0.0004	.	0.0025	.	.	38 mm Ø x 35 mm
IMZ 166A	0.036	(0.0026)	(0.0035)	.	.	40 mm Ø x 40 mm
13X 12855N	0.048	.	0.0098	0.093	0.122	.	.	~40 mm Ø x ~15 mm
13X 14828A	0.008	0.0128	.	.	~40 mm Ø x ~15 mm
VS LG81	0.409	~45 mm Ø x ~28 mm
VS LG77	~45 mm Ø x ~28 mm
IMZ 164	0.040	(0.005)	(0.002)	.	(0.003)	.	.	40 mm Ø x 40 mm
13X 17003A	40 mm Ø x 15 mm
VS LG73	~45 mm Ø x ~28 mm
KUT S20	30-35 mm Ø x 18 or 40 mm
VS LG80	0.025	~45 mm Ø x ~28 mm
BS 253	0.016	0.005	.	.	.	0.044	.	.	.	0.006	25(pre-17025)	.	38 mm Ø x ~7 or 19+ mm
IARM 234C	0.035	(0.001)	0.0023	.	(0.0017)	.	(0.005)	(0.001)	.	0.0017	(0.003)	(0.006)	31 mm Ø x 2 or 18 mm
SS 462	.	0.007	0.0005	38 mm Ø x 19 mm
13X 12537T	(0.062)	.	0.0029	0.0401	0.0194	.	~40 mm Ø x ~15 mm
DSZU C015	(0.008)	.	.	.	0.0017	40 mm Ø x 25 mm
SS 464/1	.	(0.003)	0.0004	38 mm Ø x 19 mm
13X 17004B	0.043	.	0.0066	0.057	.	~40 mm Ø x ~15 mm
IMZ 165	0.038	(0.003)	(0.001)	.	0.003	.	.	40 mm Ø x 40 mm
SS 467/1	.	0.004	0.004	.	.	0.0017	.	38 mm Ø x 19 mm
13X 12854M	.	.	0.0101	0.0052	0.068	.	0.020	0.0146	~40 mm Ø x ~15 mm
VS LG35/5	0.087	~38 mm Ø x ~25 mm
13X 17001C	0.0312	.	0.0085	0.0124	.	~40 mm Ø x ~15 mm
KUT S26	30-35 mm Ø x 18 or 40 mm
NCS HS41750	0.009	38 mm Ø x 35 mm
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
ECRM 270-1D	(0.0023)	(0.0034)	Ce: 0.0487	La: 0.0154	(0.0007)	(0.0035)	.	(0.002)	38 mm Ø x 25 mm
VS LG78	0.15	~45 mm Ø x ~28 mm
BS 192	1.17	(0.005)	(0.0003)	.	0.0007	.	0.0014	25(pre-17025)	.	0.008	(0.001)	.	38 mm Ø x ~7 or 19+ mm
BS 83G	(0.004)	.	(0.001)	.	.	.	0.0064	.	.	0.003	.	.	38 mm Ø x ~7 or 19+ mm
NM 301	35 mm Ø x 20 mm
VS LG72	0.089	~45 mm Ø x ~28 mm
NM 302	35 mm Ø x 20 mm
13X 12534X	0.0485	0.031	.	~40 mm Ø x ~15 mm
IARM 316A	0.006	0.007	(0.0003)	.	0.0017	0.064	0.0052	(0.0001)	.	0.006	(0.003)	.	31 mm Ø x 2 or 18 mm
IARM 18D	(0.006)	.	(0.0011)	(0.007)	.	.	31 mm Ø x 18 mm
13X 12853L	0.18	.	0.0018	0.034	.	~40 mm Ø x ~15 mm
VS LG63	0.45	~47 mm Ø x ~30 mm
KUT S25	30-35 mm Ø x 18 or 40 mm
SRM 1171	31 mm Ø x 19 mm
BS 9841	(<0.006)	(0.003)	0.0026	25(pre-17025)	.	(0.011)	(0.001)	(0.006)	0.006	.	.	(0.002)	44 mm Ø x ~7 or 19+ mm
SS 465/1	0.026	.	0.0006	(<0.001)	38 mm Ø x 19 mm
BS 192A	0.98	(0.0035)	(0.0003)	.	(0.0006)	.	(0.0006)	.	.	0.008	25(pre-17025)	.	38 mm Ø x ~7 or 19+ mm
IMZ 152	40 mm Ø x 40 mm
IMZ 152A	(0.004)	(0.002)	0.0022	(0.001)	.	.	38 mm Ø x 20 mm
VS LG71	0.072	~45 mm Ø x ~28 mm
IARM 7C	0.017	.	0.0027	.	.	.	0.0021	(0.0001)	last	0.0020	(0.002)	(0.001)	31 mm Ø x 2 mm Mg:15ppm
CT 304	<0.001	.	0.017	.	.	30-35 mm Ø x ~16 mm Ag: 7ppm
BS 82E	0.006	.	0.0024	.	0.0014	0.006	.	.	38 mm Ø x ~7 or 19+ mm
13X 31008A	~38 mm Ø x ~15 mm
KUT H7/1	30-35 mm Ø x 18 or 40 mm
CT 316	0.001	.	0.006	.	.	30-35 mm Ø x ~19 mm Ag: 5ppm
VS LG36/5	0.080	~38 mm Ø x ~25 mm
BS 321D	0.103	0.0040	0.0012	.	(0.0003)	.	0.0009	(0.0003)	(0.001)	0.0091	17025	(0.001)	44 mm Ø x ~7 or 19+ mm Fe,Mg
13X NSB2D	40 mm Ø x 15 mm
BS 9842	0.014	(0.002)	0.0025	.	0.0010	.	(0.0044)	.	.	0.005	25(pre-17025)	.	38 mm Ø x ~7 or 19+ mm
BS 82D	(0.002)	.	0.0040	.	0.0007	.	0.007	.	.	0.004	.	last	38 mm Ø x ~7 mm
13X 30908A	0.0035	.	0.0027	.	(0.0005)	~38 mm Ø x ~15 mm
SRM 1172	<0.001	.	32 mm Ø x 19 mm
VS LG82	0.076	~45 mm Ø x ~28 mm
IARM 3E	0.0045	(0.005)	(0.0005)	.	0.0015	.	0.0048	(0.0003)	(0.0013)	0.007	(0.005)	0.0018	31 mm Ø x 2 or 18 mm
BS 87F	0.004	0.005	(0.0006)	.	0.0007	.	0.005	.	.	0.004	.	.	41 mm Ø x ~7 or 19+ mm
13X 19001B	40 mm Ø x 15 mm
BS 86F	(0.007)	(0.003)	0.0026	.	(0.001)	.	.	(0.001)	.	0.004	(0.019)	.	44 mm Ø x ~7 or 19+ mm
DSZU C017	0.28	.	.	.	0.0031	40 mm Ø x 25 mm
IARM Fe304H-18	(0.005)	0.0076	(0.008)	.	.	(0.014)	.	.	31 mm Ø x 2 or 18 mm
BS 347B	0.002	(0.003)	0.0036	.	(0.0005)	.	0.005	.	.	0.006	(<0.004)	.	38 mm Ø x ~7 or 19+ mm
BS 347A	(0.002)	(0.003)	(0.0004)	.	(0.0002)	.	0.0047	.	.	0.007	(<0.004)	.	38 mm Ø x 19+ mm
BS 188A	0.19	.	0.0065	.	.	.	0.0012	<0.001	.	0.002	.	.	38 mm Ø x ~7 mm last of stock
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units

STAINLESS STEEL WITH C < 0.05 %

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

analysis listed in mass %

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	ECRM 269-1D	0.0499	1.262	0.0313	0.0010	0.441	0.366	8.044	18.150	0.1116	0.397	0.0460	0.0242	0.0006	0.0991	0.0306
1	IARM 8H *	0.049	1.81	0.0250	(0.002)	0.40	0.192	9.08	17.14	0.083	0.237	0.027	0.48	0.0027	0.049	(0.016)
1	IARM 6i	0.049	1.76	0.0208	(0.023)	0.31	0.202	9.20	17.76	0.052	0.133	(0.013)	(0.018)	0.60	0.048	(0.023)
1	ECRM 289-1D	0.0489	1.016	0.0114	0.0027	0.531	.	24.68	14.63	0.065	1.102	.	.	2.01	0.260	.
1	IMZ 150A	0.048	1.35	0.0064	0.0095	0.59	0.090	12.75	18.89	0.125	0.12	.	0.0026	0.021	(0.027)	0.11
1	IARM 4F	0.047	1.17	0.0195	0.0015	0.494	0.146	20.1	24.5	0.067	0.142	0.056	0.007	0.0031	0.146	0.012
1	13X 14211R	0.047	0.787	0.0093	0.008	1.73	0.336	12.64	24.48	0.034	0.395	0.0115	0.150	0.206	0.039	2.99
1	13X 32100A	0.0463	1.52	0.0298	0.0011	0.498	0.415	9.32	17.39	0.105	0.282	0.023	0.0191	0.376	0.106	0.021
1	IARM FE303-18	0.046	1.55	0.033	0.35	0.47	0.61	8.12	17.2	0.140	0.42	0.069	0.015	.	0.072	0.029
1	BS 188B	0.046	0.247	0.016	(0.0007)	0.266	0.120	24.81	14.32	0.274	1.30	0.0021	0.099	2.20	0.264	0.043
1	IARM 4G	0.0454	1.36	0.027	0.0008	0.630	0.320	19.2	24.9	0.085	0.580	0.058	0.008	0.029	0.092	0.017
1	IARM 6J	0.045	1.52	0.028	(0.002)	0.62	0.383	9.00	17.74	0.191	0.387	0.0109	0.010	0.34	0.081	0.026
1	BS 303	0.044	1.80	0.028	0.326	0.415	0.627	8.17	17.23	0.071	0.410	0.023	0.008	0.017	0.056	0.023
1	IARM 4E	0.044	1.07	0.0224	0.0006	0.514	0.234	20.18	24.25	0.066	0.32	0.038	0.024	(0.003)	0.052	0.046
3	CZ SL-3A	0.043	1.73	0.024	0.002	0.53	0.22	19.6	24.6	0.06	0.38	0.065	0.013	0.003	0.066	0.03
1	KUT S15	0.043	0.38	(0.02)	0.013	0.26	1.54	3.90	16.7	.	2.46	.	0.64	.	.	.
1	IARM 8i	0.0424	1.395	0.0352	0.0118	0.38	0.441	9.01	17.08	0.301	0.416	0.052	0.60	(0.008)	0.057	0.060
1	13X 14216P	0.0424	0.663	0.0048	0.0070	1.566	0.231	12.06	23.44	0.248	0.209	0.0152	0.248	.	0.0722	2.25
1	IARM 8G	0.042	1.468	0.0327	0.0126	0.36	0.390	9.02	17.20	0.162	0.359	0.046	0.53	0.0024	0.062	0.032
1	VS LG70	0.042	0.834	0.042	0.0020	0.382	0.062	9.17	17.10	0.209	0.096	0.0134	.	0.305	.	0.0053
1	NILAB 500HA D	0.041	1.541	0.024	0.012	0.720	0.182	11.00	16.93	0.139	2.73	0.1154	0.023	.	0.074	.
1	13X 12538J	0.04	0.78	.	.	0.64	.	6.07	23.72	.	1.53
1	NCS HS28741	0.039	1.07	0.037	0.016	0.425	0.399	8.19	18.31	0.208	0.027	0.069	.	(0.002)	0.106	.
1	13X 14207L	0.0388	0.597	0.0061	0.0060	1.448	0.186	12.43	19.63	0.0089	0.573	0.0099	0.258	0.0119	0.0043	2.99
1	IRSID 1821	0.037	1.72	(0.025)	(0.004)	0.542	0.058	10.42	17.04	0.266	2.04	0.0125	.	0.297	.	.
1	IMZ 153A	0.037	1.49	0.021	0.0073	0.73	0.102	13.57	16.45	0.015	2.61	0.107	0.034	0.036	0.020	.
1	ECRM 292-1D	0.0367	1.744	0.0175	0.0055	0.402	0.0391	10.09	18.00	0.0255	0.0464	0.0640	0.571	.	.	.
1	13X 65286A	0.036	1.172	0.0173	(0.0006)	0.216	0.195	25.21	15.00	0.083	1.190	0.0040	.	1.92	0.264	0.098
2	BS 184A	0.035	0.06	0.007	0.001	0.080	0.041	8.34	12.66	0.036	2.20	0.0045	(0.006)	0.051	0.014	0.032
1	SS 462/1	0.0345	0.722	0.0053	0.0041	0.463	0.0112	12.85	11.888	.	0.0304
1	SRM C1151a	0.034	2.37	0.017	0.038	0.29	0.385	7.25	22.59	0.033	0.79	.	.	.	0.040	.
1	13X 31400A	0.033	1.60	0.026	0.0006	2.23	0.210	18.76	24.38	0.129	0.240	0.0288	0.018	.	0.092	0.015
1	BS 9812	0.031	0.485	0.018	0.004	0.43	1.65	6.61	14.82	0.110	0.76	0.0195	0.645	(0.005)	0.088	0.025
1	13X NSA9B	0.030	1.52	0.0237	0.0009	0.290	0.154	5.75	22.39	0.033	3.27	0.184	0.021	.	0.060	0.033
1	13X 30403B	0.0277	1.820	0.0321	0.0266	0.288	0.497	8.13	18.30	0.178	0.313	0.083	0.0201	0.0013	0.0700	0.035
2	HRT FE2014-H	0.027	1.91	0.023	(0.002)	0.39	0.25	9.92	17.16	.	0.41	(0.018)	.	0.31	.	.
2	BS 317L	0.027	1.17	0.029	0.0014	0.67	0.23	13.53	18.16	0.14	3.07	0.056	0.031	.	0.09	0.018
1	VS LG75	0.027	0.728	0.0046	0.0026	0.298	0.029	24.5	14.80	0.190	0.052	0.0044	.	1.76	0.09	4.14
1	BS 9811	0.027	0.380	0.016	0.0010	0.36	1.63	6.55	14.87	0.055	0.744	0.0196	0.62	(0.003)	0.086	0.013
1	SRM 1155a	0.0260	1.593	0.0271	(0.0020)	0.521	0.2431	12.471	17.803	0.225	2.188	(0.0428)	0.0082	0.0039	0.0725	0.0809
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
2	HRT FE2013-H	0.026	0.61	0.022	0.005	0.38	0.13	6.20	25.71	.	3.63	0.28	.	.	0.05	.
1	13X 32900A	0.0251	1.478	0.0276	0.0269	0.556	0.354	5.57	24.91	0.0724	1.310	0.097	.	0.0139	0.0938	0.017
1	IARM 162D	0.0240	1.82	0.0296	0.0271	0.570	0.52	8.15	18.31	0.074	0.573	0.097	0.0090	0.013	0.063	0.028
1	IARM FE304L-18	0.024	1.39	0.034	0.029	0.43	0.54	8.17	18.34	0.156	0.462	0.081	0.013	0.0056	0.076	0.056
1	IARM 153C	0.0225	1.60	0.0289	0.0288	0.349	0.442	11.10	18.22	0.251	3.00	0.086	0.015	0.004	0.058	0.043
1	ECRM 297-1D	0.0223	0.897	0.0137	0.0101	0.344	0.204	12.33	18.37	0.0413	0.290	0.0152	(0.0089)	0.0072	0.0535	(0.0057)
1	NCS HS28746	0.021	1.87	0.031	0.0009	0.510	0.340	8.24	17.19	0.191	0.069	0.011	.	0.184	0.096	.
1	BS 9942	0.021	1.84	0.025	0.006	0.049	0.305	13.55	18.21	0.086	3.30	0.071	0.005	(0.002)	0.072	0.032
1	BS 9941	0.021	1.78	0.027	0.024	0.33	0.424	13.68	18.48	0.178	3.24	0.036	0.015	(0.002)	0.062	0.068
1	IARM Fe316L-18	0.021	1.70	0.033	0.029	0.438	0.550	10.12	16.7	0.209	2.02	0.067	(0.027)	(0.003)	(0.067)	(0.06)
1	IRSID 1820	0.021	1.61	(0.021)	0.0079	0.428	0.045	9.07	19.51	0.151	0.115	0.064
1	BS 2205A	0.021	1.48	0.029	0.0006	0.53	0.300	5.26	22.73	0.071	3.17	0.157	0.010	(0.002)	0.083	(0.02)
1	NCS HS28742	0.021	0.940	0.034	0.0028	0.414	0.043	8.11	18.2	0.216	0.025	0.059	.	0.006	0.089	.
1	IARM 301B	0.0206	0.807	0.0251	0.0010	0.419	0.192	7.01	25.06	0.055	3.75	0.297	0.020	(0.003)	0.070	0.050
1	13X NSA8B	0.0206	0.596	0.0248	0.0007	0.285	0.589	7.48	25.49	0.0448	3.49	0.232	0.026	.	0.0583	0.599
1	13X NSA13A	0.020	0.761	0.0249	0.0005	0.257	0.156	6.73	25.27	0.032	3.73	0.269	0.028	.	0.0712	0.035
1	SS 463/1	0.019	1.400	0.025	0.019	0.270	0.276	10.20	18.46	0.116	0.265	0.063
1	BS 2205	0.0199	1.029	0.0227	0.0005	0.564	0.196	5.27	22.92	0.041	3.26	0.169	0.0052	0.0019	0.0560	0.0309
1	13X NSA12A	0.0192	1.272	0.0267	0.0007	0.492	1.485	24.84	19.63	0.090	4.20	0.0662	0.0088	.	0.0660	0.047
1	IARM 212D	0.019	1.21	0.024	0.0007	0.34	0.125	5.53	22.60	0.049	3.27	0.182	(0.009)	(0.002)	0.063	0.014
1	13X FV520BA	0.0181	0.655	0.0221	0.0016	0.342	1.462	5.29	13.73	0.030	1.334	0.0197	0.301	.	0.080	0.020
2	HRT FE2000-H	0.018	2.02	0.022	(0.003)	0.36	0.15	5.98	22.15	0.048	3.27	0.20	0.010	0.005	0.042	0.063
1	IARM FE2205-18	0.018	1.18	0.023	(0.0013)	0.46	0.208	5.57	22.6	0.104	3.20	0.17	0.011	(0.003)	0.063	0.024
1	NCS HS28745	0.018	1.17	0.042	0.0057	0.317	0.334	10.34	16.61	0.185	2.05	0.070	.	(0.002)	0.070	.
1	SS 476	0.0171	1.755	0.0302	0.0234	0.323	0.302	10.17	16.88	0.162	2.04	0.0794	0.0107	.	0.066	0.041
1	BS 304B	0.017	1.72	0.022	0.023	0.540	0.257	8.68	18.3	0.220	0.42	0.081	0.074	(0.0018)	0.097	(0.01)
1	IARM 239C	0.017	0.87	0.023	(0.0010)	0.38	1.49	6.14	25.8	0.039	3.33	0.228	(0.006)	(0.004)	0.083	(0.05)
1	IARM FEz100-18	0.017	0.52	0.026	(0.0009)	0.24	0.55	7.1	25.5	0.123	3.61	0.22	(0.005)	.	0.090	0.56
1	BS 179C	0.0164	0.878	0.0236	0.0003	0.373	1.53	6.10	25.9	0.0386	3.34	0.236	0.009	(0.0005)	0.080	0.056
1	BS 179B	0.0161	0.890	0.0243	0.0002	0.371	1.56	6.17	25.9	0.0394	3.34	0.239	0.008	(0.0008)	0.079	0.053
1	ECRM 287-1D	0.016	1.48	0.027	0.0014	0.569	0.203	10.35	18.61	0.148	0.247	0.019
1	13X 34700A	0.016	1.290	0.028	(0.0006)	0.483	0.163									

STAINLESS STEEL WITH C < 0.05 %

CONTINUED FROM THE PREVIOUS PAGE

analysis listed in mass %

Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
ECRM 269-1D		0.0061						0.0099		35 mm Ø x 25 mm
IARM 8H	(0.005)		(0.0002)					(0.008)	(0.01)	31 mm Ø x 2 or 18 mm
IARM 61	0.084	(0.005)	0.0034	(0.0004)	0.0012			(0.0060)		31 mm Ø x 2 or 18 mm
ECRM 289-1D	0.199		0.0044					0.111		38 mm Ø x 30 mm
IMZ 150A	0.022									40 mm Ø x 40 mm
IARM 4F	0.015	(0.003)	(0.0012)	(0.002)	(0.004)		(0.001)	(0.005)	(0.007)	31 mm Ø x 2 or 18 mm
13X 14211R	0.089								0.0152	~40 mm Ø x ~15 mm
13X 32100A	0.0247		0.0025					0.0115		~38 mm Ø x ~15 mm
IARM Fe303-18		0.007	(0.0012)		(0.006)			(0.015)		31 mm Ø x 2 or 18 mm
BS 188B	0.168	0.0045	0.0047	(0.00003)	0.0006	(0.0001)	(0.0006)	0.0051		38 mm Ø x ~7 or 19+ mm Fe: 55.8 17025
IARM 4G	0.008	(0.005)	0.0032	(0.001)	(0.003)	(0.0005)	(0.001)	0.008	(0.008)	31 mm Ø x 2 or 18 mm
IARM 6J	0.0195		0.0024		(0.001)			(0.009)	(0.01)	31 mm Ø x 2 or 18 mm
BS 303	0.0019		0.0013	(0.0015)	0.0058			0.0091		44 mm Ø x ~7 or 19+ mm 17025 Fe:[70.7]
IARM 4E	0.004	(0.005)	0.0011		0.0021			0.0060	0.005	31 mm Ø x 2 or 18 mm
CZ SL-3A	0.007		0.002					0.006		~39 mm Ø x 25 mm
KUT S15										30-35 mm Ø x 18 or 40 mm
IARM 81	(0.0030)		(0.0005)		(0.004)			(0.012)		31 mm Ø x 2 or 18 mm
13X 14216P										~40 mm Ø x ~15 mm
IARM 8G	0.0030	(0.007)	(0.0005)	(0.0005)	(0.003)			0.0107	(0.004)	31 mm Ø x 2 or 18 mm
VS 1G70	0.029									~45 mm Ø x ~28 mm
NILAB 500HA D										38 mm Ø x 20 mm
13X 12538J										40 mm Ø x 15 mm
NCS HS28741		0.0035				0.0001		0.0051		38 mm Ø x 35 mm
13X 14207L	0.0226								0.082	~40 mm Ø x ~15 mm
IRSD 1821										47 mm x 47 mm x 30 mm
IMZ 153A	0.036									38 mm Ø x 20 mm
ECRM 292-1D	(0.002)	(0.008)		(0.0006)					(0.001)	38 mm Ø x 25 or 30 mm
13X 66286A	0.193		0.0044							~40 mm Ø x ~15 mm
BS 184A	1.00		(0.0004)	(0.0003)	(0.0003)			(0.002)	(0.002)	38 mm Ø x ~7 or 19+ mm
SS 462/1										38 mm Ø x 19 mm
SRM C1151a						0.0039				32 mm Ø x 19 mm
13X 31400A	0.022			0.0024						~40 mm Ø x ~15 mm
BS 9812	(0.002)	(0.005)	(0.0003)	0.0012	(0.007)			0.004		50 mm Ø x ~7 or 19+ mm 25(pre-17025)
13X NSA9B			0.0018							~40 mm Ø x ~15 mm
13X 30403B	0.0056			0.0027				0.0139		~40 mm Ø x ~15 mm
HRT FE2014-H										35mm Ø x 20 mm
BS 317L	(0.005)	(0.003)	0.0013	(0.001)	0.007			0.005		37 mm Ø x ~7 or 19+ mm
VS 1G75	0.113									~45 mm Ø x ~28 mm
BS 9811	(0.003)	(0.003)	(0.0003)	0.0014	(0.0060)			0.004		38 mm Ø x ~7 or 19+ mm 25(pre-17025)
SRM 1155a	<0.01	(0.007)	(0.002)		(0.003)	<0.005		(0.0069)		32 mm Ø x 19 mm
Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
HRT FE2013-H										40 mm Ø x 20 mm last of stock
13X 32900A	0.007		0.0028	0.0033						~40 mm Ø x ~15 mm
IARM 162D	(0.0026)	0.0072	0.0027	(0.003)	0.005		(0.0019)	0.0102	(0.005)	31 mm Ø x 2 or 18 mm
IARM Fe304L-18	(0.003)	0.007	(0.0012)		(0.006)			(0.013)		31 mm Ø x 2 or 18 mm
IARM 153C	(0.003)	0.0061	0.0009	(0.0026)	0.006	(0.001)	(0.002)	0.010	(0.006)	31 mm Ø x 2 or 18 mm
ECRM 297-1D	0.0195	0.0040	1.146	(0.0002)						40 mm Ø x 30 mm
NCS HS28746	0.086	0.0032				0.0002		0.0065		38 mm Ø x 35 mm
BS 9942	0.004	(0.004)	0.0014	0.0014	(0.0023)			0.006		44 mm Ø x ~7 or 19+ mm 25(pre-17025)
BS 9941	0.004	(0.010)	0.0025	(0.0003)	(0.0058)			0.007		38 mm Ø x ~7 or 19+ mm 25(pre-17025)
IARM Fe316L-18	(0.006)				(0.005)			(0.013)		31 mm Ø x 18 mm
IRSD 1820			(0.0013)							47 mm x 47 mm x 30 mm
BS 2205A	(0.004)	0.0072	0.0022	0.0007	0.0046			0.0058		38 mm Ø x ~7 or 19+ mm 17025 Fe: 66.2
NCS HS28742		0.0025				0.0001		(0.0001)		38 mm Ø x 35 mm
IARM 301B	0.005	(0.004)	0.0024	(0.0009)	0.0069	(0.0003)	(0.0006)	0.0051	(0.003)	31 mm Ø x 2 mm
13X NSA8B			0.0017	0.0011						~38 mm Ø x ~15 mm
13X NSA13A	(0.007)		0.0030			(0.0008)		0.0046		~40 mm Ø x ~15 mm
SS 463/1			0.0022							38 mm Ø x 19 mm
BS 2205	0.0080	0.0059	0.0016	0.0014	0.0034	(0.0001)	0.0010	0.0050	17025	38 mm Ø x ~7 or ~15 mm Fe:[67.0] Mg:(0.0004) last
13X NSA12A	0.0169		0.0020							~40 mm Ø x ~15 mm
IARM 212D	(0.005)	(0.01)	0.001	(0.001)	0.0034	(0.001)		(0.003)	(0.003)	31 mm Ø x 2 mm last of stock
13X FV520BA										~40 mm Ø x ~15 mm
HRT FE2000-H			0.0013							40 mm Ø x 20 mm
IARM Fe2205-18	(0.007)				(0.004)			(0.006)		31 mm Ø x 2 or 18 mm
NCS HS28745		0.0055				0.0001		0.0073		38 mm Ø x 35 mm
SS 476		0.0053		0.0028				0.0059		38 mm Ø x 19 mm
BS 304B	0.0036	0.0051	(0.0004)	0.0009	0.0038	(0.0008)		0.0057		38 mm Ø x ~7 or 19+ mm 17025 Fe: 69.6
IARM 239C	0.007	(0.004)	0.0014					(0.003)	(0.004)	31 mm Ø x 2 or 18 mm
IARM FeZ100-18	(0.017)		0.002		(0.003)			(0.006)		31 mm Ø x 2 or 18 mm
BS 179C	0.0078	0.0034	0.0015	(0.0003)	0.0038	(0.00002)	0.0005	0.0018	(0.0006)	38 mm Ø x ~7 or 19+ mm 17025 Fe:[61.6]
BS 179B	0.0070	0.0036	0.0015	(0.0004)	0.0037	(0.00002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm 17025 Fe:[61.5]
ECRM 287-1D			0.924							38 mm Ø x 25 or 30 mm
13X 34700A	0.023		0.0008							~38 mm Ø x ~15 mm
13X NSA11A	(0.021)									~38 mm Ø x ~15 mm
CZ SL-2A	0.005	0.008	0.002					0.01		~39 mm Ø x 25 mm
BS 316F	(0.002)	0.0067	0.0019	0.0018	0.0055	(0.0002)		0.0092	Fe:68.1	38 mm Ø x ~7 or 19+ mm 17025
IARM 319A	(0.010)	(0.004)	0.0020		0.0025			0.0055	(0.002)	31 mm Ø x 2 mm
ECRM 298-1D	0.0285		0.0021			0.00008				38 mm Ø x 25 mm Fe: 63.38
SS 466/2	0.0018	0.0020	0.0039							38 mm Ø x 19 mm
BS SS3951	0.002		(0.0006)	0.0005	0.0075			0.007		41 mm Ø x ~7 or 19+ mm
IARM 163E *	0.0039	(0.008)	0.0019	(0.002)	0.007		(0.002)	0.012		31 mm Ø x 2 mm * Provisional Analysis, last
HRT FE2016-H										30 mm Ø x 20 mm
SS 461/1	0.069									38 mm Ø x 19 mm
13X 30600A	0.020				Mg:0.0016					~32 mm Ø x ~20 mm
BS SS1961	0.067	0.004	0.0022		(0.002)			0.004		38 mm Ø x 12 mm last
JK 27B			0.00072	0.0022				0.0068		~37 mm Ø x 25 mm
BS SS1962	0.062	0.002	0.0018		(0.001)			0.004		38 mm Ø x ~7 or 19+ mm
IARM 354A	(0.05)	(0.002)	0.0023	(0.0003)	(0.0012)	(0.004)	(0.0002)			31 mm Ø x 2 or 18 mm
CT IS0123A	0.027		0.0021							30-35 mm Ø x ~16 mm Fe: 74.72
13X 46500A	0.069		0.0016					0.0030		~32 mm Ø x ~20 mm
ECRM 284-3D		0.00131	0.00020					0.00074		39 mm Ø x 28 mm
Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units

RM TRACE ELEMENTS IN STAINLESS STEEL

certified analysis							informational analysis													40 mm Ø x 20 mm		
Number	As	Pb	Sb	Sn	Zn		C	Mn	P	Si	Cu	Ni	Cr	Mo	N	B	Ca	Ti	V			
DSZU C25	0.093	0.038	0.094	0.095	0.034		0.3	0.1	0.02	0.3	0.7	1.6	13	0.1	0.10	0.03	0.004		0.03			
DSZU C35	0.064	0.086	0.058	0.064	0.058		0.1	1.1	0.03	0.3	0.5	11	16	1.4	0.02	0.002	0.001	0.05	0.03			
DSZU C22	0.051	0.023	0.050	0.051	0.019		0.4	0.1	0.02	0.2	0.5	1.5	13	0.1	0.04	0.03	0.002		0.03			
DSZU C33	0.021	0.0046	0.015	0.020	0.019		0.1	1.1	0.03	1.0	0.3	16	17	1.2	0.14	0.02	0.0004	0.05	0.03			
DSZU C24	0.014	0.0017	0.010	0.011	0.0035		0.4	0.1	0.02	0.2	0.3	1.5	13	0.1	0.12	0.007	0.003		0.03			
DSZU C31	0.012	0.0017	0.007	0.010	0.028		0.1	1.4	0.03	0.8	0.2	10	17	0.8	0.04	0.02	0.008	0.05	0.03			
DSZU C23	0.008	0.0008	0.006	0.010	0.0028		0.4	0.1	0.02	0.3	0.2	1.4	13	0.1	0.10	0.004	0.002		0.03			
DSZU C32	0.008	0.0005	0.0015	0.006	0.015		0.1	1.2	0.03	0.6	0.2	11	17	1.0	0.04	0.02	0.005	0.05	0.03			
DSZU C21	0.005	0.0002	0.0011	0.003	0.0026		0.4	0.1	0.02	0.3	0.2	1.2	13	0.1	0.03	0.002	0.001		0.03			

STAINLESS STEEL XRF SETS

AVAILABLE IN SETS OR INDIVIDUALLY

~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	V	W
SET BS SS-17															
15-5PH	BS 185A	0.033	0.49	0.022	0.002	0.38	3.41	4.43	14.46	0.026	0.30	0.027	0.32	0.048	(0.014)
17-4PH	BS 17-4PHA	0.018	0.85	0.023	0.022	0.40	3.30	4.69	15.40	0.072	0.34	0.022	0.204	0.043	
17-7PH	BS 192	0.075	0.84	0.025	0.001	0.38	0.41	7.10	16.42	0.104	0.42	0.029	0.17	0.13	0.04
253 MA	BS 253	0.094	0.58	0.018	<0.001	1.81	0.14	10.89	20.68	0.15	0.21	0.146	0.017	0.050	0.03
255	BS 179C	0.0164	0.878	0.0236	0.0003	0.373	1.53	6.10	25.9	0.0386	3.34	0.236	0.009	0.080	0.056
2205 (318)	BS 2205	0.0199	1.029	0.0227	0.0005	0.564	0.196	5.27	22.92	0.041	3.26	0.169	0.0052	0.0560	0.0309
303	BS 303	0.044	1.80	0.028	0.326	0.415	0.627	8.17	17.23	0.071	0.410	0.023	0.008	0.056	0.023
304 L	BS 81P	0.026	1.35	0.023	0.012	0.36	0.19	10.06	18.15	0.21	0.41	0.069		0.078	0.037
309	BS 82E	0.062	1.61	0.027	0.001	0.58	0.26	12.49	22.38	0.12	0.31	0.072	0.062	0.064	0.041
310	BS 83G	0.073	1.66	0.024	0.004	0.56	0.114	19.15	24.50	0.153	0.085	0.026	0.061	0.077	0.007
316	BS 316F	0.015	1.46	0.029	0.026	0.55	0.437	10.09	16.79	0.126	2.10	0.061	0.011	0.062	0.045
317 L	BS 317L	0.027	1.17	0.029	0.0014	0.67	0.23	13.53	18.16	0.14	3.07	0.056	0.031	0.09	0.018
321	BS 85D	0.048	1.69	0.024	0.024	0.54	0.45	9.98	17.09	0.97	0.59	(0.02)	0.062	0.132	(0.07)
330	BS 86F	0.054	1.30	0.021	0.0011	1.22	0.23	34.99	18.74	0.098	0.24	0.035	0.19	0.061	(0.03)
347	BS 347B	0.051	1.57	0.028	0.026	0.51	0.15	9.16	17.24	0.05	0.38	0.056	0.71	0.04	(0.005)
355	BS 355	0.136	0.862	0.0171	0.0003	0.374	0.173	4.18	15.43	0.053	2.73	0.081	0.0103	0.106	0.0069
PH13-8 Mo	BS 184A	0.035	0.06	0.007	0.001	0.080	0.041	8.34	12.66	0.036	2.20	0.0045	(0.006)	0.014	0.032
SET BS 400-SS-16															
182PM	BS 150	0.048	1.71	0.020	0.33	0.43	0.042	0.19	18.61	0.024	1.97	0.029	0.003	0.054	0.01
410	BS 410C	0.131	0.381	0.0206	0.0051	0.366	0.084	0.352	12.78	0.0185	0.055	0.039	0.0056	0.0006	0.0131
416	BS 90F	0.085	0.53	0.023	0.328	0.58	0.12	0.30	13.01	0.021	0.14	0.037	0.011	0.076	0.032
416 Se	BS 151	0.090	0.41	0.021	0.018	0.65	0.11	0.24	13.19	0.018	0.088	0.022	0.005	0.046	0.010
420	BS 98	0.309	0.48	0.019	0.0014	0.72	0.098	0.21	13.35	0.020	0.034	0.0181	0.003	0.075	0.009
420F	BS 152	0.32	0.36	0.022	0.275	0.44	0.050	0.14	13.41	0.015	0.061	0.020	0.006	0.051	<0.01
422	BS 97	0.216	0.71	0.021	0.0004	0.39	0.066	0.76	11.82	0.041	1.05	0.030	0.007	0.21	0.95
430	BS 91E	0.066	0.42	0.017	0.002	0.52	0.05	0.17	16.58	0.02	0.035	0.032	(0.004)	0.09	0.01
430F	BS 153	0.026	0.41	0.018	0.280	0.53	0.052	0.140	17.38	0.017	0.30	0.021	0.002	0.045	(0.002)
431	BS 92B	0.150	0.42	0.021	0.003	0.42	0.13	2.12	15.92	0.04	0.17	0.073	(0.006)	0.07	0.02
440C	BS 93E	1.02	0.52	0.022	0.0010	0.90	0.12	0.35	17.33	0.048	0.50	0.0359	0.005	0.24	0.11
440F	BS 155	1.00	0.35	0.014	0.145	0.40	0.035	0.13	16.64	0.019	0.46	0.032	0.002	0.10	
440F Se	BS 156	1.06	1.15	0.022	0.007	0.47	0.09	0.35	16.87	0.047	0.50	0.041	0.005	0.13	0.11
446	BS 94C	0.057	0.45	0.024	0.002	0.62	0.056	0.43	25.90	0.042	0.20	0.065	0.032	0.12	(0.03)
450	BS 95A	0.035	0.58	0.026	0.004	0.46	1.50	6.42	14.72	0.081	0.73	0.0255	0.55	0.052	0.02
455	BS 96A	0.009	0.04	0.007	0.004	0.06	2.07	8.38	11.62	0.03	0.021		0.26	0.07	
Number	Al	B	Ca	Se	Sn	Ti									
SET BS SS-17															
BS 185A	0.002	0.0017	(0.0002)	.	0.007	(0.001)									
BS 17-4PHA	.	0.0016	Ta: (0.002)								
BS 192	1.15	(0.0004)	0.0007	.	0.009	0.078									
BS 253	0.016	.	.	.	0.006	0.005	Ce: 0.044	As: 0.005							
BS 179C	0.0078	0.0015	(0.0003)	.	0.0018	(0.0005)	As: 0.0034	O: 0.0038	Sb: 0.0005	17025					
BS 2205	0.0080	0.0016	0.0014	.	0.0050	0.0019	As: 0.0059	Fe: [67.0]	O: 0.0034	Sb: 0.0010	17025				
BS 303	0.0019	0.0013	(0.0015)	.	0.0091	0.017	O: 0.0058	17025							
BS 81P	(0.003)	0.0026	(0.0004)	.	0.007	0.003	O: (0.0064)								
BS 82E	0.006	0.0024	0.0014	.	0.006	0.003									
BS 83G	(0.004)	(0.001)	O: 0.0064	.	0.003	(0.003)									
BS 316F	(0.002)	0.0019	0.0018	.	0.0092	0.011	As: 0.0067	Fe: 68.1	O: 0.0055	17025					
BS 317L	(0.005)	0.0013	(0.001)	.	0.005	.									
BS 85D	0.13	(0.001)	0.0004	.	0.0062	0.48	17025								
BS 86F	(0.007)	0.0026	(0.001)	.	0.004	(0.006)									
BS 347B	0.002	0.0036	(0.0005)	.	0.006	(0.002)									
BS 355	0.0192	0.0039	(0.0002)	.	0.0038	0.0007	O: 0.0020								
BS 184A	1.00	(0.0004)	(0.0003)	.	(0.002)	0.051									
SET BS 400-SS-16															
BS 150	0.002	.	.	.	(0.003)	(0.002)									
BS 410C	0.0079	(0.0001)	0.0022	.	0.0023	0.0006	17025								
BS 90F	(0.006)	.	.	.	0.005	(0.002)									
BS 151	(0.002)	.	.	0.328	0.005	<(0.003)									
BS 98	0.003	.	(0.0005)	.	0.006	0.002									
BS 152	(0.002)	.	.	.	0.003	(0.002)									
BS 97	0.018	.	.	.	(0.003)	(0.002)									
BS 91E	(0.002)	.	0.0008	.	0.004	(0.002)									
BS 153	(0.004)	.	.	.	0.002	(0.004)									
BS 92B	(0.002)	.	(0.0009)	.	0.006	(0.002)									
BS 93E	0.009	.	.	.	0.003	0.007									
BS 155	(0.001)	.	.	.	(0.003)	(0.002)									
BS 156	<(0.002)	.	.	0.142	(0.004)	0.001									
BS 94C	0.004	.	0.0008	.	0.006	.									
BS 95A	0.002	0.0010	0.0008	.	0.008	(0.003)									
BS 96A	0.08	(0.0017)	.	.	.	1.18									

HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V
3	CZ SP-8B	2.37	0.86	0.022	0.012	1.40	0.075	2.72	37.6	0.13	0.075	0.10	.	0.04	0.13	0.13
2	CZ SP-4C	0.34	1.66	0.020	0.010	1.75	0.056	37.1	22.1	0.011	0.065	0.105	(0.04)	0.022	0.031	0.059
1	IARM 242A	0.24	0.018	0.002	0.0004	0.02	0.007	11.1	3.00	0.004	13.5	1.21	0.0003	0.004	0.009	0.01
1	SRM 1246	0.082	0.91	0.018	0.001	0.18	0.49	30.8	20.1	0.30	0.076	0.36	(0.018)	(0.09)	0.32	(0.040)
2	23X DS5E	0.080	1.04	.	.	1.98	0.30	36.6	8.64	0.083	0.50	0.30	.	.	0.17	.
1	NCS HS41747	0.071	0.807	0.015	0.0006	0.36	0.038	32.27	20.72	0.299	0.050	0.297	.	.	0.49	.
3	HH 5157A	0.067	0.95	0.012	0.003	0.43	0.33	29.31	21.48	0.45	0.55	.
2	DSZU C103	0.064	0.287	0.027	(0.006)	0.34	0.066	0.21	27.04	5.28	.	0.013	.	(0.002)	0.29	0.035
2	DSZU C104	0.055	0.838	0.035	0.019	0.78	0.199	0.51	29.77	6.58	.	0.18	.	0.52	0.76	0.22
1	IARM 24B	0.053	0.82	0.009	0.0010	0.28	0.052	35.86	0.121	0.002	0.036	0.011	0.0017	<0.01	0.002	<0.005
1	SS 479	0.0529	0.680	0.0029	0.0030	0.553	0.0052	24.87	19.922	(0.013)	(0.002)	(0.003)	0.0057	0.625	0.0306	0.0052
2	23X DS4E	0.05	1.02	.	.	2.01	0.30	37.1	16.83	0.037	0.48	0.29	.	.	0.20	.
1	BS CD4MCU	0.045	0.568	0.025	0.021	0.71	2.93	5.62	24.46	0.063	(0.03)	1.98	0.229	(0.004)	0.021	0.108
1	SRM 1230	0.044	0.64	0.023	0.0007	0.43	0.14	24.2	14.8	0.24	0.15	1.18	.	.	2.12	0.23
3	HH 5179A	0.042	0.87	0.012	0.003	0.38	0.26	34.13	22.20	0.30	0.46	.
2	BS 186A	0.040	0.72	0.008	0.0053	0.19	0.016	35.86	0.16	(0.001)	0.028	0.0032	0.0026	(<0.002)	(<0.003)	0.0012
2	DSZU C102	0.038	0.265	0.025	(0.006)	1.27	0.031	0.19	24.41	4.98	.	0.022	.	(0.005)	0.25	0.089
3	HH 5196A	0.036	1.05	0.011	0.002	0.45	0.24	31.46	20.66	0.31	1.13	.
3	HH 5300A	0.026	0.86	0.013	0.003	0.35	0.28	33.56	18.18	0.45	0.54	.
1	13X 14934Q	0.0254	0.254	0.024	0.0288	0.502	.	17.60	0.388	0.15	9.03	4.22	0.0132	.	0.694	.
1	SRM 1158	0.025	0.468	0.004	0.005	0.194	0.039	36.03	0.062	.	0.008	0.010	.	.	.	0.001
2	DSZU C101	0.024	0.198	0.013	(0.006)	0.32	0.055	0.34	21.77	5.06	.	0.026	.	(0.011)	0.31	0.023
1	IARM 302B	0.0226	0.93	0.0256	0.0007	0.56	0.701	17.7	20.33	0.0159	0.072	6.24	0.180	0.012	0.0031	0.052
2	BS 187A	0.022	0.52	0.017	0.0025	0.26	3.10	33.06	19.75	(0.009)	0.32	2.06	0.0157	0.57	(0.002)	0.10
1	13X 17005E	0.0217	0.209	0.0040	0.0431	1.739	0.120	20.06	24.65	0.049	0.0265	0.599	0.0097	0.101	0.0073	.
2	CT ISO139A	0.021	1.00	0.001	0.0005	0.015	<0.001	41.69	0.004	.	0.066	<0.001
1	SRM 1247	0.021	0.38	0.018	0.002	0.32	1.75	43.5	23.4	0.060	0.089	2.73	(0.017)	(0.46)	0.75	(0.048)
1	BS CD4MCU-A	0.021	0.38	(0.008)	0.0072	0.31	2.92	5.18	24.6	(0.009)	(0.005)	1.92	0.0112	(0.009)	0.021	(0.006)
2	BS 187C	0.020	0.77	0.024	<0.002	0.77	3.17	32.93	20.16	0.10	0.096	2.07	0.022	0.36	(0.001)	0.059
2	CT ISO141A	0.0199	0.31	0.001	<0.001	0.28	<0.001	47.16	<0.001	0.001	0.030	<0.001	<0.001	.	0.014	0.024
2	CT ISO136A	0.018	0.44	0.001	<0.001	0.198	<0.001	44.92	0.002	.	0.009	<0.001	.	.	0.009	0.050
1	IARM 157D	0.0154	0.626	0.016	0.0005	0.28	0.196	23.9	20.31	0.020	0.102	6.08	0.203	0.149	0.009	0.050
1	ECRM 299-1D	0.0154	0.2678	0.0152	0.00022	0.299	0.0382	0.172	22.32	5.33	0.0187	0.0186	0.0198	.	0.1289	0.0329
1	BS 189A	0.0147	0.639	0.019	(0.001)	0.30	0.184	23.8	20.4	0.0129	0.100	6.04	0.198	(0.13)	0.0065	0.054
1	NILAB 501HA D	0.014	0.858	0.020	0.003	.	0.761	17.69	19.79	0.003	0.159	6.14	0.2243	0.007	.	0.044
1	KUT S22	0.014	0.34	0.009	0.008	0.61	(0.02)	28.2	1.00	.	.	0.82	.	.	0.13	.
1	ECRM 379-1D	0.0121	1.804	0.0166	0.0006	0.393	0.984	30.83	26.79	(0.00246)	0.0390	3.290	0.0550	(0.0028)	(0.0014)	0.0663
1	NCS HS41753a	0.012	0.973	0.021	0.013	0.480	1.26	24.28	19.16	.	0.180	4.25	0.041	0.812	0.004	0.075
2	CT ISO124A	0.011	0.73	0.007	0.006	0.40	0.015	48.07	0.079	.	0.012	0.009
1	14X 93603A	0.0101	0.339	0.0050	0.0045	0.153	0.0460	35.79	0.024	0.0404	0.0974	0.0145	0.0057	.	0.0011	.
1	SRM 1159	0.007	0.30	0.003	0.003	0.32	0.038	48.2	0.06	.	0.022	0.01
1	IARM 98B	0.007	0.18	0.002	0.0007	0.17	0.028	29.4	0.012	0.07	17.0	0.010	0.0024	0.002	0.03	(0.003)
1	BS 160A	0.0064	0.180	0.0007	(0.0002)	0.158	0.026	29.6	0.0138	0.088	17.0	0.0100	0.0026	0.0014	0.026	0.0008
3	CZ SP-7A	0.006	0.08	0.007	0.010	0.036	0.08	47.3	0.01	0.003	0.003	0.01	.	.	0.004	0.001
1	BS 161A	0.004	0.031	0.004	0.0007	0.032	0.22	18.40	0.12	0.14	9.22	4.82	(0.002)	(0.004)	0.65	0.031
1	IARM 26D	0.038	0.224	0.013	(0.0008)	(0.05)	0.047	24.6	14.29	0.29	0.040	1.23	0.0035	(0.007)	2.17	0.223
2	CT ISO138A	0.002	0.48	0.001	0.006	<0.010	<0.001	39.98	<0.001	.	0.64	<0.001	.	.	0.34	.
1	IARM 326A	(0.002)	0.003	0.0013	0.0011	0.029	(0.002)	0.037	(0.002)	(0.003)	48.4	(0.002)	0.0004	0.038	(0.002)	1.94
1	ECRM 285-2D	0.0018	0.0168	0.0053	0.0025	0.0117	0.0094	18.07	0.0236	0.1067	7.76	4.99	0.0007	.	0.520	.

Number	As	B	Ca	Ce	Mg	O	Se	Sn	Ta	W	Zr	Units
CZ SP-8B	0.05	0.03	0.06	.	0.05	.	~39 mm Ø x 25 mm
CZ SP-4C	(0.01)	.	.	~39 mm Ø x 25 mm
IARM 242A	.	(0.0005)	.	.	.	0.0006	.	(0.001)	0.008	<0.01	.	31 mm Ø x 2 mm
SRM 1246	(0.004)	<0.001	Ga: (0.004)	.	.	(0.003)	35 mm Ø x 19 mm
23X DS5E	40 mm Ø x 15 mm
NCS HS41747	38 mm Ø x 30 mm
HH 5157A	44 mm Ø x 12 mm
DSZU C103	(0.004)	(0.001)	.	38 mm Ø x 18 mm
DSZU C104	(0.008)	0.28	.	36 mm Ø x 18 mm
IARM 24B	<0.005	(0.001)	.	.	.	0.003	0.19	0.0018	<0.005	<0.04	<0.005	31 mm Ø x 2 or 18 mm
SS 479	(0.002)	<0.0005	38 mm Ø x 19 mm
23X DS4E	40 mm Ø x 15 mm
BS CD4MCU	0.0040	0.0028	(0.001)	.	(0.0003)	0.019	<u>17025</u>	(0.03)	.	0.024	(0.002)	36 mm Ø x 26 mm
SRM 1230	.	0.0055	32 mm Ø x 19 mm
HH 5179A	41 mm Ø x 12 mm
BS 186A	0.229	(0.002)	.	(0.01)	.	38 mm Ø x ~7 or 19+ mm
DSZU C102	(0.020)	(0.003)	.	38 mm Ø x 18 mm
HH 5196A	44 mm Ø x 12 mm
HH 5300A	41 mm Ø x 12 mm
13X 14934Q	40 mm Ø x ~12 mm
SRM 1158	32 mm Ø x 19 mm
DSZU C101	(0.011)	(0.003)	.	38 mm Ø x 18 mm
IARM 302B	(0.009)	0.0027	(0.0031)	.	(0.0009)	0.0032	(0.0006)	0.0075	0.004	0.025	.	31 mm Ø x 2 mm
BS 187A	.	0.0022	.	(0.025)	.	0.0024	0.003	0.003	<0.002	(0.02)	.	41 mm Ø x ~7 - 19 mm
13X 17005E	.	0.0030	0.015	.	.	~40 mm Ø x ~15 mm
CT ISO139A	30-35 mm Ø x ~16 mm
SRM 1247	(0.003)	0.002	Ga: (0.011)	.	(0.005)	(0.005)	.	35 mm Ø x 19 mm
BS CD4MCU-A	0.0022	(0.0008)	(0.001)	.	(0.0003)	0.0061	<u>17025</u>	0.0024	.	(0.009)	(0.002)	44 mm Ø x 19+ mm
BS 187C	.	(0.0019)	.	.	.	0.0024	.	0.004	(0.002)	.	.	44 mm Ø x 12 mm
CT ISO141A	0.0002	30-35 mm Ø x ~16 mm
CT ISO136A	30-35 mm Ø x ~16 mm
IARM 157D	.	0.0007	0.0036	.	0.036	.	31 mm Ø x 2 or 18 mm
ECRM 299-1D	0.0054	0.0002	0.1775	.	40 mm Ø x 25 mm
BS 189A	0.0039	(0.0002)	(0.0004)	.	.	0.0024	<u>17025</u>	0.0035	.	0.037	(0.001)	38 mm Ø x ~7 or 19+ mm
NILAB 501HA D	38 mm Ø x 20 mm
KUT S22	30-35 mm Ø x 18 or 40 mm
ECRM 379-1D	(0.0018)	0.00190	0.0033	.	(0.0006)	(0.0027)	.	0.0021	.	(0.0091)	(0.00033)	38 or 45 mm Ø x 25 mm
NCS HS41753a	0.058	.	37 mm Ø x 35 mm
CT ISO124A	0.167	30-35 mm Ø x ~11 or ~19 mm
14X 93603A	0.0019	(0.0009)	~40 mm Ø x ~15 mm
SRM 1159	31 mm Ø x 19 mm
IARM 98B	<0.002	0.001	<0.0005	.	0.0040	0.0021	.	0.002	<0.05	(0.02)	<0.01	31 mm Ø x 2 mm
BS 160A	0.0011	0.0010	(0.0004)	.	0.0032	0.0022	<u>17025</u>	0.0024	Ta, W			

HIGH ALLOY STEEL XRF SET

Part Number:	BS HAS-12	RM except CRM as noted, available as set or individually											* Provisional Analysis				~7 mm Ø discs		
Number Grade	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Co	N	Nb	Sn	Ti	V	W	O
BS 189A AL6XN CRM	0.0147	0.639	0.019	(0.001)	0.30	0.184	23.8	20.4	6.04	0.0129	(0.0002)	0.100	0.198	(0.13)	0.0035	0.0065	0.054	0.037	0.0024
BS 179A Alloy 255	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	3.24	(0.009)	(0.001)	0.58	0.184	0.030	0.005	0.006	0.070	(0.2)	.
BS 183B * Greek Ascology	0.18	0.35	0.018	0.005	0.41	0.075	1.97	12.43	0.33	0.0008	0.001	0.030	0.044	0.009	0.004	0.002	0.17	3.42	<0.05
BS 186A Invar 36	0.040	0.72	0.008	0.0053	0.19	0.016	35.86	0.16	0.0032	(0.001)	.	0.028	0.0026	(<0.002)	(0.002)	(<0.003)	0.0012	(0.01)	.
BS 187A Carp. 20Cb3	0.022	0.52	0.017	0.0025	0.26	3.10	33.06	19.75	2.06	(0.009)	0.0022	0.32	0.0157	0.57	0.003	(0.002)	0.10	(0.02)	.
BS 188A A-286	0.050	0.139	0.015	0.0049	0.15	0.099	24.61	14.04	1.10	0.19	0.0065	0.18	0.0029	0.050	0.002	2.21	0.24	0.055	.
BS 190 Nitronic® 40	0.022	9.72	0.015	0.001	0.46	0.072	6.74	19.57	0.15	(0.004)	0.0005	0.044	0.255	(0.004)	0.003	0.002	0.11	0.015	0.0045
BS 180A Nitronic® 50	0.018	5.05	0.012	0.001	0.32	0.067	13.19	21.09	2.04	0.012	(0.0024)	0.039	0.334	0.20	(0.002)	(0.002)	0.20	0.02	0.003
BS 181A Nitronic® 60	0.071	8.16	0.019	0.001	4.03	0.18	8.15	16.52	0.21	0.022	0.0009	0.072	0.148	0.017	0.005	0.007	0.094	0.04	0.0010
BS 193 18Cr-12Mn	0.104	12.11	0.018	0.002	0.66	0.088	1.82	18.48	0.21	(0.003)	0.0007	0.028	0.37	0.014	0.004	0.003	0.107	(0.007)	.
BS 182 17Cr-15Mn	0.037	15.09	0.022	(0.003)	0.46	0.56	1.11	16.67	0.99	.	.	0.032	(0.40)	(0.005)	(0.003)	(0.003)	0.059	(0.01)	.
BS 191 16Cr-6Mn-4Si	0.098	5.71	0.024	0.023	3.66	0.33	5.34	16.33	0.36	(0.002)	(0.0006)	0.11	0.117	0.024	(0.006)	0.012	0.083	0.033	.

CRM

CAST IRON SETS

AVAILABLE IN SETS ONLY, as grouped

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Sn	Ti	V	Ce	La	Mg	N
30 mm Ø x 28 mm																	
NCS HS11712a-6	4.02	1.41	0.021	0.026	0.163	1.83	1.89	0.112	0.019	0.726	0.057	0.238	0.509	<0.0001	<0.0001	0.104	0.013
NCS HS11712a-7	3.94	1.38	0.085	0.0048	0.918	1.10	1.37	1.05	0.214	0.168	0.134	0.114	0.390	<0.0001	<0.0001	0.056	0.0063
NCS HS11712a-5	3.52	0.311	0.420	0.019	1.17	0.389	1.03	0.766	.	0.629	0.013	0.161	0.324	<0.0001	<0.0001	0.021	0.0047
NCS HS11712a-4	3.16	0.462	0.396	0.017	1.96	0.921	0.778	1.40	0.0073	0.428	0.024	0.065	0.166	<0.0001	<0.0001	0.025	0.0073
NCS HS11712a-2	2.22	0.301	0.043	0.058	2.44	0.458	0.341	2.13	0.060	0.087	0.044	0.065	0.055	0.0010	0.010	0.0085	0.024
NCS HS11712a-3	2.55	0.878	0.071	0.045	1.50	0.641	0.519	0.417	0.034	0.354	0.021	0.027	0.085	0.027	0.0061	0.024	0.024
NCS HS11712a-1	1.75	0.080	0.580	0.119	3.40	0.025	0.030	2.48	0.248	0.031	0.0031	0.038	0.021	<0.0001	<0.0001	0.0006	0.015
30 mm Ø x 30 mm																	
NCS HS19701-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	.	.	0.043	0.399	0.821
NCS HS19701-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	(0.112)	0.0018	0.105	0.506
NCS HS19701-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	(0.68)	0.0022	0.066	0.335
NCS HS19701-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	(0.031)	0.0017	0.030	0.158
NCS HS19701-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	.	.	0.009	0.043	0.071
NCS HS19701-2	2.99	0.329	0.033	0.038	0.937	.	0.194	0.080	.	.	0.024	0.216	0.044
NCS HS19701-1	2.46	0.072	0.011	0.019	0.099	.	0.183	0.511	.	.	0.005	0.0059	0.0090

RM GRAY IRON as cast (not chill cast) CONTAINS FREE GRAPHITE **OES regularly requires extension of preburn time to analyze correctly**

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	Sb	Sn	Ti	V	mm Ø x mm H
BS 20G	3.33	0.58	0.028	0.029	3.02	0.54	0.38	0.086	0.008	0.004	0.022	0.19	(<0.001)	0.12	0.012	0.018	47 x 19+
BS 20W	3.27	0.62	0.045	0.036	2.64	0.29	0.082	0.092	0.004	0.004	0.005	0.054	(<0.001)	0.086	0.015	0.007	47 x 13
BS 20R	3.25	0.62	0.047	0.034	2.72	0.35	0.096	0.094	0.005	0.004	0.006	0.053	(<0.001)	0.104	0.015	0.007	47 x 19+
BS 20E	3.24	0.80	0.042	0.044	2.29	0.23	0.156	0.088	0.006	(0.003)	0.006	0.042	(<0.002)	0.093	0.017	0.007	47 x 19+
BS 20P	3.22	0.63	0.032	0.044	2.62	0.067	0.143	0.079	0.008	(0.004)	0.018	0.033	(<0.001)	0.099	0.018	0.017	44 x 19+

DUCTILE / NODULAR IRON

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Ce	Co	Mg	Mo	Ti	V
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	.	.	.	0.083	0.0979	0.1069	0.0486
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	.	0.110	.	0.070	.	.	0.103
1	BS 285BI	3.45	0.73	0.047	0.0126	1.92	0.319	1.37	1.05	0.0169	.	0.0038	0.053	0.238	0.043	0.121
1	BS 285BH	3.43	0.732	0.0470	0.0128	1.93	0.321	1.38	1.05	0.0168	.	0.0034	0.052	0.238	0.0429	0.122
1	BS 286CI *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.052	0.26	0.052	0.15
1	BS 285BG	3.44	0.731	0.0469	0.0126	1.93	0.321	1.39	1.05	0.0165	.	0.0038	0.051	0.238	0.0427	0.122
1	BS 286CH *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.051	0.26	0.052	0.15
1	BS 285BF	3.43	0.732	0.0472	0.0127	1.93	0.320	1.386	1.047	0.0164	.	0.0033	0.050	0.238	0.0424	0.122
1	BS 286CG *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.050	0.26	0.052	0.15
1	BS 285BE	3.45	0.732	0.0474	0.0128	1.93	0.321	1.38	1.047	0.0162	.	(0.003)	0.049	0.238	0.0428	0.122
1	BS 286CF *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.049	0.26	0.052	0.15
1	BS 285BD	3.45	0.730	0.0471	0.0126	1.93	0.322	1.39	1.047	0.0160	.	0.0036	0.048	0.238	0.0427	0.121
1	BS 286CE *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.048	0.26	0.052	0.15
1	BS 285BC	3.42	0.724	0.047	0.0124	1.93	0.320	1.38	1.05	0.0157	.	(0.003)	0.047	0.237	0.043	0.121
1	BS 286CD *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.047	0.26	0.052	0.15
1	BS 286CC *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.046	0.26	0.052	0.15
1	BS 291FI *	3.36	0.50	0.023	0.017	2.35	0.21	0.097	0.021	0.039	<0.5	0.004	0.043	0.035	0.026	0.017
1	BS 286CB *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.043	0.26	0.052	0.15
1	BS 291FH *	3.36	0.50	0.023	0.017	2.35	0.21	0.097	0.021	0.039	<0.5	0.004	0.042	0.035	0.026	0.017
1	BS 286CA *	3.27	0.72	0.21	0.014	2.02	0.36	1.42	0.35	0.013	<0.5	0.027	0.042	0.26	0.052	0.15
1	BS 291FG *	3.36	0.50	0.023	0.017	2.35	0.21	0.097	0.021	0.039	.	0.004	0.041	0.035	0.026	0.017
1	SCRM 670/21	3.69	0.332	0.023	0.015	2.27	0.90	0.89	0.49	.	0.0108	.	0.040	0.011	0.109	0.023
1	BS 291FF *	3.36	0.50	0.023	0.017	2.35	0.21	0.097	0.021	0.039	.	0.004	0.040	0.035	0.026	0.017
1	BS 291FE *	3.36	0.50	0.023	0.017	2.35	0.21	0.097	0.021	0.039	.	0.004	0.039	0.035	0.026	0.017
1	BS 291FD *	3.36	0.50	0.023	0.017	2.35	0.21	0.097	0.021	0.039	.	0.004	0.038	0.035	0.026	0.017
1	BS 291FC *	3.36	0.50	0.023	0.017	2.35	0.21	0.097	0.021	0.039	.	0.004	0.037	0.035	0.026	0.017
1	BS 291FB *	3.36	0.50	0.023	0.017	2.35	0.21	0.097	0.021	0.039	.	0.004	0.036	0.035	0.026	0.017
2	BAS SIMO 1/5	2.72	0.330	0.031	0.014	3.94	0.005	0.035	0.889	0.029	.	0.004	0.034	0.738	0.008	0.004
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	(0.007)	0.016	.	0.032	0.86	(0.04)	0.019
1	BAS SIMO 2/2	2.14	0.434	0.025	0.007	4.75	0.010	0.0189	0.856	0.013	0.006	0.0029	0.026	0.484	0.005	0.009
1	SCRM 669/14	2.955	0.526	.	.	2.201	0.194	0.473	0.214	.	0.0415	.	0.022	0.0550	0.0499	0.532
1	SCRM 668/13	3.724	0.712	.	.	1.400	0.751	0.097	0.962	.	0.0245	.	0.011	0.0193	0.091	0.193
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	(<0.01)	0.0046	(0.05)	0.006	0.019	0.050	0.083

Number	As	B	Ca	Fe	La	Nb	Pb	Sn	W	Zr	Units
SCRM 666/12	48 mm x 42 mm x 12 mm
SCRM 667/13	48 mm x 42 mm x 12 mm
BS 285BI	0.0007	0.0083	0.0009	90.6	Sb:(0.2)	0.0041	(0.0008)	0.0015	0.061	0.0053	-35 mm Ø x 30 mm 17025
BS 285BH	0.0007	0.0084	0.0010	90.54	Sb:(0.2)	0.0040	0.0009	0.0017	0.0612	0.0055	-35 mm Ø x 30 mm 17025
BS 286CI *	0.004	0.008	0.001	[91.0]	<0.05	0.005	<0.05	0.011	0.002	0.006	35 mm Ø x 30 mm
BS 285BG	0.0008	0.0084	0.0010	90.54	Sb:(0.2)	0.0039	0.0009	0.0017	0.0611	0.0055	-35 mm Ø x 30 mm 17025
BS 286CH *	0.004	0.008	0.001	[91.0]	<0.05	0.005	<0.05	0.011	0.002	0.006	35 mm Ø x 30 mm
BS 285BF	0.0009	0.0084	0.0010	90.54	Sb:(0.2)	0.0039	0.0008	0.0018	0.0608	0.0054	-35 mm Ø x 30 mm 17025
BS 286CG *	0.004	0.008	0.001	[91.0]	<0.05	0.005	<0.05	0.011	0.002	0.006	35 mm Ø x 30 mm
BS 285BE	0.0010	0.0084	0.0009	90.53	Sb:(0.2)	0.0038	0.0007	0.0016	0.0607	0.0054	-35 mm Ø x 30 mm 17025
BS 286CF *	0.004	0.008	0.001	[91.0]	<0.05	0.005	<0.05	0.011	0.002	0.006	35 mm Ø x 30 mm
BS 285BD	0.0010	0.0084	0.0009	90.54	Sb:(0.2)	0.0039	0.0007	0.0017	0.0608	0.0055	-35 mm Ø x 30 mm 17025
BS 286CE *	0.004	0.008	0.001	[91.0]	<0.05	0.005	<0.05	0.011	0.002	0.006	35 mm Ø x 30 mm
BS 285BC	0.0011	0.0084	0.0008	90.6	Sb:(0.2)	0.0039	(0.0006)	0.0018	0.061	0.0054	-35 mm Ø x 30 mm 17025
BS 286CD *	0.004	0.008	0.001	[91.0]	<0.05	0.005	<0.05	0.011	0.002	0.006	35 mm Ø x 30 mm
BS 286CC *	0.004	0.008	0.001	[91.0]	<0.05	0.005	<0.05	0.011	0.002	0.006	35 mm Ø x 30 mm
BS 291FI *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
BS 286CB *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
BS 291FH *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
BS 286CA *	0.004	0.008	0.001	[91.0]	<0.05	0.005	<0.05	0.011	0.002	0.006	35 mm Ø x 30 mm
BS 291FG *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
SCRM 670/21	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	48 mm x 42 mm x 12 mm
BS 291FF *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
BS 291FE *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
BS 291FD *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
BS 291FC *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
BS 291FB *	<0.05	0.014	<0.005	[93.2]	.	<0.05	<0.005	0.057	0.041	<0.05	-35 mm Ø x -25 mm
BAS SIMO 1/5	(0.001)	0.052	.	.	48 mm x 42 mm x 12 mm
SRM C1137a	32 mm Ø x 19 mm
BAS SIMO 2/2	0.039	0.038	.	.	48 mm x 42 mm x 12 mm
SCRM 669/14	48 mm x 42 mm x 12 mm
SCRM 668/13	48 mm x 42 mm x 12 mm
SRM C2424	.	(0.002)	.								

CAST IRON WITH MAGNESIUM - continued on the next page

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 20034 17b	4.38	0.501	0.089	0.0040	0.178	0.111	2.34	0.200	0.009	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17a	4.30	0.494	0.115	0.0034	0.170	0.082	2.38	0.200	0.007	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17c	4.08	0.503	0.104	0.0033	0.150	0.037	2.32	0.178	0.007	.	(0.002)	(0.003)	0.043	0.030	0.015	0.076
1	Y 2863-11	4.03	0.61	0.613	0.026	0.79	0.96	0.46	1.65	0.0075	0.94	0.29	0.079
2	CZ SPL17 43A	3.98	1.322	0.190	0.008	1.63	0.385	0.411	0.032	(0.04)	.	0.024	0.017	0.045	0.152	0.065	0.152
2	CZ SPL17 42A	3.94	0.764	0.294	0.0040	1.94	0.199	0.492	0.145	(0.06)	.	0.087	0.039	0.010	0.021	0.126	0.093
1	Y 451045	3.90	0.12	0.023	0.0027	2.29	0.022	0.45	0.028	0.033	0.0030	0.016	0.0014
1	CZ 02033 2g	3.78	0.096	0.125	0.009	1.10	0.88	0.650	0.027	0.036	(0.004)	0.019	0.013	0.012	(0.002)	0.029	0.017
1	Y 2863-12	3.77	0.158	0.053	0.057	0.150	0.55	0.192	2.31	0.0024	0.44	0.030	0.229
1	CZ 02033 2f	3.77	0.091	0.159	0.009	1.23	0.89	0.658	0.022	0.053	.	0.024	0.018	(0.003)	(0.002)	0.021	0.010
1	Y 4510251B-16	3.75	0.39	0.034	0.012	1.69	0.423	0.60	0.52	0.053	.	0.061	0.034	.	0.203	0.036	0.198
1	Y 451047	3.73	2.35	0.51	0.0036	2.02	1.98	3.57	1.58	0.060	0.050	0.40	0.018
1	SCRM 668/13	3.724	0.712	.	.	1.400	0.751	0.097	0.962	0.0116	.	.	0.0245	.	0.0193	0.091	0.193
1	SCRM 670/21	3.69	0.332	.	0.015	2.27	0.90	0.89	0.49	0.040	.	.	0.0108	.	0.011	0.109	0.023
1	CZ 02033 3c	3.68	0.333	0.026	0.007	2.15	0.421	0.040	0.100	0.006	(0.005)	0.024	0.013	0.026	0.490	0.021	0.016
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	0.0838	0.0979	0.1069	0.0486
2	CZ SPL17 31A	3.54	0.041	0.025	0.006	2.10	0.005	0.538	0.019	0.070	.	0.005	(0.004)	0.022	0.004	0.007	0.008
1	CZ 20034 15b	3.52	0.048	0.054	0.0031	1.66	1.322	0.681	0.067	0.037	.	0.029	0.021	0.027	0.004	0.025	0.013
2	CZ SPL17 34A	3.48	0.980	0.105	0.008	2.29	0.230	0.493	0.102	0.026	.	0.010	0.008	0.025	0.072	0.044	0.073
1	11X SG2A	3.48	0.297	0.0353	0.0075	3.03	0.0245	0.0263	0.0304	0.055	.	0.0238	.	.	.	0.0146	.
1	Y 451042	3.47	0.71	0.043	0.012	2.11	0.35	1.39	1.02	0.023	0.22	0.029	0.15
1	CZ 02033 2e	3.47	0.168	0.106	0.010	1.03	0.89	0.620	0.043	0.038	(0.006)	0.025	0.017	0.005	(0.002)	0.039	0.026
1	CZ 20034 15c	3.47	0.060	0.054	0.0028	1.68	1.123	0.728	0.078	0.040	.	0.010	0.030	0.026	(0.002)	0.036	0.019
2	CZ SPL17 32A	3.39	0.288	0.037	0.007	2.74	0.306	0.015	0.060	0.024	.	0.029	(0.004)	(0.002)	0.116	0.044	0.005
1	CZ 02033 3b	3.38	0.260	0.012	0.012	1.74	0.400	0.049	0.235	0.012	.	0.026	0.006	0.012	0.456	0.023	0.009
2	CZ SPL17 40A	3.38	0.042	0.021	0.0035	1.98	0.010	0.045	0.031	0.007	.	0.096	0.012	0.027	0.005	0.015	0.014
1	VS ChG 28	3.29	0.414	0.025	0.015	2.22	1.29	0.166	0.127	0.010	.	0.015	.	.	0.0024	0.0041	0.0020
1	CZ 20034 14b	3.26	0.240	0.0115	0.0096	2.34	0.640	0.020	0.042	0.015	.	0.012	0.012	0.005	0.635	0.021	0.012
1	CZ 02033 3d	3.24	0.317	0.008	0.006	2.12	0.396	0.025	0.236	0.016	.	0.055	0.006	0.014	0.453	0.016	0.072
1	CZ 02033 1f	3.23	0.693	0.043	0.005	2.68	0.018	0.373	0.035	0.070	(0.007)	0.073	0.036	0.024	0.182	0.041	0.014

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 02033 1g	3.22	0.701	0.036	0.007	2.53	0.027	0.357	0.044	0.050	.	0.062	0.023	0.010	0.185	0.054	0.019
1	CZ 20034 13c	3.15	0.704	0.0261	0.0044	2.23	0.089	1.299	0.124	0.064	.	0.022	0.011	0.024	0.360	0.015	0.043
1	CZ 02033 1e	3.15	0.718	0.037	0.006	2.72	0.012	0.367	0.037	0.044	.	0.058	0.027	0.022	0.185	0.046	0.015
1	CZ 20034 14c	3.14	0.275	0.0162	0.0081	2.49	0.585	0.030	0.045	0.017	.	0.007	0.019	0.009	0.646	0.018	0.013
1	CZ 20034 13a	3.13	0.691	0.0244	0.0046	2.19	0.021	1.266	0.122	0.053	.	0.017	0.011	0.024	0.364	0.014	0.048
1	CZ 20034 13b	3.12	0.692	0.0243	0.0041	2.12	0.021	1.313	0.125	0.054	.	0.019	0.011	0.024	0.364	0.012	0.048
1	VS ChG 24	3.05	0.245	0.260	0.0048	2.50	0.100	0.87	0.031	0.015	.	0.007	.	.	0.031	0.060	0.0067
1	Y 2863-9	3.04	1.43	0.049	0.015	1.53	0.269	1.59	0.72	0.043	1.38	0.212	0.41
1	VS ChM5/1	3.04	0.311	0.056	0.016	1.37	.	.	.	0.045	.	0.013
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	0.070	.	.	0.110	.	.	.	0.103
1	BS CC-11A	3.07	1.23	0.020	0.011	1.90	0.007	0.046	0.048	0.014	0.026	0.0055	0.018	(0.007)	0.0063	0.0091	0.0066
1	BS CC-11B	2.97	1.17	0.020	0.008	1.94	0.0210	0.173	0.189	0.025	0.019	0.028	0.045	(0.022)	0.018	0.031	0.0179
1	VS ChM6/1	3.03	0.54	0.055	0.0074	2.75	.	.	.	0.072	.	0.022
1	VS ChM8/1	3.02	0.83	0.055	0.0034	3.39	.	.	.	0.105	.	0.041
2	CZ SPL17 36A	3.02	0.057	0.026	0.010	2.13	0.007	0.011	0.014	0.012	.	(0.003)	0.0007	(0.004)	0.004	0.021	0.021
1	VS ChM13	2.96	1.05	0.043	0.009	2.98	0.062	1.65	0.273	0.09	.	0.065	.	.	.	0.018	0.0096
1	SCRM 669/14	2.955	0.526	.	.	2.201	0.194	0.473	0.214	0.0224	.	.	0.0415	.	0.0550	0.0499	0.532
1	VS ChG 26	(2.9)	0.126	0.123	0.0041	2.98	0.014	1.52	0.050	0.044	.	0.038	.	.	0.075	0.0026	0.040
1	VS ChM10	2.89	0.43	0.067	0.017	1.13	0.082	0.85	0.067	0.024	.	0.005	.	.	.	0.028	0.079
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	0.032	.	(0.007)	0.016	.	0.86	(0.04)	0.019
2	CZ SPL17 33A	2.75	0.710	0.060	0.007	3.10	0.730	0.389	0.239	0.021	.	0.054	0.026	0.015	0.220	0.130	0.356
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	0.006	.	(<0.01)	0.0046	(0.05)	0.019	0.050	0.083
1	VS ChM9	2.61	1.28	0.075	0.021	1.59	0.095	0.38	0.083	0.011	.	0.016	.	.	.	0.027	0.068
1	VS ChM11	2.26	0.77	0.032	0.011	2.32	0.067	1.75	0.122	0.066	.	0.035	.	.	.	0.014	0.0044
1	Y 2863-7	1.98	3.42	0.067	0.0061	3.10	0.089	4.47	0.150	0.050	.	.	0.019	.	0.052	0.060	0.87

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
		BS: 28-34 mm Ø x 17-35 mm				CKD 24x: 37 mm x 37 mm x -15-20 mm				SCRM: 48 mm x 42 mm x 12 mm				VS: ~40 mm Ø x ~40 mm			
						CZ: 40 mm Ø x 18 mm				SRM: 32 mm Ø x 19 mm				Y: 30 mm Ø x 30 mm			

CAST IRON WITH MAGNESIUM - continued from the previous page

sizes shown below

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other	
CZ 20034 17b	0.008	(0.0002)	(0.001)	(0.002)	.	.	(0.002)	0.004	.	.	
CZ 20034 17a	0.007	(0.0002)	(0.001)	(0.002)	.	.	(0.002)	0.004	.	.	
CZ 20034 17c	0.0005	(0.0006)	(0.002)	(0.002)	.	.	(0.002)	0.004	.	.	
Y 2863-11	(0.022)	0.053	0.33	(0.0057)	(0.174)	.	(0.108)	0.010	.	.	
CZ SPL17 43A	.	0.0014	(0.002)	.	.	.	0.008	0.014	(0.004)	.	0.067	0.038	Zn:0.013	.	
CZ SPL17 42A	.	0.0036	(0.002)	.	.	.	0.045	0.020	0.015	.	0.027	0.020	Zn:0.013	.	
Y 451045	
CZ 02033 2g	.	0.0023	0.006	0.008	0.029	.	0.015	(0.004)	.	Zn: 0.020	
Y 2863-12	(0.0097)	0.0078	0.21	(0.056)	(0.471)	.	(0.307)	0.13	.	.	
CZ 02033 2f	.	0.0020	(0.002)	0.005	0.028	.	0.014	(0.003)	(0.005)	Zn: 0.018	
Y 4510251B-16	.	0.0044	.	.	.	0.016	0.030	.	.	.	
Y 451047	.	0.31	0.012	
SCRM 668/13	
SCRM 670/21	
CZ 02033 3c	(0.007)	0.0044	(0.002)	0.005	.	.	0.009	(0.003)	.	.	
SCRM 666/12	
CZ SPL17 31A	.	(0.0004)	(0.003)	(0.005)	.	.	
CZ 20034 15b	(0.003)	0.0033	0.010	0.058	.	0.005	0.007	.	.	
CZ SPL17 34A	.	0.0076	(0.005)	.	.	.	0.014	(0.006)	0.007	.	0.051	0.016	Zn:0.007	.	
11X SG2A	0.0022	Zn:0.040	-50Ø x -15mm	
Y 451042	
CZ 02033 2e	.	0.0024	0.005	(0.004)	0.028	.	0.015	0.008	.	Zn: 0.025	
CZ 20034 15c	(0.003)	0.0057	0.008	0.056	.	0.006	0.004	.	.	
CZ SPL17 32A	.	(0.0005)	(0.007)	0.022	0.023	.	(0.012)	(0.008)	Zn:0.011	.	
CZ 02033 3b	.	0.0042	0.001	0.009	.	.	0.019	.	.	.	
CZ SPL17 40A	.	0.0008	(0.004)	.	Zn:(0.002)	.	
VS ChG 28	0.015	.	0.0017	.	.	.	
CZ 20034 14b	0.034	0.0100	0.007	(0.005)	0.016	.	0.028	(0.005)	0.014	Zn: 0.009	
CZ 02033 3d	(0.018)	0.0071	(0.002)	0.005	0.007	.	0.009	.	.	.	
CZ 02033 1f	.	0.0043	(0.001)	0.009	.	.	0.030	0.022	(0.008)	.	
Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other	
CZ 02033 1g	.	0.0034	0.005	0.016	.	.	0.028	0.015	(0.004)	.	
CZ 20034 13c	(0.002)	(0.002)	.	0.014	(0.003)	(0.02)	.	
CZ 02033 1e	.	0.0036	(0.002)	0.007	.	.	0.032	0.021	(0.007)	Zn: 0.009	
CZ 20034 14c	0.035	0.0123	0.020	.	0.025	(0.003)	0.013	Zn: 0.010	
CZ 20034 13a	(0.002)	(0.002)	.	0.014	(0.003)	0.029	.	
CZ 20034 13b	(0.002)	(0.002)	.	0.014	(0.003)	0.023	.	
VS ChG 24	0.009	.	0.077	.	.	.	
Y 2863-9	(0.041)	0.153	0.11	(0.093)	(0.116)	.	(0.124)	.	.	.	
VS ChM5/1	
SCRM 667/13	
BS CC-11A	0.0018	0.0008	(0.005)	(0.0009)	93.6	(0.004)	(0.007)	(0.002)	(0.01)	Zn:0.0032	(0.004)	(0.017)	(0.0025)	17025	
BS CC-11B	0.0074	0.0033	(0.016)	(0.002)	93.2	(0.008)	0.043	0.014	0.026	Zn:0.008	0.021	0.028	0.0165	17025	
VS ChM6/1	
VS ChM8/1	
CZ SPL17 36A	.	0.022	(0.007)	0.016	.	.	(0.002)	.	Zn:(0.002)	.	
VS ChM13	
SCRM 669/14	
VS ChG 26	0.031	.	.	.	
VS ChM10	
SRM C1137a	
CZ SPL17 33A	.	0.0064	(0.002)	.	.	.	0.032	0.010	0.019	.	0.039	0.079	Zn:0.009	.	
SRM C2424	.	(0.002)	.	.	.	0.0011	
VS ChM9	
VS ChM11	
Y 2863-7	(0.021)	0.100	0.041	(0.0025)	(0.010)	.	(0.0073)	.	.	.	
Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other	
BS: 28-35 mm Ø x 17-35 mm				CZ: 40 mm Ø x 18 mm				SRM: 32 mm Ø x 19 mm				VS ChM: ~39 mm Ø x ~39 mm			
				SCRM: 48 mm x 42 mm x 12 mm				Y: 30 mm Ø x 18-30 mm				VS ChG: ~34 mm x ~35 mm X ~22 mm			

RM CAST IRON WITH YOUR CHOICE OF MAGNESIUM LEVELS each unit: 2 pcs mushroom 43 mm Ø x 5 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Al	Ce	Co	Sn	Ti	V	Zn	Other
CTIF 6134	3.70	0.25	0.030	<0.01	1.60	0.020	2.00	0.040	*	.	<0.03
CTIF 8532	3.7	0.288	0.05	.	2.6	0.0443	0.888	0.04	*	.	<0.025	.	0.0303	0.02	0.07	.	.
CTIF 6135	3.6	0.38	0.0130	(0.003)	0.9	0.0219	1.98	0.04	*	(0.006)	.	0.037	.	0.007	0.0155	.	.
CTIF 4500	3.38	0.60	0.059	(0.002)	1.97	.	1.45	0.014	*	0.033	0.023	0.065
CTIF 5781	3.35	0.26	0.030	(0.0025)	2.50	0.0061	0.83	0.040	*	.	.	(0.004)	.	0.0208	0.0150	.	.
CTIF 4497	3.12	0.605	0.043	(-0.002)	2.66	0.048	1.90	0.040	*	.	.	.	0.094	0.031	0.44	.	.
CTIF 7160	3.1	0.57	0.05	(0.001)	2.4	0.08	1.0	(0.1)	*	(0.02)	0.02	0.09	.	0.013	0.018	.	As: 0.009
CTIF 5037	3.04	0.76	0.043	(0.0025)	3.40	.	0.64	0.014	*	0.029	.	.	.
CTIF 3601B	3.0	0.35	0.037	(0.005)	2.1	0.019	1.08	0.029	*	.	<0.01	.	.	0.016	(0.005)	<0.05	Pb:(<0.002)
CTIF 8018	3.0	0.7	0.07	(0.0015)	3.0	0.08	0.127	0.09	*	0.02	(<0.02)	.	0.07	0.06	0.39	.	Sb:(0.01)
CTIF 6736	2.8	0.65	0.012	(0.002)	1.6	0.0258	1.7	0.03	*	0.008	(0.03)	.	.
CTIF 5783	2.55	0.2	0.0266	(0.003)	2.3	0.110	1.23	0.05	*	.	.	0.0074	.	0.015	0.0127	.	As: 0.0016

Magnesium level available in the below samples. X = available

For Mg Range	Order Suffix	3601B	4497	4500	5037	5781	5783	6134	6135	6736	7160	8018	8532
<0.005	<0.005	X	.	.	.	X	X	X	X
0.005 - 0.009	0.005	X	.	.	X	X	X	.	.	X	.	X	X
0.010 - 0.014	0.01	.	.	.	X	X	X	.	.	X	X	X	X
0.015 - 0.024	0.02	X	.	.	X	X	X	.	X	X	X	X	X
0.025 - 0.034	0.03	.	.	.	X	.	X	.	X	X	X	X	X
0.035 - 0.044	0.04	.	.	.	X	.	X	.	X	X	X	X	X
0.045 - 0.054	0.05	.	.	.	X	.	X	.	X	X	X	X	X
0.055 - 0.064	0.06	.	X	X	.	.	X	.	X	X	X	X	X
0.065 - 0.074	0.07	.	X	X	.	.	X	.	X	X	X	X	X
0.075 - 0.084	0.08	.	X	X	.	.	X	X	X	X	X	X	X
0.085 - 0.094	0.09	.	X	X	.	.	X	X	X	X	X	X	X
0.095 - 0.104	0.10	X	X	X	X	X	X	X
0.105 - 0.114	0.11	X	X	X	X	X	X
0.115 - 0.124	0.12	X	X	X	X	X	X
0.125 - 0.134	0.13	X	X	X	X	X	X
0.135 - 0.144	0.14	X	X	X	X	X	X
0.145 - 0.154	0.15	X	.	.
0.155 - 0.164	0.16	X	.	.
0.165 - 0.174	0.17	X	.	.
0.175 - 0.184	0.18	X	.	.

The above cast iron samples can be ordered with your choice of Magnesium. Examples:
 to order CTIF 6736 with Mg 0.035 - 0.044 then order as part number CTIF 6736 0.04
 to order CTIF 8018 with 0.08 % Mg, order as part number CTIF 8018 0.08

CRM WHITE IRON analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	Nb	Ti	V
BS WI-2	3.61	0.80	0.22	0.056	0.52	0.0124	0.254	0.229	0.0118	0.219	0.128	0.089	0.215
SRM CII45	2.92	0.187	0.215	0.191	0.271	0.46	0.62	0.63	0.058	0.48	.	0.012	0.112
VS ChG 8/6	(2.7)	1.51	0.040	0.013	3.93	.	.	(0.2)	(0.3)
VS ChG 10/6	(2.7)	0.86	0.103	0.0072	2.86	.	.	(0.2)	(0.3)
VS ChG 11/6	(2.7)	0.312	0.23	0.039	1.79	.	.	(0.2)	(0.3)
VS ChG 9/6	(2.7)	0.155	0.38	0.071	0.80	.	.	(0.2)	(0.3)
BS WI-1	1.75	0.24	0.051	0.114	1.90	0.027	0.053	0.048	0.0074	0.0103	0.027	0.020	0.008

17025

17025

Number	Al	As	B	Bi	Ca	Fe	Mg	Pb	Sb	Sn	W	Zr	Units
BS WI-2	0.0192	0.0016	0.0008	.	(0.00013)	[93.6]	(0.0002)	0.013	0.023	0.0042	0.023	0.0045	~35 mm Ø x ~30 mm
SRM CII45	(0.04)	(0.03)	(0.02)	(<0.01)	.	.	.	0.0012	(0.04)	(0.10)	.	(0.002)	32 mm Ø x 19 mm
VS ChG 8/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
VS ChG 10/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
VS ChG 11/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
VS ChG 9/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
BS WI-1	0.075	0.0067	0.0032	.	0.0005	[95.5]	0.0009	0.115	.	0.0081	0.185	0.0034	~35 mm Ø x ~30 mm

CAST IRON WITH C > 2.75%

CONTINUED ON THE NEXT PAGE

= Class, 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
2	CZ SPL17 35A	4.55	0.096	0.024	0.011	0.078	0.004	0.024	0.022	(0.002)	0.023	0.003	.	(0.002)	(0.002)	0.009	.
1	CZ 02033 4e	4.45	0.034	0.023	0.006	0.090	0.005	0.049	0.030	(0.003)	0.033	0.002	.	(0.001)	0.011	0.015	.
1	SCRM 672/1	4.322	0.474	0.198	0.036	0.143	0.100	0.083	0.0186	0.0102	0.139	0.117	.	0.0047	0.0373	0.0988	.
1	CZ 02033 4d	4.19	0.112	0.050	0.041	0.259	0.084	0.063	0.056	0.007	(0.003)	0.024	.	(0.001)	0.009	0.012	0.009
1	SCRM 659/9	4.174	1.010	0.0215	0.0372	1.361
1	Y 2582-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	0.399	0.821	.
1	DSZU CH04	4.01	1.77	0.074	0.018	0.73	0.55	0.273	0.100	0.014	(0.05)	(0.004)	(0.005)	(0.002)	0.025	(0.004)	.
1	DSZU CH05	3.99	2.23	0.119	0.039	0.46	0.61	0.85	1.63	(0.002)	(0.07)	0.109	(0.3)	(0.01)	0.070	0.200	.
1	CZ 02033 4b	3.95	0.145	0.041	0.046	0.252	0.062	0.023	0.049	0.003	0.005	0.005	.	0.001	0.006	0.004	0.008
1	Y 2582-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	.	(0.112)	.	.	0.105	0.506	.
1	VS CHG 2/9	3.93	0.456	0.513	0.078	0.387	0.082	.	0.060	0.080	0.049	.
1	DSZU CH06	3.88	0.85	0.050	0.050	0.28	1.03	1.23	(2.8)	0.025	(0.07)	0.29	(0.05)	(0.03)	0.33	0.205	.
1	CZ 20034 16c	3.87	1.311	0.173	0.0243	0.95	0.345	0.376	0.332	0.004	0.006	0.195	.	0.125	0.057	0.027	0.017
1	CZ 20034 16a	3.80	1.292	0.171	0.0266	1.00	0.332	0.390	0.374	0.007	0.010	0.203	.	0.125	0.0763	0.021	0.019
1	11X C6W	3.80	0.967	0.088	0.064	0.81	0.952	0.072	0.396	0.021	0.046	1.32	0.010	0.030	0.195	0.045	0.0045
1	CZ 20034 16b	3.78	1.327	0.170	0.0236	1.00	0.332	0.388	0.378	0.007	0.010	0.202	.	0.121	0.070	0.029	0.020
1	VS CHG 32	3.74	1.90	0.061	0.018	0.60	0.171	.	0.031	.	.	0.113	.	0.060	0.040	0.294	.
1	SCRM 674/1	3.71	1.437	0.0180	0.078	0.484	.	0.161	0.0296	0.0061	0.0066	0.0497	.	0.0164	0.0131	0.0125	.
1	Y 2582-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	.	(0.31)	.	0.030	0.158	.	.
2	CZ SPL17 39A	3.70	0.812	0.160	0.045	1.90	0.298	0.032	0.488	0.008	(0.002)	0.203	.	(0.003)	(0.074)	0.232	0.035
1	Y 451043	3.69	0.49	0.063	0.049	1.50	0.34	0.23	0.47	.	.	0.22	.	.	.	0.11	.
1	11X HPC5A	3.68	1.028	0.246	0.223	1.175	.	.	1.42
1	Y 2582-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	.	(0.68)	.	.	0.066	0.335	.
1	VS CHG 1/9	3.61	1.12	0.184	0.038	1.13	0.041	.	0.017	0.014	0.006	.
1	CZ 02033 7b	3.61	0.304	0.021	0.020	1.82	0.036	1.28	0.536	0.022	0.050	0.96	.	.	0.015	0.007	.
1	CZ 02033 7c	3.55	0.389	0.028	0.026	1.73	0.016	1.26	0.542	0.040	0.048	0.966	.	(0.004)	0.026	0.067	.
1	DSZU CH03	3.54	0.40	0.023	0.034	0.57	0.194	0.187	0.612	0.035	(0.05)	(0.019)	(0.010)	(0.004)	0.059	0.009	.
1	VS CHG 3/9	3.54	0.387	0.037	0.053	0.516	0.123	.	0.100	0.125	0.096	.
1	VS CHG 27	3.53	1.21	0.044	0.029	1.82	0.348	0.022	0.162	0.008	.	0.147	.	0.115	0.056	0.160	.
1	SCRM 660/10	3.522	0.398	0.143	0.1089	1.719
1	VS CHG 5/9	3.51	0.60	0.104	0.036	0.84	0.037	.	0.307	(0.1)	0.441	.
1	11X HPC4Q	3.48	1.19	1.63	0.102	1.70	0.078	2.03	0.788	.	.	0.101	.	.	.	0.029	.
1	Y 2863-5	3.47	0.78	0.564	0.070	0.89	0.365	0.62	1.53	.	.	0.67	.	.	0.133	0.129	.
1	11X C3AD	3.45	0.896	0.539	0.180	1.06	0.351	4.34	1.669	0.0104	0.240	0.235	0.021	0.166	0.127	0.605	0.007
2	CZ SPL17 41A	3.41	0.512	0.199	0.068	1.92	0.151	0.104	0.125	(0.003)	0.031	0.041	.	0.066	0.048	0.011	(0.001)
1	CZ 02033 8c	3.41	0.408	0.168	0.058	1.93	0.158	0.102	0.125	0.004	0.030	0.041	.	0.067	0.022	0.015	.
1	VS CHL1/1	3.39	0.53	0.048	0.029	1.32	0.344	0.410	0.264	.	0.017	0.036	.	.	0.061	0.073	.
2	CZ SPL17 38A	3.39	0.401	0.067	0.036	2.37	0.510	0.306	0.141	0.034	0.021	0.101	0.008	0.032	0.012	0.061	0.028
1	11X C10D	3.38	0.754	0.104	0.086	1.89	0.643	0.873	0.429	0.024	0.059	0.288	.	0.035	0.0474	0.1048	.
1	VS CHG 35	3.34	1.23	0.102	0.021	0.617	0.090	2.15	0.233	.	.	0.027	.	.	0.022	0.043	.
1	KUT 120	3.34	0.59	0.059	0.18	1.84
1	NCS HS11783	3.33	0.756	0.083	0.090	1.73	0.666	0.304	0.386	.	.	0.238	.	0.066	0.057	0.174	.
1	Y 2863-3	3.32	1.27	0.115	0.049	2.27	0.62	2.01	0.49	.	.	0.313	.	.	0.176	0.45	.
1	KUT 121	3.32	0.61	0.135	0.17	(1.86)
1	KUT 205	3.32	0.80	0.025	(0.010)	1.88	0.81	0.61	0.64	.	.	1.79	.	(0.035)	.	.	.
1	KUT 206	3.32	0.75	0.027	(0.010)	1.84	1.01	0.21	0.12	.	.	2.14	.	(0.107)	.	.	.
1	KUT 122	3.31	0.61	0.22	0.20	1.72
1	KUT 123	3.30	0.69	0.31	0.074	(1.87)
1	NCS HS11784	3.30	0.528	0.78	0.031	2.68	0.015	0.024	0.812	(0.0012)	.	0.142	(0.0012)	0.0005	0.084	0.020	.
1	Y 2582-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	0.043	0.071	.
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	11X HPC1H	3.29	0.620	0.808	0.0035	3.27	.	.	1.056	.	.	0.060
1	SCRM 665/4	3.25	0.24	1.09	0.053	1.66	.	.	(1)
1	11X C9D	3.24	1.886	0.069	0.0260	1.462	0.581	2.79	1.206	0.051	0.1301	0.155	0.0766	0.040	(0.062)	0.359	0.009
1	VS CHG 4/9	3.24	1.42	0.030	0.024	0.455	0.199	0.024	0.155	0.10	0.169	.
1	11X HPC3K	3.24	1.00	2.52	0.078	1.37	0.132	1.52	1.19	.	.	0.172	.	.	.	0.042	.
2	BAS NCRM3	3.24	0.67	0.125	0.090	0.29	1.21	3.64	3.95	.	.	0.78	.	.	.	0.02	.
1	NCS HS11782	3.21	1.09	0.088	0.035	1.64	0.042	0.014	0.061	.	.	0.0048	.	.	0.027	0.0079	.
1	KUT 125	3.20	0.73	0.70	0.019	(1.87)
1	VS CHG 31	3.19	0.97	0.047	0.043	1.60	0.281	.	0.156	.	.	0.0069	.	0.013	0.0063	0.0035	.
1	NCS HS11785	3.19	0.482	0.79	0.030	2.52	0.021	0.031	0.817	(0.0030)	.	0.139	(0.0009)	0.0010	0.076	0.018	.
1	DSZU CH02	3.18	1.09	0.007	0.0116	1.35	0.038	0.658	0.59	0.026	(0.06)	0.224	(0.4)	(0.014)	0.161	(0.005)	.
1	11X C2V	3.17	1.23	0.256	0.077	1.180	0.191	1.803	1.126	0.104	0.116	0.116	0.0160	0.0627	0.0870	0.328	0.0115
1	VS CHM 12	3.17	1.00	0.030	0.007	3.10	0.062	1.65	0.039	0.050	0.013	0.0027	.
1	SCRM 671/1	3.165	0.811	0.108	0.0503	0.868	.	0.0627	0.0609	0.030	0.098	0.0259	.	0.0103	0.0407	0.0122	.
1	KUT 126	3.16	0.81	1.41	0.016	1.90
1	KUT 202	3.16	0.81	0.024	(0.010)	1.77	0.24	2.07	2.36	.	.	0.44	.	(0.21)	.	.	.
1	SCRM 657/9	3.157	0.112	0.101	0.0401	3.209
1	KUT 204	3.15	0.80	0.023	(0.009)	1.79	0.64	1.09	1.22	.	.	1.38	.	(0.215)	.	.	.
1	KUT 127	3.14	0.79	1.55	0.014	1.81
1	CZ 02033 6c	3.11	1.25	0.097	0.019	3.25	0.273	0.021	1.33	0.024	0.005	0.006	.	0.131	0.107	0.192	.
1	CZ 02033 7a	3.11	0.321	0.043	0.019	1.83	0.022	1.29	0.479	0.029	0.044	1.07	.	.	0.027	0.005	.
1	SCRM 653/4	3.10	0.110	0.023	0.050	1.22	.	.	(1)
2	CZ SPL17 37A	3.07	0.211	0.025	0.023	3.30	0.149	0.106	0.328	0.039	0.031	0.325	.	0.073	0.008	0.122	(0.001)
1	VS CHG 30	3.06	2.10	0.090	0.035	1.97	0.576	.	0.24	.	.	0.0061	.	0.015	0.012	0.0074	.
2	BAS NCRM1	3.05	1.22	0.300	0.156	0.95	2.17	0.57	0.55	.	.	1.02	.	.	.	0.03	.
1	VS CHL3/1	3.04	0.250	0.067	0.024	2.39	0.60	1.08	0.533	.	0.016	0.262	.	.	0.043	0.103	.
1	DSZU CH08	3.02	0.79	0.056	0.058	2.05	1.60	2.52	2.13	0.29	(0.07)	0.96	(0.3)	(0.008)	0.315	0.34	.
1	VS CHG 39	3.01	0.82	0.304	0.088	1.45	0.414	1.09	1.08	.	.	0.113	.	.	0.168	0.274	.
2	BS CC-11	3.00	1.18	0.022	(0.024)	1.92											

CAST IRON WITH C > 2.75%

CONTINUED FROM THE PREVIOUS PAGE

analysis in mass % except * = mg/kg

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
CZ SPL17 35A	.	(0.0002)	(0.002)	.	.	.	(0.005)	.	40 mm Ø x 18 mm
CZ 02033 4e	.	.	(0.002)	(0.002)	40 mm Ø x 18 mm
SCRM 672/1	0.0079	40 mm x 37 mm x 10 mm
CZ 02033 4d	(0.012)	(0.0001)	(0.002)	0.007	40 mm Ø x 18 mm
SCRM 659/9	48 mm x 42 mm x 12 mm
Y 2582-7	0.043	30 mm Ø x 18-30 mm
DSZU CH04	.	(0.0007)	.	(7)	.	.	(0.0001)	.	(0.007)	.	.	.	(<0.0002)	.	~30 mm x ~35 mm x ~19mm
DSZU CH05	.	(0.03)	.	(20)	.	.	(0.001)	~30 mm x ~35 mm x ~19mm
CZ 02033 4b	0.004	(0.001)	40 mm Ø x 18 mm
Y 2582-6	0.0018	30 mm Ø x 18-30 mm
VS ChG 2/9	(0.003)	~38 mm Ø x ~40 mm
DSZU CH06	.	(0.02)	.	(10)	0.1	.	~35 mm x ~35 mm x ~19mm
CZ 20034 16c	(0.003)	0.020	0.015	0.010	.	.	0.015	(0.002)	40 mm Ø x 18 mm
CZ 20034 16a	0.005	0.018	0.006	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
11X C6W	0.0544	0.0043	0.007	Cd:(0.0003)	Ag:0.0042	.	.	0.0070	0.007	0.058	0.006	0.013	0.0242	.	~40 mm Ø x ~15 mm
CZ 20034 16b	0.005	0.018	0.007	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
VS ChG 32	.	.	0.361	~37 mm x ~37 mm x ~24 mm
SCRM 674/1	40 mm x 37 mm x 10 mm
Y 2582-4	30 mm Ø x 18-30 mm
CZ SPL17 39A	0.0017	.	0.008	0.017	0.037	40 mm Ø x 18 mm
Y 451043	0.12	30 mm Ø x 28 mm last
11X HPC5A	40 mm Ø x 17 mm
Y 2582-5	0.0022	30 mm Ø x 18-30 mm
VS ChG 1/9	(0.003)	~38 mm Ø x ~40 mm
CZ 02033 7b	0.045	.	40 mm Ø x 18 mm
CZ 02033 7c	.	0.0008	(0.002)	(0.006)	0.037	.	40 mm Ø x 18 mm
DSZU CH03	(0.004)	(0.001)	.	(20)	.	.	(0.0001)	.	(0.01)	.	.	.	(0.006)	.	~30 mm x ~35 mm x ~16mm
VS ChG 3/9	(0.003)	~38 mm Ø x ~40 mm
VS ChG 27	0.029	~35 mm x ~35 mm x ~22 mm
SCRM 660/10	48 mm x 42 mm x 12 mm
VS ChG 5/9	(0.003)	~38 mm Ø x ~40 mm
11X HPC4Q	~40 mm Ø x ~15 mm
Y 2863-5	.	0.060	0.158	.	30 mm Ø x 18-30 mm
11X C3AD	0.086	0.0253	0.0124	0.0075	0.0170	0.243	0.028	.	0.040	.	~40 mm Ø x ~15 mm
CZ SPL17 41A	.	(0.0004)	(0.007)	0.010	0.016	.	.	0.012	.	40 mm Ø x 18 mm
CZ 02033 8c	(0.006)	.	0.009	0.008	0.014	.	.	.	40 mm Ø x 18 mm
VS ChL1/1	~38 mm Ø x ~38 mm
CZ SPL17 38A	.	0.0027	(0.002)	(0.003)	0.018	.	.	(0.005)	.	40 mm Ø x 18 mm
11X C10D	0.019	0.0030	.	Cd:(0.0004)	.	.	.	0.0057	0.006	0.040	.	.	0.308	.	~40 mm Ø x ~15 mm
VS ChG 35	~34 mm Ø x ~37 mm
KUT 120	30 x 30 x 13 mm
NCS HS11783	0.0085	0.142	31 mm Ø x 28 mm
Y 2863-3	.	0.056	30 mm Ø x 18-30 mm
KUT 121	30 x 30 x 13 mm
KUT 205	30 x 30 x 13 mm
KUT 206	30 x 30 x 13 mm
KUT 122	30 x 30 x 13 mm
KUT 123	30 x 30 x 13 mm
NCS HS11784	0.0041	.	0.0083	0.0002	0.0007	31 mm Ø x 28 mm
Y 2582-3	0.009	30 mm Ø x 18-30 mm
Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
11X HPC1H	~40 mm Ø x ~15 mm
SCRM 665/4	48 mm x 42 mm x 12 mm
11X C9D	0.068	0.0049	0.0052	0.149	.	0.011	0.304	.	~40 mm Ø x ~15 mm
VS ChG 4/9	(0.003)	~38 mm Ø x ~40 mm
11X HPC3K	~40 mm Ø x ~15 mm
BAS NCRM3	40 mm x 37 mm x 10 mm
NCS HS11782	0.0065	31 mm Ø x 28 mm
KUT 125	30 x 30 x 13 mm
VS ChG 31	.	.	0.068	~37 mm x ~37 mm x ~24 mm
NCS HS11785	0.0049	.	0.013	0.0002	0.0005	31 mm Ø x 28 mm
DSZU CH02	.	(0.016)	.	(10)	.	.	(0.002)	~35 mm Ø x ~18 mm
11X CVV	0.0541	0.0098	0.0084	0.0096	0.0133	0.115	0.0157	.	0.0228	.	~40 mm Ø x ~15 mm
VS ChM 12	(0.08)	~38 mm Ø x ~38 mm
SCRM 671/1	40 mm x 37 mm x 12 mm
KUT 126	30 x 30 x 13 mm
KUT 202	30 x 30 x 13 mm
SCRM 657/9	48 mm x 42 mm x 12 mm
KUT 204	30 x 30 x 13 mm
KUT 127	30 x 30 x 13 mm
CZ 02033 6c	.	0.0024	(0.003)	0.044	.	0.007	.	40 mm Ø x 18 mm
CZ 02033 7a	0.022	.	40 mm Ø x 18 mm last
SCRM 653/4	48 mm x 42 mm x 12 mm last
CZ SPL17 37A	.	0.0124	(0.002)	(0.002)	.	.	.	0.026	.	40 mm Ø x 18 mm
VS ChG 30	.	.	0.082	~37 mm x ~37 mm x ~24 mm
BAS NCRM1	40 mm x 37 mm x 10 mm
VS ChL3/1	~38 mm Ø x ~38 mm
DSZU CH08	.	(0.08)	.	(10)	~35 mm x ~35 mm x ~19mm
VS ChG 39	~34 mm Ø x ~37 mm
BS CC-11	0.006	0.0012	(<0.0005)	2	(0.001)	(0.001)	(0.013)	.	0.0007	0.14	.	(0.002)	(0.002)	(0.002)	32 mm Ø x 17 mm last
BAS LARM2	0.044	.	.	.	0.008	.	.	.	0.007	40 mm x 37 mm x 10 mm
BAS LARM4	.	0.006	0.011	.	0.008	.	.	.	0.018	40 mm x 37 mm x 10 mm
BAS LARM1	.	0.0012	0.0010	.	0.005	40 mm x 37 mm x 10 mm
BAS LARM5	0.018	0.0012	0.0010	0.0005	40 mm x 37 mm x 10 mm last
BAS LARM3	0.092	0.003	0.022	40 mm x 37 mm x 10 mm
Y 2863-4	.	0.041	30 mm Ø x 18-30 mm
BAS LARM5/1	.	0.0016	0.0012	<0.001	40 mm x 37 mm x 10 mm
BAS NCRM2	40 mm x 37 mm x 10 mm
KUT 124	30 x 30 x 13 mm
CZ 02033 6b	0.049	40 mm Ø x 18 mm
SCRM 662/4	48 mm x 42 mm x 12 mm
VS ChG 36	~34 mm Ø x ~37 mm
SCRM 657/8	48 mm x 42 mm x 12 mm last
CZ 20034 12b	0.024	0.047	0.006	0.009	0.046	.	.	0.007	(0.002)	40 mm Ø x 18 mm
SRM C1145a	(0.03)	(0.02)	0.0012	(0.04)	.	.	.	(0.002)	32 mm Ø x 19 mm
11X C1R	0.0141	0.0357	0.011	0.0091	0.005	0.046	0.0050	.	0.100	0.0030	~40 mm Ø x ~15 mm
VS ChG 34	.	.	0.223	~37 mm x ~37 mm x ~24 mm
CZ 20034 12a	0.022	0.036	0.005	0.007	0.046	.	.	0.011	(0.002)	40 mm Ø x 18 mm
NCS HS11786	0.0075	.	0.015	0.0003	0.0008	31 mm Ø x 28 mm
11X C5Y	0.0203	0.0058	0.005	.	.	.									

CAST IRON WITH C < 2.75%

= Class, 1 = CRM and 2 = RM

analysis in mass % except * = mg/kg

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	VS ChL4/1	2.69	1.37	0.054	0.027	1.99	0.161	0.725	0.92	.	0.017	0.116	.	.	0.11	0.258	.
1	SRM C1291	2.67	1.14	0.028	0.032	1.34	0.26	4.34	2.78	.	.	0.32	.	.	.	0.031	.
1	VS ChG 6/9	2.65	0.83	0.54	0.027	0.53	0.34	.	0.241	0.028	0.130	.
1	DSZU CH01	2.61	0.258	0.012	0.0045	1.95	0.097	0.072	0.88	0.079	(0.06)	0.070	(0.010)	(0.05)	0.132	0.134	.
1	Y 2863-2	2.59	1.56	0.059	0.019	1.60	0.98	1.61	1.47	.	.	0.229	.	.	0.18	0.325	.
1	11X C8V	2.60	0.394	1.00	0.204	1.643	0.310	0.275	0.148	0.086	0.126	0.148	0.0217	0.1063	0.235	0.064	0.0068
1	SCRM 661/4	2.56	0.30	0.84	0.068	2.96	.	.	(1)
1	SCRM 656/9	2.537	0.820	0.060	0.108	2.504
1	11X C7N	2.51	1.942	0.0266	0.0101	0.829	0.075	0.0303	0.507	0.0127	0.0335	0.071	0.051	0.0114	0.022	0.036	0.0226
1	Y 2863-2	2.50	1.83	0.069	0.026	3.14	0.020	3.73	0.136	.	.	0.096	.	.	0.066	0.61	.
1	VS ChG 37	2.49	0.92	0.038	0.046	2.03	0.512	0.90	0.82	.	.	0.55	.	.	0.092	0.227	.
1	SCRM 673/1	2.455	0.123	0.317	0.0112	1.702	.	0.103	0.0423	0.0287	0.053	0.0092	.	0.0206	0.0718	0.052	.
1	CZ 20034 11b	2.44	0.382	0.271	0.140	3.67	0.130	0.082	1.178	0.067	0.005	1.144	.	0.074	0.041	0.182	.
1	VS ChG 38	2.43	0.302	0.386	0.084	2.30	1.20	0.162	1.98	.	.	0.046	.	.	0.105	0.119	.
1	CZ 02033 5b	2.42	0.812	0.033	0.073	1.32	0.031	0.188	0.061	0.062	.	0.089	.	.	0.007	0.005	.
1	VS ChL2/1	2.38	1.03	0.054	0.023	0.55	0.97	0.114	0.077	.	0.013	0.012	.	.	0.009	0.050	.
1	CZ 20034 11a	2.37	0.343	0.271	0.163	3.31	0.086	0.084	1.219	0.046	0.005	1.130	.	0.070	0.028	0.184	.
1	SCRM 652/4	2.34	1.19	0.071	0.129	0.878	.	.	(1)
1	DSZU CH07	2.33	1.36	0.090	0.064	3.01	0.35	0.403	0.34	0.036	.	0.66	(0.08)	(0.07)	0.150	0.52	.
1	CZ 02033 5a	2.30	0.804	0.035	0.100	1.26	0.014	0.096	0.054	0.060	.	0.100	.	.	0.008	0.005	.
1	CZ 02033 5c	2.30	0.704	0.027	0.091	1.40	0.013	0.188	0.085	0.103	0.013	0.104	.	(0.002)	0.008	0.054	.
1	11X C4S	1.954	0.565	0.1014	0.096	2.98	0.095	3.21	1.382	0.006	0.0210	0.177	0.0233	0.0140	0.080	0.0165	0.0037
1	SCRM 675	1.92	1.81	0.045	0.072	1.29	0.012	0.210	0.080	0.007	0.023	0.034	.	0.0062	0.007	0.178	0.0006
1	SCRM 655/4	1.90	0.44	0.180	0.076	2.110	.	.	(1)
1	Y 2863-1	1.78	2.41	0.021	0.009	3.62	0.022	4.77	0.031	.	.	0.038	0.0052	.	0.068	1.13	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
	Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units		
	VS ChL4/1	~38 mm Ø x ~38 mm		
	SRM C1291	32 mm Ø x 19 mm		
	VS ChG 6/9	(0.003)	~38 mm Ø x ~40 mm		
	DSZU CH01	.	(0.03)	.	(10)	.	(0.0005)	(0.02)	.	~30 mm x ~35 mm		
	VS ChG 40	~34 mm Ø x ~37 mm		
	11X C8V	0.0812	0.0366	0.014	.	.	.	0.0065	0.0052	0.069	0.0210	0.0049	0.0258	0.0064	~40 mm Ø x ~15 mm		
	SCRM 661/4	48 mm x 42 mm x 12 mm		
	SCRM 656/9	48 mm x 42 mm x 12 mm		
	11X C7N	0.0159	0.0097	0.0137	.	.	.	0.025	0.0106	0.025	.	.	0.066	(0.003)	40 mm Ø x 15 mm		
	Y 2863-2	.	0.0025	30 mm Ø x 18-30 mm		
	VS ChG 37	~34 mm Ø x ~37 mm		
	SCRM 673/1	40 mm x 37 mm x 10 mm		
	CZ 20034 11b	0.005	0.0032	0.007	0.007	0.011	.	.	(0.005)	0.007	40 mm Ø x 18 mm		
	VS ChG 38	~34 mm Ø x ~37 mm		
	CZ 02033 5b	.	0.014	0.020	40 mm Ø x 18 mm		
	VS ChL2/1	~38 mm Ø x ~38 mm		
	CZ 20034 11a	0.005	0.0018	0.011	0.017	0.013	.	.	(0.005)	0.007	40 mm Ø x 18 mm		
	SCRM 652/4	48 mm x 42 mm x 12 mm		
	DSZU CH07	.	(0.13)	.	(10)	.	(0.01)	~35 mm x ~35 mm x ~19mm		
	CZ 02033 5a	40 mm Ø x 18 mm		
	CZ 02033 5c	.	0.0078	0.007	(0.002)	(0.010)	.	(0.009)	40 mm Ø x 18 mm		
	11X C4S	0.0235	0.0351	0.0070	.	.	.	0.0126	0.034	0.0055	0.009	.	0.099	.	~40 mm Ø x ~15 mm		
	SCRM 675	0.035	40 mm x 37 mm x 10 mm		
	SCRM 655/4	48 mm x 42 mm x 12 mm		
	Y 2863-1	.	0.0024	30 mm Ø x 18-30 mm		

ALLOYED CAST IRON, CHART 1 of 2

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
2	DSZU CH021	3.93	3.66	0.064	0.009	0.52	0.369	5.86	9.07	0.168	4.42	.	.	0.093	0.61	.	.
2	BAS NCRM5	3.70	0.27	0.025	0.015	1.15	0.204	6.74	10.44	.	0.10	.	.	.	0.06	.	.
1	SRM C1292	3.47	0.55	0.049	0.016	0.59	0.36	5.04	11.4	.	0.25	.	.	.	0.041	.	.
2	BAS CRRM5/2	3.43	0.30	0.029	0.018	0.20	0.22	0.36	30.35	0.15	0.63	.	.	0.009	0.11	.	.
1	Y 451052-1	3.31	1.54	0.369	0.0047	0.098	0.449	2.57	1.17	.	1.47	.	.	.	0.952	.	.
1	BS PM15	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0025	1.22	(0.00001)	0.0034	0.0029	14.79	(0.0002)	0.111
1	Y 451052-7	3.13	0.201	0.024	0.116	2.48	0.154	0.129	31.26	.	0.086	.	.	0.033	0.087	.	.
1	58A SC01141	3.08	0.62	0.045	0.036	0.56	0.77	1.21	15.32	.	2.70	.	.	0.020	0.28	.	.
1	SRM C1290	3.04	0.66	0.030	0.013	0.971	0.065	0.917	30.5	.	(0.041)	.	.	.	0.442	.	.
1	Y TSK205	3.03	0.16	0.041	0.088	1.65	0.35	0.37	30.35	.	0.22	.	.	.	0.077	.	0.108
1	Y 451054-2	3.00	1.42	0.133	0.016	0.56	0.324	1.43	7.23	.	2.48	.	.	0.015	0.88	.	.
1	NCS HS11788	2.97	1.62	0.191	0.010	3.29	0.51	17.77	2.56	(0.0023)	0.0013	.	0.0003	0.043	0.017	.	.
1	Y 451052-2	2.96	1.24	0.211	0.0077	0.491	1.57	1.99	9.75	.	2.17	.	.	0.300	0.669	.	.
2	BAS NIRM5/1	2.95	1.01	0.103	0.005	1.50	0.21	21.7	0.51	0.055	.
2	58A ZS01036	2.95	0.719	0.077	0.024	0.970	0.448	0.806	13.89	.	0.683	.	0.048	0.035	0.135	.	.
2	BAS CRRM4/2	2.93	0.58	0.049	0.042	0.45	0.53	0.58	21.93	<0.005	1.15	.	.	0.008	0.11	.	.
2	11X 20003K	2.91	1.53	0.174	0.007	3.03	0.52	17.8	2.53
1	11X S/1 Cr3J	2.91	0.861	0.072	0.023	1.07	9.01	14.53	1.61
2	DSZU CH022	2.90	1.76	0.033	0.018	0.43	2.53	2.19	14.85	0.053	2.65	.	.	0.078	0.45	.	.
2	11X 20001J	2.90	0.58	0.005	0.143	1.01	0.01	21.4	1.50
2	11X S/2 Cr1E	2.83	1.68	0.31	0.011	2.85	0.02	16.5	2.48
1	11X 0331-1J	2.82	1.646	0.069	0.13	2.50	7.59	12.43	0.607	0.122	0.120	0.0327	0.0439	0.1099	.	.	.
2	BAS NIRM2/1	2.81	2.08	0.129	0.010	1.50	5.98	13.95	1.48	0.050	.
1	Y 451054-3	2.73	1.09	0.105	0.036	0.99	0.451	1.20	12.97	.	2.08	.	.	0.045	0.66	.	.
1	VS ChG45	(2.7)	1.01	0.096	0.047	2.96	0.040	0.60	32.65	.	0.198	.	.	0.011	0.111	.	.
2	11X 20002J	2.67	1.06	0.060	0.045	2.04	0.30	20.0	2.03
2	BAS NCRM4	2.66	0.40	0.203	0.012	2.13	0.68	5.34	7.94	.	0.57	.	.	.	0.11	.	.
1	NCS HS11787	2.65	1.08	0.067	0.037	2.07	0.306	19.84	1.98	(0.085)	0.0014	.	0.0054	0.022	0.0096	.	.
1	Y TSK201	2.56	1.07	0.253	0.023	0.66	1.53	2.44	10.14	.	2.56	.	.	.	0.42	.	0.029
2	BAS NIRM6/1	2.53	4.07	0.225	0.049	2.68	0.11	26.9	1.02	.	0.51
2	BAS NIRM3	2.51	0.51	0.208	0.096	2.21	1.00	17.8	2.43

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
---	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	---	----	---

Number	B	Ce	Co	Nb	W	Zr	Units	Other
DSZU CH021	35 mm x 35 mm x 16 mm	
BAS NCRM5	40 mm x 37 mm x 10 mm	
SRM C1292	32 mm Ø x 19 mm	
BAS CRRM5/2	48 mm x 42 mm x 12 mm	
Y 451052-1	0.177	.	.	0.018	0.015	.	30 mm Ø x 18-30 mm	
BS PM15	.	.	0.0330	0.014	0.109	(0.0005)	38 mm Ø x 19+ mm	17025 Fe:[73.0] As:0.0040 N:0.111 O:0.0129
Y 451052-7	0.015	.	.	0.010	0.175	.	30 mm Ø x 18-30 mm	
58A SC01141	-35 mm Ø x -30 mm	
SRM C1290	32 mm Ø x 19 mm	
Y TSK205	35 mm Ø x 18-30 mm	
Y 451054-2	30 mm Ø x 18-30 mm	
NCS HS11788	0.0008	.	(0.0063)	.	(0.0002)	.	31 mm Ø x 28 mm	As: 0.014
Y 451052-2	0.142	.	.	0.182	1.99	.	30 mm Ø x 18-30 mm	
BAS NIRM5/1	.	0.016	.	0.15	.	.	48 mm x 42 mm x 12 mm	
58A ZS01036	.	.	0.024	0.025	0.172	.	-32 mm Ø x -30 mm	As: (0.003)
BAS CRRM4/2	48 mm x 42 mm x 12 mm	
11X 20003K	40 mm Ø x 15 mm	
11X S/1 Cr3J	-40 mm Ø x -15 mm	
11X 20001K	40 mm Ø x 15 mm	
11X S/2 Cr1E	40 mm Ø x 15 mm	
11X 0331-1J	.	.	0.1117	0.149	.	.	-40 mm Ø x -15 mm	
BAS NIRM2/1	.	0.015	48 mm x 42 mm x 12 mm	
Y 451054-3	30 mm Ø x 18-30 mm	
VS ChG45	-36 mm x -36 mm Ø x -18 mm	last
DSZU CH022	35 mm x 35 mm x 16 mm	
11X 20002J	40 mm Ø x 15 mm	
BAS NCRM4	40 mm x 37 mm x 10 mm	
NCS HS11787	0.0007	.	(0.0054)	.	(0.0002)	.	31 mm Ø x 28 mm	As: 0.0075
Y TSK201	35 mm Ø x 18-30 mm	
BAS NIRM6/1	.	0.006	48 mm x 42 mm x 12 mm	
BAS NIRM3	.	0.007	.	0.09	.	.	40 mm x 37 mm x 10 mm	

Number	B	Ce	Co	Nb	W	Zr	Units	Other
--------	---	----	----	----	---	----	-------	-------

ALLOYED CAST IRON, CHART 2 of 2

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
1	Y 451052-3	2.40	1.06	0.115	0.015	0.821	0.953	1.55	13.30	.	0.869	.	.	0.171	0.482	.	.
2	BAS CRRM3/2	2.37	0.92	0.073	0.087	1.21	1.09	1.35	18.78	0.102	1.58	.	.	0.015	0.042	.	.
2	DSZU CH023	2.33	0.43	0.023	0.073	0.98	0.054	0.715	23.45	0.255	1.46	.	.	0.38	0.288	.	.
1	Y 451054-4	2.31	0.725	0.071	0.046	1.40	0.739	0.914	17.60	.	1.44	.	.	0.084	0.46	.	.
1	Y TSK200	2.11	0.82	0.319	0.022	0.17	1.86	3.22	4.97	.	3.50	.	.	.	0.60	.	0.021
2	BAS NIRM1	2.05	6.72	0.055	0.005	3.15	0.20	11.80	0.246	0.021	.
2	BAS NIRM7	2.05	0.71	0.058	0.020	3.05	0.52	32.9	3.53	.	0.99	0.019	.
2	DSZU CH024	2.01	1.22	0.102	0.037	2.18	0.88	0.222	27.84	0.096	3.86	.	.	0.099	0.164	.	.
1	Y 451052-4	2.00	0.803	0.090	0.025	1.16	0.738	1.07	18.28	.	0.598	.	.	0.087	0.380	.	.
2	BAS NIRM4	1.97	2.37	0.051	0.008	3.03	0.52	20.2	3.56	0.014	.
1	NCS HS11789	1.97	1.08	0.048	0.076	2.58	6.39	17.80	2.51	0.061	0.062	0.015	0.014	0.011	0.0093	.	.
2	BAS CRRM2/1	1.92	1.11	0.097	0.079	1.18	1.59	1.61	14.13	0.054	2.44	.	.	0.070	0.063	.	.
2	BAS CRRM1/1	1.83	1.45	0.132	0.099	1.53	2.01	2.03	11.18	0.117	3.05	.	.	0.096	0.040	.	.
1	Y 451054-5	1.83	0.466	0.043	0.091	1.80	0.904	0.517	23.40	.	0.739	.	.	0.068	0.26	.	.
1	Y TSK202	1.81	1.16	0.201	0.057	2.00	1.10	1.91	15.42	.	2.20	.	.	.	0.33	.	0.075
2	DSZU CH025	1.80	0.387	0.030	0.026	2.70	1.23	1.77	35.14	0.351	0.302	.	.	0.117	0.044	.	.
2	DSZU CH026	1.62	0.305	0.050	0.032	1.14	0.288	3.63	35.87	0.059	0.96	.	.	0.013	0.067	.	.
1	Y 451052-5	1.48	0.579	0.041	0.058	1.37	0.583	0.708	22.55	.	0.359	.	.	0.056	0.314	.	.
2	BAS NIRM8/2	1.45	1.58	0.105	0.014	5.61	0.23	35.3	2.47	.	0.77	0.033	.
1	Y 451054-6	1.45	0.254	0.024	0.123	2.38	1.15	0.216	28.96	.	0.213	.	.	0.084	0.13	.	.
2	BAS NIRM8/1	1.34	1.60	0.109	0.010	5.42	0.23	35.2	2.34	.	0.75	0.043	.
1	VS ChG44	1.24	0.87	(1.2)	0.076	1.50	2.27	0.175	25.44	.	0.035	.	.	0.104	0.079	.	.
1	Y TSK203	1.23	0.68	0.117	0.044	0.46	0.75	1.55	19.93	.	1.58	.	.	.	0.22	.	0.094
1	Y 451052-6	1.16	0.302	0.033	0.086	1.44	0.845	0.289	25.76	.	0.150	.	.	0.019	0.146	.	.
1	Y TSK204	0.91	0.34	0.078	0.063	1.00	0.53	0.97	25.37	.	0.95	.	.	.	0.14	.	0.114

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
	Number	B	Ce	Co	Nb	W	Units		Other								
	Y 451052-3	0.102	.	.	0.149	1.57	30 mm Ø x 18-30 mm										
	BAS CRRM3/2	40 mm x 37 mm x 10 mm										
	DSZU CH023	35 mm x 35 mm x 16 mm										
	Y 451054-4	30 mm Ø x 18-30 mm										
	Y TSK200	35 mm Ø x 18-30 mm										
	BAS NIRM1	.	0.018	.	.	.	40 mm x 37 mm x 10 mm										
	BAS NIRM7	.	0.005	.	.	.	40 mm x 37 mm x 10 mm										
	DSZU CH024	35 mm x 35 mm x 16 mm										
	Y 451052-4	0.086	.	.	0.071	1.05	30 mm Ø x 18-30 mm										
	BAS NIRM4	.	0.011	.	0.37	.	40 mm x 37 mm x 10 mm										
	NCS HS11789	0.0008	.	(0.0075)	.	(0.0002)	31 mm Ø x 28 mm		As: 0.0076		Bi: 0.067						
	BAS CRRM2/1	40 mm x 37 mm x 10 mm										
	BAS CRRM1/1	40 mm x 37 mm x 10 mm										
	Y 451054-5	30 mm Ø x 18-30 mm										
	Y TSK202	35 mm Ø x 18-30 mm										
	DSZU CH025	35 mm x 35 mm x 16 mm										
	DSZU CH026	35 mm x 35 mm x 16 mm										
	Y 451052-5	0.076	.	.	0.022	0.694	30 mm Ø x 18-30 mm										
	BAS NIRM8/2	.	0.013	.	.	.	48 mm x 42 mm x 12 mm										
	Y 451054-6	30 mm Ø x 18-30 mm										
	BAS NIRM8/1	.	0.013	.	.	.	48 mm x 42 mm x 12 mm		last								
	VS ChG44	~36 mm x ~36 mm Ø x ~18 mm		last								
	Y TSK203	35 mm Ø x 18-30 mm										
	Y 451052-6	0.055	.	.	0.014	0.370	30 mm Ø x 18-30 mm										
	Y TSK204	35 mm Ø x 18-30 mm										
	Number	B	Ce	Co	Nb	W	Units		Other								

RM CAST IRON MUSHROOMS CONTINUED ON THE NEXT PAGE

typical analysis

each unit is one pair of 43 mm Ø x 5 mm mushroom discs

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF F019	4.04	1.05	1.05	0.032	0.057
CTIF F012	3.71	1.86	0.44	0.038	0.004	0.77	.	.	0.008	.	.	0.011	.	.	.
CTIF F08	3.6	1.04	0.37	0.107	0.021	0.215	0.30	0.30	.	.	0.005	0.05	0.055	0.014	.
CTIF FCR7	3.59	1.07	0.365	0.099	0.0427	0.704	0.947	33.65	.	.	2.62
CTIF F06	3.49	0.55	0.715	0.87	0.106	0.120	0.128	0.45	.	.	0.202	0.039	0.080	0.110	.
CTIF F010	3.5	0.67	1.05	0.20	0.101	0.114	0.118	0.38	.	.	0.20	.	0.1	0.08	.
CTIF NH3	3.47	0.85	0.175	0.36	0.024	0.031	2.53	1.76	.	.	0.73
CTIF F011	3.45	1.57	0.685	0.052	0.103	0.211	0.235	0.34	.	(0.013)	0.225	0.066	0.078	0.113	.
CTIF F018	3.43	1.24	0.590	1.34	0.136	0.049	0.140	0.170	.	.	0.179	0.046	0.057	0.102	.
CTIF NH7-1	3.43	0.95	0.63	0.035	0.022	0.105	5.53	9.02
CTIF FCR5	3.43	0.35	0.62	0.052	0.0175	1.02	2.69	28.5	.	.	3.27
CTIF FT2-1	3.39	1.415	0.78	0.045	0.095	0.01	0.070	0.030	0.100	0.405	.
CTIF NiMo1	3.22	2.585	0.200	0.0590	(0.0030)	0.376	2.165	0.0353	.	0.0205	0.457	0.0020	0.0190	0.0169	.
CTIF FL7	3.22	2.550	0.100	1.34	0.048	0.351	0.232	0.043	.	.	0.335	0.0291	0.0525	0.0796	.
CTIF FT3	3.2	1.55	0.345	0.063	0.051	0.015	0.092	0.685	0.2	0.016	.
CTIF NH7-2	3.2	1.20	0.91	0.034	0.0120	0.108	5.53	8.87
CTIF F05	3.2	0.7	0.2	1.30	0.027	0.12	0.172	0.3	.	.	0.41	0.109	0.04	0.14	.
CTIF NH9	3.13	1.24	0.65	0.087	0.029	0.203	4.11	11.70	.	.	0.059
CTIF NR Cu1	3.12	1.465	0.172	0.090	0.99	4.95	18.02	0.994	(0.095)
CTIF FL6	3.1	1.4	0.6	0.012	0.18	0.079	1.03	0.167	.	0.028	0.50	0.005	0.15	0.033	.
CTIF FL10	3.1	1.3	0.85	0.323	0.066	0.104	0.10	(0.07)	(0.03)	.	0.0335	0.028	0.045	0.048	(0.02)
CTIF FFA 1	3.090	0.0300	0.100	0.0022	0.0009	0.0622	0.0450	0.0710	.	0.0097	0.0109	.	0.0010	0.0010	.
CTIF NR 8S	3.05	1.41	4.39	0.124	0.071	14.20	0.191
CTIF F017	3.01	2.48	0.475	0.470	0.168	(0.006)	0.021	(0.016)	.	0.032	.	0.024	0.032	0.018	.
CTIF FAL 1	3.0	1.0	0.2	0.04	<0.001	0.2	0.06	0.04	2.1	.	0.015	.	0.01	.	.
CTIF NR 3L	2.99	3.05	0.72	0.088	0.052	0.26	21.58	2.97
CTIF NH1	2.98	1.35	0.90	0.060	0.105	1.99	1.38	0.83	.	.	1.45
CTIF NH8	2.98	0.80	0.57	0.052	0.076	0.065	8.16	5.03	.	.	0.125
CTIF NR 3S	2.92	2.91	0.77	0.024	0.025	0.33	24.63	3.05
CTIF FT1	2.9	2.12	0.71	0.12	0.025	0.012	0.11	0.057	.	.	.	0.067	0.19	0.525	.

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF NR 8L	2.89	1.70	5.19	0.054	0.030	0.075	13.33	0.165
CTIF NH4	2.84	0.49	0.28	0.12	0.022	0.09	3.60	2.46	.	.	0.30
CTIF F04	2.81	1.51	0.64	0.58	0.009	0.31	0.32	0.17	.	.	0.095	0.013	0.075	0.049	.
CTIF FCR2	2.86	1.07	0.740	0.137	0.055	0.135	1.87	11.8	.	.	3.88
CTIF FL5	2.8	2.3	0.4	0.02	(0.005)	0.5	0.05	0.35	.	0.010	0.01	0.07	0.01	0.01	.
CTIF FCR Ni3	2.74	0.69	0.47	0.036	0.011	.	11.05	31.65
CTIF NH6	2.70	2.28	0.355	0.066	0.036	0.115	7.06	6.60	.	.	0.11
CTIF F09	2.7	1.5	0.7	0.02	0.015	0.31	0.355	0.18	.	.	0.13	0.144	0.017	0.022	.
CTIF FL4	2.6	2.91	0.5	0.288	0.137	0.0168	0.061	0.45	.	.	0.090	0.011	0.0296	0.116	.
CTIF NR 1S	2.58	3.02	1.54	0.19	0.0015	0.11	20.60	2.00
CTIF NR 1L	2.50	3.00	1.34	0.125	0.10	0.49	25.87	1.74
CTIF NH2	2.50	1.81	1.04	0.047	0.058	1.02	1.78	1.26	.	.	1.01
CTIF NR Cu2	2.48	2.07	1.078	0.113	0.049	6.50	15.85	2.05
CTIF NR 4S	2.47	4.87	1.71	0.145	0.066	0.63	18.30	1.50
CTIF FCR4	2.47	1.40	2.05	0.097	0.066	1.32	0.571	24.2	.	.	2.16
CTIF FCR1	2.46	0.48	0.63	0.019	0.007	0.031	1.30	18.71	.	.	1.41
CTIF F07	2.45	0.675	0.70	0.84	0.085	0.125	0.15	0.455	.	.	0.26	.	0.065	0.13	.
CTIF NR 4L	2.41	5.89	1.495	0.155	0.010	0.758	15.90	1.403
CTIF NR 2S	2.32	1.43	0.530	0.062	0.0210	0.210	36.3	0.51
CTIF NH5	2.31	0.31	0.24	0.115	0.04	0.035	4.90	2.85	.	.	0.017
CTIF FL3	2.3	2.1	0.27	0.729	(0.013)	0.102	0.553	0.107	.	.	0.106	0.111	0.05	0.049	.
CTIF NR 4G	2.24	5.60	1.72	0.11	(0.002)	0.64	21.30	1.40
CTIF NR 2G	2.25	1.47	0.380	0.0476	(0.003)	0.232	36.34	0.395
CTIF FL2	2.18	3.61	0.0400	0.049	0.082	0.0497	0.0238	0.440	(0.006)	0.0263	(0.004)	0.140	0.0750	0.201	.
CTIF FL1	2.1	3.2	0.80	0.118	0.0765	0.0195	0.245	0.06	.	(0.022)	0.038	0.305	0.020	0.015	.
CTIF FCR Ni2	2.02	1.50	0.61	0.185	0.024	.	13.05	29.00
CTIF NR Cu3	1.94	3.12	0.60	0.046	0.016	8.05	13.3	3.50
CTIF NR 6S	1.82	2.44	0.99	0.019	0.031	0.03	30.75	1.06
CTIF NR 5L	1.77	2.99	1.207	0.037	0.083	0.48	33.89	0.27
CTIF NR 6L	1.76	2.07	0.70	0.031	0.063	0.020	30.37	3.49
CTIF NR 5S	1.67	1.97	1.23	0.035	.	0.50	27.05	0.24
CTIF FCR6	1.44	0.76	1.47	0.201	0.086	0.480	0.188	30.84	.	.	0.455
CTIF FCR Ni1	1.27	1.63	0.71	0.41	0.06	0.02	16.50	26.20

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
--------	---	----	----	---	---	----	----	----	----	----	----	----	----	---	---

CAST IRON MUSHROOMS

CONTINUED FROM THE PREVIOUS PAGE

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF F019	0.0005	.
CTIF F012
CTIF F08
CTIF FCR7
CTIF F06
CTIF F010
CTIF NH3
CTIF F011
CTIF F018	0.0040
CTIF NH7-1
CTIF FCR5
CTIF FT2-1
CTIF NiMo1
CTIF FL7	(0.0266)	(0.010)	.	(0.010)	.	0.0035
CTIF FT3
CTIF NH7-2
CTIF F05
CTIF NH9
CTIF NR Cu1
CTIF FL6	.	0.008
CTIF FL10	(0.022)	.	(0.012)	(0.004)	.	.	(0.018)	(0.002)	(0.032)	(0.001)	(0.029)
CTIF FFA 1	0.0109	0.0125
CTIF NR 8S
CTIF F017
CTIF FAL 1
CTIF NR 3L
CTIF NH1
CTIF NH8
CTIF NR 3S
CTIF FT1

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF NR 8L
CTIF NH4
CTIF F04	last of stock
CTIF FCR2
CTIF FL5	.	(0.002)	.	(0.0005)
CTIF FCR Ni3
CTIF NH6
CTIF F09
CTIF FL4	(0.05)	.	.	(0.003)	.	0.007
CTIF NR 1S
CTIF NR 1L
CTIF NH2
CTIF NR Cu2	(0.0079)
CTIF NR 4S
CTIF FCR4
CTIF FCR1
CTIF F07
CTIF NR 4L
CTIF NR 2S
CTIF NH5
CTIF FL3	0.008
CTIF NR 4G
CTIF NR 2G	0.27
CTIF FL2	.	.	.	(0.0135)
CTIF FL1
CTIF FCR Ni2
CTIF NR Cu3
CTIF NR 6S
CTIF NR 5L
CTIF NR 6L
CTIF NR 5S
CTIF FCR6
CTIF FCR Nil

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
--------	----	---	----	----	----	---	----	----	----	----	----

CARBON STEEL

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 VS UG128	0.816	0.405	0.014	0.0139	0.324	0.0235	0.032	0.038	0.0078	.	.	0.0088	0.0046	.
1 VS UG129	0.728	.	.	0.013	0.0014
1 IARM Fe1050-18	0.499	0.79	0.0045	0.027	0.223	0.179	0.068	0.100	(0.003)	0.0056	0.018	0.0097	0.0270	.
1 VS UG131	0.39	0.56	0.0100	0.0031	0.207	0.030	0.026	0.853	.	.	.	0.0070	.	.
1 IARM Fe1020-18	0.226	0.547	0.006	0.024	0.235	0.198	0.078	0.125	(0.003)	0.0065	0.0252	0.0098	0.036	.
1 VS UG132	0.180	0.466	0.0075	0.0030	0.201	0.039	0.024	0.035	.	.	.	0.0054	.	.
1 BS XCAS *	0.029	0.47	0.008	0.006	0.34	0.022	0.032	0.038	0.029	0.009	0.007	0.006	0.021	0.009

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units	Others
VS UG128	~38 mm Ø x ~20 mm	.
VS UG129	~38 mm Ø x ~20 mm	.
IARM Fe1050-18	(0.0030)	(0.0005)	98.0	(0.0013)	0.0026	0.0015	0.0103	0.0008	1050	31 mm Ø x 2 or 18 mm	.
VS UG131	~39 mm Ø x ~25 mm	.
IARM Fe1020-18	0.0044	.	98.5	(0.0012)	(0.007)	0.0018	0.0080	.	1020	31 mm Ø x 2 or 18 mm	.
VS UG132	~39 mm Ø x ~25 mm	.
BS XCAS *	0.002	<0.005	[98.9]	0.002	<0.05	<0.05	0.002	0.001	1008	38 mm Ø x 30 mm	.

RESULFURIZED STEEL

= Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 IARM 307B	0.162	1.45	(0.012)	0.094	(0.30)	0.191	0.195	0.105	0.034	0.0101	0.045	(0.011)	(0.003)	.
2 CZ CM-22A	0.154	1.443	0.086	0.084	0.248	0.419	3.10	0.167	(0.004)	0.130	0.132	0.0065	0.653	0.59

Number	As	Nb	Sn	Ti	Alloy	Units
IARM 307B	.	(0.0013)	0.010	(0.003)	1118	31 mm Ø X 2 or 18 mm
CZ CM-22A	0.057	0.019	0.069	0.0038	.	~39 mm Ø x ~25 mm

SILICON STEEL

= Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 CZ CM-20A	0.63	0.594	0.0383	0.020	1.74	0.237	1.007	0.97	0.076	0.124	0.365	0.0086	0.225	0.104
2 CZ LA-3G	0.626	0.68	0.047	0.035	1.29	0.236	1.01	1.377	0.047	0.127	0.326	0.011	0.232	0.105
1 IMZ 52/1	0.41	0.25	0.012	(0.009)	1.38	0.094	2.35	0.12	.	.	(0.041)	.	.	.
2 CZ CM-12C	0.038	0.275	0.0103	0.0110	3.7	0.175	0.046	0.081	0.145	0.0044	0.012	0.0056	0.027	(0.004)

Number	As	B	Nb	Pb	Sb	Sn	Ti	Units	Others
CZ CM-20A	0.073	0.0071	0.074	0.015	0.025	0.033	0.175	~37 mm Ø x ~25 mm	Zn:0.007 Zr:0.083
CZ LA-3G	0.051	0.0039	0.071	0.0098	0.024	0.031	0.143	~39 mm Ø x ~25 mm	Ca:0.0016 Zr:0.068
IMZ 52/1	40 mm Ø x 40 mm	.
CZ CM-12C	0.0030	0.0033	0.0066	.	.	(0.005)	0.0128	~39 mm Ø x ~25 mm	Ca:0.0010

LOW ALLOY AND TOOL STEEL

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 HRT FE2019-H	1.54	0.39	0.025	(0.003)	0.51	0.08	0.14	11.89	0.015	.	0.86	.	0.80	.
1 IARM FeM62-18	1.32	0.27	0.016	0.015	0.37	0.115	0.129	3.86	(0.006)	0.105	10.2	0.045	2.02	6.31
2 CZ LA-4D	1.143	1.266	0.028	0.0091	0.181	0.066	0.367	1.83	0.067	0.037	0.136	0.0064	0.103	0.025
1 ECRM 268-1D	1.134	0.293	0.0209	0.0154	0.373	0.123	0.143	4.57	.	0.0290	3.20	2.03	8.47	3.70
1 VS UG127	0.962	0.93	0.020	0.029	0.427	0.145	0.151	0.188	0.0051	.	.	0.0155	0.141	.
1 VS UG126	0.856	0.78	0.0128	0.0077	0.348	0.030	0.029	0.591	0.0015	.	.	0.0123	0.075	.
1 VS UG130	0.80	0.228	0.0078	0.0071	0.226	0.252	0.104	0.258
2 CZ CM-1D	0.735	1.80	0.0218	0.026	0.341	0.186	0.547	0.456	0.024	0.029	0.100	0.0124	0.089	0.063
1 12X LA4C	0.657	0.374	0.050	0.0258	0.482	0.265	0.485	0.526	0.183	0.099	0.405	0.0116	0.372	0.091
1 BS 33F	0.569	0.295	0.0134	0.0009	0.76	0.039	0.211	1.31	0.019	0.017	0.202	0.0124	0.25	2.28
1 BS TS-7A *	0.528	0.74	0.013	0.016	0.84	0.13	0.022	3.35	0.060	<0.05	1.6	0.12	0.27	<0.005
1 12X 41400B	0.452	0.764	0.0095	0.041	0.32	0.161	0.156	0.999	0.0137	.	0.177	0.0124	.	.
2 CZ LA-5B	0.439	1.87	0.017	0.0088	0.394	0.138	2.59	3.815	0.081	0.088	0.86	0.024	0.536	0.631
1 IMZ 54/1	0.43	0.14	(0.009)	0.010	0.17	(0.034)	4.01	0.12	.	.	(0.007)	.	0.19	.
2 PV 101/1	0.424	0.798	0.014	0.027	0.177	0.108	0.091	1.013	.	.	0.099	.	.	.
1 BS 4140C *	0.42	0.93	0.01	0.03	0.28	0.26	0.12	0.95	0.02	0.008	0.17	<0.05	0.003	<0.05
1 IARM 170B	0.400	0.821	(0.005)	(0.004)	0.21	(0.005)	0.197	0.009	0.230	(0.005)	(0.003)	.	(0.002)	.
1 IARM Fe5140H-18	0.37	0.93	0.014	0.022	0.187	0.253	0.266	0.67	0.13	0.0081	0.031	0.007	(0.0024)	(0.003)
1 BS 4330MOD *	0.31	0.92	0.005	0.001	0.27	0.10	1.8	0.85	0.032	0.035	0.48	<0.05	0.08	0.001
1 IARM 378A	0.274	1.38	0.018	0.037	0.307	0.299	0.142	0.187	(0.0029)	0.013	0.031	(0.02)	0.0844	(0.006)
1 IARM 169B	0.232	0.75	(0.004)	(0.004)	(0.32)	(0.005)	(0.010)	0.010	0.36	(0.003)	(0.004)	.	(0.002)	(0.003)
1 IARM Fe8620-18	0.211	0.857	0.012	0.026	0.23	0.197	0.446	0.536	0.0246	0.0085	0.197	0.007	0.0061	(0.004)
1 SRM 1763b	0.20	1.60	0.0123	0.022	0.627	0.0417	0.507	0.503	0.042	0.0924	0.49	.	0.307	0.0021
1 IARM Fe4820-18	0.192	0.541	(0.011)	0.0018	0.26	0.167	3.51	0.144	0.022	0.0107	0.287	0.007	0.0015	(0.004)
2 PV 102/1	0.186	1.226	0.024	0.018	0.184	0.109	0.140	0.995	.	.	0.030	.	.	.
1 IRSID 1658	0.180	0.618	0.014	0.032	0.160	0.345	0.241	0.147	0.029	.	0.046	.	(0.002)	.
2 HRT FE2019-N	0.17	1.27	0.015	(0.001)	0.30	0.03	0.33	0.75	0.068	(0.003)	0.40	0.0040	(0.003)	.
1 VS RG31	0.169	0.291	0.0048	0.006	0.39	0.46	2.08	1.31	0.28	0.306	.	.	0.207	0.39
1 IARM FeE9310-18	0.121	0.62	0.009	0.0128	0.256	0.158	3.07	1.09	0.036	0.009	0.086	0.0070	0.0030	.
1 IARM FeDP1080-18	0.110	1.88	0.014	(0.006)	0.11	0.042	0.554	0.554	(0.002)	0.069	0.445	(0.009)	(0.0043)	(0.030)
2 HRT FE2003-H	0.104	0.46	0.013	0.002	0.43	0.05	0.26	8.66	(0.004)	0.013	0.93	.	0.217	.
1 IARM FeF9-18	0.104	0.459	(0.011)	0.0036	0.345	0.093	0.148	8.72	.	0.013	0.94	0.0323	0.214	0.0030
1 BS 3310 *	0.10	0.55	0.010	0.015	0.26	0.20	3.48	1.56	0.035	0.010	0.054	<0.05	0.003	0.004
1 IARM Fe91-18	0.099	0.453	0.015	(0.002)	0.27	0.041	0.187	8.24	(0.006)	0.013	0.94	0.046	0.198	(0.003)
1 IARM FeP92-18	0.092	0.737	(0.005)	(0.005)	0.20	0.074	0.82	9.4	(0.005)	0.036	0.52	(0.0036)	0.188	1.97
1 IARM FeT23-18	0.068	0.82	0.012	0.006	0.18	0.046	0.53	2.47	.	0.085	0.261	(0.003)	0.238	1.60
1 VS UG102	0.045	1.78	0.0082	.	0.222	0.172	0.277	0.0143	0.036	.	0.209	.	.	.
1 12X LA6D	0.009	0.086	0.0041	0.0057	0.075	0.0250	0.033	0.099	0.174	0.0051	0.0110	0.0070	0.0033	.

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
HRT FE2019-H	.	.	.	0.071	.	.	.	0.012	.	.	40	mm Ø x 20	mm	.
IARM FeM62-18	.	(0.003)	.	(0.017)	(0.003)	.	.	(0.003)	M-62	.	31	mm Ø x 2 or 18	mm	.
CZ LA-4D	0.010	.	.	0.0046	.	.	0.014	0.0154	.	.	~39	mm Ø x ~25	mm	Pb:0.040
ECRM 268-1D	0.0062	0.0009	.	.	.	0.0017	0.0078	.	.	.	38	mm Ø x 25	mm	.
VS UG127	0.0094	.	.	~38	mm Ø x ~20	mm	Bi:0.011 Pb:0.0049
VS UG126	~38	mm Ø x ~20	mm	Bi:0.0055 Pb:0.009
VS UG130	0.0093	~39	mm Ø x ~25	mm	.
CZ CM-1D	.	0.0017	.	0.050	.	0.0112	0.0144	0.054	.	.	~39	mm Ø x ~25	mm	.
12X LA4C	0.018	~40	mm Ø x ~15	mm	Zn:0.006
BS 33F	(0.003)	(0.0007)	94.0	(0.002)	0.0024	(0.01)	(0.004)	(0.002)	S-1 MOD	.	38	mm Ø x ~7 - 19+	mm	17025
BS TS-7A *	0.006	<0.05	[92.39]	<0.05	0.005	0.004	0.007	0.003	S-7	.	36	mm Ø x 25	mm	.
12X 41400B	0.015	0.0099	.	4140	.	~38	mm Ø x ~20	mm	Zn:0.0012
CZ LA-5B	0.026	.	.	0.057	Pb:0.015	0.018	0.031	0.048	.	.	~37	mm Ø x 25	mm	.
IMZ 54/1	40	mm Ø x 40	mm	.
PV 101/1	42CrMo4	40	mm Ø x 25	mm	.
BS 4140C *	<0.05	<0.005	[96.8]	0.002	<0.05	0.003	0.01	0.001	4140	.	38	mm Ø x ~7 or 19+	mm	.
IARM 170B	.	(0.0004)	.	(0.004)	.	.	(0.002)	(0.19)	CLA7	.	31	mm Ø x 2 or 18	mm	.
IARM Fe5140H-18	(0.011)	.	.	(0.002)	.	.	0.0089	0.0015	5140H	.	31	mm Ø x 2 or 18	mm	.
BS 4330MOD *	<0.05	<0.005	[95.0]	0.008	<0.005	.	<0.05	0.003	4330M	.	44	mm Ø x ~7 or 19+	mm	.
IARM 378A	.	(0.0006)	.	(0.003)	.	.	0.0236	(0.003)	A615-75	.	31	mm Ø x 2 or 18	mm	.
IARM 169B	.	0.0003	.	(0.004)	.	.	(0.002)	0.23	CLA6	.	31	mm Ø x 2 or 18	mm	.
IARM Fe8620-18	0.009	0.0072	0.0015	8620	.	31	mm Ø x 2 or 18	mm	.
SRM 1763b	0.053	0.0053	(95.5)	0.099	.	0.011	0.0109	0.31	.	.	34	mm Ø x 19	mm	Ta:0.011 Zr:0.044
IARM Fe4820-18	(0.006)	.	.	(0.003)	(0.003)	.	.	(0.0011)	4820	.	31	mm Ø x 2 or 18	mm	.
PV 102/1	16MnCr5	.	40	mm Ø x 25	mm	.
IRSID 1658	0.034	0.022	(0.002)	.	.	40	mm Ø x 30	mm	.
HRT FE2019-N	.	0.0016	.	0.029	.	.	.	0.004	.	.	40	mm x 40 mm x 20	mm	Ca:0.0014
VS RG31	0.21	.	.	~45	mm Ø x ~28	mm	.
IARM FeE9310-18	.	.	94.6	0.285	(0.0017)	.	0.008	.	9310	.	31	mm Ø x 2 or 18	mm	.
IARM FeDP1080-18	.	.	.	0.014	(0.0055)	.	(0.0064)	(0.0013)	DP1080	.	31	mm Ø x 2 or 18	mm	.
HRT FE2003-H	.	0.004	.	0.064	F-91	.	40	mm Ø x 20	mm	.
IARM FeF9-18	0.006	.	88.9	0.078	0.0025	(0.0026)	0.0062	0.0028	F-9	.	31	mm Ø x 2 or 18	mm	.
BS 3310 *	<0.05	<0.005	[93.7]	0.001	<0.005	<0.05	0.001	0.001	3310	.	44	mm Ø x ~7 or 19+	mm	.
IARM Fe91-18	.	0.0026	.	(0.011)	(0.013)	.	(0.006)	(0.003)	F-91	.	31	mm Ø x 2 or 18	mm	.
IARM FeP92-18	F-92 MOD	.	31	mm Ø x 2 or 18	mm	.
IARM FeT23-18	.	0.0020	.	0.052	0.0044	.	(0.004)	(0.004)	T23	.	31	mm Ø x 2 or 18	mm	.
VS UG102	.	.	.	0.071	~45	mm Ø x ~25	mm	Ca:0.0018
12X LA6D	~40	mm Ø x ~15	mm	Zn:0.0083

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
--------	---	----	---	---	----	----	----	----	----	----	----	---	---	---

STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 IARM FeAl100-18	0.222	(0.013)	(0.004)	(<0.0010)	(0.039)	(0.010)	11.2	2.98	(0.007)	13.4	1.19	(0.0010)	(0.007)	(0.006)
2 BS 183B *	0.18	0.35	0.018	0.005	0.41	0.075	1.97	12.43	0.0008	0.030	0.33	0.044	0.17	3.42
1 BS 183C *	0.17	0.37	0.014	0.004	0.43	0.063	1.87	12.71	0.002	0.028	0.19	0.04	0.11	2.77
1 BS 309 *	0.061	1.61	0.028	0.001	0.25	0.35	12.17	22.4	0.003	0.20	0.19	0.074	0.073	0.03
1 BS 347C *	0.051	1.67	0.022	0.022	0.67	0.11	10.1	17.3	0.004	0.072	0.268	0.039	0.097	0.012
2 CZ SP-1B	0.050	1.67	0.039	0.30	0.505	0.47	8.32	17.42	(0.003)	0.161	0.40	0.063	0.060	0.032
2 PV 112/1	0.047	1.577	0.018	0.023	0.515	0.102	11.14	17.56	.	.	2.03	.	.	.
1 IARM Fe174PH-18	0.041	0.47	0.024	(<0.0040)	0.52	3.33	4.73	15.10	0.007	0.047	0.315	0.0436	0.051	0.015
1 13X 41008B	0.034	0.684	0.013	0.0070	0.761	0.267	0.338	12.36	0.028	0.053	0.042	0.0088	0.061	.
1 BS 2507 *	0.025	0.78	0.024	0.0005	0.32	0.22	6.9	25.3	0.005	0.041	3.78	0.28	0.064	0.076
2 TL 2001D	0.0244	0.679	0.022	0.0006	0.27	0.612	7.5	25.58	.	0.046	3.49	0.279	0.079	0.57
1 IARM FeKovar-18	0.024	0.26	(0.004)	(0.0055)	(0.09)	0.077	29.0	0.068	.	17.3	0.062	.	.	(0.020)
2 PV 111/1	0.0226	1.538	0.019	0.026	0.485	0.105	8.57	18.49	.	.	0.173	.	.	.
1 BS 186B *	0.022	0.28	0.003	0.002	0.25	0.060	36.4	0.12	0.008	0.044	0.025	<0.05	<0.05	0.01
1 BS 254 *	0.019	0.95	0.025	0.002	0.31	0.61	18.4	20.3	0.008	0.093	6.07	0.22	0.063	0.03
1 IARM Fe155PH-18	0.015	0.616	0.021	(0.0004)	0.430	3.35	4.79	15.13	0.014	0.024	0.129	0.0494	0.055	0.019
2 TL 2002D	0.0149	1.30	0.022	0.0206	0.53	0.438	11.0	16.7	.	0.087	2.05	0.0341	0.068	.
1 IARM 99D	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	9.24	4.8	0.0014	(0.037)	(0.010)

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units
IARM FeAl100-18	.	.	.	0.070	(0.0009)	.	(0.004)	(0.008)	Aermet 100	31 mm Ø x 2 or 18 mm
BS 183B *	0.005	0.001	[80.60]	0.009	<0.05	0.001	0.004	0.002	Greek Ascology	38 mm Ø x -7 or 19+ mm
BS 183C *	0.004	0.001	[81.18]	0.006	<0.05	0.001	0.003	0.002	Greek Ascology	38 mm Ø x -7 or 19+ mm
BS 309 *	<0.05	<0.005	[62.6]	0.009	<0.05	<0.05	0.009	0.002	309, 309H	38 mm Ø x -7 or 19+ mm
BS 347C *	0.002	0.0018	[69.02]	0.59	<0.05	0.004	0.005	0.004	347	44 mm Ø x -7 or 19+ mm
CZ SP-1B	(0.003)	0.0007	.	(0.012)	.	.	0.013	(0.002)	.	-37 mm Ø x -25 mm
PV 112/1	0.394	316 Ti	40 mm Ø x 25 mm
IARM Fe174PH-18	.	.	.	(0.0015)	0.0035	.	0.0069	.	17-4 PH	31 mm Ø x 2 or 18 mm
13X 41008B	.	.	.	0.019	.	.	0.0081	.	410	-40 mm Ø x -15 mm Zr:0.047
BS 2507 *	<0.05	0.002	[62.4]	0.009	<0.005	<0.005	0.005	0.003	2507 Duplex	38 mm Ø x -7 or 19+ mm
TL 2001D	.	.	.	0.024	Super Duplex	40 mm Ø x 20 mm
IARM FeKovar-18	.	.	53.3	.	.	.	0.0021	.	Kovar	31 mm Ø x 2 or 18 mm
PV 111/1	304 L	40 mm Ø x 25 mm
BS 186B *	<0.05	<0.005	[62.6]	0.003	<0.005	<0.005	<0.005	0.003	Invar 36	43 mm Ø x -7 or 19+ mm
BS 254 *	<0.05	0.002	[53.1]	0.03	<0.05	<0.05	0.006	0.002	254 SMO	38 mm Ø x -7 or 19+ mm
IARM Fe155PH-18	(0.0026)	(0.0005)	75.03	0.273	0.0028	.	0.0021	.	15-5PH	31 mm Ø x 2 or 18 mm
TL 2002D	0.0098	316 MOD	40 mm Ø x 20 mm
IARM 99D	.	0.0026	.	(0.011)	.	.	.	0.67	Maraging 300	31 mm Ø x 2 or 18 mm

CAST IRON

= Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	V	W
1 VS ChG 56	(3.8)	(0.2)	(0.8)	(0.01)	(0.5)	(0.4)	(0.1)	(0.1)	(0.01)	(0.005)	(0.01)	(0.02)	(0.004)
1 VS ChG 57	(3.8)	(0.2)	1.17	(0.03)	(0.6)	(0.3)	(0.3)	(0.4)	(0.06)	(0.01)	(0.01)	(0.04)	(0.01)
1 SCRUM 658/12	3.33	0.55	0.243	0.076	2.03

Number	As	B	Nb	Sb	Sn	Ti	Units
VS ChG 56	0.18	(0.001)	(0.002)	0.014	.	(0.06)	Disc -37 mm Ø x -17 mm
VS ChG 57	0.095	(0.002)	(0.004)	(0.001)	(0.01)	(0.08)	Disc -37 mm Ø x -17 mm
SCRUM 658/12	Block 48 mm x 42 mm x 12 mm

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
1.0812		ECRM 191-2D	15-5PH		IARM Fe155PH-18	310		IARM 4F
1.2344		ECRM 271-1D	15-5PH		ECRM 273-1D	310		IARM 4G
1.2367		HRT FE2012-H	15-5PH		IARM 22C	310		SS 464/1
1.4435, 1.4436		JK 27B	16MnCr5		PV 102/1	3115		BS XCCT
1.4765		ECRM 299-1D	17-4PH		13X PH2	314		IMZ 165
1.5415		HRT FE2012-N	17-4PH		13X PH17400	314		IMZ 166A
1.6587		HRT FE2013-N	17-4PH		BS 17-4PHA	316	17025	BS 316C
1.7149 20MnCrS5		ECRM 187-2D	17-4PH		BS 17-4PHB	316		IARM 5H
1.7160		ECRM 194-1D	17-4PH		BS 17-4PHC	316		IARM 5i
1.8550		ECRM 129-3D	17-4 PH		IARM Fe174PH-18	316		NILAB 500HAD
1.8519		HRT FE2010-N	17-4PH		SRM C2400	316		SRM 1155A
1.8928		ECRM 194-2D	17-7PH		13X PH17700	316 H		13X NSA2
1005	17025	BS 1005	17-7PH 25(preceded 17025)		BS 192	316 H		CT 316
1005		ECRM 064-2D	17-7PH 25(preceded 17025)		BS 192A	316 H		IARM 339A
1005		RM Fe 1/5	17-7PH		IARM 152C	316 L		13X 31603
1005		SRM 1765	17-7PH		IARM Fe177PH-18	316 L	17025	BS 316F
1005		SRM 1766	182FM		BS 150	316 L		CZ SL-2A
1005		SS 111/1	18Cr2Ni12Mn		CT ISO035A	316 L		IARM Fe316L-18
1008		BS XCAS	201		BS 191	316 L		IARM 163E
1008		ECRM 057-2D	201		SRM 1297	316 L		SS 466/2
1009	17025	BS 1009	20Cb3		BS 187A	316 MOD		TL 2002
1009		IMZ 71	20Cb3		CT 20 Cb-3	316 Ti		IRSID 1821
100C6		IRSID 1747	20MoCr4		ECRM 197-1D	316 Ti		PV 112/1
1010		IMZ 111	2101		IARM 292A	316 Ti		VS LG72
1010		IRSID 1665	21Cr6Ni9Mn		CT ISO129A	317 L		BS 317L
1011		IMZ 73	2205	17025	BS 2205	317 L	25(pre-17025)	BS 9941
1016	17025	BS 1016	2205	17025	BS 2205A	317 L	25(pre-17025)	BS 9942
1017		IMZ 112B	2205		IARM 212D	317 L		IARM 153C
1017		IRSID 1664	2205		IARM Fe2205-18	318	17025	BS 2205
1018		12X 10180B	2304		IARM 317A	318		BS 2205A
1018	17025	12X 10180C	2507		BS 2507	321		13X 32100
1018		BS 1018	2507		IARM 301B	321	17025	BS 85D
1018		ECRM 087-1D	253 MA	25(pre-17025)	BS 253	321	17025	BS 321D
1018		IARM 28K	253 MA		IARM 316A	321		IARM 6i
1020	17025	BS 1020	254 SMO		BS 254	321		IARM 6J
1020		IARM Fe1020-18	254 SMO		IARM 302B	321		SRM 1171
1026	17025	BS 1026	254 SMO		NILAB 501HAD	321		SS 465/1
1026		IARM 359A	255, Duplex		IARM 239B	321 - Ti		IMZ 152
1030	17025	BS 1030	255, Duplex		IARM 239C	32750		13X NSA13
1030		IARM 209D	300M		12X 44220	330		IARM 7C
1033		IRSID 1663	300M	17025	BS 300	3310		BS 3310
1035	17025	BS 1035	300M		IARM 340A	347		13X 34700
1035		IRSID 1645	301		IARM 289A	347		BS 347A
1035		IARM 360A	301		IARM 289B	347		BS 347B
1039		IRSID 1637	301		IRSID 1819	347		BS 347C
1040		12X 10400	302		IARM 241D	347		IARM 8G
1040	17025	BS 3941	302 HQ		IARM 234C	347		IARM 8H
1040		IARM 210D	303		13X 30300	347		IARM 8i
1040		IRSID 1657	303	17025	BS 303	347 H		BS 87F
1042		IRSID 1656	303		CT 303	348		SRM 1172
1042		NM EN-8	303		CZ SP-1A	355	17025	BS 355
1043		IRSID 1652	303		IARM Fe303-18	355		IARM 335A
1045	17025	BS 1045	303 Se		IARM 253A	35MV7		IRSID 1750
1045		BS 56E	303 Se		IARM 253B	405		SRM 1295
1045		IARM 200D	304 H		13X NSB1	409		13X 40900
1045		IPT 503	304 H + Ca	17025	BS CA304-4	409		13X 40930
1050		IARM Fe1050-18	304 H		CT 304	409 + Cr		NCS HS20743
1060		IARM 373A	304 H		IARM Fe304H-18	410		13X 41008
1069		ECRM 059-2D	304 H		SS 468/1	410	25(pre-17025)	BS 0021
1070	17025	BS 54H	304 L		13X 30403	410, F6NM	25(pre-17025)	BS 0022
1078		ECRM 056-2D	304 L	17025	BS 304B	410	17025	BS 410C
1078		SRM 1224	304 L		BS SS3951	410		CT 410
1090		SS 602/2	304 L		IARM 162D	410		IARM Fe410-18
1095		BS 64C	304 L		IARM Fe304L-18	410 + Mo		ECRM 296-1D
1095		SRM 1227	304 L		ECRM 287-1D	410 + Mo		IMZ 161
1117 25(preceded 17025)		BS 3993	304 L		ECRM 292-1D	410 H		13X 41001
1117		BS 65C	304 L		IARM 162C	4130	17025	BS 4130
1117		IARM 29E	304 L		PV 111/1	4130		IARM 143F
1118		IARM 307A	304 L		SS 463/1	4130		SRM 1225
1118		IARM 307B	305		ECRM 297-1D	4130 H		IPT 501
1140 P		BS 52D	306		13X 30600A	4140		12X 41400
1141		BS 66B	308		DSZU C017	4140	25(pre-17025)	BS 1962
1141		IARM 348A	309		13X 30908	4140		BS 4140C
1144	17025	BS 1144	309		BS 82E	4140		IARM 30H
1144	17025	BS 1144A	309		BS 309	4140		IARM 30J
1144		IARM 199C	309		IARM 3E	4140 Bi		BS 4140A
11L17	17025	BS 75F	310		13X 31008	4140 Bi		BS 4140B
11L17	17025	BS 75G	310		BS 83G	41L40MOD	17025	BS 70B
1215	17025	BS 66L	310	25(pre-17025)	BS 9841	41L40MOD		BS 70C
1215		IARM 206B	310	25(pre-17025)	BS 9842	4150 Bi & S		BS 4150MOD
12L14	17025	BS 74C	310		CZ SL-3A	4150 S	17025	BS 4150MOD-A
12L14		BS 74D	310		IARM 4E	4150 S	17025	BS 42
12L14		IARM 183C				4150 S		BS 42A
12Mn18Cr		BS 193				416		BS 90F
1345		BS XCCV				416	17025	BS 416
13-8PH		13X PH13800				416		CT 416
13-8PH		BS 184A				416		IARM 10D
13-8PH		CT X92834				416		SRM 1223
13-8PH		IARM 21D				416 H		13X 41600
1429		ECRM 058-2D				416 Se		BS 151
1513		IMZ 76				418		IARM Fe418-18
1526 MOD		SRM 1269				41CAD7		IRSID 1749
1541		IARM 349A				41L40	17025	BS 70B
1541		IPT 504				41L50	17025	BS 72B
1541		IRSID 1648				42		CT ISO138A
1544		IRSID 1644				42		CT ISO139A
15-5PH		BS 185A				42CrMo4		PV 101/1
15-5PH		BS 9621				420		BS SS4951
15-5PH		BS 9622				420		BS SS4952

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
420		ECRM 272-1D	A-286	17025	BS 188B	Invar-36		BS 186B
420		IARM 154C	A-286		IARM 26D	Invar-36 + Se		BS 186A
420		SS 469	A-286		SRM 1230	Invar-36 + Se		IARM 24B
420 F		BS 152	A-36		IARM 213C	Invar 42		14X 94100
420 F S		IARM 352A	A-36		IARM 213D	ISO 898-1		SS 457/2
422		13X 42200	A-36		SRM 1767	Kovar	17025	BS 160A
422	17025	BS 422	A-485-1		BS A485-1	Kovar		IARM 98B
422		IARM 205D	A-6		BS 40B	Kovar		IARM FeKovar-18
430	17025	BS 430	A-6		IARM 40B	L-2, 6150		BS 43A
430		IARM 11D	A-6		IARM 40C	L-6	17025	BS 39B
430		NCS HS20742	A615-75		IARM 378A	L-6		IARM 43B
430 F		BS 153	A706-60		IARM 380A	LDX2101		13X 32101
430 F		BS 154	A706-60		IARM 380B	LF-2	17025	BS LF2B
430 F S		IARM 355A	A706-80		IARM 381A	LF-2		SS 601/2
431	17025	BS 431	Aermet 100		CT ISO045A	LF-3		BS LF3
431		BS 92B	Aermet 100		IARM 242A	M-1		CT M1
431		IARM 12C	Aermet 100		IARM FeA100-18	M-1		IARM 304A
431		HRT FE2010-H	AL6XN	17025	BS 189A	M-10		CT M10
431		SRM 1219	AL6XN		IARM 157D	M-10		IARM 324A
4320		BS 3961	C-.5Mo		BS 3952	M-152		13X 64152
4330 MOD		BS 4330MOD	C-.5Mo		IARM 229B	M-152		IARM 291A
4330 MOD		BS 4330V	C-250		IARM 308A	M-2		BS 32D
4330 MOD		IARM 330B	C-350		IARM 309A	M-2		CT M2
4340	17025	BS 4340	CA6NM		HRT FE2009-H	M-2		IARM 44C
4340	17025	BS 4340A	CA6NM		IARM 327A	M-2		SRM 1157
4340		IARM 31G	CD3MN		ECRM 298-1D	M-35		IARM 320A
439 MOD		NCS HS11721-4	CD4MCU	17025	BS CD4MCU	M-4		IARM 251A
440 C		13X 44004	CD4MCU	17025	BS CD4MCU-A	M-42		SS 487/1
440 C	17025	BS 93F	CD6MN		VS LG58	M-47	17025	BS M-47
440 C		IARM 13D	CF-3		IRSID 1820	M-50	17025	BS M-50
440 F		BS 155	CLA6		IARM 169B	M-50		IARM 306B
440 F Se		BS 156	CLA7		IARM 170B	M-65		IARM FeM62-18
440 F Se		IARM 353A	CLA11		IARM 180A	M-7		CT M7
441		NCS HS11721-4	CLA5		IARM 168A	Maraging 250		CT 250
446		BS 94C	CLA9		IARM 172A	Maraging 300	25(pre17025)	BS 161A
450		BS 450	CPM15V	17025	BS PM15	Maraging 300		CT 300
450	25(pre-17025)	BS 9811	D-2		BS 37G	Maraging 300		IARM 99D
450	25(pre-17025)	BS 9812	D-2		CT D2	Mold Steel	17025	BS PP20
450		IARM 15C	D-2		IARM 41D	NIT 135M		IARM 305B
450		CT 450	D-3, D-4		ECRM 288-1D	Nitriding 135G		BS 68B
455		13X 45500	D-6	17025	BS D-6	Nitriding 135G	17025	BS 68E
455		BS SS1961	D6-AC		IARM 299A	Nitronic 40		13X NSC6
455		BS SS1962	DP1080		IARM FeDP1080-18	Nitronic 40		BS 190
455		CT 455	Duplex		13X NSA9	Nitronic 40		BS 19C
455		IARM 16C	Duplex	17025	BS 2205	Nitronic 50		BS 180A
446		IARM 14C	Duplex		IMZ 163A	Nitronic 50	17025	BS 180B
4615		BS 3962	Duplex		IMZ 164	Nitronic 50		IARM 17D
4620		BS 4620	Duplex		TL 2001	Nitronic 50		IARM FeN50-18
4620		BS 51F	E52100		BS 53G	Nitronic 60		13X 21800
4620		IARM 33D	E52100		IARM 49E	Nitronic 60		BS 181A
465		13X 46500	E52100 Bi		BS 53MOD	Nitronic 60	17025	BS 181B
465		IARM 354A	Elect./ Magnetic		SRM 1159	Nitronic 60		IARM 18D
465		CT ISO123A	Electrolytic		SRM 1265A	NMS 100		IARM 214A
4820	17025	BS 4820A	F-11		BS 45A	NMS 140		IARM 295A
4820		IARM 155F	F-11	17025	BS 45B	NMS J38		IARM 294A
4820		IARM Fe4820-18	F-11		IARM 35L	O-1	17025	BS 35D
5140H		IARM Fe5140H-18	F-2		CT X27081	O-1	17025	CT O1
5160		IMZ 116	F-22	17025	BS 46B	O-6		BS 41
6150		BS 4941	F-22		IARM 36C	O-6	25(preceded 17025)	BS 41A
6150		IARM 34C	F-22		SRM 1270	O-6		IARM 45A
630		CT 630	F-22 + Cr		HRT FE2009-N	O-6		IARM 45B
6418		BS 6418	F-5		BS 47A	P-20		BS 55G
6418		BS 69B	F-5		BS 47B	PP-20	17025	BS PP20
6526		BS 9-4-30	F-5		IARM 37C	Permendur 2V		IARM 326A
709		CT X67975	F-51	17025	BS 2205	RA330		BS 86F
8620		BS 8620A	F-51		BS 2205A	Railroad Steel	17025	BS 54H
8620	17025	BS 8620F	F-9	17025	BS 48B	S-1		BS 33D
8620		IARM Fe8620-18	F-9		IARM FeF9-18	S-1		BS 33E
8620		IPT 502	F-91		13X 90901	S-1		IARM 46B
86L20	25(preceded 17025)	BS 73B	F-91	17025	BS 9905A	S-1 MOD	17025	BS 33F
86L20		BS 73C	F-91		HRT FE2003-H	S-5		BS 38C
86L20		IARM 182B	F-91		IARM Fe91-18	S-5		IARM 47B
8630	17025	BS 8630	Ferallium 255	17025	BS 179B	S-7		BS TS-7A
8740	17025	BS 67C	Ferallium 255	17025	BS 179C	S-7		IARM 259A
8740		IARM 252C	F6NM 25(preceded 17025)		BS 0022	S-7		SRM 1772
8740		IARM 252D	Greek Ascoloy		BS 183A	S42027		13X 42027A
8740		IARM 252E	Greek Ascoloy		BS 183B	SA213-T22		IMZ 159
8740		IARM 252F	Greek Ascoloy		BS 183C	SA213-T22		IMZ 160
904L		13X NSA12	Greek Ascoloy		IARM 20C	SA213-T22		IMZ 169
904L		ECRM 295-1D	H-10		BS 49	SAE G2500		BS 20E
9310		BS 58C	H-11		ECRM 276-2D	STA 361		IARM 268B
9310		BS 58E	H-11		IARM 255A	T-1		14X HS1
9310		IARM Fe9310-18	H-11		IARM 255B	T-1	17025	BS 30D
9325	17025	BS 9325A	H-11		IMZ 173	T-1		IARM FeT1-18
9-4-30		IARM 341A	H-13	17025	BS H-13	T-4		IARM 281A
A-10		BS A-10	H-13	17025	BS H-13A	T-15	17025	BS TS15
A-11		BS 10V	H-13		CT H13	T23		IARM FeT23-18
A-11	17025	BS A-11	H-13		IARM 42C	VM12		IMZ 196
A-106 Gr B		SRM 1228	H-13		IMZ 174	W-5		14X 72305
A-193 B16		BS 4942	H-19	17025	BS H-19	Z30C13		IRSID 1825
A-193 B16	17025	BS 4942A	HC 250+V		SRM C1290	Zeron 100, Duplex		13X NSA8
A-2		BS 36D	High Perm		CT ISO124A	Zeron 100, Duplex		IARM 319A
A-2		CT A2	High Perm		CT ISO136A	Zeron 100, Duplex		IARM FeZ100-18
A-2		IARM 39B	High Perm 49		CT ISO141A			
A-2		IARM 39C	HSLA 100		SRM 1271			
A-20		BS 187C	HY 130		SRM 1226			
A-242		IPT 500	HY 80		SRM 1286			
A-242 Mod		SRM C1285	Hy-Tuff		IARM 342A			
A-286		BS 188A	Invar		14X 93603			

Please use the Adobe Acrobat "search" function to find the chemistry.

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S
1005	<0.06	<0.35	<0.03	<0.05
1006	<0.08	0.25-0.40	<0.03	<0.05
1008	<0.10	0.30-0.50	<0.03	<0.05
1009	<0.15	<0.60	<0.03	<0.05
1010	0.08-0.13	0.30-0.60	<0.03	<0.05
1011	0.09-0.14	0.60-0.90	<0.03	<0.05
1012	0.10-0.15	0.30-0.60	<0.03	<0.05
1013	0.11-0.16	0.50-0.80	<0.03	<0.05
1015	0.13-0.18	0.30-0.60	<0.03	<0.05
1016	0.13-0.18	0.60-0.90	<0.03	<0.05
1017	0.15-0.20	0.30-0.60	<0.03	<0.05
1018	0.15-0.20	0.60-0.90	<0.03	<0.05
1019	0.15-0.20	0.70-1.00	<0.03	<0.05
1020	0.18-0.23	0.30-0.60	<0.03	<0.05
1021	0.18-0.23	0.60-0.90	<0.03	<0.05
1022	0.18-0.23	0.70-1.00	<0.03	<0.05
1023	0.20-0.25	0.30-0.60	<0.03	<0.05
1025	0.22-0.28	0.30-0.60	<0.03	<0.05
1026	0.22-0.28	0.60-0.90	<0.03	<0.05
1029	0.25-0.31	0.60-0.90	<0.03	<0.05
1030	0.28-0.34	0.60-0.90	<0.03	<0.05
1033	0.29-0.36	0.70-1.00	<0.03	<0.05
1034	0.32-0.38	0.50-0.80	<0.03	<0.05
1035	0.32-0.38	0.60-0.90	<0.03	<0.05
1037	0.32-0.38	0.70-1.00	<0.03	<0.05
1038	0.35-0.42	0.60-0.90	<0.03	<0.05
1039	0.37-0.44	0.70-1.00	<0.03	<0.05
1040	0.37-0.44	0.60-0.90	<0.03	<0.05
1042	0.40-0.47	0.60-0.90	<0.03	<0.05
1043	0.40-0.47	0.70-1.00	<0.03	<0.05
1044	0.43-0.50	0.30-0.60	<0.03	<0.05
1045	0.43-0.50	0.60-0.90	<0.03	<0.05
1046	0.43-0.50	0.70-1.00	<0.03	<0.05
1049	0.46-0.53	0.60-0.90	<0.03	<0.05
1050	0.48-0.55	0.60-0.90	<0.03	<0.05
1053	0.48-0.55	0.70-1.00	<0.03	<0.05
1055	0.50-0.60	0.60-0.90	<0.03	<0.05
1059	0.55-0.65	0.50-0.80	<0.03	<0.05
1060	0.55-0.65	0.60-0.90	<0.03	<0.05
1064	0.60-0.70	0.50-0.80	<0.03	<0.05
1065	0.60-0.70	0.60-0.90	<0.03	<0.05
1069	0.65-0.75	0.40-0.70	<0.03	<0.05
1070	0.65-0.75	0.60-0.90	<0.03	<0.05
1074	0.70-0.80	0.50-0.80	<0.03	<0.05
1078	0.72-0.85	0.30-0.60	<0.03	<0.05
1080	0.75-0.88	0.60-0.90	<0.03	<0.05
1084	0.83-0.93	0.60-0.90	<0.03	<0.05
1085	0.80-0.94	0.70-1.00	<0.03	<0.05
1086	0.80-0.93	0.30-0.50	<0.03	<0.05
1090	0.85-0.98	0.60-0.90	<0.03	<0.05
1095	0.90-1.03	0.30-0.50	<0.03	<0.05
Number	C	Mn	P	S

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si
1513	0.10-0.16	1.10-1.40	<0.03	<0.05	.
1522	0.18-0.24	1.10-1.40	<0.04	<0.05	.
1524	0.19-0.25	1.35-1.65	<0.04	<0.05	.
1526	0.22-0.29	1.10-1.40	<0.04	<0.05	.
1527	0.22-0.29	1.20-1.50	<0.04	<0.05	.
1533	0.30-0.37	1.10-1.40	<0.04	<0.05	.
1534	0.30-0.37	1.20-1.50	<0.04	<0.05	.
1541	0.36-0.44	1.35-1.65	<0.04	<0.05	.
1544	0.40-0.47	0.80-1.10	<0.04	<0.05	.
1545	0.43-0.50	0.80-1.10	<0.04	<0.05	.
1546	0.44-0.52	1.00-1.30	<0.04	<0.05	.
1548	0.44-0.52	1.10-1.40	<0.04	<0.05	.
1552	0.47-0.55	1.20-1.50	<0.04	<0.05	.
1553	0.48-0.55	0.80-1.10	<0.04	<0.05	.
1566	0.60-0.70	0.85-1.15	<0.04	<0.05	.
1570	0.65-0.75	0.80-1.10	<0.04	<0.05	.
1580	0.75-0.88	0.80-1.10	<0.04	<0.05	.
1590	0.85-0.98	0.80-1.10	<0.04	<0.05	.
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30

Number	C	Mn	P	S	Si
--------	---	----	---	---	----

RESULFURIZED STEEL SPECIFICATIONS

Number	C	Mn	P	S
1108	0.08-0.13	0.50-0.80	<0.04	0.08-0.13
1109	0.08-0.13	0.60-0.90	<0.04	0.08-0.13
1110	0.08-0.13	0.30-0.60	<0.04	0.08-0.13
1116	0.14-0.20	1.10-1.40	<0.04	0.16-0.23
1117	0.14-0.20	1.00-1.30	<0.04	0.08-0.13
1118	0.14-0.20	1.30-1.60	<0.04	0.08-0.13
1119	0.14-0.20	1.00-1.30	<0.04	0.24-0.33
1123	0.20-0.27	1.20-1.50	<0.04	0.06-0.09
1132	0.27-0.34	1.35-1.65	<0.04	0.09-0.13
1137	0.32-0.39	1.35-1.65	<0.03	0.08-0.13
1139	0.35-0.43	1.35-1.65	<0.04	0.13-0.20
1140	0.37-0.44	0.70-1.00	<0.03	0.08-0.13
1141	0.37-0.45	1.35-1.65	<0.03	0.08-0.13
1144	0.40-0.48	1.35-1.65	<0.03	0.24-0.33
1145	0.41-0.49	0.70-1.00	<0.04	0.08-0.13
1146	0.42-0.49	0.70-1.00	<0.04	0.08-0.13
1151	0.48-0.55	0.70-1.00	<0.04	0.08-0.13
1152	0.48-0.55	0.70-1.00	<0.04	0.06-0.09
1211	<0.13	0.60-0.90	0.07-0.12	0.10-0.15
1212	<0.13	0.70-1.00	0.07-0.12	0.16-0.23
1213	<0.13	0.70-1.00	0.07-0.12	0.24-0.33
1215	<0.09	0.75-1.05	0.04-0.09	0.26-0.35

Number	C	Mn	P	S
--------	---	----	---	---

These are specifications,
not samples for sale.

LOW ALLOY STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
1330	0.28-0.33	1.60-1.90	<0.035	<0.04	0.15-0.35
1335	0.33-0.38	1.60-1.90	<0.035	<0.04	0.15-0.35
1340	0.38-0.43	1.60-1.90	<0.035	<0.04	0.15-0.35
1345	0.43-0.48	1.60-1.90	<0.035	<0.04	0.15-0.35
3140	0.38-0.43	0.70-0.90	<0.04	<0.04	0.15-0.35	1.10-1.40	0.55-0.75	.	.	.
4023	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4027	0.25-0.30	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4028	0.25-0.30	0.70-0.90	<0.035	0.035-0.050	0.15-0.35	.	.	0.20-0.30	.	.
4037	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4047	0.45-0.50	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4118	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.08-0.15	.	.
4120	0.18-0.23	0.80-1.20	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.15-0.25	.	.
4121	0.18-0.23	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.45-0.65	0.15-0.25	.	.
4130	0.28-0.33	0.40-0.60	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4135	0.33-0.38	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4137	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4140	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L40	0.38-0.43	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4142	0.40-0.45	0.45-0.65	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4145	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4147	0.45-0.50	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4150	0.48-0.53	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L50	0.48-0.53	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4320	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	0.40-0.60	0.20-0.30	.	.
4340	0.38-0.43	0.60-0.80	<0.035	<0.04	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
4615	0.13-0.18	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4617	0.15-0.20	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4620	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4715	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.70-1.00	0.45-0.65	0.45-0.65	.	.
4720	0.17-0.22	0.50-0.70	<0.035	<0.04	0.15-0.35	0.90-1.20	0.35-0.55	0.15-0.25	.	.
4815	0.13-0.18	0.40-0.60	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
4820	0.18-0.23	0.50-0.70	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
50B46	0.44-0.49	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.20-0.35	.	.	B: 0.0005-0.003
5120	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51L20	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	0.15-0.35	.
5130	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	.
5132	0.30-0.35	0.60-0.80	<0.035	<0.04	0.15-0.35	.	0.75-1.00	.	.	.
5140	0.38-0.43	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5160	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51B60	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	B: >0.0005
6150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	V: >0.15
8615	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8617	0.15-0.20	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8620	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
86L20	0.18-0.21	0.70-0.90	<0.035	0.02-0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	0.15-0.35	.
8622	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8630	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8637	0.35-0.40	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8640	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8645	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8720	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8740	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8822	0.20-0.25	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.30-0.40	.	.
9259	0.56-0.64	0.75-1.00	<0.035	<0.04	0.70-1.10	.	0.45-0.65	.	.	.
9260	0.56-0.64	0.75-1.00	<0.035	<0.04	1.80-2.20
E4340	0.38-0.43	0.65-0.85	<0.025	<0.025	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
E51100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	0.90-1.15	.	.	.
E52100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	1.30-1.60	.	.	.
E9310	0.08-0.13	0.45-0.65	<0.025	<0.025	0.15-0.35	3.00-3.50	1.00-1.40	0.08-0.15	.	.
F-11	0.10-0.20	0.30-0.80	<0.04	<0.04	0.50-1.00	.	1.00-1.50	0.44-0.65	.	.
F-22	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	2.00-2.50	0.90-1.10	.	.
F-5	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	4.00-6.00	0.45-0.65	.	.
F-9	<0.15	0.30-0.60	<0.03	<0.03	0.50-1.0	.	8.00-10.00	0.90-1.10	.	.
F-91	0.08-0.12	0.30-0.60	<0.02	<0.01	0.20-0.50	<0.40	8.00-9.50	0.85-1.05	.	Al: <0.04 N: 0.03-0.07
F-91	continued									Nb: 0.06-0.10 V: 0.18-0.25
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30
LF3	<0.20	<0.90	<0.035	<0.04	0.20-0.35	3.25-3.75
Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other

These are specifications,
not samples for sale.

TOOL STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
A-2	0.95-1.05	<1.00	<0.03	<0.03	<0.50	.	4.75-5.50	.	0.90-1.40	0.15-0.50	.	.
A-4	0.95-1.05	1.80-2.20	<0.03	<0.03	<0.50	.	0.90-2.20	.	0.90-1.40	.	.	.
A-6	0.65-0.75	1.80-2.50	<0.03	<0.03	<0.50	.	0.90-1.20	.	0.90-1.40	.	.	.
A-7	2.00-2.85	<0.80	<0.03	<0.03	<0.50	.	5.00-5.75	.	0.90-1.40	3.90-5.15	0.50-1.50	.
A-8	0.50-0.60	<0.50	<0.03	<0.03	0.75-1.10	.	4.75-5.50	.	1.15-1.65	.	1.00-1.50	.
A-9	0.45-0.55	<0.50	<0.03	<0.03	0.95-1.15	1.25-1.75	4.75-5.50	.	1.30-1.80	0.80-1.40	.	.
A-10	1.25-1.50	1.60-2.10	<0.03	<0.03	1.00-1.50	1.55-2.05	.	.	1.25-1.75	.	.	.
A-11	2.45	0.50	.	.	0.90	.	5.25	.	1.30	9.75	.	.
D-2	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	<1.00	0.70-1.20	<1.10	.	.
D-3	2.00-2.35	<0.60	<0.03	<0.03	<0.60	.	11.00-13.50	.	.	<1.00	<1.00	.
D-4	2.05-2.40	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	.	0.70-1.20	<1.00	.	.
D-5	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	2.50-3.50	0.70-1.20	<1.00	.	.
D-7	2.15-2.50	<0.60	<0.03	<0.03	<0.60	.	11.50-13.50	.	0.70-1.20	3.80-4.40	.	.
H-10	0.35-0.45	0.25-0.70	<0.03	<0.03	0.80-1.20	.	3.00-3.75	.	2.00-3.00	0.25-0.75	.	.
H-11	0.33-0.43	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.60	0.30-0.60	.	.
H-12	0.30-0.40	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.25-1.75	<0.50	1.00-1.70	.
H-13	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.75	0.80-1.20	.	.
H-14	0.35-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	.	.	4.00-5.25	.
H-19	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.00-4.75	4.00-4.50	0.30-0.55	1.75-2.20	3.75-4.50	4.50
H-21	0.26-0.36	0.15-0.40	<0.03	<0.03	0.15-0.50	.	3.00-3.75	.	.	0.30-0.60	8.50-10.00	.
H-22	0.30-0.40	0.15-0.40	<0.03	<0.03	0.15-0.40	.	1.75-3.75	.	.	0.25-0.50	10.00-11.75	.
H-23	0.25-0.35	0.15-0.40	<0.03	<0.03	0.15-0.60	.	11.00-12.75	.	.	0.75-1.25	11.00-12.75	.
H-24	0.42-0.53	0.15-0.40	<0.03	<0.03	0.15-0.40	.	2.50-3.50	.	.	0.40-0.60	14.00-16.00	.
H-26	0.45-0.55	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-4.50	.	.	0.75-1.25	17.25-19.00	.
H-42	0.55-0.70	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
L-2	0.45-1.00	0.10-0.90	<0.03	<0.03	<0.50	.	0.70-1.20	.	<0.25	0.10-0.30	.	.
L-6	0.65-0.75	0.25-0.80	<0.03	<0.03	<0.50	1.25-2.00	0.60-1.20	.	<0.50	.	.	.
M-1	0.78-0.88	0.15-0.40	<0.03	<0.03	0.20-0.50	.	3.50-4.00	.	8.20-9.20	1.00-1.35	1.40-2.10	.
M-2	0.78-1.05	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
M-3.1	1.00-1.10	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.25-2.75	5.00-6.75	.
M-3.2	1.15-1.25	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.75-3.25	5.00-6.75	.
M-4	1.25-1.40	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.75	.	4.25-5.50	3.75-4.50	5.25-6.50	.
M-6	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	11.00-13.00	4.50-5.50	1.30-1.70	3.75-4.75	.
M-7	0.97-1.05	0.15-0.40	<0.03	<0.03	0.20-0.55	.	3.50-4.00	.	8.20-9.20	1.75-2.25	1.40-2.10	.
M-10	0.84-1.05	0.10-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	7.75-8.50	1.80-2.20	.	.
M-30	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.25	4.50-5.50	7.75-9.00	1.00-1.40	1.30-2.30	.
M-33	0.85-0.92	0.15-0.40	<0.03	<0.03	0.25-0.55	.	3.50-4.00	7.75-8.75	9.00-10.00	1.00-1.35	1.30-2.10	.
M-34	0.85-0.92	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.00	7.75-8.75	7.75-9.20	1.90-2.30	1.40-2.10	.
M-36	0.80-0.90	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	7.75-8.75	4.50-5.50	1.75-2.25	5.50-6.50	.
M-41	1.05-1.15	0.20-0.60	<0.03	<0.03	0.15-0.50	.	3.75-4.50	4.75-5.75	3.25-4.25	1.75-2.25	6.25-7.00	.
M-42	1.05-1.15	0.15-0.40	<0.03	<0.03	0.15-0.65	.	3.50-4.25	7.75-8.75	9.00-10.00	0.95-1.35	1.15-1.85	.
M-46	1.22-1.30	0.20-0.40	<0.03	<0.03	0.40-0.65	.	3.70-4.20	7.80-8.80	8.00-8.50	3.00-3.30	1.90-2.20	.
M-48	1.50	3.75	9.00	5.25	3.10	10.0	.
M-52	0.90	4.00	.	4.00	2.00	1.25	.
M-61	1.60	4.00	.	6.50	5.00	12.0	.
M-62	1.30	3.75	.	10.5	2.00	6.25	.
O-1	0.85-1.00	1.00-1.40	<0.03	<0.03	<0.50	.	0.40-0.60	.	.	<0.30	0.40-0.60	.
O-2	0.85-0.95	1.40-1.80	<0.03	<0.03	<0.50	.	<0.35	.	<0.30	<0.30	.	.
O-6	1.25-1.55	0.30-1.10	<0.03	<0.03	0.55-1.50	.	<0.30	.	0.20-0.30	.	.	.
O-7	1.10-1.30	<1.00	<0.03	<0.03	<0.60	.	0.35-0.85	.	<0.30	<0.40	1.00-2.00	.
P-20	0.28-0.40	0.60-1.00	<0.03	<0.03	0.20-0.80	.	1.40-2.00	.	0.30-0.55	.	.	.
P-21	0.18-0.22	0.20-0.40	<0.03	<0.03	0.20-0.40	4.00-4.25	0.20-0.30	.	.	0.15-0.25	.	Al: 1.05-1.25
P-6	0.05-0.15	0.35-0.70	<0.03	<0.03	0.10-0.40	3.25-3.75	1.25-1.75
S-1	0.40-0.55	0.10-0.40	<0.03	<0.03	0.15-1.20	.	1.00-1.80	.	<0.50	0.15-0.30	1.50-3.00	.
S-2	0.40-0.55	0.30-0.50	<0.03	<0.03	0.90-1.20	.	0.90-1.20	.	0.30-0.60	<0.50	.	.
S-4	0.50-0.65	0.60-0.95	<0.03	<0.03	1.75-2.25	.	<0.35	.	.	<0.35	.	.
S-5	0.50-0.65	0.60-1.00	<0.03	<0.03	1.75-2.25	.	<0.35	.	0.20-1.35	<0.35	.	.
S-6	0.40-0.50	1.20-1.50	<0.03	<0.03	2.00-2.50	.	1.20-1.50	.	0.30-0.50	0.20-0.40	.	.
S-7	0.45-0.55	0.20-0.80	<0.03	<0.03	0.20-1.00	.	3.00-3.50	.	1.30-1.80	0.20-0.30*	.	.
T-1	0.65-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	.	.	0.90-1.30	17.25-18.25	.
T-15	1.50-1.60	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-5.00	4.75-5.25	<1.00	4.50-5.25	11.75-13.00	.
T-4	0.70-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	0.80-1.20	17.50-19.00	.
T-5	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-5.00	7.00-9.50	0.50-1.25	1.80-2.40	17.50-19.00	.
T-6	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	4.00-4.75	11.00-13.00	0.40-1.00	1.50-2.10	18.50-21.00	.
T-8	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	1.80-2.40	13.25-14.75	.
W-1	0.70-1.50	0.10-0.40	<0.025	<0.025	0.10-0.40	<0.20	<0.15	.	<0.10	<0.10	<0.15	Cu: <0.20
W-2	0.85-1.50	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	<0.15	.	<0.10	0.15-0.35	<0.15	Cu: <0.20
W-5	1.05-1.15	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	0.40-0.60	.	<0.10	<0.10	<0.15	Cu: <0.20

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
--------	---	----	---	---	----	----	----	----	----	---	---	-------

These are specifications,
not samples for sale.

STAINLESS AND HIGH ALLOY STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	N	Nb	Other
13-8PH	<0.05	<0.20	<0.01	<0.008	<0.10	.	7.50-8.50	12.25-13.25	2.00-2.50	<0.01	.	Al: 0.90-1.35
15-5PH	<0.07	<1.00	<0.04	<0.03	<1.00	2.50-4.50	3.50-5.50	14.00-15.50	.	.	0.15-0.45	
17-4PH	<0.07	<1.00	<0.04	<0.03	<1.00	3.00-5.00	3.00-5.00	15.00-17.50	.	.	0.15-0.45	
201	<0.15	5.5-7.5	<0.060	<0.03	<1.00	.	3.50-5.50	16.00-18.00	.	<0.25	.	
202	<0.15	7.5-10.0	<0.060	<0.03	<1.00	.	4.00-6.00	17.00-19.00	.	<0.25	.	
301	<0.15	<2.00	<0.045	<0.03	<1.00	.	6.00-8.00	16.00-18.00	.	.	.	
302	<0.15	<2.00	<0.045	<0.03	<1.00	.	8.00-10.00	17.00-19.00	.	.	.	
302B	<0.15	<2.00	<0.045	<0.03	2.00-3.00	.	8.00-10.00	17.00-19.00	.	.	.	
303	<0.15	<2.00	<0.20	>0.15	<1.00	.	8.00-10.00	17.00-19.00	<0.60*	.	.	Zr: <0.60*
304	<0.08	<2.00	<0.045	<0.03	<1.00	.	8.00-10.50	18.00-20.00	.	.	.	
304L	<0.03	<2.00	<0.045	<0.03	<1.00	.	8.00-12.00	18.00-20.00	.	.	.	
305	<0.12	<2.00	<0.045	<0.03	<1.00	.	10.00-13.00	17.00-19.00	.	.	.	
308	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-12.00	19.00-21.00	.	.	.	
309	<0.20	<2.00	<0.045	<0.03	<1.00	.	12.00-15.00	22.00-24.00	.	.	.	
310	<0.25	<2.00	<0.045	<0.03	<1.50	.	19.00-22.00	24.00-26.00	.	.	.	
314	<0.25	<2.00	<0.045	<0.03	1.50-3.00	.	19.00-22.00	23.00-26.00	.	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316L	<0.03	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
321	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-12.00	17.00-19.00	.	.	.	Ti: >5xC
347	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
348	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	Ta: <0.10
384	<0.08	<2.00	<0.045	<0.03	<1.00	.	17.00-19.00	15.00-17.00	.	.	.	
385	<0.08	<2.00	<0.045	<0.03	<1.00	.	14.00-16.00	11.50-13.50	.	.	.	
403	<0.15	<1.00	<0.04	<0.03	<0.50	.	.	11.50-13.00	.	.	.	
405	<0.08	<1.00	<0.04	<0.03	<1.00	.	.	11.50-14.50	.	.	.	Al: 0.10-0.30
409	<0.08	<1.00	<0.04	<0.01	<1.00	.	<0.50	10.50-11.75	.	.	.	Ti: 6\mtC-0.75
410	<0.15	<1.00	<0.04	<0.03	<1.00	.	.	11.50-13.50	.	.	.	
414	<0.15	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	11.50-13.50	.	.	.	
416	<0.15	<1.25	<0.06	>0.15	<1.00	.	.	12.00-14.00	<0.60*	.	.	Zr: <0.60*
420	>0.15	<1.00	<0.04	<0.03	<1.00	.	.	12.00-14.00	.	.	.	
422	0.20-0.25	<1.00	<0.04	<0.03	<0.75	<0.50	0.50-1.00	11.00-12.50	0.75-1.25	.	.	V: 0.15-0.30
422	continued											W: 0.75-1.25
430	<0.12	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	.	.	.	
430F	<0.12	<1.25	<0.06	>0.15	<1.00	.	.	16.00-18.00	<0.60*	.	.	Zr: <0.60*
431	<0.20	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	15.00-17.00	.	.	.	
440A	0.60-0.75	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440B	0.75-0.95	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440C	0.95-1.20	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
450	<0.05	<1.00	<0.03	<0.03	<1.00	1.25-1.75	5.00-7.00	14.00-16.00	0.50-1.00	.	8\mtC	
455	<0.05	<0.50	<0.04	<0.03	<0.50	1.50-2.50	7.50-9.50	11.00-12.50	<0.50	.	0.10-0.50	Ti: 0.80-1.40
501	>0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
502	<0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
Duplex	<0.05	<3.00	<0.035	<0.03	<1.50	<2.50*	4.00-7.00	18.00-25.00	0.20-5.50	<0.40	.	

These are specifications,
not samples for sale.